

## INDEX

- ALLOY LISTING 50  
 ALLOY SPECIFICATIONS 52  
 ALLOYED CAST IRON 40, 41  
 ALUMINUM IN STAINLESS STEEL 19  
 ALUMINUM IN STEEL 2, 6  
 ANTIMONY IN STEEL 5  
 ARSENIC IN STEEL 5
- BISMUTH STEEL 5, 8  
 BORON IN STEEL 2
- CALCIUM IN STAINLESS STEEL 19  
 CALCIUM IN STEEL 6  
 CARBON STEEL 2, 3, 4, 44  
 CARBON STEEL SPECIFICATIONS 52  
 CAST IRON  
   32, 33, 34, 35, 37, 38, 39, 40, 41, 42, 43, 49  
 CAST IRON WITH MAGNESIUM 34, 35, 36  
 COBALT IN STAINLESS STEEL 21  
 COPPER IN STAINLESS STEEL 20  
 Cr-Mo STEEL 6, 7
- DUCTILE IRON 33
- EPMA SETS 6
- GRAY IRON 33
- HIGH ALLOY STEEL 31, 32, 48  
 HIGH ALLOY STEEL SPECIFICATIONS 55  
 HIGH CHROMIUM CAST IRON 40, 41
- IRON 2
- LEADED STEEL 8  
 LOW ALLOY STEEL  
   5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 45, 46  
 LOW ALLOY STEEL SPECIFICATIONS 53  
 LOW ALLOY STEEL WITH  $0.13\% < C < 0.3\%$  13, 14  
 LOW ALLOY STEEL WITH  $C < 0.13\%$  15  
 LOW ALLOY STEEL WITH  $C > 0.3\%$  11, 12  
 LOW ALLOY STEEL WITH EXTENSIVE ANALYSIS 13
- MANGANESE STAINLESS STEEL 22  
 MANGANESE STEEL 8  
 MARAGING STEEL 21
- NICKEL BINARY 22  
 NITROGEN IN STEEL 6  
 NODULAR IRON 33
- PHOSPHORUS IN STAINLESS STEEL 23
- RESULFURIZED STAINLESS STEEL 23  
 RESULFURIZED STEEL 9, 44  
 RESULFURIZED STEEL SPECIFICATIONS 52
- SELENIUM IN STAINLESS STEEL 23  
 SET 2, 6, 8, 9, 16, 30, 32  
 Si-Mo CAST IRON 33  
 SILICON STEEL 10, 46  
 SOLUBLE ALUMINUM 2  
 SOLUBLE BORON 2  
 STAINLESS STEEL  
   19, 20, 21, 22, 23, 24, 25, 26, 27, 28, 29, 30, 31, 47, 48  
 STAINLESS STEEL SPECIFICATIONS 55  
 STAINLESS STEEL WITH  $C < 0.05\%$  28, 29  
 STAINLESS STEEL WITH  $C > 0.05\%$  26, 27  
 STAINLESS STEEL WITH  $NI < 5.0\%$  24, 25  
 SULFUR IN STAINLESS STEEL 23
- TOOL STEEL 16, 17, 18, 45, 46  
 TOOL STEEL SPECIFICATIONS 54  
 TUNGSTEN IN STAINLESS STEEL 21
- WHITE IRON 36
- XRF 2, 6, 8, 9, 16, 30, 32

PURE IRON

Table with columns: #, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Mo, Al, Co, N, O. Includes rows for SRM 1265a, BS 50F, CZ LA-0A, CZ LA-0B, IARM 27G, BS LC-7B, BS LC-7A, BS 50G, VS RG24/1, TL 1669, BS 50D, ECRM 098-1D, and ECRM 097-2D.

Table with columns: Number, As, B, Mg, Nb, Pb, Sn, Ti, V, W, Units. Includes rows for SRM 1265a, BS 50F, CZ LA-0A, CZ LA-0B, IARM 27G, BS LC-7B, BS LC-7A, BS 50G, VS RG24/1, TL 1669, BS 50D, ECRM 098-1D, and ECRM 097-2D.

\*\* TL-1669 also contains in ppm Ca: 1.7, Sb: 4.9, Zn: 2.7

RM CARBON STEEL XRF SET

Part Number: BS CS-10 AVAILABLE INDIVIDUALLY 17025 ~7 mm discs

Table with columns: Grade, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Mo, Al, As, Co, N, Sn, V. Lists various grades of carbon steel including Pure Iron 1018, 1020, 1026, 1035, 1040, 1045, 1095, 1522 (LF2), and 1345.

CRM CARBON STEEL SET

AVAILABLE IN SET/6 ONLY

38 mm Ø x 30 mm

Table with columns: Number, C, Mn, P, S, Si, Cu, Ni, Cr, Al, Al.Sol, Ti, Ti.Sol, V. Lists grades of carbon steel including NCS HS11719-5, -1, -3, -4, -2, -6.

CRM SOLUBLE ALUMINUM AND SOLUBLE BORON STEEL SET

available in set/6 only as grouped .T = total .S = soluble

37 mm Ø x 30 mm

Table with columns: Number, Al.T, Al.S, B.T, B.S, C, Mn, P, S, Si, Cu, Ni, Cr, Co, Mo. Lists grades of soluble aluminum and boron steel including NCS HS93703-1a, -2, -3, -4, -5, -6.

Table with columns: Number, As, Bi, Ca, Nb, Pb, Sb, Sn, Ti, V, W, Zr. Lists grades of soluble aluminum and boron steel including NCS HS93703-1a, -2, -3, -4, -5, -6.

CARBON STEEL

CONTINUED ON THE NEXT PAGE

# = Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	B	Ca	Co	Mo
1	IRSID 1660	1.20	0.280	0.014	0.010	0.173	0.059	0.072	(0.026)	(0.009)	.	.	.	.	.	.
1	ECRM 090-1D	1.05	0.226	0.013	0.0095	0.281	.	0.053	0.121	.	.	.	.	.	.	0.009
1	SRM 1227	0.97	0.402	0.014	0.026	0.215	.	0.006	0.007	0.019	.	.	.	.	0.003	0.003
1	SS 602/2	0.94	0.66	0.023	0.031	0.057	(0.06)	(0.02)	(0.03)	0.096	.	.	.	.	(0.007)	(0.004)
2	BS 64C	0.920	0.22	0.015	0.0024	0.22	0.016	0.038	0.261	(0.005)	.	.	.	.	0.004	0.008
2	HRT FE2014-N	0.91	1.97	0.012	(0.004)	0.24	0.01	0.02	0.35	0.016	.	.	.	.	.	0.01
1	ECRM 056-2D	0.8181	0.5073	0.0103	0.0093	0.2006	0.0129	0.0218	0.0146	.	0.00024	.	.	.	.	.
1	SRM 1224	0.75	0.41	0.009	0.039	0.173	0.072	0.054	0.071	0.060	.	.	.	.	.	0.013
1	<b>BS 524H</b>	0.737	0.829	0.0030	0.0044	0.521	0.046	0.373	0.369	0.032	.	0.0036	(0.0001)	(0.0001)	0.0030	0.0106
1	VS RG28	0.70	0.84	0.031	.	1.161	0.050	0.154	0.135	0.066	.	.	.	.	.	0.090
1	VS RG28/1	0.68	0.91	0.031	0.0071	2.36	0.040	0.168	0.194	0.068	.	.	.	.	0.072	0.104
1	IARM 373A	0.63	0.70	0.0123	0.031	0.22	0.107	0.048	0.096	0.002	.	0.0046	0.0003	0.0005	0.005	0.0176
1	VS UG20/6	0.58	0.473	(0.008)	(0.02)	0.229	0.249	0.360	0.396	.	.	.	.	.	.	.
1	SS 435/1	0.52	0.41	0.033	0.031	0.54	.	0.060	0.14	.	.	.	.	.	.	.
1	SS 435/2	0.489	0.390	0.037	0.042	0.328	.	0.133	0.184	.	.	.	.	.	0.011	.
2	<b>BS 56E</b>	0.483	0.72	0.010	0.025	0.24	0.015	0.015	0.021	0.062	.	0.0035	.	<0.0005	0.005	0.005
1	IRSID 1636	0.47	0.78	0.029	0.037	0.40	0.135	0.092	(0.060)	(0.007)	.	.	.	.	.	.
1	SS 459/2	0.467	0.909	0.0482	0.0481	0.640	.	.	0.015	(0.013)	.	0.0110	.	.	0.0890	.
1	<b>BS 1045</b>	0.458	0.796	0.0069	0.023	0.215	0.190	0.060	0.108	(0.001)	.	0.0050	(0.0003)	0.0013	0.0056	0.0170
1	IARM 200D	0.453	0.749	0.0103	0.024	0.225	0.232	0.097	0.109	(0.004)	.	0.0050	.	.	0.007	0.0217
1	VS UG123	0.45	0.552	0.016	0.026	0.216	0.196	0.084	0.111	0.024	.	.	.	.	.	.
1	IRSID 1657	0.445	0.724	0.028	(0.013)	0.274	.	0.048	(0.022)	0.004	.	0.0051	.	.	.	(0.008)
1	NM 306	0.44	0.80	0.043	0.042	0.34	.	.	0.26	.	.	.	.	.	.	.
1	IRSID 1648	0.432	1.41	0.031	(0.070)	0.242	0.408	0.165	0.170	(0.004)	.	(0.038)	.	.	.	(0.028)
1	NM EN-8	0.42	0.82	0.02	0.02	0.21	.	.	.	.	.	.	.	.	.	.
1	IRSID 1642	0.418	0.929	0.031	(0.031)	0.388	0.097	0.068	(0.035)	(0.020)	.	(0.042)	.	.	.	(0.009)
1	IRSID 1647	0.418	0.701	0.019	(0.027)	0.299	(0.104)	0.093	0.490	(0.060)	.	.	.	.	.	.
1	IARM 210D	0.412	0.73	0.0052	0.030	0.230	0.273	0.122	0.096	(0.002)	(0.0555)	0.0059	0.0004	0.0009	0.007	0.034
1	SS 434/1	0.41	1.49	0.050	0.027	0.31	0.300	0.178	0.189	0.0020	.	0.005	0.0003	0.0015	0.0085	0.059
1	IARM 349A	0.41	1.49	0.011	0.025	0.192	0.300	0.178	0.189	0.0020	.	0.005	0.0003	0.0015	0.0085	0.059
1	IRSID 1652	0.406	0.931	(0.017)	0.040	0.386	0.345	0.190	0.184	.	(0.0013)	0.038	.	.	.	(0.042)
1	IRSID 1637	0.401	0.940	0.030	0.030	0.378	0.097	0.068	(0.033)	0.022	.	0.042	.	.	.	(0.006)
1	SS 605/2	0.400	0.345	0.054	0.015	0.54	(0.06)	(0.05)	(0.06)	0.027	.	.	.	.	(0.008)	(0.01)
1	IRSID 1644	0.394	0.594	0.021	0.031	0.287	0.265	0.158	0.138	(0.017)	.	.	.	.	.	.
1	ECRM 084-1D	0.391	0.860	.	0.029	0.265	0.267	0.154	.	.	.	.	.	.	.	0.033
1	IRSID 1649	0.384	0.930	0.045	(0.047)	0.250	0.418	0.226	0.321	0.004	.	0.037	.	.	.	0.043
1	SS 460/2	0.383	0.616	0.0374	0.0099	0.126	.	.	0.024	(0.019)	.	.	0.0027	.	0.0106	.
1	VS RG30	0.38	0.357	.	0.013	0.45	0.161	0.62	3.06	.	.	.	.	.	0.50	0.62
1	<b>BS 1035</b>	0.362	0.758	0.0100	0.028	0.246	0.241	0.123	0.151	0.0008	.	0.0051	(0.0002)	0.0017	0.0073	0.049
1	IRSID 1655	0.355	1.018	(0.018)	(0.060)	0.443	0.415	0.188	0.157	(0.004)	.	(0.036)	.	.	.	(0.043)
1	IRSID 1663	0.353	0.967	0.0090	0.034	0.235	0.180	0.148	0.206	0.037	.	0.028	.	.	.	0.042
1	VS UG90	0.34	0.286	0.0079	0.012	0.221	0.200	0.265	0.261	0.037	0.032	0.0044	.	.	.	0.046
1	VS UG19/6	0.34	0.274	(0.03)	(0.03)	0.136	0.148	0.262	0.227	.	.	.	.	.	.	.
1	IARM 360A	0.331	0.733	0.008	0.023	0.260	0.235	0.078	0.113	0.0016	.	0.0060	0.0004	0.0017	0.0067	0.024
1	<b>BS 1030</b>	0.331	0.682	0.0101	0.0299	0.261	0.269	0.078	0.124	0.0014	.	0.0055	0.0003	0.0012	0.0069	0.0182
1	IARM 209D	0.322	0.68	0.0084	0.021	0.268	0.243	0.079	0.137	(0.003)	.	0.0060	0.0002	0.002	0.007	0.037
1	IRSID 1653	0.312	0.962	0.034	(0.039)	0.400	0.453	0.218	0.358	<0.004	.	(0.039)	.	.	.	(0.038)
1	VS RG27	0.30	0.91	0.054	0.0032	0.42	0.188	0.135	1.53	0.88	.	.	.	.	0.071	0.222
1	SS 434/2	0.275	1.54	0.061	0.0141	0.51	.	0.037	0.238	.	.	.	.	.	.	.

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	B	Ca	Co	Mo
1	IRSID 1654	0.270	0.979	0.036	(0.047)	0.354	0.441	0.241	0.328	.	.	0.040	.	.	.	(0.043)
1	IARM 359A	0.267	0.686	0.0094	0.020	0.233	0.186	0.068	0.121	0.002	.	0.0073	0.0003	0.0013	0.0069	0.023
1	<b>BS 1026</b>	0.260	0.715	0.0171	0.0191	0.268	0.247	0.096	0.163	0.0330	.	0.0100	(0.0002)	0.0017	0.0072	0.0289
1	VS UG94	0.26	0.186	0.0037	0.0026	0.101	0.088	0.178	0.206	0.017	.	.	.	.	.	0.0005
1	VS UG18/6	0.242	0.213	(0.003)	(0.003)	0.20	0.063	0.273	0.237	.	.	.	.	.	.	.
2	HRT FE2016-N	0.23	0.85	0.015	0.011	0.32	0.02	0.15	0.21	0.033	.	.	.	.	.	.
1	<b>BS 1020</b>	0.210	0.568	0.0058	0.0249	0.250	0.184	0.059	0.109	0.0006	.	0.0074	(0.0001)	0.0022	0.0070	0.018
1	IARM 213C	0.201	0.922	0.007	0.025	0.25	0.149	0.068	0.099	0.0019	.	0.0058	0.0003	0.0014	0.0074	0.022
1	IRSID 1664	0.2008	0.472	0.0106	0.0259	0.0616	0.0820	0.0547	0.0707	.	0.0193	0.0115	(0.0002)	(0.0005)	(0.0084)	0.0157
1	VS RG25/1	0.196	0.29	0.019	0.0088	0.100	0.065	0.037	0.060	0.067	.	.	.	0.012	0.010	.
1	<b>BS 1018</b>	0.195	0.79	0.012	0.024	0.237	0.130	0.104	0.177	0.029	.	0.0041	(0.0002)	(0.0004)	0.0058	0.044
1	<b>BS LF2B</b>	0.176	1.05	0.007	0.0067	0.209	0.318	0.115	0.138	0.0287	.	0.0052	(0.0002)	0.0010	0.0071	0.0382
1	IARM 28K	0.174	0.80	0.012	0.027	0.291	0.171	0.0638	0.107	(0.025)	.	(0.005)	0.0005	.	0.0060	0.0210
1	<b>BS 1016</b>	0.172	0.77	0.011	0.030	0.193	0.153	0.107	0.091	0.0200	.	0.0066	(0.0003)	(0.0004)	0.0193	0.040
1	12X 10180C	0.171	0.803	0.0150	0.0200	0.147	0.0500	0.0284	0.0793	0.0198	.	0.0029	.	.	.	0.0047
1	12X 10180B	0.169	0.722	0.0101	0.0056	0.114	0.0544	0.0333	0.0451	0.043	.	0.0059	.	.	.	0.0062
2	TL 1000	0.1692	1.4281	0.0142	0.0164	0.2258	0.0120	0.0312	0.0635	0.0226	.	(0.0016)	0.00018	0.00039	0.0042	0.0076
1	VS RG25	0.167	0.131	0.014	0.084	.	0.046	0.057	0.015	.	.	.	.	.	.	0.0028
1	VS UG124	0.165	1.41	0.019	0.032	0.384	0.020	0.015	0.035	0.039	.	.	.	.	.	.
1	VS UG109	0.161	0.353	0.020	0.0037	0.151	0.082	0.0053	0.048	0.0093	.	.	.	.	.	.
1	IARM 213D	0.158	0.725	0.0120	0.031	0.226	0.207	0.076	0.093	(0.003)	.	(0.006)	(0.0004)	.	0.009	0.0131
1	SS 456/3	0.1215	0.2121	0.0228	0.0246	0.267	.	0.0174	0.0257	0.0393	.	.	0.0014	.	0.0520	0.0013
1	VS UG93	0.100	0.140	0.0033	0.0024	0.48	0.028	0.126	0.137	0.15	.	.	.	.	.	0.0008
1	VS UG17/6	0.097	0.106	(0.003)	(0.004)	0.37	(0.02)	0.105	0.127	.	.	.	.	.	.	.
1	SS 433/2	0.096	1.188	0.011	0.0083	0.007	.	0.037	0.026	.	.	.	.	.	.	.
1	IRSID 1661	0.086	1.48	0.018	(0.006)	0.406	(0.113)	(0.029)	(0.021)	(0.028)	(0.025)	(0.003)	.	.	.	(0.006)
1	VS UG125	0.086	1.147	0.0044	0.0021	0.554	0.147	0.230	0.102	.	.	.	.	.	.	.
1	VS UG108	0.074	0.104	0.050	0.0082	.	0.0087	0.0092	.	.	.	.	.	.	.	.
1	SRM 1228	0.072	0.365	0.004	0.018	0.007	0.012	0.018	0.016	0.061	.	.	.	.	.	0.009
1	ECRM 057-2D	0.0507	0.246	0.0120	0.0127	.	0.0146	0.0096	0.0114	0.059	.	.	.	.	.	.
1	NM 305	0.034	0.270	0.011	0.007	0.031	.	.	0.025	.	.	.</				

**CARBON STEEL                      CONTINUED FROM THE PREVIOUS PAGE**

Number	N	Nb	O	Pb	Sb	Sn	Ti	V	W	Zn	Zr	Units
IRSID 1660												37 mm Ø x 30 mm
ECRM 090-1D	0.0146	0.00043		0.00239	0.00090			0.204		0.00209		38 mm Ø x 25 or 30 mm
SRM 1227								0.002				32 mm Ø x 19 mm
SS 602/2								(0.001)			(<0.005)	44 mm Ø x 19 mm
BS 64C	0.0084	(<0.003)				(0.001)	(0.002)	0.005				44 mm Ø x ~7 or 19+ mm
HRT FE2014-N	0.0052							0.066				-35mm Ø x 20 mm
ECRM 056-2D												44 mm Ø x 25 or 30 mm
SRM 1224								0.002				32 mm Ø x 19 mm
<b>BS 54H</b>	0.0039	(0.0003)	(0.001)	(0.001)	(0.001)	0.0030	0.0009	0.0008	(0.003)	Fe:97.0	(0.0008)	44 mm Ø x 19+ mm <b>17025</b>
VS RG28		0.029				0.0041	0.022	0.006				-45 mm Ø x ~28 mm
VS RG28/1		0.041					0.022	0.035	0.0041			-45 mm Ø x ~28 mm
IARM 373A	0.0088	0.001	0.002	(0.001)	(0.002)	0.0069	0.0017	0.023	(0.002)	(0.003)	(0.003)	31 mm Ø x 2 or 18 mm
VS UG20/6												-45 mm Ø x ~28 mm
SS 435/1		0.039										38 mm Ø x 19 mm
SS 435/2		0.134										38 mm Ø x 19 mm
BS 56E	0.0056	(<0.002)		(0.0001)	0.0004	(0.0006)	(0.001)	(<0.002)				44 mm Ø x ~7 to ~18 mm    last
IRSID 1636												48 mm Ø x 30 mm
SS 459/2		0.0102		0.0044	0.0121			0.0585			(0.074)	38 mm Ø x 19 mm
<b>BS 1045</b>	0.0113	0.026	0.0040	(0.0005)	0.0017	0.0084	0.0011	(0.002)	(0.0007)	Fe:98.1	(0.0009)	38 mm Ø x ~7 or 19+ mm <b>17025</b>
IARM 200D	0.009	0.0010				0.0079	(0.0013)	0.0244	(0.003)			31 mm Ø x 2 or 18 mm
VS UG123	0.0078							0.0019				-45 mm Ø x ~25 mm
IRSID 1657								(0.001)				42 mm Ø x 30 mm
NM 306												40 mm Ø x 25 mm    last
IRSID 1648						0.033						40 mm Ø x 28 mm
NM EN-8												40 mm Ø x 20 mm
IRSID 1642								(0.002)				45 mm Ø x 30 mm
IRSID 1647												41 mm Ø x 30 mm
IARM 210D	0.011	0.001	0.0034	0.001	0.002	0.010	0.0104	0.024	(0.002)		(0.001)	31 mm Ø x 2 or 18 mm
SS 434/1		0.078										38 mm Ø x 19 mm
IARM 349A	0.0100	0.0012	0.003	(0.001)	(0.003)	0.015	0.0013	0.027	0.004	(0.003)	(0.002)	31 mm Ø x 2 or 18 mm
IRSID 1652						0.030						45 mm Ø x 30 mm
IRSID 1637								(0.002)				45 mm Ø x 30 mm
SS 605/2								(0.001)			(0.12)	44 mm Ø x 19 mm
IRSID 1644												45 mm Ø x 30 mm
ECRM 084-1D						0.023						38 mm Ø x 25 or 30 mm
IRSID 1649						0.028						40 mm Ø x 28 mm
SS 460/2		0.068		0.0005	(0.0006)			0.0322			(<0.0005)	38 mm Ø x 19 mm
VS RG30		0.139						0.63	0.91			-45 mm Ø x ~28 mm
<b>BS 1035</b>	0.0105	(0.001)	0.0036	(0.001)	(0.002)	0.0027	0.0007	0.026	0.0020	Fe:97.9	(0.0009)	40 mm Ø x ~7 or 19+ mm <b>17025</b>
IRSID 1655						0.046						40 mm Ø x 34 mm
IRSID 1663						0.0143	0.051					44 mm Ø x 30 mm
VS UG90					0.0011		0.039					-47 mm Ø x ~30 mm
VS UG19/6												-45 mm Ø x ~28 mm
IARM 360A	0.0102	0.0015	0.004	(0.001)	0.0023	0.010	0.0010	0.039	(0.001)	(0.003)	(0.001)	31 mm Ø x 2 or 18 mm
<b>BS 1030</b>	0.0107	(0.0004)	0.005	0.0005	0.0024	0.0114	0.0005	0.031	0.0012	last	(0.0002)	38 mm Ø x ~7 mm <b>17025</b>
IARM 209D	0.0107	0.0014	0.005	0.001	0.004	0.012	0.0011	0.042	(0.002)	(0.003)		31 mm Ø x 2 or 18 mm
IRSID 1653						0.066						40 mm Ø x 34 mm
VS RG27								0.064	0.170			-45 mm Ø x ~28mm
SS 434/2	0.0104	0.038										38 mm Ø x 19 mm
Number	N	Nb	O	Pb	Sb	Sn	Ti	V	W	Zn	Zr	Units
IRSID 1654						0.030						40 mm Ø x 34 mm
IARM 359A	0.0094	0.002	0.0044	(0.001)	(0.002)	0.0100	0.0009	0.027	(0.001)		(0.001)	31 mm Ø x 2 or 18 mm
<b>BS 1026</b>	0.0083	(0.0004)	0.0031	(0.0002)	0.0019	0.0112	(0.0004)	0.0016	0.0021	last	(0.0002)	38 mm Ø x ~10 or 19 mm <b>17025</b>
VS UG94							0.053	(0.001)				-40 mm Ø x ~28 mm
VS UG18/6												-45 mm Ø x ~28 mm
HRT FE2016-N	0.0055											35 mm Ø x 20 mm
<b>BS 1020</b>	0.0109	(0.0003)	0.0046	(0.0002)	(0.0018)	0.0090	(0.0005)	0.0363	(0.0004)		(0.0005)	44 mm Ø x ~7 or 19+ mm <b>17025</b>
IARM 213C	0.0116	0.0011	0.0042	0.0011	0.002	0.0081	0.0010	0.035	(0.002)	(0.006)	(0.0004)	31 mm Ø x 2 mm
IRSID 1664	0.0072	(0.0002)		0.0002	0.0012	0.0108	0.0013	(0.0005)	<0.002	(0.0007)	(0.0001)	37 mm Ø x 30 mm
VS RG25/1		0.016				0.055	0.0110					-45 mm Ø x ~28 mm
<b>BS 1018</b>	0.0079	(0.0006)	0.0014	(0.0006)	(0.001)	0.0099	0.0009	0.0009	0.0014	Fe:98.2	(0.001)	38 mm Ø x ~7 or 19+ mm <b>17025</b>
<b>BS LF2B</b>	0.0078	(0.0003)	0.0024	(0.0001)	0.0018	0.0092	0.0009	0.0300	0.0027	<b>17025</b>	Fe:97.9	38 mm Ø x ~7 or 19+ mm <b>17025</b>
IARM 28K	(0.008)	0.0017	(0.005)			0.0075	(0.0015)	(0.0014)				31 mm Ø x 2 or 18 mm
<b>BS 1016</b>	0.0113	(0.0009)	(0.003)	(0.004)	Fe:98.4	0.013	0.0010	0.0011	(0.0013)	<b>17025</b>	(0.001)	Hexagon ~60 mm Ø x 19+ mm
12X 10180C	0.0052					0.0024				0.0005		-40 mm Ø x ~15 mm
12X 10180B	0.0071					0.0065				0.0079		-40 mm Ø x ~15 mm
TL 1000	(0.0093)	0.0293		Mg: (0.00005)		(0.00106)	0.0011	(0.0033)	(0.0002)			36 mm Ø x 20 mm
VS RG25							0.039					-45 mm Ø x ~28 mm
VS UG124	0.0072							0.0043				-45 mm Ø x ~25 mm
VS UG109							0.071					-45 mm Ø x ~25 mm
IARM 213D	(0.008)	(0.0012)	(0.01)		(0.0032)	0.0147	0.0011	0.0010	(0.003)	(0.002)	(0.0015)	31 mm Ø x 2 or 18 mm
SS 456/3		0.0113		0.0153	0.0222			0.0214				38 mm Ø x 19 mm
VS UG93							0.075	0.0008				-40 mm Ø x ~28 mm
VS UG17/6												-45 mm Ø x ~28 mm
SS 433/2		0.059										38 mm Ø x 19 mm
IRSID 1661					(0.0005)	(0.0085)						40 mm x 42 mm x 30 mm
VS UG125	0.0112							0.035				-45 mm Ø x ~28 mm
VS UG108							0.071		0.074			-45 mm Ø x ~25 mm
SRM 1228								<0.001				32 mm Ø x 19 mm
ECRM 057-2D	0.0023											38 mm Ø x 25 or 30 mm
NM 305												40 mm Ø x 20 mm
ECRM 083-2D	0.00157									0.00439		39 mm Ø x 28 mm
DSZU C03		(0.002)		(0.009)	(0.003)	0.011	0.002	0.004	(0.009)	(0.0037)	(0.0006)	40 mm Ø x 30 mm
VS RG26							0.121		0.0052			-45 mm Ø x ~28 mm
SS 431/2	0.0052	0.0040										38 mm Ø x 19 mm
VS UG2/11	(0.007)											-45 mm Ø x ~28 mm
RM Fe 1/5	0.002	<0.005		<0.002		0.0008	<0.0005	<0.0005	0.002		<0.005	40 mm Ø x 40 mm
VS UG2/5		(0.002)					(0.01)	0.005	(0.02)			-45 mm Ø x ~28 mm
<b>BS 1005</b>	0.0044	0.0008	0.0058	(0.0003)	(0.0007)	0.0009	0.0010	(0.0007)	(0.0003)	Fe:99.6	(0.0008)	38 mm Ø x ~7 or 19+ mm <b>17025</b>
<b>BS 1009</b>	0.0043	(0.0008)	0.0060	(0.0004)	(0.0009)	0.0007	0.0007	(0.0006)	(0.001)	Fe:99.6	(0.0006)	38 mm Ø x ~7 or 19+ mm <b>17025</b>
SS 111/1	0.0025					0.0006	0.0004	0.0002				44 mm Ø x 19 mm
SS 432/2	0.0066	0.0174										38 mm Ø x 19 mm
CZ LA-1B	0.003	(0.001)		(0.0007)	(0.002)	(0.001)	(0.001)	0.004	0.010		(0.002)	-37 mm Ø x 25 mm
IMZ 110A	0.0037						(0.0006)	(0.0014)				43 mm Ø x 20 mm
VS 004							0.0013					-45 mm Ø x ~25 mm
VS 002						0.00040	0.0005					-45 mm Ø x ~25 mm
Number	N	Nb	O	Pb	Sb	Sn	Ti	V	W	Zn	Zr	Units

## ARSENIC AND ANTIMONY IN STEEL

# = Class, where 1 = CRM and 2 = RM analysis listed in mass % except \* which is mg/kg

#	Number	As	Sb	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Sn	Ti
2	CZ CM-2B	0.12	0.020	0.247	0.894	0.082	0.0114	1.95	0.99	1.20	1.53	0.046	.	0.45	0.33	0.091	0.342
1	12X 12749X	0.081	.	0.176	1.41	0.023	0.066	0.48	0.253	0.47	0.453	0.202	.	0.426	0.195	0.018	0.0178
1	IMZ 120	0.065	0.031	0.60	0.40	(0.049)	0.026	0.34	0.10	0.085	0.20	0.033	.	.	.	0.008	.
1	12X 15266V	0.0640	.	0.455	1.240	0.0344	0.0258	0.674	0.226	1.317	3.49	0.526	.	0.286	0.298	0.0082	.
1	12X 350C	0.057	.	0.159	0.758	0.0296	0.040	0.467	0.196	0.160	0.335	0.290	.	0.030	0.147	0.0382	0.076
1	IRSID 1656	0.055	.	0.477	0.730	0.027	0.013	0.277	.	(0.048)	(0.017)	(0.002)	.	.	(0.007)	.	.
1	12X 354B	0.023	.	0.252	5.03	0.0478	0.0105	0.200	0.0679	0.082	0.0487	0.0150	.	0.0237	0.0328	0.0154	0.0248
1	<b>BS 1762</b>	0.025	(0.02)	0.363	2.04	0.032	0.037	0.38	0.133	1.16	0.929	0.049	.	0.064	0.347	0.079	0.096
1	ECRM 055-2D	0.0187	0.00376	0.5199	0.687	0.0102	0.0205	0.3094	0.2089	0.3121	0.3217	.	.	0.0257	0.0960	0.0162	0.00104
1	SS 55	0.013	0.002	.	.	.	.	.	.	0.23	0.22	0.028	.	.	0.16	0.046	0.013
1	12X 357D	0.0127	0.018	0.312	0.219	0.0101	0.066	0.211	0.203	0.188	0.21	0.138	.	0.198	0.025	0.0145	0.074
1	IMZ 68	0.0057	0.0020	0.102	0.346	0.028	0.015	0.13	0.166	0.049	0.33	.	.	0.008	.	0.0066	0.0033
1	<b>BS 1030</b>	0.0055	0.0024	0.331	0.682	0.0101	0.0299	0.261	0.269	0.078	0.124	0.0014	.	0.0069	0.0182	0.0114	0.0005
1	VS UG90	0.0044	0.0011	0.34	0.286	0.0079	0.012	0.221	0.200	0.265	0.261	0.037	0.032	.	0.046	.	0.039
1	VS UG89	0.0043	0.0011	0.92	0.76	0.0085	0.01	0.385	0.373	0.51	0.420	0.01	0.007	.	0.044	.	0.012
1	VS UG92	0.0027	0.0005	0.69	0.79	0.05	0.0029	1.98	0.111	0.155	0.200	0.091	0.08	.	0.119	.	0.022
1	IRSID 1670	0.0018	.	0.0011	0.3981	0.0128	0.0075	0.0046	0.0134	0.0142	0.0174	0.0479	.	0.0018	0.0009	0.0017	0.0078
1	VS UG88	0.0007	0.0003	0.62	1.26	0.0026	0.0043	1.22	0.171	0.52	0.474	0.01	0.009	.	0.104	.	0.107
1	VS UG91	0.0004	0.00009	0.49	.	0.0038	0.0021	2.23	0.057	0.039	0.064	0.048	0.048	.	0.058	.	0.038
1	SS 458/2	.	0.089	0.198	0.479	0.0281	0.0314	0.504	.	.	.	0.055	0.053	0.198	.	.	.
1	SS 457/2	.	0.050	0.307	0.327	0.0098	0.0448	0.105	.	.	.	0.088	0.084	0.0217	.	.	.
1	SS 56	.	0.005	.	0.32	.	.	.	0.36	.	.	0.005	.	0.023	.	.	.

Number	B	Bi	Ca*	Ce*	Mg*	N	Nb	O*	Pb	Se	Ta	V	W	Zn	Zr	Units	
CZ CM-2B	0.0010	.	.	.	.	0.0062	(0.58)	.	0.087	.	.	0.109	0.22	.	0.013	~39 mm Ø x ~25 mm	
12X 12749X	.	.	.	.	.	.	.	.	0.016	.	.	0.068	0.036	.	.	~40 mm Ø x ~15 mm	
IMZ 120	.	.	.	.	.	0.0115	.	.	0.077	.	.	.	.	.	.	40 mm Ø x 40 mm	
12X 15266V	.	.	.	.	.	.	1.438	.	.	.	0.116	0.106	.	.	.	~40 mm Ø x ~15 mm	
12X 350C	.	.	.	.	.	.	.	.	.	.	.	0.0115	0.260	.	.	~40 mm Ø x ~15 mm	
IRSID 1656	.	.	.	.	.	.	.	.	.	.	.	(0.002)	.	.	.	40 mm Ø x 35 mm	
12X 354B	.	.	.	.	.	0.0027	0.0802	.	.	.	.	0.0204	0.0248	.	.	~40 mm Ø x ~15 mm	
<b>BS 1762</b>	0.0048	.	(20)	.	(3)	0.017	0.074	64	(0.011)	Fe:93.9	(0.03)	0.193	0.029	(0.01)	(0.01)	37 mm Ø x 25 mm <b>17025</b>	
ECRM 055-2D	.	.	.	.	.	0.01069	.	.	.	.	.	0.00245	0.0166	.	.	38 mm Ø x 25 or 30 mm	
SS 55	.	.	.	.	.	.	.	.	.	.	.	.	0.12	.	.	38 mm Ø x 19 mm	
12X 357D	0.0036	0.0024	.	.	.	0.011	.	0.040	0.0057	.	.	0.127	0.0213	.	0.0049	~40 mm Ø x ~15 mm	
IMZ 68	.	.	.	.	.	0.0086	.	.	.	.	.	0.046	.	.	.	38 mm Ø x 20 mm	
<b>BS 1030</b>	0.0003	.	12	.	(2)	0.0107	(0.0004)	50	0.0005	.	(0.001)	0.031	0.0012	last	(0.0002)	38 mm Ø x ~7 mm <b>17025</b>	
VS UG90	.	.	.	.	.	0.015	.	.	.	.	.	.	.	.	.	.	~47 mm Ø x ~30 mm
VS UG89	.	.	.	.	.	0.017	0.0043	.	0.0003	.	.	0.021	.	.	.	.	~47 mm Ø x ~30 mm
VS UG92	.	.	.	.	.	0.016	0.034	.	0.00017	.	.	0.024	.	.	.	.	~47 mm Ø x ~30 mm
IRSID 1670	0.0007	.	.	(2)	.	0.0016	(0.0003)	.	.	.	.	(0.0005)	.	.	.	.	37 mm Ø x 30 mm
VS UG88	.	.	.	.	.	0.020	0.059	.	0.00015	.	.	0.117	.	.	.	.	~47 mm Ø x ~30 mm
VS UG91	.	.	.	.	.	0.010	0.097	.	0.00006	.	.	0.049	.	.	.	.	~47 mm Ø x ~30 mm
SS 458/2	0.0069	.	.	.	.	0.0510	.	0.0140	.	.	.	0.105	.	.	(0.064)	38 mm Ø x 19 mm	
SS 457/2	0.0046	.	.	.	.	0.0174	.	0.0098	.	.	.	0.153	.	.	0.025	38 mm Ø x 19 mm	
SS 56	0.001	.	.	.	.	.	.	0.014	.	.	.	0.057	.	.	.	38 mm Ø x 19 mm last	

## RM

## BISMUTH STEEL

Number	Bi	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	N
BS 4140A	0.105	0.40	0.84	0.021	0.076	0.21	0.15	0.15	0.97	0.016	0.005	0.010	0.16	0.0098
BS 53MOD	0.102	1.01	0.36	0.011	0.012	0.26	0.070	0.072	1.37	0.019	0.004	0.007	0.024	0.0086
BS 4150MOD	0.070	0.47	0.90	0.024	0.079	0.21	0.19	0.15	1.01	0.012	0.005	0.012	0.21	0.0087

Number	Ca	O	Pb	Sn	Ti	V	Units
BS 4140A	(0.0003)	(0.0025)	(0.001)	0.011	(0.003)	0.004	38 mm Ø x ~7 tp 19+ mm
BS 53MOD	(0.001)	(0.002)	0.0005	0.008	.	0.005	38 mm Ø x ~12 to 19 mm last
BS 4150MOD	0.0010	(0.003)	0.0010	0.013	(0.002)	0.008	38 mm Ø x ~7 mm last

## CALCIUM IN STEEL

# = Class, where 1 = CRM and 2 = RM analysis listed in mass % except \* which is mg/kg

#	Number	Ca	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	V
1	<b>BS HiCal-1</b>	0.0140	0.271	1.00	(0.007)	0.0007	1.29	0.152	3.28	1.55	0.070	.	0.0024	0.379	.	0.0027
1	SS 115	0.0058	0.6224	0.682	0.0123	0.00093	0.2078	.	0.0196	0.0198	0.0527	.	.	.	0.0067	.
1	SS 116	0.0036	0.617	0.6756	0.0092	0.00176	0.201	.	0.0155	0.0141	0.0587	.	.	.	0.0069	.
1	<b>BS 1020</b>	0.0022	0.210	0.568	0.0058	0.0249	0.250	0.184	0.059	0.109	0.0006	.	0.0070	0.018	0.0109	0.0363
2	HRT FE2009-N	0.0020	0.12	0.55	0.010	0.003	0.32	0.08	0.25	2.56	0.030	.	.	1.02	.	0.015
2	BS 4150MOD	0.0010	0.47	0.90	0.024	0.079	0.21	0.19	0.15	1.01	0.012	.	0.012	0.21	0.0087	0.008
1	<b>BS 4130</b>	0.0007	0.303	0.541	0.0105	0.0113	0.245	0.221	0.088	0.924	0.0242	.	0.0065	0.168	0.0072	0.0037
2	BS 4942	0.0006	0.414	0.56	0.015	0.021	0.22	0.165	0.16	0.97	(0.004)	.	0.010	0.54	0.0080	0.28
1	<b>BS PP20</b>	0.0003	0.382	1.41	0.018	0.0070	0.262	0.119	1.00	1.94	0.0132	.	0.0145	0.212	0.0080	0.066
1	IMZ 111	0.0003	0.106	0.31	0.010	0.039	0.55	0.036	0.23	0.072	0.017	0.007	.	0.084	0.0133	0.022
2	TL 1669	0.00017	0.00226	0.0955	0.0137	0.0100	0.0093	0.0217	0.0160	0.0246	0.03553 (tot)	.	0.0019	0.0011	0.0024	(0.0006)

Number	As	B	Bi	Nb	O	Pb	Sb	Sn	Ti	W	Zr	Other
<b>BS HiCal-1</b>	0.0022	(0.0001)	.	(0.002)	.	(0.0005)	.	(0.0002)	0.0037	(0.0009)	(0.0008)	~38 mm Ø x ~30 mm <b>17025</b>
SS 115	.	.	.	.	.	.	.	.	0.0027	.	.	38 mm Ø x 19 mm
SS 116	.	.	.	.	.	0.00012	.	.	0.00171	.	.	44 mm Ø x 19 mm
<b>BS 1020</b>	0.0074	(0.0001)	.	(0.0003)	0.0046	(0.0002)	(0.0018)	0.0090	(0.0005)	(0.0004)	(0.0005)	44 mm Ø x ~7 or 19+ mm <b>17025</b>
HRT FE2009-N	.	.	.	.	.	.	.	.	.	.	Zn: 0.004	40 mm Ø x 40 mm
BS 4150MOD	0.005	.	0.070	.	(0.003)	0.0010	.	0.013	(0.002)	.	.	38 mm Ø x ~7 or 19 mm last
<b>BS 4130</b>	0.0048	(0.0002)	.	0.0015	0.0015	(0.00003)	(0.0021)	0.0099	0.0009	0.0011	(0.0002)	38 mm Ø x ~17 or 19 mm last
BS 4942	0.005	.	.	.	(0.0021)	.	.	0.014	.	.	.	38 mm Ø x ~7 mm last
<b>BS PP20</b>	0.0049	0.00011	.	0.0048	(0.0010)	.	0.0013	0.0069	0.0007	0.0058	.	38 mm Ø x ~7 or 19+ mm <b>17025</b>
IMZ 111	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
TL 1669	0.0017	0.00038	.	0.00046	.	0.00013	0.00049	0.0071	0.0504	.	(0.00021)	38 mm Ø x 25 mm Zn: 2.7*

## CRM AL, Ca, AND N IN LOW ALLOY STEEL

Number	Al	Ca	N	Units
IMZ 133	.	.	<b>0.0360</b>	40 mm Ø x 40 mm
IMZ 131	0.0043	.	<b>0.0333</b>	40 mm Ø x 40 mm
IMZ 135	0.0274	0.0008	<b>0.0238</b>	40 mm Ø x 40 mm
IMZ 169	0.075	.	<b>0.0193</b>	40 mm Ø x 40 mm
IMZ 141	0.0071	.	<b>0.0154</b>	40 mm Ø x 40 mm
IMZ 130	0.0046	0.0024	<b>0.0153</b>	40 mm Ø x 40 mm
IMZ 139	(0.029)	0.0031	<b>0.0113</b>	40 mm Ø x 40 mm
IMZ 132	0.0021	0.0002	<b>0.0097</b>	40 mm Ø x 40 mm
IMZ 137	0.0017	0.00025	<b>0.0083</b>	40 mm Ø x 40 mm
IMZ 140	0.0307	0.0015	<b>0.0083</b>	40 mm Ø x 40 mm
IMZ 138	0.0022	.	<b>0.0063</b>	40 mm Ø x 40 mm
IMZ 134	0.0124	0.0005	.	40 mm Ø x 40 mm
IMZ 136	0.0034	0.00031	.	40 mm Ø x 40 mm

## C-Mo and Cr-Mo STEEL XRF SET

# = class, where 1 = CRM ISO **17025** and 2 = RM,

Set Part Number: BS MOLY-5

AVAILABLE INDIVIDUALLY

~7 mm discs

#	Grade	Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Co	N	Sn	V
2	C-.5Mo	4419	BS 3952	0.208	0.546	0.011	0.021	0.264	0.202	0.112	0.105	0.519	0.048	.	(0.0005)	.	.
1	1.25Cr-.5Mo	F-11	<b>BS 45B</b>	0.140	0.502	0.0068	0.017	0.583	0.101	0.136	1.14	0.60	0.030	0.0090	0.0066	0.0069	0.0083
1	2.25Cr-1Mo	F-22	<b>BS 46B</b>	0.126	0.472	0.0087	0.0187	0.219	0.128	0.081	2.28	1.00	0.020	0.0074	0.0100	0.0073	0.0073
2	5Cr-.5Mo	F-5	BS 47A	0.130	0.44	0.017	0.015	0.27	0.11	0.12	4.22	0.47	0.015	0.011	0.018	0.008	0.016
1	9Cr-1Mo	F-9	<b>BS 48B</b>	0.110	0.365	0.0228	0.0068	0.75	0.070	0.165	8.78	0.949	0.0157	0.0165	0.0088	0.0049	0.033

## CRM EPMA SETS

available in sets only, as grouped 4x10x15mm

Number	Cr	Number	Ni
NMIJ 1001-a	5.00	NMIJ 1006-a	5.04
NMIJ 1002-a	14.96	NMIJ 1007-a	10.05
NMIJ 1003-a	19.87	NMIJ 1008-a	20.02
NMIJ 1004-a	29.84	NMIJ 1009-a	39.92
NMIJ 1005-a	39.69	NMIJ 1010-a	60.07

Cr-Mo STEEL (Cr > 1, Mo > 0.1)

# = Class, where 1 = CRM and 2 = RM \* Provisional Analysis

Main table with columns for chemical elements (Cr, Mo, C, Mn, P, S, Si, Cu, Ni, Al, As, Co, N, Sn, V) and rows for various steel grades like BS 48B, BS 9905A, IARM 37C, etc.

Continuation table with columns for chemical elements (B, Ca, Nb, O, Pb, Sb, Ta, Ti, W, Zr) and rows for various steel grades with additional analysis data and units.



LEADED STEEL

# = Class, where 1 = CRM and 2 = RM OES regularly requires extension of preburn time

Table with columns: #, Number, Pb, C, Mn, P, S, Si, Cu, Ni, Cr, Al, As, Co, Mo, N, Sn, V. Lists various steel grades and their chemical compositions.

Table with columns: Number, B, Ca, Nb, O, Sb, Ti, W, Zn, Grade, Units. Provides detailed specifications and units for various steel grades.

RM LEADED AND BISMUTH STEEL XRF SET

Part Number: BS PB-BI-7 AVAILABLE INDIVIDUALLY -7 mm discs 17025

Table with columns: Grade, Number, C, Mn, P, S, Si, Cu, Ni, Cr, Mo, Al, Bi, Pb, Sn, V, N. Lists RM steel grades and their XRF analysis results.

MANGANESE STEEL

14X:~400x~15~17mm BS:320xx~15~17mm CZ:~390x25mm DSZU:390x20mm ECRM:350x25mm IMN:50~560x15mm NCS:360x36mm SS:48x42x12mm VS:~380x~18mm

Table with columns: #, Number, Mn, C, P, S, Si, Cu, Ni, Cr, Al, Mo, N, Nb, Sn, V, Other. Lists manganese steel grades and their detailed chemical compositions and properties.

\*\* IRSID 1833 also contains As: 0.0034, Co: 0.0089, Pb: 0.00007, and Ti: 0.0011. Sample size 35 mm Ø x 25 mm.

CRM MANGANESE STEEL SET

AVAILABLE IN SET/6 ONLY 30 mm Ø x 24 mm

Table with columns: Number, C, Mn, P, S, Si, Cu, Ni, Cr, B, Co, Mo, N, Ti, V. Lists CRM manganese steel grades and their chemical compositions.



## RESULFURIZED STEEL

# = Class, where 1 = CRM and 2 = RM

OES regularly requires extension of preburn time to analyze correctly

#	Number	S	C	Mn	P	Si	Cu	Ni	Cr	Al	Co	Mo	N	Sn	Ti	V
1	IMZ 123	0.38	0.25	1.57	0.030	0.23	0.093	0.057	0.16	0.032	.	.	0.0171	(0.007)	.	.
1	ECRM 085-1D	0.336	0.067	0.977	0.062	0.008	0.291	.	.	.	0.019	.	.	.	.	0.0021
2	BS 66K	0.322	0.051	0.86	0.062	(0.004)	0.013	0.012	0.006	0.002	0.005	0.003	(0.0074)	.	<0.002	0.001
1	<b>BS 66L</b>	0.315	0.065	0.844	0.061	(0.002)	0.007	0.015	0.026	0.0008	0.0035	0.0012	0.0031	(0.0010)	(<0.0010)	0.0006
1	14X 12130A	0.305	0.0871	1.219	0.061	0.022	0.0201	0.0345	0.0505	0.0024	.	0.0102	0.0097	0.0054	.	.
1	IARM 199C	0.281	0.469	1.55	0.0155	0.21	0.193	0.085	0.190	0.0019	0.007	0.0293	0.0070	0.0084	0.0016	(0.0037)
1	IMZ 124	0.28	0.10	0.60	0.082	(0.019)	0.060	0.046	0.11	0.005	.	.	0.0059	0.009	.	.
1	<b>BS 1144A</b>	0.271	0.468	1.43	0.0108	0.214	0.147	0.063	0.076	0.0020	0.0064	0.0154	0.0095	0.0079	(0.0008)	0.0015
1	<b>BS 1144</b>	0.243	0.483	1.55	0.022	0.262	0.462	0.097	0.193	(0.002)	0.011	0.017	0.0093	0.0113	(0.002)	0.0039
1	14X MSFM 4A	0.224	0.226	1.141	0.0386	0.469	0.429	6.22	1.69	(0.007)	0.0253	0.974	0.0220	0.0141	.	0.0151
1	IMZ 122	0.21	0.27	1.33	0.073	0.43	0.25	0.25	0.19	(0.027)	.	.	0.0110	0.12	.	.
1	14X 606M36TA	0.196	0.378	1.574	0.0359	0.167	0.179	0.0931	0.163	0.0071	.	0.272	0.0096	0.0103	.	.
1	14X 11390A	0.190	0.420	1.040	0.0342	0.198	0.0395	0.0239	0.0609	0.0026	.	0.0067	0.0042	0.0022	.	.
1	ECRM 058-2D	0.1712	0.424	1.186	0.0098	0.1080	0.261	0.199	0.1211	.	.	0.0589	0.0107	.	.	.
1	14X MSFM3G	0.147	0.438	1.809	0.0297	0.292	0.205	0.161	0.454	(0.18)	0.0494	0.390	0.0206	0.0378	.	0.0199
1	IARM 29E	0.121	0.193	1.19	0.0157	0.239	0.253	0.082	0.105	0.0032	0.008	0.0269	0.0093	0.0109	0.0014	0.0255
1	14X 11170A	0.120	0.154	1.129	0.0133	0.151	0.1101	0.0877	0.1126	0.0023	.	0.0317	0.0112	0.0110	.	.
2	BS 65C	0.115	0.150	1.19	0.007	0.24	0.24	0.063	0.066	(0.007)	0.012	0.0084	.	.	.	0.002
2	BS 66B	0.112	0.418	1.56	0.018	0.017	0.028	0.032	0.093	(0.001)	0.005	0.019	0.0056	0.0016	(0.001)	0.0014
1	IARM 348A	0.102	0.384	1.46	0.0121	0.270	0.230	0.081	0.123	(0.002)	(0.010)	0.026	(0.010)	0.0112	0.0015	0.0029
1	IARM 307A	0.096	0.163	1.44	0.0113	0.281	0.190	0.197	0.104	0.032	(0.010)	0.045	0.0108	0.0090	0.0015	(0.0028)
1	<b>BS 3993</b>	0.094	0.152	1.16	0.012	0.260	0.111	0.045	0.072	0.002	0.006	0.010	0.0071	0.006	(0.0008)	0.002
1	IMZ 121	0.097	0.39	1.18	0.057	(0.056)	0.032	0.029	0.036	0.016	.	.	0.0125	0.059	.	.
1	12X 15253T	0.0821	0.222	1.208	0.0900	0.347	0.266	0.991	2.022	0.0242	0.265	1.039	0.029	0.309	.	0.276
2	BS 4150MOD	0.079	0.47	0.90	0.024	0.21	0.19	0.15	1.01	0.012	0.012	0.21	0.0087	0.013	(0.002)	0.008
2	BS 42A	0.078	0.52	1.08	0.012	0.258	0.285	0.147	0.80	0.025	(0.007)	0.195	0.008	.	.	0.004
1	12X 15217R	0.078	0.166	0.885	0.064	1.392	0.257	0.860	1.011	0.081	(0.193)	0.311	0.014	0.058	.	0.607
1	NM 307	0.073	1.03	0.52	0.073	0.22	.	.	1.19	.	.	.	.	.	.	.
2	<b>BS 42</b>	0.073	0.516	1.24	0.021	0.235	0.252	0.183	0.67	0.020	0.012	0.190	0.0080	0.012	(0.003)	0.003
1	12X 15255R	0.067	0.392	1.09	0.080	1.01	0.288	0.317	1.49	0.161	0.045	0.113	0.0058	0.106	(0.052)	0.491
1	KUT B2/2	0.064	0.065	1.22	0.087	(0.38)	0.32	1.49	.	0.10	.	1.06	.	.	(0.25)	0.87
1	<b>BS 4150MOD-A</b>	0.062	0.503	1.12	0.0172	0.253	0.192	0.095	0.799	0.0023	0.0070	0.170	0.0081	0.0090	0.0018	0.029
1	IMZ 125	(0.057)	0.029	0.95	(0.018)	0.15	0.044	0.023	0.18	(0.007)	.	.	.	0.002	.	.
1	KUT B12	0.048	0.43	0.76	0.028	0.34	0.41	1.62	1.32	0.007	0.011	0.21	.	0.032	0.011	0.026
1	KUT B4	0.043	0.55	1.07	0.047	1.72	0.49	.	.	.	.	.	.	.	.	.
1	IARM 381A	0.043	0.272	1.16	0.013	0.269	0.379	0.185	0.129	0.0023	0.011	0.0341	(0.014)	0.0137	(0.002)	0.0299
1	NM 304	0.033	0.19	0.29	0.093	0.082	.	(0.007)	.	.	.	.	.	.	.	.
	Number	As	B	Bi	Ca	Nb	O	Pb	Sb	W	Zn	Zr	Unite			
	IMZ 123	0.033	.	.	.	.	.	0.030	0.030	.	.	.	40 mm Ø x 40 mm			
	ECRM 085-1D	.	.	.	.	.	.	0.0010	0.0073	.	0.0025	.	38 mm Ø x 25 or 30 mm			
	BS 66K	.	.	.	.	.	.	.	.	.	.	.	41 mm Ø x -7 or 19+ mm			
	<b>BS 66L</b>	0.0020	(<0.0003)	.	(<0.0010)	(0.0012)	.	0.0007	0.0021	(<0.0010)	.	.	44 mm Ø x -7 or 19+ mm			17025
	14X 12130A	0.0016	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm			
	IARM 199C	0.0059	0.0012	0.003	(0.0011)	0.0016	0.0037	(0.001)	(0.003)	0.0023	(0.0006)	.	31 mm Ø x 2 or 18 mm			
	IMZ 124	0.004	.	.	.	.	.	(0.002)	0.002	.	.	.	40 mm Ø x 40 mm			
	<b>BS 1144A</b>	0.0052	(0.0003)	Fe:97.3	(0.0005)	(0.002)	0.0019	(0.0006)	(0.002)	(0.0009)	.	(0.0006)	38 mm Ø x -7 or 19+ mm			17025
	<b>BS 1144</b>	0.009	.	.	(0.004)	.	0.0016	(0.001)	.	(0.003)	.	last	38 mm Ø x -15 mm			17025
	14X MSFM 4A	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 15 mm			
	IMZ 122	0.007	.	.	.	.	.	(0.020)	0.019	.	.	.	40 mm Ø x 40 mm			
	14X 606M36TA	0.0085	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm			
	14X 11390A	0.0028	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm			
	ECRM 058-2D	0.0095	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 25 or 30 mm			
	14X MSFM3G	.	0.0043	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm			
	IARM 29E	0.0085	0.0007	.	0.0012	0.0024	(0.005)	(0.001)	(0.003)	.	(0.004)	.	31 mm Ø x 2 or 18 mm			
	14X 11170A	0.0044	.	.	.	.	.	0.0011	.	.	.	.	-40 mm Ø x -15 mm			
	BS 65C	.	.	.	.	.	.	.	.	.	.	.	37 mm Ø x -7 or 19+ mm			
	BS 66B	.	0.0003	.	.	.	.	.	.	.	.	.	41 mm Ø x -7 or 19+ mm			
	IARM 348A	(0.007)	(0.0013)	<0.02	0.0010	0.027	(0.003)	(0.002)	(0.003)	(0.009)	<0.003	(0.003)	31 mm Ø x 2 or 18 mm			
	IARM 307A	0.008	<0.005	<0.02	<0.0005	(0.002)	(0.003)	(0.002)	<0.004	(0.005)	<0.002	(0.002)	31 mm Ø x 2 or 18 mm			
	<b>BS 3993</b>	0.004	.	.	(0.0002)	.	(0.0030)	.	.	.	.	.	38 mm Ø x -7 or 19+ mm			25(pre-17025)
	IMZ 121	0.002	.	.	.	.	.	0.011	0.017	.	.	.	40 mm Ø x 40 mm			
	12X 15253T	0.0216	.	.	.	0.374	.	Ta:0.007	0.276	.	.	.	-40 mm Ø x -15 mm			
	BS 4150MOD	0.005	.	0.070	0.0010	.	(0.003)	0.0010	.	.	.	last	38 mm Ø x -7 mm			
	BS 42A	.	.	.	.	.	.	.	.	.	.	.	37 mm Ø x 19 mm			last
	12X 15217R	.	0.0044	.	.	0.102	.	.	.	0.100	.	.	-40 mm Ø x -15 mm			
	NM 307	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 25 mm			
	<b>BS 42</b>	(0.004)	.	.	.	(0.002)	.	.	.	(0.002)	.	.	44 mm Ø x -7 or 19+ mm			17025
	12X 15255R	.	.	.	.	0.203	.	Ta:0.034	.	0.143	.	(0.011)	-40 mm Ø x -15 mm			
	KUT B2/2	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 39 mm			
	<b>BS 4150MOD-A</b>	0.0038	(0.0004)	.	(0.0007)	(0.002)	0.0017	(0.0004)	(0.002)	0.0026	Fe:96.7	(0.0005)	38 mm Ø x -7 or 19+ mm			17025
	IMZ 125	0.065	.	.	.	.	.	.	0.014	.	.	.	40 mm Ø x 40 mm			
	KUT B12	0.011	0.0035	.	.	0.022	.	.	.	.	.	(0.002)	30-35 mm Ø x 39 mm			
	KUT B4	.	.	.	.	.	.	.	.	.	.	0.09	30-35 mm Ø x 39 mm			
	IARM 381A	0.0055	.	.	.	0.0018	.	.	.	(0.003)	.	.	31 mm Ø x 2 or 18 mm			
	NM 304	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 25 mm			

RM RESULFURIZED STEEL XRF SET Part Number: BS RESUL-4 AVAILABLE INDIVIDUALLY -7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Co	N	Sn	V	As
1117	BS															

## SILICON STEEL

# = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Mo	N	Sn	Ti
2	CZ SST-4A	4.73	0.062	0.376	0.031	0.020	0.111	0.082	0.105	0.514	.	0.019	0.0058	0.025	0.035
2	CZ SST-3A	3.27	0.035	0.221	0.007	0.0093	0.096	0.061	0.043	0.009	.	0.036	0.0088	0.015	0.009
1	SRM 1218	(3.2)	0.0029	0.014	(0.002)	0.0011	0.003	(0.002)	0.006	0.005	.	(0.003)	.	.	(0.004)
1	SRM 1135	3.19	0.027	0.094	0.006	0.026	0.056	0.050	0.022	0.0028	.	0.014	.	0.004	.
2	CZ SST-2A	3.07	0.083	0.160	0.026	0.0089	0.205	0.066	0.138	0.010	.	0.054	0.0078	0.055	0.016
1	SRM 1134	2.889	0.0261	0.2751	0.0276	0.0095	0.0707	0.0375	0.0198	(0.329)	.	0.0087	.	0.0034	.
2	CZ SST-1A	2.57	0.072	0.062	0.041	0.0043	0.654	0.155	0.209	0.061	.	(0.002)	0.0059	0.110	0.004
1	VS UG91	2.23	0.49	.	0.0038	0.0021	0.057	0.039	0.064	0.048	0.048	0.058	0.010	.	0.038
1	12X 15251U	2.05	1.017	0.910	0.0253	0.0215	0.1194	0.896	0.612	0.1085	.	0.205	0.0031	0.0108	.
1	VS UG92	1.98	0.69	0.79	0.05	0.0029	0.111	0.155	0.200	0.091	0.08	0.119	0.016	.	0.022
1	KUT T4/1	1.97	0.17	0.23	0.012	0.041	0.16	0.077	0.24	.	.	.	.	.	( $<0.005$ )
1	12X 15259Q	1.81	0.603	0.401	0.0401	0.0704	0.200	4.02	0.512	0.1488	.	0.407	0.0151	0.053	.
1	ECRM 196-2D	1.808	0.0060	0.364	0.00369	0.00065	0.0057	0.0401	0.0282	0.2167	.	0.0142	0.00178	0.00047	0.00253
1	VS UG4/5	1.80	0.56	1.26	(0.008)	(0.006)	0.098	0.68	0.17	0.010	.	0.087	.	0.17	.
1	NCS HS11751a	1.76	0.574	0.792	0.020	0.014	0.011	0.019	0.024	.	.	.	.	.	.
2	CZ LA-2E	1.725	0.081	0.111	0.060	0.044	0.577	2.015	0.149	0.357	.	0.652	0.0071	0.087	0.343
1	ECRM 186-1D	1.72	0.610	0.870	0.022	0.035	0.281	0.190	0.218	0.014	.	0.048	.	.	.
1	12X 44220A	1.662	0.417	0.874	0.0050	0.0009	0.031	1.89	0.846	0.029	.	0.401	0.0030	0.0019	.
1	VS UC111	1.64	0.52	0.625	0.0028	0.0035	0.065	0.036	0.058	0.049	.	0.039	.	.	0.025
1	VS UG1/9	1.63	0.63	0.84	0.030	0.017	0.020	0.105	0.046	0.027	.	0.135	(0.002)	(0.002)	0.069
1	IARM 340A	1.63	0.414	0.755	0.011	0.001	0.103	1.80	0.84	0.062	.	0.39	0.0020	0.005	0.0098
1	IARM 342A	1.63	0.257	1.37	0.006	0.0051	0.110	1.76	0.38	0.019	.	0.42	0.0102	0.021	0.0028
1	VS UG4/10	1.61	0.695	0.834	0.031	0.0060	0.050	0.156	0.130	0.064	.	0.089	0.0192	.	0.0044
1	KUT B1/1	1.58	0.97	0.205	0.017	0.032	0.14	3.96	1.66	.	.	.	.	.	.
1	VS UG1/10	1.51	0.51	0.659	0.0053	0.0042	0.096	0.190	0.067	0.015	.	0.051	0.0164	0.0030	0.016
1	KUT A11/1	(1.46)	0.043	0.21	0.011	0.0137	0.047	0.04	0.02	0.02	.	1.20	.	0.002	0.17
1	VS UC4/6	1.25	0.59	1.23	(0.003)	0.0008	0.169	0.47	0.400	0.032	.	0.083	( $<0.0005$ )	0.017	0.131
1	VS UG87	1.25	0.59	1.18	0.026	0.022	0.030	0.50	0.260	0.024	0.02	0.044	0.010	.	0.103
1	VS UG1/5	1.23	0.62	0.79	(0.02)	(0.03)	(0.01)	0.048	0.069	0.022	.	0.061	.	.	0.045
1	VS UG88	1.22	0.62	1.26	0.0026	0.0043	0.171	0.52	0.474	0.01	0.009	0.104	0.020	.	0.107
1	DSZU C046	1.21	0.785	0.257	0.025	0.0153	0.211	1.47	2.67	0.47	.	0.69	0.0099	0.0033	0.115
1	KUT A12	1.19	0.031	0.31	0.014	0.082	0.18	2.43	1.25	0.18	.	0.47	.	.	0.05
1	12X 15258P	1.01	0.392	1.23	0.067	0.032	0.109	0.497	0.631	0.087	.	0.361	.	0.071	0.100
1	SS 603/2	0.97	0.79	0.236	0.020	0.056	(0.05)	(0.03)	(0.04)	0.076	.	(0.004)	.	.	.
1	SS 405/2	0.947	0.044	0.903	0.0095	0.058	0.022	0.102	0.206	0.330	.	0.025	(0.011)	.	.
1	SS 113	0.931	0.837	1.207	0.0595	0.0294	0.179	0.0784	1.248	0.0151	.	0.056	0.0109	0.0067	0.0390
1	SS 604/2	0.75	0.199	1.91	0.016	0.072	(0.07)	(0.09)	(0.06)	0.008	.	(0.02)	.	.	.

#	Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Mo	N	Sn	Ti
---	--------	----	---	----	---	---	----	----	----	----	-----	----	---	----	----

Number	As	B	Ca	Co	Nb	O	Pb	Sb	Ta	V	W	Zr	Units
CZ SST-4A	0.004	0.0006	.	0.012	.	.	0.008	(0.003)	.	0.031	0.026	(0.003)	~37 mm Ø x 25 mm
CZ SST-3A	(0.003)	0.0019	.	0.038	.	Zn:0.011	0.013	.	.	0.041	0.016	.	~37 mm Ø x 25 mm
SRM 1218	.	.	.	(0.002)	.	.	.	.	.	( $<0.001$ )	.	(0.002)	32 mm Ø x 19 mm
SRM 1135	.	.	.	.	.	.	.	.	.	$<0.01$	.	.	31 mm Ø x 19 mm
CZ SST-2A	.	0.0089	.	0.022	.	Zn:0.011	0.015	0.008	.	0.024	0.019	0.017	~37 mm Ø x 25 mm
SRM 1134	.	.	.	.	.	.	.	.	.	.	.	.	31 mm Ø x 19 mm
CZ SST-1A	(0.002)	0.0003	.	0.005	.	.	(0.002)	(0.002)	.	0.006	.	.	~37 mm Ø x 25 mm
VS UG91	0.0004	.	.	.	0.097	.	0.00006	0.00009	.	0.049	.	.	~47 mm Ø x ~30 mm
12X 15251U	.	.	.	0.228	0.266	.	.	.	.	0.391	0.0393	.	~40 mm Ø x ~15 mm
VS UG92	0.0027	.	.	.	0.034	.	0.00017	0.0005	.	0.024	.	.	~47 mm Ø x ~30 mm
KUT T4/1	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 39 mm last
12X 15259Q	.	.	.	0.141	0.249	.	.	.	.	0.139	0.49	.	~40 mm Ø x ~25 mm last
ECRM 196-2D	0.00033	0.00014	0.00071	0.0138	Mg:0.00075	.	.	.	.	0.00368	.	Zn:0.00019	38 mm Ø x 25 mm
VS UG4/5	.	.	.	.	0.053	.	.	.	.	0.054	0.14	.	~45 mm Ø x ~28 mm
NCS HS11751a	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
CZ LA-2E	0.083	0.0043	.	0.268	0.111	.	0.068	0.033	.	0.310	0.307	.	~37 mm Ø x 25 mm
ECRM 186-1D	.	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 25 or 30 mm
12X 44220A	0.0026	.	.	.	.	.	.	.	.	0.0764	.	.	~38 mm Ø x ~15 mm
VS UC111	.	.	.	.	.	.	.	.	.	0.058	0.056	.	~45 mm Ø x ~28 mm
VS UG1/9	(0.001)	(0.0003)	.	.	0.124	.	(0.002)	.	.	0.024	0.063	.	~45 mm Ø x ~28 mm
IARM 340A	(0.004)	0.0004	(0.0004)	0.006	0.015	(0.001)	(0.001)	0.0021	.	0.064	(0.005)	(0.002)	31 mm Ø x 2 mm
IARM 342A	(0.006)	0.0004	(0.0001)	0.008	(0.002)	0.0006	0.0008	0.0021	.	0.023	(0.005)	(0.002)	31 mm Ø x 2 or 18 mm
VS UG4/10	.	.	.	.	0.030	.	.	.	.	0.0239	0.006	.	~45 mm Ø x ~28 mm
KUT B1/1	.	.	.	.	.	.	.	.	.	.	.	0.001	30-35 mm Ø x 39 mm
VS UG1/10	.	.	.	.	0.091	.	.	.	.	0.042	0.074	.	~45 mm Ø x ~28 mm
KUT A11/1	.	.	.	.	0.16	.	.	< 0.001	.	0.46	.	.	30-35 mm Ø x 39 mm
VS UC4/6	(0.001)	.	.	(0.004)	(0.03)	.	.	(0.0005)	( $<0.0005$ )	0.051	0.111	.	~45 mm Ø x ~28 mm
VS UG87	0.116	.	.	.	.	.	.	0.00008	0.0012	0.0038	.	.	~47 mm Ø x ~30 mm
VS UG1/5	.	.	.	.	0.078	.	.	.	.	0.070	(0.01)	.	~45 mm Ø x ~28 mm
VS UG88	0.0007	.	.	.	0.059	.	0.00015	0.0003	.	0.117	.	.	~47 mm Ø x ~30 mm
DSZU C046	0.0020	(0.0004)	0.0007	0.006	(0.005)	.	.	.	.	0.72	0.47	.	40 mm Ø x 25 mm
KUT A12	0.007	.	.	0.012	(0.03)	.	.	0.013	.	0.042	.	.	30-35 mm Ø x 39 mm
12X 15258P	.	0.0100	.	0.310	0.133	.	.	.	(0.002)	0.378	0.125	.	~40 mm Ø x ~15 mm
SS 603/2	.	.	.	(0.01)	.	.	.	.	.	(0.001)	.	( $<0.005$ )	44 mm Ø x 19 mm
SS 405/2	.	.	.	.	.	.	.	.	.	0.411	.	.	38 mm Ø x 19 mm
SS 113	0.0020	0.0066	.	0.0415	0.0487	.	.	.	.	0.201	0.012	0.0029	44 mm Ø x 19 mm
SS 604/2	.	.	.	(0.01)	.	.	.	.	.	(0.001)	.	( $<0.005$ )	44 mm Ø x 19 mm

Number	As	B	Ca	Co	Nb	O	Pb	Sb	Ta	V	W	Zr	Units
--------	----	---	----	----	----	---	----	----	----	---	---	----	-------

LOW ALLOY STEEL WITH C > 0.3%

CONTINUED ON THE NEXT PAGE

# = Class, where 1=CRM, 2=RM, 3=RM no uncertainties

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Nb	Ti
1	VS UG0/9	1.33	0.208	0.0040	0.0045	0.170	0.307	0.36	0.55	0.139	(0.001)	.	0.024	0.0022	0.041	0.029
1	VS UG0/10	1.321	0.268	0.0090	0.0044	0.244	0.265	0.353	0.596	0.101	.	0.052	0.0120	0.0033	0.017	.
1	VS UG0/5	1.32	(0.2)	(0.01)	(0.007)	(0.2)	0.265	0.351	0.60	0.108	.	(0.05)	.	(0.01)	(0.01)	.
1	SS 402/2	1.311	0.288	0.0161	0.0138	0.111	0.302	0.808	0.652	0.161	.	.	0.140	0.0069	.	.
1	ECRM 035-2D	1.277	0.305	0.0038	0.011	0.216	0.0085	0.0190	0.0104	0.0193	.	0.0056	0.0230	.	.	0.0030
1	IMZ 65/2	1.19	0.27	0.013	0.007	0.13	0.059	0.067	0.079	0.030	.	.	.	.	.	.
1	DSZU C049	1.17	0.237	0.0166	0.0147	0.227	0.069	0.044	0.131	(0.005)	.	(0.003)	(0.002)	(0.007)	.	(0.003)
1	KUT A18	1.16	(1.99)	0.014	0.007	0.15	0.066	0.125	0.90	(0.02)	.	.	.	.	0.035	0.011
1	VS UG0/11	1.16	0.196	0.0054	0.0078	0.233	0.134	0.114	0.163	0.009	.	0.0109	0.011	0.005	.	0.0041
3	CZ CM-5B	1.09	1.28	0.021	0.012	0.39	0.13	0.23	2.07	0.083	.	0.022	0.10	0.0135	0.06	0.05
1	14X 72305A	1.085	0.349	0.0128	0.0028	0.206	0.149	0.089	0.425	0.0049	.	.	0.0231	0.0068	.	.
2	CZ CM-5C	1.04	1.17	0.029	0.021	0.54	0.151	0.42	2.45	0.063	.	0.022	0.132	0.014	0.014	0.031
1	VS UG9/9	1.04	0.310	0.0053	0.021	0.319	0.163	0.242	0.310	0.073	(0.003)	.	0.308	0.0027	0.0046	0.130
1	IMZ 172	1.03	0.71	0.018	0.047	0.21	0.128	0.12	4.47	0.062	.	0.012	0.95	0.0192	.	(0.002)
1	IARM 49E	1.03	0.364	(0.006)	(0.002)	0.248	0.076	0.043	1.43	0.024	.	(0.006)	0.017	(0.003)	(0.003)	0.0060
1	12X 52986A	1.023	0.372	0.0049	0.0011	0.246	0.077	0.0411	1.418	0.0258	(0.002)	.	0.0169	(0.002)	.	.
2	BS 53G	1.02	0.35	0.014	0.015	0.23	0.160	0.090	1.53	0.019	.	0.008	0.034	0.0084	.	(0.002)
1	NILAB 100LA D	1.002	0.333	0.012	0.018	.	0.019	0.027	1.517	0.005	.	0.007	0.012	0.0046	.	0.0007
1	IARM 324A	0.99	1.01	0.009	0.028	0.163	0.22	0.081	0.42	0.002	.	0.007	0.022	0.0082	0.014	0.0016
2	BS A485-1	0.98	1.10	0.019	0.004	0.62	0.16	0.13	1.07	0.017	.	0.010	0.029	0.0060	.	0.003
1	KUT B15	0.98	0.69	0.030	0.031	0.80	0.14	0.15	3.70	0.13	.	0.21	1.20	.	.	(0.32)
1	VS UG75	0.98	0.286	0.0127	0.0089	0.248	0.111	0.201	1.43	(0.03)	.	.	(0.01)	.	(0.01)	(0.001)
2	CZ LA-4C	0.95	1.63	0.021	0.012	0.07	0.056	0.045	1.78	0.048	.	(0.006)	0.008	0.012	0.053	(0.002)
1	VS UG9/11	0.94	0.895	0.027	0.0085	0.312	0.163	0.354	0.985	(0.04)	.	.	0.094	0.0119	.	0.010
1	12X 19965A	0.936	0.600	0.0196	0.0081	0.247	0.148	0.141	1.713	0.0256	.	.	0.210	0.0087	.	.
1	SS 401/2	0.935	1.19	0.026	0.0078	0.60	0.101	0.019	0.138	0.074	.	0.0042	0.49	0.0159	.	.
1	IMZ 119	0.93	1.15	0.018	0.006	0.16	0.042	0.049	0.062	0.010	0.007	.	.	0.0086	.	(0.0007)
1	VS UG89	0.92	0.76	0.0085	0.01	0.385	0.373	0.51	0.420	0.01	0.007	.	0.044	0.017	0.0043	0.012
1	VS UG21/6	0.83	0.74	(0.02)	(0.02)	0.312	0.346	0.47	0.50	.	.	.	.	.	.	.
2	IARM 172A	0.78	0.010	0.007	0.004	1.29	0.40	0.025	3.52	0.39	.	0.006	0.014	0.0004	0.004	0.003
1	SS 403/2	0.750	1.677	0.055	0.0381	0.209	0.221	0.223	0.463	0.0485	.	.	0.088	(0.010)	.	.
1	IMZ 64/2	0.75	0.47	0.012	(0.005)	0.22	0.12	0.081	0.090	0.020	.	.	.	.	.	.
1	VS UG8/11	0.728	1.97	0.036	0.0019	0.31	0.160	0.291	1.74	(0.01)	.	.	0.622	0.0138	.	.
1	ECRM 059-2D	0.721	0.495	0.0046	0.0084	0.188	0.0074	0.0198	0.0090	0.00045	0.00020	.	0.0018	0.0051	.	.
2	CZ CM-4B	0.72	0.50	0.023	0.012	0.80	0.40	1.40	2.23	0.025	.	0.115	0.33	0.013	0.071	0.12
1	SS 404/2	0.696	0.532	0.0479	0.0228	1.121	0.427	0.393	0.774	0.017	.	.	0.307	0.0089	.	.
1	IMZ 118	0.69	1.72	0.026	(0.049)	0.30	0.18	0.19	0.14	(0.014)	(0.004)	.	0.058	0.0120	.	.
1	IMZ 116	0.64	0.94	0.025	0.035	0.25	0.33	0.022	0.72	0.025	0.012	.	0.074	0.0130	.	(0.0008)
1	VS UG1/11	0.61	0.667	0.0098	0.011	1.74	0.155	0.080	0.108	0.032	.	0.0195	0.0067	0.0100	.	0.0047
1	VS UG96	0.60	0.52	0.0046	0.0029	0.290	0.256	0.396	0.399	0.031	.	.	0.0042	.	.	0.0025
1	VS UG119	0.55	0.70	0.012	(0.02)	1.63	0.207	0.142	0.195	0.039	.	.	0.0113	0.0047	.	0.0030
1	12X 10550	0.549	0.685	0.0184	0.0055	0.281	0.0290	0.0247	0.338	0.0325	.	.	0.0086	0.0051	.	.
1	12X 61500A	0.530	0.912	0.0104	0.0102	0.240	0.157	0.0976	1.023	(0.007)	0.0067	.	0.0195	.	.	.
2	CZ CM-6A	0.52	0.37	0.016	0.058	0.27	0.05	0.19	0.37	0.02	.	0.03	0.04	0.009	0.028	0.03
2	CZ BO-2B	0.515	0.745	0.0093	0.0016	0.309	0.100	0.057	0.212	0.0196	.	0.0055	0.006	0.004	.	0.0017
1	12X LA3C	0.500	1.693	0.0274	0.0442	0.163	0.213	0.280	0.375	0.0410	.	0.0475	0.303	0.0039	.	.
1	IARM 34C	0.50	0.739	0.0090	0.0011	0.30	0.078	0.085	0.914	0.068	.	0.005	0.022	0.0030	0.004	0.0045
2	BS 4941	0.490	0.79	0.012	0.017	0.27	0.106	0.074	0.96	0.024	.	0.008	0.039	0.0076	.	.
1	BS 43A	0.49	0.82	0.0074	0.025	0.252	0.18	0.24	0.92	(0.003)	.	0.008	0.059	0.0072	(0.0017)	(0.002)
1	IMZ 117	0.49	0.77	0.038	0.015	0.34	0.41	0.29	0.94	0.023	0.013	.	0.024	0.0154	0.041	(0.0014)
1	BS 1144	0.483	1.55	0.022	0.243	0.262	0.462	0.097	0.193	(0.002)	.	0.011	0.017	0.0093	(0.004)	0.002
1	IPT 503	0.456	0.682	0.027	0.027	0.218	0.129	0.063	0.160	0.018	.	0.006	0.020	0.0082	.	0.0011
1	SRM C1173	0.453	0.174	0.031	0.0092	1.38	0.204	4.04	2.63	.	.	.	1.46	.	.	0.037
1	12X 41450A	0.446	1.011	0.0093	0.0031	0.261	0.1318	0.187	1.194	0.0220	.	.	0.340	0.0080	.	.
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Nb	Ti
1	VS UG5/11	0.445	0.64	0.010	0.0037	0.29	0.146	1.40	0.912	.	.	0.0195	0.269	0.0119	.	.
2	BS XCCV	0.44	1.75	0.012	0.024	0.28	0.015	0.019	0.041	0.033	.	0.006	0.007	0.0056	(<0.002)	(0.002)
1	12X LA3B	0.439	1.176	0.0215	0.0379	0.16	0.173	0.300	0.357	0.0300	.	0.0300	0.302	0.0080	.	.
1	NM PC-4	0.43	0.80	0.043	0.045	0.34	.	.	0.26	.	.	.	.	.	.	.
1	IARM 30H	0.425	0.937	0.015	0.022	0.253	0.131	0.063	0.97	0.020	.	0.0071	0.199	0.0081	(0.003)	(0.0024)
1	IARM 305B	0.425	0.58	0.011	0.014	0.349	0.214	0.156	1.63	0.92	.	0.007	0.32	0.0044	0.002	0.0044
1	IARM 252D	0.423	0.842	0.0075	0.0128	0.256	0.270	0.424	0.468	0.024	.	0.0078	0.204	0.0068	0.0013	0.0012
1	BS 4340A	0.423	0.766	0.0062	(0.0008)	0.253	0.128	1.80	0.879	0.031	.	0.0111	0.259	0.0102	(0.002)	(0.0011)
1	SRM 1173	0.423	0.19	0.033	0.092	1.28	0.204	4.06	2.70	.	.	.	1.50	.	.	.
2	HRT FE2015-N	0.42	0.83	0.007	0.028	0.24	0.15	0.32	1.03	0.023	.	.	0.21	0.0057	.	.
1	BS 4340	0.418	0.695	0.0119	0.0187	0.279	0.149	1.79	0.807	0.028	.	0.0068	0.231	0.0080	(0.001)	0.0014
1	IARM 252C	0.416	0.92	0.025	0.008	0.248	0.109	0.505	0.501	0.017	.	0.008	0.205	0.0083	0.002	0.001
2	BS 4942	0.414	0.56	0.015	0.021	0.22	0.165	0.16	0.97	(0.004)	.	0.010	0.54	0.0080	.	.
1	IARM 252E	0.413	0.87	(0.009)	(0.012)	0.257	0.164	0.407	0.486	0.028	.	0.0093	0.204	0.0064	.	0.0010
2	BS 1962	0.41	0.94	0.007	0.011	0.242	0.224	0.16	1.05	0.018	.	0.008	0.229	0.0095	.	0.004
1	VS UG116	0.41	0.59	0.012	0.027	0.246	0.221	1.13	0.89	0.026	.	.	0.044	0.0089	.	0.0022
1	IARM 252F	0.406	0.88	0.011	0.009	0.247	0.182	0.412	0.463	0.026	.	0.0086	0.210	0.0059	0.0016	0.0010
1	IARM 30J	0.405	0.884	0.010	0.036	0.256	0.173	0.187	0.972	0.023	.	0.0098	0.205	(0.010)	0.0016	0.0013
1	SS 114	0.403	0.416	0.0044	0.0046	0.295	0.358	1.502	0.187	0.078	.	0.0171	0.184	0.0043	0.0042	0.0096
1	IMZ 55/1A	0.401	0.490	0.009	0.0053	0.406	0.112	0.570	0.998	0.006	.	0.0039	0.247	0.0023	0.010	0.012
1	IARM 31G	0.40	0.689	0.0136	(0.013)	0.262	0.183	1.814	0.820	0.0214	.	0.0083	0.223	0.0069	(0.0023)	0.0015
1	IMZ 63/2	0.40	0.63	0.017	0.009	0.16	0.14	0.13	0.16	(0.010)	.	.	.	.	.	.

Number	LOW ALLOY STEEL WITH C > 0.3%						CONTINUED FROM THE PREVIOUS PAGE						Units	
	As	B	Ca	Fe	Mg	O	Pb	Sb	Sn	Ta	V	W		Zr
VS UG0/9		(0.0002)					(0.002)		(0.0008)		0.0087	0.074		~45 mm Ø x ~28 mm
VS UG0/10								0.0043		0.0037	(0.006)			~45 mm Ø x ~28 mm
VS UG0/5										(0.01)	(0.01)			~45 mm Ø x ~28 mm
SS 402/2										0.194				38 mm Ø x 19 mm
ECRM 035-2D	0.0017													40 mm Ø x 20 mm
IMZ 65/2														40 mm Ø x 40 mm
DSZU C049	(0.004)	(0.0002)	(0.003)					(0.004)		(0.003)				40 mm Ø x 25 mm
KUT A18	0.003	(0.011)						0.005		0.10				30-35mm Ø x 38 mm
VS UG0/11								0.0051		0.0035	0.0032			~45 mm Ø x ~28 mm
CZ CM-5B	0.018	0.002					0.01	0.006	0.012	0.06	0.03	0.09		~37 mm Ø x 25 mm
14X 72305A									0.0101	0.0045				~40 mm Ø x ~15 mm
CZ CM-5C	0.020	0.0012	(0.0006)				0.009	0.005	0.018	0.106	0.034	(0.07)		~39 mm Ø x 25 mm
VS UG9/9		(0.0002)					(0.002)		(0.001)	0.215	1.60			~45 mm Ø x ~28 mm
IMZ 172									0.010	0.20	0.011			40 mm Ø x 40 mm
IARM 49E	0.0029					(0.002)			0.0065	0.066				31 mm Ø x 2 or 18 mm
12X 52986A									0.0063	0.0615				~38 mm Ø x ~15 mm
BS 53G	0.004	(0.0001)	(0.0001)			0.001			0.007	0.006	(0.13)	last		44 mm Ø x ~17 or 19 mm
NILAB 100LA D	0.004									0.004				34 mm Ø x 20 mm
IARM 324A	0.006	0.0004	0.0009			0.003		(0.002)	0.011	0.0017	(0.003)	(0.001)		31 mm Ø x 2 mm
BS A485-1	0.006					(0.0008)			0.011	0.003				39 mm Ø x ~7 or 19+ mm
KUT B15										(0.33)				30-35mm Ø x 39 mm
VS UG75										(0.006)	(0.02)			~40 mm Ø x ~26 mm
CZ LA-4C	(0.003)	0.0005							(0.006)	(0.010)	0.008			~37 mm Ø x 25 mm
VS UG9/11									0.0064	0.048	1.27			~45 mm Ø x ~28 mm
12X 19965A									0.0070	0.0087		Zn:0.0008		~41 mm Ø x ~15 mm
SS 401/2										0.496				38 mm Ø x 19 mm
IMZ 119			(0.0002)							0.006				40 mm Ø x 40 mm
VS UG89	0.0043						0.0003	0.0011		0.021				~47 mm Ø x ~30 mm
VS UG21/6														~45 mm Ø x ~28 mm
IARM 172A	(0.005)	0.0003				0.0006	(<0.01)		0.003		0.038			31 mm Ø x 2 mm
SS 403/2										0.341				38 mm Ø x 19 mm
IMZ 64/2														40 mm Ø x 40 mm
VS UG8/11									0.0058	0.181	0.70			~45 mm Ø x ~28 mm
ECRM 059-2D														38 mm Ø x 25 or 30 mm
CZ CM-4B	0.015	0.017					0.022	0.052	0.028	0.18	0.116	Zn:0.007		~39 mm Ø x 25 mm
SS 404/2										0.107				38 mm Ø x 19 mm
IMZ 118			(0.0002)						0.22	0.059				40 mm Ø x 40 mm
IMZ 116										0.076				40 mm Ø x 40 mm
VS UG1/11									0.0035					~45 mm Ø x ~28 mm
VS UG96										0.0030				~40 mm Ø x ~28 mm
VS UG119														~45 mm Ø x ~25 mm
12X 10550	0.0059								0.0018			Zn:(0.0016)		~40 mm Ø x ~15 mm
12X 61500A									0.0114	0.110		Zn: 0.0055		~38 mm Ø x ~15 mm
CZ CM-6A	0.025	0.015					0.017	0.03	0.017	0.05	0.04	0.04		~39 mm Ø x 25 mm
CZ BO-2B	0.0057		(0.0008)						0.0062	(0.001)	(0.005)			~37 mm Ø x ~25 mm
12X LA3C	0.0301	Zn:(0.004)					(0.004)			0.157		0.0197		~40 mm Ø x ~15 mm
IARM 34C	0.0024	0.0003	(0.0004)			0.0008	(0.0003)	(0.001)	0.0058	0.206	(0.003)	(0.001)		31 mm Ø x 2 or 18 mm
BS 4941	(0.004)		(0.0002)			0.0017			0.006	0.164				41 mm Ø x ~7 or 19+ mm
BS 43A	(0.005)	(0.0002)	(0.0006)	[96.8]	(0.0001)	(0.003)		(0.002)	0.011	0.145	(0.005)	(0.001)		41 mm Ø x ~7 or 19+ mm
IMZ 117			(0.0002)							0.087				40 mm Ø x 40 mm
BS 1144	0.009					0.0016	(0.001)		0.0113	0.0039	(0.003)	last		38 mm Ø x ~16 mm <b>17025</b>
IPT 503							0.008							35 mm Ø x 20 mm
SRM C1173										0.42				32 mm Ø x 19 mm
12X 41450A	0.0053								0.0090	0.0385				~38 mm Ø ~15 mm
Number	As	B	Ca	Fe	Mg	O	Pb	Sb	Sn	Ta	V	W	Zr	Units
VS UG5/11									0.0047		0.148	0.049		~45 mm Ø x ~28 mm
BS XCCV	0.002					(0.0018)	(<0.0006)	(0.0003)	(0.0004)		(<0.003)		(<0.0002)	36 mm Ø x ~7 or 19+ mm
12X LA3B		0.0015					0.0149			Zn:0.0098	0.157		(0.027)	~40 mm Ø x ~15 mm
NM PC-4														40 mm Ø x 20 mm last
IARM 30H	0.0046	(0.0007)	(0.0009)		(0.001)	(0.0016)	(0.0005)	0.0013	0.008		(0.0040)	(0.007)	(0.002)	31 mm Ø X 2 mm
IARM 305B	(0.006)	0.0006	0.0007		(0.002)	0.0006	(0.0003)	(0.004)	0.011	0.004	(0.004)	(0.004)	0.0011	31 mm Ø X 2 or 18 mm
IARM 252D	0.0053	(0.0002)	(0.001)		(0.0002)	(0.0013)	(0.0004)	0.0024	0.012		0.0022	(0.004)	(0.0013)	31 mm Ø x 2 mm
BS 4340A	0.0059	(0.0002)	(0.0002)	95.4	0.0004	0.0007	(0.0003)	(0.0018)	0.0081		0.0024	0.0005	0.0016	38 mm Ø x ~7 or 19+ mm <b>17025</b>
SRM 1173										0.42				32 mm Ø x 19 mm
HRT FE2015-N										0.006				35 mm Ø x 20 mm
BS 4340	0.0043	(0.0002)	0.0005	95.5	(0.0002)	0.0012	(0.0002)	(0.0013)	0.0063		0.0033	0.0012	0.0005	38 mm Ø x ~7 mm <b>17025</b> last
IARM 252C	0.004	(0.0001)	(0.0003)			(0.002)	0.001	<0.005	0.007		0.005	<0.005	<0.002	31 mm Ø x 2 mm
BS 4942	0.005		0.0006			(0.0021)			0.014		0.28			38 mm Ø x ~7 mm last
IARM 252E	0.0046								0.0075		(0.0028)			31 mm Ø X 2 or 18 mm
BS 1962	0.007		25(pre-17025)		(0.0001)		(0.001)		0.010		0.004			41 mm Ø x ~7 mm last
VS UG116														~45 mm Ø x ~25 mm
IARM 252F	(0.006)								0.006		(0.003)	(0.003)		31 mm Ø X 2 or 18 mm
IARM 30J	(0.002)								0.0109		0.0045	(0.005)		31 mm Ø X 2 mm
SS 114	0.0025	0.0008							0.041		0.0086		0.0051	44 mm Ø x 19 mm
IMZ 55/1A		0.0018							0.017		0.107			38 mm Ø x 20 mm
IARM 31G	(0.004)	0.0004							0.0077		0.0036	(0.004)	(0.0012)	31 mm Ø X 2 or 18 mm
IMZ 63/2														40 mm Ø x 40 mm
SS 225/2														38 mm Ø x 19 mm
IPT 504														36 mm Ø x 20 mm
12X 826M40A	0.0056								0.0085					~38 mm Ø x ~15 mm
BS 4942A	0.0031	(0.0001)	0.0012	96.8	0.0004	0.0020	(0.0007)	(0.001)	0.0044		0.280	(0.0009)	(0.001)	38 mm Ø x ~7 or 19+ mm <b>17025</b>
VS RG30/1											0.70	0.89		~45 mm Ø x ~28 mm
VS UG79											(0.02)	(0.01)		~40 mm Ø x ~26 mm
IRSID 1731														44 mm Ø x 30 mm
DSZU C045	0.0052	(0.0004)	0.0005						0.0050		0.004	(0.011)		40 mm Ø x 25 mm last
VS UG3/10									0.0057		0.0053	0.006		~45 mm Ø x ~28 mm
12X 605M36A	0.0102		0.0033						0.0101					~38 mm Ø x ~15 mm
12X 12700A	0.0060	0.0014									0.0033		Zn:0.0120	~50 mm Ø x ~20 mm
IMZ 115											(0.063)			40 mm Ø x 40 mm
IRSID 1750	0.0188	(0.0002)	(0.0002)		(<0.0002)		(<0.001)	0.0031	0.0137	(<0.0010)	0.114	(0.004)	(0.0002)	38 mm Ø x 25 mm
IMZ 114A	0.0035	0.0019					0.021	0.018	0.014		0.096	(0.007)	Zn:(0.006)	38 mm Ø x 20 mm
12X 352E	0.029								0.109	(0.018)	0.0251	0.275		~40 mm Ø x ~15 mm
VS UG7/10									0.0006		0.234	0.34		~45 mm Ø x ~28 mm
IMZ 174									0.010		0.98	0.021		40 mm Ø x 40 mm
DSZU C05a	(0.005)	0.010					(0.003)	(0.0005)	0.010		0.20	0.27		40 mm Ø x 25 mm
12X 349E	0.0107													

**LOW ALLOY STEEL WITH 0.13 % < C < 0.3 % - CONTINUED ON THE NEXT PAGE**

#=Class, where 1=CRM and 2=RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	Co	Mo	N	Sn	V
1	IARM 330A	0.299	1.00	(0.005)	(0.001)	0.273	0.074	1.80	0.90	0.045	.	(0.003)	0.0063	0.404	0.0024	0.0039	0.071
1	12X 16604A	0.299	0.444	0.0064	0.0018	0.239	0.131	1.892	1.912	0.0111	.	.	0.0366	0.334	0.0046	0.0060	0.0069
1	SRM 1269	0.298	1.35	0.012	0.0061	0.189	0.095	0.108	0.201	0.016	.	.	.	0.036	.	.	0.004
1	ECRM 086-1D	0.297	0.879	0.024	0.037	0.206	0.320	0.168	0.150	.	.	0.023	.	.	.	0.026	.
2	CZ CM-3A	0.295	0.37	0.016	0.0013	0.27	0.16	1.82	1.87	0.05	.	0.005	0.012	0.33	0.007	0.007	0.007
1	VS UG9/10	0.294	0.616	.	(0.003)	0.235	0.169	0.144	0.170	0.280	.	.	.	0.282	0.015	0.0017	1.25
1	VS RG27/1	0.290	0.74	0.044	0.0043	0.28	0.208	0.142	1.83	1.07	.	.	0.025	0.191	.	.	0.072
1	IMZ 178	0.29	0.65	0.016	0.003	0.28	0.140	2.09	1.26	0.051	.	.	0.015	0.20	0.0160	0.011	0.011
1	SRM 1225	0.274	0.48	0.007	0.014	0.221	.	0.018	0.91	.	.	.	.	0.166	.	.	0.004
1	<b>BS HiCal-1</b>	0.271	1.00	(0.007)	0.0007	1.29	0.152	3.28	1.55	0.070	.	0.0022	0.0024	0.379	.	(0.0002)	0.0027
1	IARM 380A	0.268	1.24	0.021	0.025	0.181	0.265	0.114	0.192	0.0029	.	(0.007)	(0.010)	0.059	(0.012)	0.0117	0.0475
2	RM Fe 2/4	0.26	0.61	0.039	0.016	0.30	0.30	0.68	0.70	(0.001)	.	0.04	0.29	0.47	0.020	0.04	0.46
2	BS 69B	0.258	1.28	0.008	0.013	1.27	0.086	1.71	0.28	0.024	.	.	0.035	0.39	0.0057	0.006	(0.002)
1	12X 12750U	0.258	0.510	0.0078	0.0053	0.599	0.106	0.786	0.792	0.253	.	.	0.581	0.088	.	0.110	0.102
1	12X 32550A	0.257	1.350	0.0061	0.0054	1.59	0.108	1.750	0.377	0.0178	.	0.0054	.	0.417	0.0101	0.0206	0.0222
2	BS 6418	0.255	1.42	0.010	0.004	1.54	0.11	1.74	0.34	0.027	.	0.0044	0.010	0.42	0.0066	0.006	0.003
1	IARM 380B	0.243	1.27	0.016	0.027	0.238	0.307	0.182	0.153	(0.0021)	.	0.0058	0.014	0.055	(0.013)	0.0132	0.049
2	HRT FE2018-N	0.24	0.74	0.012	(0.003)	0.29	0.06	0.43	1.46	0.017	.	.	.	0.75	.	0.0066	0.30
1	IMZ 113	0.24	0.50	0.022	0.025	0.10	0.11	0.13	1.25	0.007	0.004	.	.	0.050	0.0154	.	0.039
1	12X 722M24A	0.236	0.510	0.0135	0.0199	0.262	0.200	0.208	3.094	0.0187	.	0.0075	.	0.497	.	0.0116	0.0080
1	VS UG6/5	0.232	0.39	(0.006)	(0.008)	0.51	0.257	(0.2)	1.85	(0.4)	.	.	.	(0.2)	.	.	0.34
2	DSZU C043A	0.222	2.14	0.060	0.064	0.131	0.51	2.93	0.49	0.066	.	(0.001)	.	0.146	(0.009)	0.0023	0.25
1	IARM 229B	0.220	0.858	0.0073	0.0106	0.329	0.0153	0.030	0.017	0.025	.	(0.002)	0.0116	0.495	0.0072	0.0012	0.0059
1	ECRM 197-1D	0.219	0.792	0.0073	0.0232	0.275	0.152	0.148	0.451	0.0313	.	0.0083	0.0135	0.402	0.0114	0.0097	.
2	BS 3961	0.215	0.565	0.016	0.022	0.236	0.133	1.67	0.510	0.022	.	.	(0.010)	0.27	0.0079	(0.008)	(0.002)
2	TL 1668	0.2146	1.643	0.0137	0.0012	1.645	0.0108	0.0164	0.0173	0.0371	.	0.0016	0.0031	(0.0014)	0.0043	0.0047	0.0016
1	<b>BS 8620F</b>	0.212	0.85	0.0090	0.033	0.243	0.234	0.427	0.547	0.040	.	0.0078	0.0089	0.206	0.0106	0.0102	0.0054
1	DSZU C048	0.212	0.467	0.0102	0.0059	0.273	0.262	0.105	0.175	0.0293	.	0.0085	0.015	0.016	(0.011)	0.016	.
1	12X 86200-21	0.211	0.811	0.0128	0.0224	0.237	0.199	0.551	0.507	0.0241	.	0.0045	0.0072	0.190	0.0082	0.0094	0.0039
2	TL 1001	0.2108	0.8645	0.0141	0.0236	0.2141	0.1902	0.5378	0.5290	0.0191	.	(0.0051)	(0.0070)	0.1987	0.0102	0.0090	.
1	IPT 502	0.210	0.823	0.018	0.026	0.198	0.121	0.408	0.485	0.024	.	0.0083	0.008	0.155	0.0069	.	.
1	VS UG4/11	0.21	0.59	0.024	0.0069	0.285	0.074	0.173	1.21	0.032	.	.	0.0108	0.87	0.020	.	0.78
1	IARM 33D	0.209	0.593	0.009	0.023	0.207	0.072	1.78	0.139	0.026	.	0.0035	0.008	0.229	0.0053	0.005	0.002
2	BS 3952	0.208	0.546	0.011	0.021	0.264	0.202	0.112	0.105	0.048	.	.	.	0.519	(0.0005)	.	.
1	ECRM 187-2D	0.2038	1.257	0.0066	(0.0300)	0.2111	0.1288	0.1755	1.132	0.0223	.	0.0057	0.0112	0.0623	0.0105	0.0237	0.0122
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	Co	Mo	N	Sn	V
1	<b>BS 4820A</b>	0.203	0.64	0.008	0.014	0.185	0.212	3.28	0.116	0.029	.	0.006	0.008	0.203	0.0076	0.0097	0.0010
1	12X 12747V	0.201	1.240	0.0648	0.0275	0.298	0.232	0.494	0.58	0.0271	.	0.0075	0.211	0.606	0.025	0.144	0.0272
1	VS RG31/1	0.200	0.191	0.0039	0.0058	0.28	0.39	2.12	1.28	0.30	.	.	0.273	0.30	.	.	0.200
1	KUT B3	0.20	0.14	(0.012)	0.025	0.53	0.25	5.94	.	.	.	.	.	.	.	.	1.16
1	VS UG5/5	(0.2)	0.52	(0.005)	(0.03)	0.145	0.37	0.42	1.42	0.19	.	.	.	0.44	.	.	0.29
1	IARM 155F	0.199	0.617	0.008	(0.013)	0.223	0.219	3.36	0.144	0.0356	.	(0.006)	0.012	0.244	(0.005)	0.0084	0.0015
1	IMZ 112B ##	0.195	0.43	0.022	0.016	0.27	0.055	0.046	0.034	(0.03)	.	.	.	0.043	0.010	0.15	0.045
1	VS UG8/10	0.192	1.81	0.0064	(0.005)	0.61	0.198	0.348	0.729	0.082	.	.	.	0.030	0.0185	0.0052	.
1	VS UG114	0.190	1.65	0.010	0.0074	0.59	0.173	0.345	1.03	0.146	.	.	.	0.016	.	.	0.0031
1	IMZ 162	0.19	1.31	0.021	0.014	0.59	0.077	1.64	0.91	(0.040)	.	.	.	0.52	.	.	0.045
1	VS UG113	0.189	1.55	0.0087	0.0070	0.59	0.185	0.186	1.12	0.263	.	.	.	0.010	.	.	0.0040
2	BS 4620	0.189	0.57	0.006	0.018	0.25	0.216	1.75	0.072	0.032	.	0.0084	0.012	0.24	0.0078	0.013	(0.0008)
1	<b>BS 51F</b>	0.188	0.519	0.016	0.017	0.24	0.231	1.68	0.156	0.022	.	(0.005)	0.0086	0.224	0.0061	0.008	0.0030
1	ECRM 192-1D	0.1875	1.377	0.0029	0.0010	0.219	0.0453	0.755	0.0717	0.0306	0.0285	.	0.0055	0.482	0.0118	.	0.014
1	VS UG112	0.186	1.63	0.0065	0.0050	0.60	0.157	0.185	0.98	0.026	.	.	.	0.021	.	.	.
2	BS LF3	0.183	0.52	0.006	0.018	0.206	0.080	3.36	0.098	0.017	.	0.006	0.056	0.056	0.0054	0.006	(0.002)
2	HRT FE2012-N	0.18	0.70	0.010	0.008	0.31	0.14	0.13	0.25	0.030	.	.	.	0.26	.	.	.
1	ECRM 087-1D	0.174	0.671	0.010	0.046	0.263	0.171	0.118	0.078	.	.	0.024	0.015	0.021	.	0.017	.
1	12X 15180A	0.170	1.196	0.0110	0.0022	0.212	0.141	0.1030	0.118	0.018	.	0.0117	.	0.0231	0.0051	0.0115	.
1	ECRM 194-2D	0.1694	1.282	0.0137	0.00049	0.2974	0.0313	0.3316	0.760	0.0669	.	0.00208	0.00328	0.402	0.00319	.	0.00161
2	BS 3962	0.168	0.58	0.007	0.018	0.244	0.146	1.83	0.138	0.023	.	0.005	0.007	0.219	0.0072	0.007	(0.001)
1	VS UG7/11	0.164	0.293	0.0045	0.0062	0.39	0.468	2.09	1.31	0.276	.	.	0.291	0.298	0.014	.	0.208
2	HRT FE1999-N	0.16	0.59	0.011	0.005	0.22	0.11	0.09	0.87	0.027	.	.	.	0.46	0.0091	0.009	0.021
2	BS XCCT	0.158	0.52	0.005	0.011	0.28	0.027	1.27	0.65	0.006	.	0.004	0.017	0.020	0.0076	(0.002)	0.031
1	IMZ 176A	0.15	0.75	0.018	0.003	0.35	0.103	3.62	0.41	(0.058)	.	.	(0.010)	0.027	0.0129	0.009	(0.061)
2	BS 15A	0.142	1.12	0.016	0.008	0.058	0.030	0.029	0.044	0.041	.	0.003	0.005	0.008	.	0.002	0.012
1	ECRM 193-1D	0.14	0.97	0.007	0.009	0.40	0.60	1.18	0.18	0.025	.	0.0062	0.007	0.35	0.0108	.	(0.002)
1	12X 15252R	0.137	0.321	0.044	0.044	0.097	0.153	2.03	0.96	0.035	.	.	0.153	0.247	0.020	0.047	0.288
2	BS 47A	0.130	0.44	0.017	0.015	0.27	0.11	0.12	4.22	0.015	.	.	0.011	0.47	0.018	0.008	0.016

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	Co	Mo	N	Sn	V
---	--------	---	----	---	---	----	----	----	----	----	-----	----	----	----	---	----	---

**CRM LOW ALLOY STEEL WITH EXTENSIVE ANALYSIS** analysis listed in mass % 31-34 mm Ø x 19 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	Nb	Pb	Sn	Ta	Ti	V	W	Zr	
SRM 1264a	0.87	0.25	0.010	0.025	0.067	0.25	0.14	0.06	(0.008)	0.010	0.15	0.49	0.15	0.0022	(0.008)	0.11	0.24	0.10	0.10	0.069	
continued	analysis listed in mass %										analysis listed in mg/kg										
Number	B	Bi	Fe.diff	Ge	Sb	Te	Zn	Ag	Au	Ca	Ce	H	Hf	La	Mg	N	Nd	O	Pd	Se	Sr
SRM 1264a	(0.011)	(0.0009)	[96.7]	(0.003)	0.034	0.00018	(0.001)	(0.2)	1	0.4	2	(<5)	(13)	0.7	1.5	(32)	0.7	(10)	(0.3)	(2.1)	(5)

## LOW ALLOY STEEL WITH 0.13 % &lt; C &lt; 0.3 %

## CONTINUED FROM THE PREVIOUS PAGE

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
IARM 330A	0.0003	0.0010	.	.	(0.003)	(0.0009)	(0.0004)	(0.001)	.	0.006	(0.004)	.	0.0015	31 mm Ø x 2 mm
12X 16604A	.	.	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm
SRM 1269	.	.	.	.	.	.	0.005	.	.	.	.	.	.	32 mm Ø x 19 mm
ECRM 086-1D	.	.	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 25 or 30 mm
CZ CM-3A	0.0002	.	.	.	0.006	.	.	.	.	0.006	0.015	.	.	~39 mm Ø x 25 mm
VS UG9/10	.	.	.	.	.	.	.	.	.	0.163	1.34	.	.	~45 mm Ø x ~28 mm
VS RG27/1	.	.	.	.	.	.	.	.	.	0.110	0.170	.	.	~45 mm Ø x ~28 mm
IMZ 178	.	.	.	.	0.105	.	.	.	.	.	0.017	.	.	40 mm Ø x 40 mm
SRM 1225	.	.	.	.	.	.	.	.	.	.	.	.	.	32 mm Ø x 19 mm
<b>BS HiCal-1</b>	(0.0001)	0.0140 [91.9]	.	(0.0003)	(0.002)	.	(0.0005)	.	.	0.0037	(0.0009)	.	(0.0008)	~38 mm Ø x ~30 mm <b>17025</b>
IARM 380A	.	.	.	.	(0.0020)	.	.	.	.	.	(0.009)	.	.	31 mm Ø x 2 or 18 mm
RM Fe 2/4	(0.0027)	<0.001	.	.	(0.011)	.	<0.02	<0.03	.	(0.0065)	0.19	.	<0.02	40 mm Ø x 40 mm
BS 69B	.	.	.	.	.	.	.	.	.	(0.002)	.	.	.	38 mm Ø x ~7 or 19+ mm
12X 12750U	.	.	.	.	0.111	.	.	.	.	0.159	0.100	.	.	~40 mm Ø x ~15 mm
12X 32550A	.	.	.	.	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~15 mm
BS 6418	.	.	.	.	.	0.0012	.	.	.	0.003	.	.	.	57 mm Ø x ~7 or 19+ mm
IARM 380B	.	.	.	.	(0.0016)	.	.	.	.	0.0011	(0.003)	.	.	31 mm Ø x 2 or 18 mm
HRT FE2018-N	(0.0003)	.	.	.	.	.	.	.	.	.	.	.	.	36 mm Ø x 20 mm
IMZ 113	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
12X 722M24A	.	.	.	.	.	.	.	.	.	.	.	0.0028	.	~38 mm Ø x ~15 mm
VS UG6/5	.	.	.	.	(0.01)	.	.	.	.	(0.01)	0.16	.	.	~45 mm Ø x ~28 mm
DSZU C043A	(0.001)	0.0004	.	.	0.006	.	.	.	.	0.041	0.092	.	.	40 mm Ø x 25 mm
IARM 229B	(0.0006)	(0.0003)	.	.	(0.0019)	(0.0017)	(0.0005)	(0.0006)	(0.003)	0.0019	(0.003)	.	(0.0008)	31 mm Ø x 2 mm
ECRM 197-1D	.	.	.	.	.	.	.	.	.	0.0005	.	.	.	38 mm Ø x 25 mm
BS 3961	.	.	.	.	.	.	.	.	.	<0.003	.	.	.	44 mm Ø x ~7 or 19+ mm
TL 1668	(0.00024)	0.0019	.	(0.0003)	(0.0002)	.	(0.0007)	(0.0003)	.	0.0032	.	0.0008	(0.0003)	37 mm Ø x 20 mm
<b>BS 8620F</b>	(0.0003)	0.0020	97.1	(0.0002)	0.0025	0.0026	(0.002)	(0.002)	<b>17025</b>	0.0016	0.0016	.	(0.0008)	38 mm Ø x ~7 or 19+ mm
DSZU C048	.	(0.0017)	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 25 mm
12X 86200-21	.	.	.	.	0.0014	.	.	0.0024	.	.	(0.003)	(0.0014)	.	38 mm Ø x 19 mm
TL 1001	.	.	.	.	.	.	.	.	.	(0.0134)	.	.	.	40 mm Ø x 20 mm
IPT 502	.	.	.	.	.	.	.	.	.	0.0016	.	.	.	36 mm Ø x 20 mm
VS UG4/11	.	.	.	.	0.071	.	.	.	.	0.034	0.0092	.	.	~45 mm Ø x ~28 mm
IARM 33D	0.0002	(0.0003)	.	.	0.002	0.0013	<0.001	(0.002)	.	0.003	<0.005	.	<0.002	31 mm Ø x 2 or 18 mm
BS 3952	.	.	.	.	.	.	.	.	.	.	.	.	.	39 mm Ø x ~7 or 19+ mm
ECRM 187-2D	0.00048	.	.	.	.	.	.	.	.	.	.	.	.	39 mm Ø x 28 mm

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
<b>BS 4820A</b>	0.0002	0.0003	.	0.0003	(0.002)	0.0011	(0.0002)	0.0024	.	0.0012	(0.002)	<b>17025</b>	.	38 mm Ø x ~7 or 19+ mm
12X 12747V	.	.	.	.	.	.	.	.	.	0.099	0.0276	.	.	~40 mm Ø x ~15 mm
VS RG31/1	.	.	.	.	.	.	.	.	.	0.21	0.39	.	.	~45 mm Ø x ~28 mm
KUT B3	.	.	.	.	.	.	.	.	.	.	1.19	.	.	30-35mm Ø x 39 mm
VS UG5/5	.	.	.	.	(0.01)	.	.	.	.	(0.003)	0.38	.	.	~45 mm Ø x ~28 mm
IARM 155F	.	.	.	.	0.0016	(0.003)	.	.	.	0.0020	(0.004)	.	.	31 mm Ø x 2 or 18 mm
IMZ 112B ## BACKORDERED	.	.	.	.	0.013	.	.	.	.	0.010	.	.	.	40 mm Ø x 40 mm
VS UG8/10	.	.	.	.	(0.003)	.	.	.	.	0.0034	.	.	.	~45 mm Ø x ~28 mm
VS UG114	.	.	.	.	.	.	.	.	.	0.006	.	.	0.065	~45 mm Ø x ~25 mm
IMZ 162	.	.	.	.	.	.	.	.	.	0.12	.	.	.	40 mm Ø x 40 mm
VS UG113	.	.	.	.	.	.	.	.	.	0.006	0.007	.	0.169	~45 mm Ø x ~25 mm
BS 4620	0.00006	0.0001	.	0.0001	0.0001	0.0009	0.0002	0.0024	.	0.0026	0.0009	0.0002	.	38 mm Ø x ~7 or 19+ mm
<b>BS 51F</b>	(0.0002)	(0.0005)[96.7]	.	(0.0001)	(0.0007)	(0.002)	(0.0008)	(0.003)	(0.005)	0.0012	(0.0024)	<b>17025</b>	(0.0009)	38 mm Ø x ~7 or 19+ mm
ECRM 192-1D	.	.	.	.	.	.	.	.	.	.	.	.	.	~35 mm Ø x ~30 mm
VS UG112	.	.	.	.	.	.	.	.	.	0.0028	0.005	.	0.0047	~45 mm Ø x ~25 mm
BS LF3	0.0001	(0.0001)	.	.	.	0.004	.	.	.	.	.	.	.	38 mm Ø x ~7 or 19+ mm
HRT FE2012-N	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 20 mm
ECRM 087-1D	.	.	.	.	.	.	.	0.0046	.	.	.	.	.	38 mm Ø x 25 or 30 mm
12X 15180A	.	.	.	.	.	.	.	.	.	.	.	0.0016	.	~40 mm Ø x ~20 mm
ECRM 194-2D	0.00155	.	.	.	0.0290	.	.	.	.	0.00322	.	.	.	39 mm Ø x 28 mm
BS 3962	.	.	.	.	.	.	.	.	.	.	.	.	.	37 mm Ø x ~7 or 19+ mm
VS UG7/11	.	.	.	.	.	.	.	.	.	0.20	0.385	.	.	~45 mm Ø x ~28 mm
HRT FE1999-N	0.0002	.	.	.	0.002	.	.	.	.	0.001	.	.	.	40 mm Ø x 20 mm last
BS XCCT	.	.	.	.	(0.001)	(0.005)	<0.001	(0.0004)	.	(0.002)	.	.	<0.002	36 mm Ø x ~7 or 19+ mm
IMZ 176A	.	.	.	.	.	.	.	.	.	.	(0.015)	.	.	40 mm Ø x 40 mm
BS 15A	(0.0002)	(0.0005)	.	.	0.041	.	(0.0003)	(0.003)	.	0.008	(0.004)	.	0.022	32 mm Ø x 17 mm last
ECRM 193-1D	.	.	.	.	0.0232	.	.	.	.	(0.0013)	.	.	.	36-41 mm Ø x 28-35 mm
12X 15252R	.	.	.	.	0.067	.	.	.	.	(0.0007)	(0.0013)	.	.	~40 mm Ø x ~15 mm
BS 47A	.	.	.	.	0.002	(0.003)	.	.	.	0.003	.	.	.	38 mm Ø x ~7 or 19+ mm

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
--------	---	----	----	----	----	---	----	----	----	----	---	----	----	-------



LOW ALLOY STEEL WITH C < 0.13 %

# = Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Sn	V
1	IMZ 76	0.129	1.37	0.022	0.011	0.24	0.057	0.33	0.12	0.011	.	.	0.101	.	.	(0.006)
1	VS UG86	0.129	0.217	(0.005)	(0.007)	(0.3)	0.62	1.94	1.52	.	.	.	0.311	.	.	0.327
1	12X 15256Q	0.123	0.492	0.0125	0.0163	0.190	0.0550	5.33	0.362	0.1300	.	0.493	0.0740	0.0056	0.107	0.619
1	12X 93106A	0.122	0.605	0.0071	0.0103	0.206	0.199	3.255	1.107	0.0246	.	.	0.0879	0.0098	0.0094	0.0029
2	BS 47B	0.122	0.39	0.014	0.022	0.22	0.12	0.105	4.78	0.018	.	.	0.45	0.023	0.006	0.004
1	VS UG115	0.115	0.43	0.0084	0.012	0.227	0.173	1.63	0.81	0.024	.	.	0.0126	0.013	.	.
1	IMZ 75A	0.112	0.394	0.080	0.016	0.618	0.428	0.041	0.401	0.009	.	0.0037	0.018	0.0024	0.023	0.013
1	SRM 1138a	0.11	0.35	0.035	0.056	0.25	0.09	0.10	0.13	.	.	.	0.05	.	.	0.02
1	IPT 500	0.106	0.844	0.016	0.0048	0.282	0.270	0.018	0.612	0.046	.	0.0046	0.0013	0.0092	0.002	0.003
1	12X LALB	0.104	1.262	0.0090	0.060	0.777	0.0572	0.210	1.026	0.0104	.	0.0144	0.068	0.0144	.	0.448
2	BS 58E	0.100	0.63	0.009	0.002	0.29	0.154	3.22	1.40	0.029	.	0.013	0.110	0.0033	0.003	0.006
1	IMZ 175	0.099	0.25	0.016	0.0040	0.22	0.130	3.12	0.515	0.043	.	(0.013)	0.025	0.0099	0.011	0.014
2	BS 58C	0.098	0.57	0.011	0.014	0.29	0.14	3.20	1.29	(0.055)	.	.	0.11	.	(0.012)	.
1	IMZ 73	0.097	0.68	0.019	0.013	0.12	0.17	0.13	0.079	0.010	.	.	0.013	.	.	0.022
1	VS UG6/11	0.091	0.691	0.028	0.022	0.96	0.449	0.640	0.759	0.0107	.	0.0392	0.0082	0.0083	.	0.0075
1	KUT T3/2	0.09	0.60	0.058	0.033	0.66	0.10	0.11	0.40	.	.	.	.	.	.	.
1	IARM 268B	0.087	0.58	0.011	0.035	0.21	0.31	0.127	0.094	0.002	.	0.003	0.033	0.0015	0.010	0.047
1	IMZ 204	0.085	0.36	0.014	0.008	0.40	0.075	0.034	0.111	4.21	.	.	(0.007)	(0.0052)	.	.
1	SRM 1226	0.085	0.274	0.0022	0.0044	0.231	0.125	5.42	0.467	0.054	.	0.029	0.446	.	(0.003)	0.0018
1	DSZU C050	0.082	1.21	0.040	0.065	0.287	0.304	0.118	0.075	(0.008)	.	.	0.48	.	(0.004)	0.007
1	NCS HS20745	0.068	0.813	0.1	0.024	0.33	0.297	.	.	.	.	.	.	.	.	0.022
1	VS UG117	0.064	1.41	0.012	0.021	0.60	0.214	0.072	0.129	0.018	.	.	(0.005)	0.0085	.	.
1	SRM 1271	0.064	0.73	0.005	0.0013	0.334	1.48	3.34	0.552	0.020	.	.	0.543	.	.	0.003
1	SRM C1285	0.058	0.332	0.072	0.020	0.36	0.37	1.17	0.80	.	.	0.036	0.164	.	0.035	0.150
2	CZ CM-7A	0.05	1.17	0.011	0.016	0.56	0.09	0.05	0.10	0.13	.	0.007	0.015	0.01	0.008	0.012
1	SS 421	(0.049)	(0.11)	(0.012)	(0.027)	(0.07)	.	.	.	.	.	.	(0.028)	.	.	(<0.02)
1	VS UG82	0.046	1.83	(0.003)	(0.004)	0.334	0.056	0.201	0.59	.	.	.	0.93	.	.	0.56
1	VS UG97	0.041	0.59	0.0036	0.0025	0.194	0.0040	0.0048	0.0080	0.51	.	.	0.019	.	.	(0.001)
2	IARM 168A	0.003	0.12	0.030	0.064	0.46	0.009	2.32	0.004	0.19	.	0.003	0.69	0.0002	0.003	0.004
1	ECRM 064-2D	0.0026	0.1641	.	.	0.0065	0.0077	0.0115	.	.	.	0.0027	0.00077	0.0026	0.00051	0.00015

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Sn	V
	Number	As	B	Ca	Ce	Fe	Nb	O	Pb	Sb	Ti	W	Zr	Units		
	IMZ 76	.	(0.001)	.	.	.	0.068	.	.	.	(0.003)	.	.	.	40 mm	Ø x 40 mm
	VS UG86	.	.	.	.	.	.	.	.	.	.	.	.	.	~40 mm	Ø x ~28 mm
	12X 15256Q	.	.	.	.	.	0.0509	.	.	.	.	0.101	.	.	~40 mm	Ø x ~15 mm
	12X 93106A	0.0050	.	.	.	.	.	.	.	.	.	.	.	.	~38 mm	Ø x ~15 mm
	BS 47B	0.004	.	.	.	.	.	(0.004)	.	.	.	.	.	.	38 mm	Ø x ~7 or 19+mm
	VS UG115	.	.	.	.	.	.	.	.	.	0.0014	.	.	.	~45 mm	Ø x ~25 mm
	IMZ 75A	.	0.0021	.	.	.	0.024	.	.	.	0.023	.	.	.	38 mm	Ø x 20 mm
	SRM 1138a	.	.	.	.	.	.	.	.	.	.	.	.	.	32 mm	Ø x 13 mm
	IPT 500	0.0020	.	.	.	.	0.008	.	.	.	0.0014	.	.	.	34 mm	Ø x 18 mm
	12X LALB	0.0212	.	.	.	.	.	.	.	.	.	.	.	.	~40 mm	Ø x ~15 mm
	BS 58E	0.003	(0.0002)	(0.0002)	.	.	.	0.0008	.	.	(0.002)	.	.	.	38 mm	Ø x ~7 or 19+mm
	IMZ 175	.	.	.	.	.	.	.	.	.	.	(0.019)	.	.	40 mm	Ø x 40 mm
	BS 58C	.	.	.	.	.	.	.	.	.	.	no uncertainties	.	.	39 mm	Ø x ~17 mm last
	IMZ 73	.	.	.	.	.	0.01	.	.	.	(0.002)	.	(0.0025)	.	40 mm	Ø x 40 mm
	VS UG6/11	.	.	.	.	.	.	.	.	.	.	.	.	.	~45 mm	Ø x ~28 mm
	KUT T3/2	.	.	.	.	.	.	.	.	.	(0.01)	.	.	.	30-35mm	Ø x 39 mm
	IARM 268B	<0.005	0.0011	.	.	.	0.006	(0.015)	<0.003	.	<0.001	0.01	<0.001	.	31 mm	Ø x 2 mm
	IMZ 204	.	.	.	.	.	.	.	.	.	0.035	.	.	.	36 mm	Ø x 20 mm
	SRM 1226	.	.	.	.	.	(0.005)	.	(0.0001)	.	0.0021	(0.005)	(0.010)	.	32 mm	Ø x 19 mm
	DSZU C050	(0.002)	(0.002)	.	.	.	.	.	.	.	(0.002)	.	.	.	40 mm	Ø x 25 mm
	NCS HS20745	.	.	.	0.014	.	.	La: 0.0076	.	.	.	.	.	.	35 mm	Ø x 40 mm
	VS UG117	.	.	.	.	.	.	.	.	.	0.018	.	.	.	~45 mm	Ø x ~25 mm
	SRM 1271	.	.	.	.	.	0.025	.	.	.	.	.	.	.	32 mm	Ø x 19 mm
	SRM C1285	.	.	.	0.021	.	.	.	.	.	.	.	.	.	32 mm	Ø x 19 mm
	CZ CM-7A	0.005	0.0003	.	.	.	0.004	.	(0.0014)	(0.0003)	0.14	0.01	0.042	.	~39 mm	Ø x 25 mm
	SS 421	.	.	.	.	.	.	.	.	.	.	0.52	.	.	38 mm	Ø x 19 mm
	VS UG82	.	.	.	.	.	.	.	.	.	.	.	.	.	~40 mm	Ø x ~28 mm
	VS UG97	.	.	.	.	.	.	.	.	.	0.154	.	.	.	~40 mm	Ø x ~28 mm
	IARM 168A	(0.003)	0.0004	.	.	.	0.003	0.0008	(0.01)	.	0.004	0.52	.	.	31 mm	Ø x 2 mm
	ECRM 064-2D	0.0036	.	.	.	.	0.0146	.	0.00018	.	.	.	.	.	38 mm	Ø x 25 or 30 mm

Number	As	B	Ca	Ce	Fe	Nb	O	Pb	Sb	Ti	W	Zr	Units
--------	----	---	----	----	----	----	---	----	----	----	---	----	-------



## LOW ALLOY STEEL XRF SET

Part Number: BS LAS-24 Set of 24 samples, each 35 - 45 mm Ø x 7 mm discs CRM, 17025 others are RM

Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Ca	Co	N	Sn	V
300M	BS 4340M	0.414	0.74	0.004	<0.001	1.65	0.134	1.78	0.78	0.35	0.076	0.007	.	0.013	0.0020	0.009	0.056
1345	BS XCCV	0.44	1.75	0.012	0.024	0.28	0.015	0.019	0.041	0.007	0.033	0.0023	.	0.006	0.0056	(0.0004)	<0.003
3115	BS XCCT	0.158	0.52	0.005	0.011	0.28	0.027	1.27	0.65	0.020	0.006	0.004	.	0.017	0.0076	(0.002)	0.031
4130	BS 3932	0.321	0.54	0.016	0.018	0.33	0.200	0.19	1.00	0.229	0.020	0.004	0.0043	0.011	0.0070	0.012	0.005
4140	BS 1962	0.41	0.94	0.007	0.011	0.242	0.224	0.16	1.05	0.229	0.018	0.007	.	0.008	0.0095	0.010	0.004
4150 + S	BS 42	0.516	1.24	0.021	0.073	0.235	0.252	0.183	0.67	0.190	0.020	(0.004)	.	0.012	0.0080	0.012	0.003
4330	BS 4330MOD	0.316	0.92	0.0052	0.0010	0.269	0.105	1.83	0.848	0.478	0.031	0.0038	(0.001)	0.034	0.0031	0.0062	0.083
4340	BS 4340	0.418	0.695	0.0119	0.0187	0.279	0.149	1.79	0.807	0.231	0.028	0.0043	0.0005	0.0068	0.0080	0.0063	0.0033
4615	BS 51E	0.15	0.59	0.010	0.021	0.28	0.22	1.75	0.14	0.21	0.028	.	.	0.035	0.0086	0.010	(0.0011)
4620	BS 4620	0.189	0.57	0.006	0.018	0.25	0.216	1.75	0.072	0.24	0.032	(0.0084)	(0.0001)	0.012	0.0078	0.013	(0.0008)
4820	BS 4820	0.188	0.57	0.010	0.025	0.25	0.11	3.29	0.12	0.21	0.020	0.005	0.0046	0.008	0.0079	(0.008)	(0.002)
6150	BS 43A	0.49	0.82	0.0074	0.025	0.252	0.18	0.24	0.92	0.059	(0.003)	(0.005)	(0.0006)	0.008	0.0072	0.011	0.145
8620	BS 1931	0.194	0.84	0.007	0.018	0.235	0.116	0.42	0.50	0.168	0.021	0.007	(0.0008)	0.012	0.0079	0.007	0.002
8822	BS 8822	0.228	0.92	0.011	0.025	0.26	0.17	0.47	0.52	0.34	0.022	0.007	(0.0004)	0.019	0.0085	0.011	0.003
8740	BS 67B	0.40	0.94	0.007	0.020	0.23	0.19	0.53	0.51	0.22	0.024	.	.	0.011	0.0078	0.009	(0.002)
9310	BS 58D	0.127	0.45	0.010	0.005	0.32	0.156	3.02	1.35	0.14	0.042	.	.	0.009	0.0147	0.012	0.005
9325	BS 9325	0.25	0.91	0.008	0.007	0.32	0.13	3.29	1.48	0.31	0.030	(0.004)	0.0049	0.010	0.0089	0.009	0.004
P-20	BS 55E	0.307	0.72	0.014	0.024	0.60	0.032	0.053	1.66	0.40	(0.004)	.	.	(0.005)	0.0096	0.002	0.019
AMS 6418	BS 69B	0.2258	1.28	0.008	0.013	1.27	0.086	1.71	0.28	0.39	0.024	.	.	0.035	0.0057	0.006	(0.002)
A193	BS 4942	0.414	0.56	0.015	0.021	0.22	0.165	0.16	0.97	0.54	(0.004)	0.005	0.0006	0.010	0.0080	0.014	0.28
A485-1	BS A485-1	0.98	1.10	0.019	0.004	0.62	0.16	0.13	1.07	0.029	0.017	0.006	.	0.010	0.0060	0.011	0.003
E52100	BS 53E	1.08	0.37	0.007	0.012	0.24	0.11	0.26	1.45	0.10	0.003	.	.	0.011	0.0086	0.005	0.004
Nitriding	BS 68C	0.38	0.60	0.018	0.008	0.305	0.178	0.166	1.77	0.36	1.06	(0.004)	(0.0002)	0.011	0.0045	0.008	0.007
LF 3	BS LF 3	0.183	0.52	0.006	0.018	0.206	0.080	3.36	0.098	0.056	0.017	0.006	(0.0001)	0.056	0.0054	0.006	(0.002)

Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Ca	Co	N	Sn	V
## this item sold out, most BS are available as XRF																	

## CRM SOLUBLE ELEMENTS IN LOW ALLOY STEEL SET

available in set/7 only

-S = Soluble, -T = Total

38 mm Ø x 30 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al-S	Al-T	B-S	B-T	Mo
NCS HS11717a-1	0.0023	0.018	0.012	0.0027	0.0054	0.0036	0.011	0.023	0.0069	0.0078	0.0002	0.0004	0.0053
NCS HS11717a-2	0.0028	0.104	0.014	0.011	0.077	0.049	0.045	0.042	0.024	0.026	0.0011	0.0012	0.304
NCS HS11717a-3	0.032	0.303	0.018	0.067	1.55	0.403	0.563	0.236	0.295	0.298	0.0018	0.0020	0.034
NCS HS11717a-4	0.096	0.669	0.012	(0.050)	1.09	0.316	0.400	0.102	0.214	0.216	0.0085	0.0096	0.144
NCS HS11717a-5	0.243	1.04	0.030	0.042	0.769	0.248	0.393	0.106	0.101	0.104	0.0071	0.0074	0.105
NCS HS11717a-6	0.387	1.47	0.038	0.030	0.436	0.167	0.206	0.409	0.050	0.051	0.0047	0.0049	0.071
NCS HS11717a-7	0.498	2.10	0.050	0.022	0.176	0.075	0.107	0.612	0.022	0.024	0.0031	0.0033	0.196

Number	As	Bi	Co	N	Nb	Pb	Sb	Sn	Ti	V
NCS HS11717a-1	0.0034	(<0.00001)	0.0015	0.0016	(<0.0005)	(<0.0001)	0.00041	0.00020	0.0002	(0.0001)
NCS HS11717a-2	0.011	(<0.00001)	0.058	0.0017	0.031	(<0.0001)	0.00031	0.00073	0.020	0.011
NCS HS11717a-3	0.019	(<0.00001)	0.099	0.0032	0.079	(<0.0001)	0.00041	0.016	0.049	0.052
NCS HS11717a-4	0.073	(0.00001)	0.146	0.0031	0.223	(<0.0001)	0.00044	0.049	0.202	0.098
NCS HS11717a-5	0.071	(0.00001)	0.296	0.0048	0.318	(<0.0001)	0.00052	0.099	0.178	0.257
NCS HS11717a-6	0.045	(0.00001)	0.248	0.0049	0.106	(<0.0001)	0.00048	0.151	0.124	0.201
NCS HS11717a-7	0.034	(0.00001)	0.198	0.0063	0.153	(<0.0001)	0.00050	0.197	0.088	0.147

## RM TOOL STEEL XRF SET

Part Number: BS TS-18

AVAILABLE INDIVIDUALLY

17025

~7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	W	V	Co	N
A-2	BS 36C	0.96	0.46	0.023	0.027	0.31	0.18	0.19	5.01	0.99	.	(0.04)	0.11	0.03	.
A-10	BS A-10	1.41	1.75	0.016	0.022	1.15	0.16	1.82	0.24	1.53	0.006	<0.005	(0.004)	(0.010)	.
D-2	BS 37D	1.54	0.28	0.021	0.015	0.29	0.063	0.21	11.07	1.09	.	0.16	0.80	0.07	0.016
H-10	BS 49	0.36	0.33	0.014	0.015	0.92	0.072	0.20	3.51	2.41	0.004	0.31	0.62	2.00	0.0186
H-11	BS TH11	0.423	0.31	0.016	0.005	0.88	0.041	0.11	5.04	1.27	.	(0.01)	0.46	(0.008)	.
H-12	BS TH12	0.372	0.40	0.020	0.005	0.92	0.064	0.16	5.02	1.41	.	1.06	0.62	0.07	.
H-13	BS 34D	0.395	0.38	0.017	0.005	1.06	0.049	0.10	5.15	1.24	.	0.10	0.94	0.031	.
L-6	BS 39B	0.67	0.62	0.009	0.019	0.214	0.163	1.45	0.79	0.17	(0.011)	.	(0.01)	(0.02)	.
M-1	BS TM1	0.86	0.23	0.007	0.012	0.46	0.054	0.057	3.72	8.4	.	1.7	1.05	0.45	.
M-2	BS 32C	0.84	0.29	(0.018)	0.0010	0.29	0.13	0.35	3.98	4.85	(0.02)	6.3	2.03	0.31	.
O-1	BS 35D	0.879	1.13	0.021	0.024	0.22	0.141	0.132	0.495	0.035	(0.005)	0.46	0.181	0.012	.
O-6	BS 41	1.41	0.89	0.013	0.011	1.02	0.038	0.15	0.22	0.23	(0.007)	0.035	0.046	.	.
S-1	BS 33E	0.49	0.29	0.022	0.005	0.20	0.038	0.08	1.25	0.045	.	2.75	0.19	0.006	.
S-5	BS 38C	0.60	0.81	0.011	0.012	2.08	0.26	0.24	0.28	0.41	0.015	0.004	0.214	0.036	0.0081
S-7	BS TS7	0.529	0.70	0.016	0.010	0.27	0.05	0.10	3.18	1.34	.	0.19	0.35	0.043	.
T-1	BS 30D	0.745	0.348	0.029	0.0010	0.301	0.116	0.191	3.93	0.342	0.0123	17.73	1.077	0.101	0.0168
	BS 10V	2.46	0.52	0.019	0.079	0.89	0.076	0.08	5.41	1.30	<0.002	0.013	9.50	0.009	0.064
HP9-4-30	BS 9-4-30	0.30	0.22	0.008	<0.001	0.06	0.09	7.25	1.00	1.00	0.004	0.01	0.085	4.40	0.0015

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	W	V	Co	N
-------	--------	---	----	---	---	----	----	----	----	----	----	---	---	----	---

## TOOL STEEL

## CONTINUED ON THE NEXT PAGE

# = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Ti	V	W	Al
1	BS PML5	3.54	0.416	0.0198	0.0127	0.912	0.142	0.203	5.33	0.0330	1.22	0.111	0.0029	14.79	0.109	0.0025
2	BS 107	2.46	0.52	0.019	0.079	0.89	0.076	0.08	5.41	0.009	1.30	0.064	.	9.50	0.013	(<0.002)
1	DSZU C070	2.43	0.38	0.021	0.054	0.79	0.130	0.153	5.57	0.053	1.28	.	.	9.39	0.29	.
1	BS A-11	2.32	0.507	0.023	0.123	0.98	0.092	0.25	5.21	0.044	.	0.110	0.0019	9.24	(0.080)	0.0054
1	DSZU C082	2.42	0.33	0.029	0.014	0.36	0.118	0.239	12.24	0.035	1.11	.	.	4.02	0.17	.
1	ECRM 288-1D	2.08	0.292	0.024	(0.0012)	0.260	0.060	0.298	12.00	0.018	0.103	0.0151	.	0.055	(0.68)	0.012
1	DSZU C080	1.68	0.31	0.025	0.020	1.89	0.120	0.162	5.06	0.028	0.39	.	.	5.12	3.40	.
1	BS 37G	1.663	0.326	0.021	0.0007	0.352	0.044	0.152	11.77	0.0166	0.78	0.0310	0.0025	0.70	0.034	0.0060
1	BS TS15	1.64	0.27	(0.017)	0.067	0.357	0.065	(0.18)	4.12	4.87	0.48	0.045	0.0016	4.81	11.6	0.0032
1	ECRM 274-1D	1.563	0.397	0.0148	0.0096	1.057	0.0281	0.077	8.036	(0.0230)	1.4551	0.0769	(0.0011)	4.010	0.0087	(0.0025T)
2	CT D2	1.53	0.48	0.013	0.005	0.40	0.04	0.10	11.46	0.02	0.75	.	.	0.89	<0.01	.
1	IARM 41D	1.519	0.256	0.021	0.012	0.256	0.047	0.114	11.5	(0.020)	0.74	0.0152	(0.003)	0.77	0.034	0.014
2	BS 41A	1.50	0.93	0.004	0.001	0.97	0.034	0.17	0.20	0.006	0.19	0.0077	0.004	(0.003)	(<0.003)	0.010
1	IARM 45B	1.42	0.90	0.010	0.008	0.92	0.018	0.024	0.061	0.004	0.24	0.0080	0.002	(0.003)	(0.004)	0.010
2	BS 41	1.41	0.89	0.013	0.011	1.02	0.038	0.15	0.22	.	0.23	.	.	0.046	0.005	(0.007)
2	BS A-10	1.41	1.75	0.016	0.022	1.15	0.016	1.82	0.24	(0.010)	1.53	.	.	(0.004)	<0.0035	0.006
1	IARM 251A	1.398	0.33	0.014	0.058	0.58	0.13	0.131	4.1	0.129	5.16	0.044	0.003	3.9	5.5	0.01
2	IARM 45A	1.39	0.88	0.014	0.012	1.02	0.049	0.11	0.13	0.004	0.25	0.0079	0.003	0.005	.	0.011
1	DSZU C073	1.32	0.23	0.019	0.013	0.27	0.112	0.198	3.97	8.31	4.97	.	.	2.82	6.40	.
2	CT X27081	1.32	0.20	0.004	0.001	0.24	0.026	0.031	0.052	.	0.008	.	.	.	3.39	.
1	DSZU C072	1.40	0.29	0.024	0.019	0.55	0.106	0.192	4.25	0.011	5.39	.	.	3.59	4.33	.
3	CZ HS-2A	1.24	0.27	0.024	0.017	0.24	0.08	0.21	4.15	9.9	3.75	.	0.003	3.4	9.3	0.035
1	DSZU C077	1.16	0.19	0.030	0.024	0.40	0.142	0.271	4.07	7.73	3.05	.	.	2.04	12.17	.
1	DSZU C075	1.16	0.16	0.021	0.015	0.47	0.120	0.202	3.10	8.03	4.06	.	.	2.10	9.27	.
1	BS M-47	1.14	0.20	0.020	0.002	0.464	0.080	0.17	3.72	4.99	9.24	0.0219	(0.004)	1.23	1.36	(0.002)
1	IMZ 102/3	1.11	0.15	0.014	(0.0045)	1.06	0.13	0.021	1.59	.	0.43	.	.	(0.012)	.	0.017
1	DSZU C074	1.10	0.16	0.023	0.020	0.16	0.141	0.158	3.93	5.08	5.21	.	.	1.94	6.47	.
1	DSZU C071	1.06	0.20	0.020	0.028	0.38	0.162	0.149	3.77	8.10	9.67	.	.	1.07	1.74	.
1	SS 487/1	1.02	0.26	0.022	0.029	0.18	.	(0.14)	3.91	7.95	9.41	.	.	1.14	1.80	0.006
1	DSZU C081	1.01	0.32	0.017	0.011	1.10	0.124	0.207	7.78	0.029	2.13	.	.	0.25	0.05	.
2	CT M7	1.00	0.29	0.012	0.003	0.34	0.066	0.10	3.60	0.015	8.49	.	.	2.02	1.78	.
1	IARM 39B	0.99	0.54	0.017	0.003	0.35	0.10	0.14	4.79	0.014	1.01	0.0096	0.003	0.22	(0.026)	0.006
1	IARM 39C	0.99	0.45	0.019	0.007	0.28	0.077	0.144	4.99	0.013	0.97	0.011	0.0029	0.21	0.011	0.017
2	BS 36D	0.97	0.68	0.021	0.007	0.27	0.060	0.089	5.25	0.010	0.96	0.0108	.	0.29	0.028	0.010
2	CT A2	0.95	0.72	0.010	0.004	0.40	0.06	0.10	5.13	.	1.05	.	.	0.22	.	.
1	SS 485/1	0.94	0.41	0.043	0.039	0.30	.	(0.14)	4.02	4.97	0.66	.	.	1.02	17.8	(0.006)
1	IARM 320A	0.93	0.33	0.021	(0.0015)	0.36	0.091	0.204	4.22	4.90	4.79	(0.014)	0.0032	1.76	6.01	0.023
2	CT O1	0.91	1.27	0.009	0.004	0.36	0.05	0.06	0.49	.	0.07	.	.	0.25	0.51	.
1	ECRM 290-1D	0.91	0.24	0.016	0.016	0.08	0.081	0.33	4.18	5.12	4.81	0.0325	.	1.92	6.24	.
2	CT M10	0.88	0.27	0.016	0.004	0.30	0.061	0.14	3.97	0.012	7.89	.	.	1.99	0.008	.
2	BS 35D	0.879	1.13	0.021	0.024	0.22	0.141	0.132	0.495	0.012	0.035	.	(0.003)	0.181	0.46	(0.005)
1	IARM 304A	0.857	0.260	0.019	0.0016	0.36	0.14	0.133	3.55	0.278	8.04	0.034	0.002	1.23	1.65	0.009
2	14X 14946D	0.85	0.53	0.051	0.048	0.46	0.25	1.06	5.06	0.44	0.21	.	.	1.03	16.9	.
2	BS 32D	0.85	0.30	0.027	0.0022	0.25	0.039	0.053	4.14	0.010	4.92	0.018	.	1.82	6.15	0.018
1	IARM 306B	0.84	0.24	0.006	(0.001)	0.21	0.058	0.095	4.32	0.010	4.2	0.0049	(0.002)	0.98	(0.01)	0.08
1	SRM 1157	0.836	0.24	0.011	0.04	0.18	0.08	0.228	4.36	0.028	4.86	.	.	1.82	6.28	.
1	BS M-50	0.834	0.244	0.0066	0.0009	(0.205)	0.064	0.074	4.28	0.0151	4.29	0.0057	(0.0018)	0.97	0.0052	0.073
2	14X 14948C	0.83	0.65	0.011	0.017	0.26	0.04	0.29	4.04	0.16	0.14	.	.	0.65	18.8	.
2	CT M2	0.82	0.33	0.012	0.004	0.27	0.06	0.25	4.03	0.05	4.96	.	.	1.81	6.47	.
1	IARM 44C	0.82	0.301	0.027	0.004	0.31	0.12	0.132	4.04	0.247	5.02	0.033	0.004	1.91	6.0	0.05
2	CT M1	0.80	0.30	0.012	0.005	0.22	0.087	0.12	3.91	.	8.22	.	.	1.05	1.58	.
1	IARM FeTi-18	0.80	0.295	0.026	(<0.0010)	0.30	0.034	0.14	3.98	0.096	0.124	0.0195	0.026	1.05	18.0	0.054
1	BS 30D	0.745	0.348	0.029	0.010	0.301	0.116	0.191	3.93	0.101	0.342	0.0168	0.0189	1.077	17.73	0.0123
1	IARM 281A	0.74	0.30	0.015	0.019	0.29	0.096	0.15	3.89	4.8	0.49	0.0064	0.004	0.90	17.6	0.007
1	SS 486/1	0.74	0.21	0.029	0.021	0.27	.	(0.06)	4.54	0.08	5.20	.	.	1.82	5.80	(0.005)
1	IARM 40C	0.72	1.91	0.014	0.012	0.32	0.142	0.255	0.99	0.010	1.27	0.0083	0.008	0.010	0.009	0.019
1	14X HS1C	0.72	0.29	0.018	0.020	0.23	0.07	0.28	4.00	0.25	0.36	0.023	.	1.04	17.2	.
3	CZ HS-1A	0.72	0.28	0.023	0.011	0.28	0.08	0.14	4.15	4.7	0.06	.	0.003	1.33	17.5	0.03
1	IARM 43B	0.711	0.56	0.008	0.013	0.251	0.180	1.39	0.651	0.012	0.206	0.0093	0.0047	0.0035	<0.005	0.021
2	BS 40B	0.71	2.28	0.020	0.006	0.35	0.076	0.089	1.18	0.020	1.07	0.0076	0.002	0.10	0.11	0.002
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Ti	V	W	Al
1	DSZU C076	0.69	0.18	0.024	0.022	0.58	0.120	0.213	5.75	13.88	4.29	.	.	2.03	9.81	.
1	IARM 40B	0.68	1.98	0.012	0.003	0.39	0.050	0.096	1.04	0.015	1.22	0.0107	0.003	0.014	0.013	(0.006)
2	BS 39B	0.67	0.62	0.009	0.019	0.214	0.163	1.45	0.79	(0.02)	0.17	.	.	(0.01)	.	(0.011)
1	DSZU C078	0.67	0.22	0.022	0.019	0.117	0.116	0.121	3.98	0.022	0.14	.	.	1.04	18.30	.
1	SS 483/1	0.65	0.22	0.023	0.023	0.16	.	(0.08)	2.90	2.06	0.18	.	.	0.22	9.28	.
2	BS 38C	0.60	0.81	0.011	0.012	2.08	0.26	0.24	0.28	0.036	0.41	0.0081	0.007	0.214	0.004	0.015
1	ECRM 179-2D	0.598	0.539	0.027	.	0.578	0.111	0.0741	1.081	.	0.070	0.0068	.	0.188	1.87	.
1	IARM 47B	0.59	0.79	0.017	0.006	1.96	0.17	0.090	0.23	0.007	0.20	0.0092	0.010	0.17	(0.016)	0.014
1	DSZU C079	0.59	0.38	0.024	0.012	0.43	0.154	0.541	4.00	0.039	4.10	.	.	0.90	0.06	.
2	BS 33D	0.515	0.31	0.016	0.020	0.312	0.040	0.059	1.28	0.045	0.050	.	.	0.22	2.65	0.008
2	BS 33E	0.49	0.29	0.022	0.005	0.20	0.038	0.08	1.25	0.006	0.045	.	(0.002)	0.19	2.75	.
2	CT X67975	0.48	0.56	0.009	0.005	0.28	0.060	0.13	1.00	.	0.53	.	.	0.30	.	.
1	IARM 259A	0.479	0.399	0.020	0.0007	0.44	0.081	0.194	3.27	0.011	1.43	0.0077	0.0026	0.256	0.035	0.016
1	BS D-6	0.472	0.78	0.007	0.0008	0.228	0.130	0.602	0.99	0.012	1.01	0.0031	0.0025	0.122	0.0018	0.037
1	IMZ 57/1	0.46	1.05	0.028	0.012	0.58	0.14	0.15	1.67	.	0.48	.	.	0.34	.	.
1	IARM 46B	0.45	0.27	0.019	0.0040	0.89	0.147	0.108	1.09	0.013	0.222	0.0069	0.007	0.170	1.96	0.011
1	IMZ 53/1	0.41	0.60	0.018	0.011	1.304	0.17	0.28	2.85</							

## TOOL STEEL CONTINUED FROM THE PREVIOUS PAGE

Number	Als	As	B	Ca	Nb	O	Pb	Sb	Sn	Ta	Zr	Units
<b>BS PM15</b>	.	0.0040	(0.0002)	(0.0001)	0.014	0.0129	(0.00001)	(0.0010)	0.0034	(0.0003)	(0.0005)	38 mm Ø x 19+ mm <b>17025</b>
BS 10V	.	.	.	.	.	.	.	.	.	.	.	41 mm Ø x -7 or 19+ mm
DSZU C070	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
<b>BS A-11</b> Fe:79.5	.	0.0057	0.0008	(0.0002)	(0.0070)	0.028	(0.00006)	(0.001)	0.0055	.	(0.001)	38 mm Ø x -7 or 19+ mm <b>17025</b>
DSZU C082	.	.	.	.	.	.	.	.	.	.	.	~35 mm Ø x 25 mm
ECRM 288-1D	.	(0.0065)	.	.	.	.	.	.	.	.	.	~36-41 mm Ø x 28-35 mm
DSZU C080	.	.	.	.	.	.	.	.	.	.	.	~35 mm Ø x 25 mm
BS 37G	.	0.0026	0.0003	0.0014	0.0026	.	0.0005	0.0009	0.0010	.	.	34 mm Ø x -7 or 19+ mm
<b>BS TS15</b>	.	(0.006)	(0.0005)	(0.001)	0.009	(0.018)	.	Fe:71.4	0.0074	.	(0.003)	38 mm Ø x -7 or 19+ mm <b>17025</b>
ECRM 274-1D	.	(0.0013)	(0.0005)	.	.	(0.0026)	(0.000064)	(0.0002)	(0.0010)	.	.	38 mm Ø x 25 mm
CT D2	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
IARM 41D	.	(0.01)	(0.0006)	(0.0008)	(0.004)	(0.003)	(0.0008)	.	(0.005)	.	(0.002)	31 mm Ø x 2 or 18 mm
<b>BS 41A</b>	.	0.002	.	0.0006	.	0.002	.	.	0.002	.	.	38 mm Ø x -7 or 19+ mm <b>25(pre-17025)</b>
IARM 45B	.	(0.002)	(0.0001)	(0.001)	(0.002)	(0.0005)	(0.001)	0.008	.	.	(0.001)	31 mm Ø x 2 or 18 mm
<b>BS 41</b>	.	.	.	.	.	.	.	.	(0.008)	.	.	42 mm Ø x -7 or 19+ mm <b>17025</b>
BS A-10	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x -7 or 19+ mm
IARM 251A	.	0.016	(0.002)	(0.0005)	0.016	(0.01)	(0.002)	.	0.011	.	(0.002)	31 mm Ø x 2 mm
IARM 45A	.	(0.003)	(0.0001)	.	0.002	(0.0017)	(<0.005)	.	0.005	.	.	31 mm Ø x 2 mm
DSZU C073	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
CT X27081	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm last
DSZU C072	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
CZ HS-2A	.	.	.	.	.	.	.	.	0.01	.	.	~39 mm Ø x 25 mm
DSZU C077	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
DSZU C075	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
<b>BS M-47</b>	.	0.006	.	(0.002)	(0.004)	0.0037	.	.	0.006	.	.	38 mm Ø x -7 or 19+ mm <b>17025</b>
IMZ 102/3	.	.	(0.0007)	.	.	.	.	.	.	.	(0.007)	40 mm Ø x 40 mm
DSZU C074	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
DSZU C071	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
SS 487/1	.	(0.012)	.	.	.	.	.	.	(0.006)	.	.	38 mm Ø x 19 mm
DSZU C081	.	.	.	.	.	.	.	.	.	.	.	~35 mm Ø x 25 mm
CT M7	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
IARM 39B	.	.	.	.	0.006	.	.	.	0.004	.	.	31 mm Ø x 2 or 18 mm
IARM 39C	.	(0.005)	0.001	(0.001)	0.0040	0.001	(0.0001)	(0.002)	0.005	.	(0.002)	31 mm Ø x 2 or 18 mm
BS 36D	.	0.002	.	.	.	.	.	.	0.016	.	.	38 mm Ø x -7 or 19+ mm
CT A2	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
SS 485/1	.	(0.022)	.	.	.	.	.	.	0.019	.	.	38 mm Ø x 19 mm
IARM 320A	.	0.013	0.0011	.	(0.015)	(0.0021)	.	.	0.008	.	(0.003)	31 mm Ø x 2 or 18 mm
CT O1	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -19 mm
ECRM 290-1D	.	.	.	.	.	.	.	.	.	.	.	~36-41 mm Ø x 28-35 mm
CT M10	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
<b>BS 35D</b>	.	.	.	.	(0.001)	.	.	.	0.006	.	.	38 mm Ø x -7 or 19+ mm <b>17025</b>
IARM 304A	.	(0.01)	0.002	(0.002)	0.021	0.002	.	(0.001)	0.006	(0.002)	(0.002)	31 mm Ø x 2 (ok) or 18 (last) mm
14X 14946	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
BS 32D	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x -7 or 19+ mm
IARM 306B	.	(0.003)	(0.001)	.	0.007	(0.001)	(0.001)	0.0025	0.004	.	(0.002)	31 mm Ø x 2 or 18 mm
SRM 1157	.	.	.	.	.	.	.	.	.	.	.	32 mm Ø x 19 mm
<b>BS M-50</b>	.	0.0035	(0.0001)	(0.001)	0.0008	0.0010	(0.0001)	(0.0006)	0.0045	Fe:88.8	(0.0006)	38 mm Ø x -7 or 19+ mm <b>17025</b>
14X 14948C	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 15 mm last of stock
CT M2	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
IARM 44C	.	(0.01)	(0.002)	.	0.012	(0.003)	(0.002)	(0.004)	0.010	(0.004)	.	31 mm Ø x 2 mm last of stock
CT M1	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
IARM FeT1-18	.	.	.	.	(0.004)	(0.0027)	.	.	(0.010)	.	.	31 mm Ø x -2 or 18+ mm
<b>BS 30D</b>	.	0.0128	(0.0002)	0.0004	0.0071	0.0019	(0.0002)	0.0032	0.0246	(0.02)	(0.0001)	38 mm Ø x -7 or 19+ mm <b>17025</b>
IARM 281A	.	(0.02)	(0.003)	.	0.094	(0.003)	.	.	0.02	.	(0.002)	31 mm Ø x 2 or 18 mm
SS 486/1	.	(0.016)	.	.	.	.	.	.	0.014	.	.	38 mm Ø x 19 mm
IARM 40C	.	0.008	0.0009	(0.001)	0.003	0.0013	.	.	0.008	.	(0.002)	31 mm Ø x 2 or 18 mm
14X HS1C	.	.	.	.	.	.	.	.	(0.035)	.	.	40 mm Ø x 15 mm
CZ HS-1A	.	.	.	.	.	.	.	.	0.02	.	.	~39 mm Ø x 25 mm
IARM 43B	.	0.005	0.0002	.	0.004	0.0016	<0.0005	.	0.013	.	.	31 mm Ø x 2 or 18 mm
BS 40B	.	0.004	0.0006	.	.	.	.	.	0.005	.	.	41 mm Ø x -7 or 19+ mm
Number	Als	As	B	Ca	Nb	O	Pb	Sb	Sn	Ta	Zr	Units
DSZU C076	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
IARM 40B	.	.	(0.0010)	.	0.005	(0.0014)	.	.	0.004	.	.	31 mm Ø x 2 or 18 mm
<b>BS 39B</b>	.	.	.	.	.	.	.	.	(0.011)	.	.	41 mm Ø x -7 or 19+ mm <b>17025</b>
DSZU C078	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
SS 483/1	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm
BS 38C	.	0.011	.	.	(0.002)	.	0.022	.	0.022	.	.	38 mm Ø x -7 or 19+ mm
ECRM 179-2D	.	.	.	.	0.00144	.	.	0.00175	.	.	.	30 to 35 mm Ø x 20 mm
IARM 47B	.	.	(<0.001)	.	(0.002)	(0.0014)	(0.0003)	.	0.008	.	.	31 mm Ø x 2 or 18 mm
DSZU C079	.	.	.	.	.	.	.	.	.	.	.	~35 mm Ø x 25 mm
BS 33D	.	.	.	.	.	.	.	.	0.005	.	.	41 mm Ø x 12 mm
BS 33E	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 12 mm
CT X67975	.	.	.	.	.	.	<0.001	.	0.003	.	.	30-35 mm Ø x -16 mm last of stock
IARM 259A	.	0.006	0.0003	.	0.003	0.0014	<0.0005	.	0.004	.	0.001	31 mm Ø x 2 mm
<b>BS D-6</b>	.	0.011	(0.0003)	0.0011	(0.002)	(0.0008)	(0.0003)	0.0012	0.0104	Mg: 0.0002	.	38 mm Ø x -7 or 19 mm <b>17025</b>
IMZ 57/1	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
IARM 46B	.	(0.01)	0.0003	.	0.003	0.002	<0.002	.	0.016	.	.	31 mm Ø x 2 or 18 mm
IMZ 53/1	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
IMZ 56/1	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
<b>BS H-19</b>	.	0.0056	.	.	0.008	0.0071	.	.	0.0056	.	.	38 mm Ø x -7 or 19+ mm <b>17025</b>
IARM 255A	.	(0.002)	0.0004	(0.0004)	0.004	0.0011	<0.001	.	0.006	.	<0.005	31 mm Ø x 2 mm
IMZ 58/1	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
IMZ 51/1	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
ECRM 276-2D	.	.	.	.	.	.	.	.	0.0133	.	.	38 mm Ø x 25 or 30 mm
<b>BS H-13A</b> Fe:90.2	.	0.0050	(0.0007)	(0.0006)	0.0052	(0.016)	(0.0004)	(0.002)	(0.005)	.	(0.002)	38 mm Ø x -7 or 19+ mm <b>17025</b>
CT H13	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
IARM 255B	.	.	.	.	(0.006)	.	.	.	(0.006)	.	.	31 mm Ø x 2 or 18 mm
IARM 42C	.	(0.01)	0.0011	(0.0005)	(0.004)	0.003	0.0007	(0.004)	(0.006)	(0.004)	(0.002)	31 mm Ø x 2 or 18 mm
ECRM 271-1D	.	0.0057	.	0.0009	.	0.0020	.	.	0.0084	.	.	35 mm Ø x 25 mm
BS 49	.	.	.	.	.	.	.	.	(0.004)	.	.	49 mm Ø x -7 or 19+ mm
BS 9-4-30	.	.	.	.	.	.	.	.	.	.	.	35 mm Ø x -7 or 19+ mm
IARM 341A	.	(0.003)	0.0005	0.0011	(0.005)	0.0008	(0.001)	(0.001)	(0.005)	.	(0.003)	31 mm Ø x 2 or 18 mm
IMZ 196	.	.	0.065	.	0.073	.	.	.	.	.	.	37 mm Ø x 30 mm
IMZ 170	.	.	.	.	0.087	.	.	(0.002)	0.007	.	.	40 mm Ø x 40 mm
CZ CM-17A	0.0105	0.0060	.	.	.	.	0.0177	.	0.0109	.	.	~37 mm Ø x -25 mm
VS LG43/1	.	.	.	.	.	.	.	.	.	.	.	~45 mm Ø x -28 mm
IMZ 197	.	.	(0.007)	.	(0.011)	.	.	.	0.015	.	.	37 mm Ø x 30 mm
NCS HS20741	.	.	.	.	.	.	.	.	.	.	.	35 mm Ø x 40 mm
VS LG42/1	.	.	.	.	.	.	.	.	.	.	.	~45 mm Ø x -28 mm
VS LG37/1	.	.	.	.	.	.	.	.	.	.	.	~45 mm Ø x -28 mm
IMZ 179	.	(0.007)	.	.	(0.004)	.	.	.	0.010	.	.	40 mm Ø x 40 mm
IMZ 157	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
NCS HS20742	.	.	.	.	.	.	.	.	.	.	.	35 mm Ø x 40 mm
IMZ 177	.	.	.	.	.	.	.	.	0.008	.	.	40 mm Ø x 40 mm
13X 14713A	.	.	.	Mg:0.0016	.	.	.	.	0.0034	.	.	~40 mm Ø x -15 mm
SS 422	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm
IMZ 101/2	.	.	(0.0005)	.	.	.	.	.	.	(0.002)	.	40 mm Ø x 40 mm
SS 423	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm
SS 424	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm
NCS HS20743	0.021	.	.	.	.	.	.	.	.	.	.	35 mm Ø x 40 mm
IARM 180A	.	(										

## ALUMINUM IN STAINLESS AND HIGH ALLOY STEEL

# = Class, where 1 = CRM and 2 = RM

#	Number	Al	Ni	Cr	C	Mn	P	S	Si	Cu	Co	Mo	N	Nb	Ti	V
1	IMZ 158	1.56	0.24	25.51	0.091	1.34	0.015	0.007	2.23	0.097	.	0.025	.	.	0.12	0.078
1	13X PH17700A	1.172	6.98	16.88	0.0732	0.496	0.0181	0.0008	0.551	0.146	0.0464	0.340	0.0192	0.0201	0.051	0.0390
1	<b>BS 192</b>	1.17	7.11	16.44	0.074	0.835	0.025	0.0005	0.387	0.412	0.104	0.430	0.0290	0.168	0.076	0.124
2	CT X92834	1.14	8.32	12.57	0.035	0.044	0.003	0.003	0.019	0.030	0.030	2.20	.	0.001	0.019	<0.004
1	IARMPe177PH-18	1.09	7.11	17.08	0.080	0.730	0.020	(0.0005)	0.51	0.36	0.048	0.350	0.0153	0.009	0.083	0.062
1	13X PH13800A	1.075	8.04	12.53	0.0386	0.0332	0.0064	0.0030	0.081	0.0449	0.0220	2.10	0.0041	.	0.0122	0.0188
1	IARM 21D	1.03	8.29	12.69	0.032	0.052	0.008	(0.0014)	0.039	0.017	0.078	2.23	0.0037	(0.005)	0.016	0.017
2	BS 184A	1.00	8.34	12.66	0.035	0.06	0.007	0.001	0.080	0.041	0.036	2.20	0.0045	(0.006)	0.051	0.014
1	<b>BS 192A</b>	0.98	7.01	16.44	0.066	0.768	0.021	<0.002	0.300	0.334	0.114	0.28	0.029	0.208	0.083	0.077
1	IARM 152C	0.94	7.30	16.99	0.072	0.74	0.024	0.0006	0.263	0.316	0.113	0.36	0.0172	0.012	0.098	0.072

Number	As	B	Ca	O	Sn	Ta	W	Zr	Units
IMZ 158	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
13X PH17700A	.	0.0033	.	.	0.0055	.	0.009	.	-38 mm Ø x -15 mm
<b>BS 192</b>	(0.005)	(0.0003)	0.0007	0.0014	0.008	(0.001)	0.05	.	38 mm Ø x ~7 or 19+ mm <b>25(pre-17025)</b>
CT X92834	.	0.0009	.	.	0.002	.	.	<0.001	30-35 mm Ø x x ~19 mm last of stock
IARM Fe177PH-18	.	(0.0017)	.	.	(0.006)	.	(0.011)	.	31 mm Ø x 2 or 18 mm
13X PH13800A	.	.	.	.	0.0051	.	.	.	-38 mm Ø x -15 mm
IARM 21D	.	.	.	.	.	.	(0.012)	.	31 mm Ø x 2 or 18 mm
BS 184A	.	(0.0004)	(0.0003)	(0.0003)	(0.002)	.	0.032	.	38 mm Ø x ~7 or 19+ mm
<b>BS 192A</b>	(0.0035)	(0.0003)	(0.0006)	(0.0006)	0.008	.	0.048	.	38 mm Ø x ~7 or 19+ mm <b>25(pre-17025)</b>
IARM 152C	(0.004)	0.0029	(0.0005)	(0.001)	0.007	(0.005)	0.026	.	31 mm Ø x 2 mm

## CALCIUM IN STAINLESS AND HIGH ALLOY STEEL

# = Class, where 1 = CRM and 2 = RM

#	Number	Ca	Ni	Cr	C	Mn	P	S	Si	Cu	Co	Mo	N	Nb	V	W
1	<b>BS Ca304-4</b>	0.0075	8.77	18.26	0.096	0.783	0.0205	0.0070	0.887	0.143	(0.007)	0.0041	0.061	0.063	0.0686	0.0056
1	13X 14923A	0.0044	0.452	11.26	0.205	0.501	0.0197	0.0031	0.330	0.0563	0.0207	0.819	0.0321	0.005	0.295	.
1	ECRM 379-1D	0.0033	30.83	26.79	0.0121	1.804	0.0166	0.0006	0.393	0.984	0.0390	3.290	0.0550	(0.0028)	0.0663	(0.0091)
2	BS 193	0.0020	1.82	18.48	0.104	12.11	0.018	0.002	0.66	0.088	0.028	0.21	0.37	0.014	0.107	(0.007)
2	BS SS4952	0.0019	0.23	13.15	0.347	0.41	0.016	0.003	0.66	0.045	0.030	0.049	0.027	0.004	0.089	(0.007)
2	BS 82E	0.0014	12.49	22.38	0.062	1.61	0.027	0.001	0.58	0.26	0.12	0.31	0.072	0.062	0.064	0.041
1	<b>BS 9942</b>	0.0014	13.55	18.21	0.021	1.84	0.025	0.006	0.49	0.305	0.086	3.30	0.071	0.005	0.072	0.032
1	<b>BS 9842</b>	0.0010	20.02	24.19	0.059	1.50	0.025	0.0016	0.99	0.147	0.237	0.111	0.037	0.026	0.075	0.011
1	ECRM 272-1D	0.00090	0.2445	11.927	0.2815	0.600	0.0156	0.0196	0.420	0.0192	0.0145	0.0030	0.0508	0.0028	0.0167	.
2	BS 94C	0.0008	0.43	25.90	0.057	0.45	0.024	0.002	0.62	0.056	0.042	0.20	0.065	0.032	0.12	(0.03)
2	BS 87F	0.0007	10.12	17.30	0.055	1.64	0.024	0.025	0.67	0.28	0.17	0.29	0.037	0.57	0.13	0.050

Number	Al	As	B	O	Pb	Sb	Sn	Ti	Zn	Units
<b>BS Ca304-4</b>	0.017	0.0063	0.0031	0.013	0.0008	(0.0002)	0.0024	0.0046	Zr:0.0036	~38 mm Ø x ~38mm Fe: 70.7 <b>17025</b>
13X 14923A	0.003	.	.	.	.	.	0.004	.	.	~40 mm Ø x -15 mm
ECRM 379-1D	(0.00246)	(0.0018)	0.00190	(0.0027)	(0.000038)	0.00057	0.0021	(0.0014)	.	38 or 45 mm Ø x 25 mm
BS 193	(0.003)	.	0.0007	(0.004)	.	.	0.004	0.003	.	32 mm Ø x ~7 or 19+ mm
BS SS4952	0.003	0.002	(0.0004)	0.005	.	.	0.004	0.002	.	38 mm Ø x ~7 or 19+ mm
BS 82E	0.006	.	0.0024	.	.	.	0.006	0.003	.	38 mm Ø x ~7 to 19 mm
<b>BS 9942</b>	0.004	(0.004)	0.0014	(0.0023)	.	.	0.006	(0.002)	.	44 mm Ø x ~7 or 19+ mm <b>25(pre-17025)</b>
<b>BS 9842</b>	0.014	(0.002)	0.0025	(0.0044)	.	.	0.005	0.003	.	38 mm Ø x ~7 or 19+ mm <b>25(pre-17025)</b>
ECRM 272-1D	0.0046	0.0116	0.0018	.	.	0.0007	.	0.00096	0.0031	38 mm Ø x 25 or 30 mm
BS 94C	0.004	.	(0.0005)	0.0061	.	.	0.006	.	.	44 mm Ø x ~7 or 19+ mm
BS 87F	0.004	0.005	(0.0006)	0.005	.	.	0.004	0.004	.	41 mm Ø x ~7 or 19+ mm

## COPPER IN STAINLESS AND HIGH ALLOY STEEL

# = Class, where 1 = CRM and 2 = RM

\* Provisional Analysis

#	Number	Cu	Ni	Cr	C	Mn	P	S	Si	Co	Mo	N	Nb	Ti	V	W
1	13X PH 3N	5.83	3.03	16.0	0.110	0.39	0.0136	0.019	1.25	0.306	0.74	0.111	0.45	0.0193	0.246	.
1	13X PH 4P	5.53	4.07	15.5	0.033	0.69	0.021	0.019	0.64	0.50	0.255	0.082	0.355	0.075	0.55	.
1	13X PH 2M	4.03	3.56	16.80	0.0598	1.184	0.0201	0.0419	0.502	0.0927	1.009	0.052	0.143	0.049	0.1028	.
2	BS 9621	3.42	4.61	14.93	0.035	0.31	0.017	0.0011	0.468	0.029	0.063	0.013	0.27	(0.001)	0.096	(0.01)
2	BS 185A	3.41	4.43	14.46	0.033	0.49	0.022	0.002	0.38	0.026	0.30	0.027	0.32	(0.001)	0.048	(0.014)
1	<b>BS 17-4PHB</b>	3.35	4.52	15.60	0.042	0.559	0.022	0.023	0.43	0.040	0.110	0.047	0.315	0.0045	0.061	(0.02)
2	BS 9622	3.34	4.34	14.34	0.032	0.63	0.019	0.004	0.42	0.040	0.27	0.028	0.33	(0.001)	0.074	(0.020)
2	BS 17-4PHA	3.30	4.69	15.40	0.018	0.85	0.023	0.022	0.40	0.072	0.34	0.022	0.204	.	0.043	.
2	CT 20 Cb-3	3.28	33.55	19.63	0.034	0.19	0.017	0.003	0.38	0.035	2.25	.	0.86	.	0.053	.
2	CT 630	3.25	4.20	15.94	0.036	0.39	0.018	0.013	0.63	0.11	0.11	0.028	0.36	.	0.022	.
1	<b>BS 17-4PHC</b>	3.23	4.24	15.40	0.033	0.81	0.022	0.027	0.399	0.077	0.45	0.027	0.258	(0.001)	0.090	0.121
2	BS 187A	3.10	33.06	19.75	0.022	0.52	0.017	0.0025	0.26	0.32	2.06	0.0157	0.57	(0.002)	0.10	(0.02)
1	ECRM 273-1D	3.046	4.85	14.747	0.0336	0.785	0.0131	0.0004	0.378	0.0391	0.2462	0.0444	0.221	.	0.0512	.
1	VS LG64	2.88	28.3	24.7	0.049	0.75	0.017	0.0032	0.76	.	2.89	.	0.048	0.64	0.094	0.013
1	SRM C2400	2.63	4.07	17.06	0.036	0.71	0.013	0.003	0.61	0.10	0.23	.	0.15	.	0.092	.
2	CT 455	2.32	8.22	11.37	0.012	0.074	0.010	0.005	0.13	.	0.027	0.002	0.28	1.18	.	.
2	BS SS1962	2.22	8.32	11.42	0.008	0.06	0.006	0.0025	0.06	(0.015)	0.008	0.0025	0.27	1.11	0.071	(<0.02)
1	13X 45500A	2.20	8.36	11.39	0.0041	0.0263	0.0049	0.0020	0.059	0.0152	0.0185	0.0030	0.250	1.187	0.0689	.
1	IARM 16C	2.08	8.23	11.34	0.003	0.024	0.007	0.0046	0.03	0.017	0.009	0.0030	0.248	1.16	0.070	0.008
1	SS 475	1.94	5.66	14.14	0.050	0.89	0.037	0.008	0.21	0.22	1.59	.	0.22	.	.	.
1	<b>BS 9812</b>	1.65	6.61	14.82	0.031	0.485	0.018	0.004	0.43	0.110	0.76	0.0195	0.645	(0.005)	0.088	0.025
1	<b>BS 9811</b>	1.63	6.55	14.87	0.027	0.380	0.016	0.0010	0.36	0.055	0.744	0.0196	0.62	(0.003)	0.086	0.013
1	IARM 318B	1.63	5.71	15.9	0.050	1.02	0.022	0.0006	0.41	0.100	1.57	0.032	0.086	0.014	0.115	0.087
1	13X PH2S143A	1.61	5.20	13.45	0.044	0.544	0.0205	0.0022	0.478	0.0475	1.325	0.024	0.222	.	0.087	0.019
1	<b>BS 179B</b>	1.56	6.17	25.9	0.0161	0.890	0.0243	0.0002	0.371	0.0394	3.34	0.239	0.008	(0.0008)	0.079	0.053
1	IARM 15C	1.54	6.35	14.39	0.032	0.760	0.019	0.0018	0.26	0.024	0.722	0.0148	0.63	(0.002)	0.041	(0.020)
1	13X NSA 7B	1.53	6.37	25.69	0.013	0.864	0.0160	0.0005	0.278	0.047	3.28	0.232	(0.009)	.	0.080	0.133
1	<b>BS 179C</b>	1.53	6.10	25.9	0.0164	0.878	0.0236	0.0003	0.373	0.0386	3.34	0.236	0.009	(0.0005)	0.080	0.056
1	<b>BS 450</b>	1.51	6.24	14.4	0.029	0.596	0.016	0.0013	0.323	0.028	0.671	0.022	0.59	<0.008	0.051	0.016
2	CT 450	1.49	6.36	15.20	0.036	0.39	0.014	0.006	0.29	0.16	0.80	0.028	0.67	.	0.043	.
1	ECRM 295-1D	1.481	24.40	19.51	0.0166	1.758	0.0167	0.0004	0.418	0.0450	3.996	0.0615	.	.	0.0453	.
1	IARM 239B	1.48	5.78	25.9	0.013	0.86	0.025	0.0005	0.39	0.048	3.42	0.25	0.024	0.002	0.099	0.106
1	13X NSA 7A	1.42	5.67	25.91	0.0209	0.951	0.022	0.0009	0.359	.	3.25	0.247	0.015	.	.	.
2	HRT FE2004-H	1.33	24.25	19.08	0.021	1.83	0.021	0.004	0.47	0.046	4.17	.	0.046	0.005	0.042	.
1	13X PH 7F	0.77	5.41	13.16	0.118	1.487	0.028	0.0057	1.402	0.049	2.52	0.044	0.241	0.0196	0.043	.

Number	Al	Ag	As	B	Ca	Cd	Fe	Mg	O	Pb	Sb	Sn	Ta	Units
13X PH 3N	0.050	.	.	0.0042	.	.	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm
13X PH 4P	0.029	.	.	0.0031	.	.	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm
13X PH 2M	0.0419	.	.	0.0047	.	.	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm
BS 9621	0.003	.	.	0.0004	(0.0001)	.	.	.	.	.	.	0.003	(0.002)	38 mm Ø x ~7 or 19+ mm
BS 185A	0.002	.	.	0.0017	(0.0002)	.	.	.	(0.0021)	.	.	0.007	(0.002)	38 mm Ø x ~7 or 19+ mm
<b>BS 17-4PHB</b>	0.034	.	(0.003)	0.0036	(0.0004)	<b>17025</b>	[74.8]	(0.0002)	(0.002)	(0.001)	(0.002)	0.012	(0.002)	41 mm Ø x ~7 or 19+ mm
BS 9622	0.002	.	.	0.0004	.	.	.	.	.	.	.	0.006	.	38 mm Ø x ~7 or 19+ mm
BS 17-4PHA	.	.	.	0.0016	.	.	.	.	.	.	.	.	(0.002)	38 mm Ø x ~7 or 19+ mm
CT 20 Cb-3	.	0.0019	.	0.0023	.	.	.	.	.	0.002	.	0.003	.	30-35 mm Ø x ~19 mm
CT 630	.	0.0004	.	0.0018	.	.	.	.	.	0.001	.	0.007	.	30-35 mm Ø x ~16 mm
<b>BS 17-4PHC</b>	0.0023	.	0.0043	0.0026	0.0007	<b>17025</b>	74.8	.	0.010	(0.0001)	.	0.0100	.	44 mm Ø x ~7 or 19+ mm
BS 187A	(0.009)	.	.	0.0022	.	.	.	.	0.0029	last of stock	.	0.003	<0.002	41 mm Ø x ~7 mm
ECRM 273-1D	.	.	0.0030	.	.	.	.	.	.	.	.	0.0021	.	40 mm Ø x 20 mm
VS LG64	0.189	.	.	.	.	.	.	.	.	.	.	.	.	~47 mm Ø x ~30 mm
SRM C2400	.	.	.	.	.	.	.	.	.	.	.	.	.	32 mm Ø x 19 mm
CT 455	.	0.0002	.	0.0024	.	.	.	.	.	<0.001	.	0.004	.	30-35 mm Ø x ~19 mm
BS SS1962	0.067	.	0.002	0.0018	.	.	.	.	(0.001)	.	.	0.004	.	38 mm Ø x ~7 or 19+ mm
13X 45500A	0.073	.	.	.	.	.	.	.	.	.	.	0.0048	(0.0050)	~38 mm Ø x ~15 mm
IARM 16C	0.072	.	(0.003)	0.0011	.	.	.	.	0.0014	.	.	(0.003)	.	31 mm Ø x 2 or 18 mm
SS 475	0.013	.	.	.	.	.	.	.	.	.	.	0.015	.	38 mm Ø x 19 mm
<b>BS 9812</b>	(0.002)	.	(0.005)	(0.0003)	0.0012	.	.	.	(0.007)	<b>25(pre-17025)</b>	.	0.004	.	50 mm Ø x ~7 or 19+ mm
<b>BS 9811</b>	(0.003)	.	(0.003)	(0.0003)	0.0014	.	.	.	(0.0060)	<b>25(pre-17025)</b>	.	0.004	.	38 mm Ø x ~7 or 19+ mm
IARM 318B	(0.004)	.	(0.004)	0.0003	.	.	.	.	0.009	.	.	0.004	(0.004)	31 mm Ø x 2 or 18 mm
13X PH2S143A	.	.	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm
<b>BS 179B</b>	0.0070	.	0.0036	0.0015	(0.0004)	<b>17025</b>	[61.5]	(0.0004)	0.0037	(0.00002)	0.0005	0.0019	(0.0006)	38 mm Ø x 19+ mm
IARM 15C	(0.005)	.	0.0044	(0.0006)	(0.0004)	.	.	.	(0.003)	(0.003)	(0.003)	0.009	(0.004)	31 mm Ø x 2 or 18 mm
13X NSA 7B	0.0142	.	0.0018	.	.	.	.	.	.	0.0009	0.0020	.	.	~41 mm Ø x ~15 mm
<b>BS 179C</b>	0.0078	.	0.0034	0.0015	(0.0003)	<b>17025</b>	[61.6]	(0.0004)	0.0038	(0.00002)	0.0005	0.0018	(0.0006)	38 mm Ø x ~7 or 19+ mm
<b>BS 450</b>	(0.003)	.	0.0033	(0.0003)	<0.005	<b>17025</b>	75.5	.	0.0027	<0.005	0.0010	0.0046	.	44 mm Ø x ~7 or 19+ mm
CT 450	.	0.0013	.	.	.	.	.	.	.	0.001	.	0.008	.	30-35 mm Ø x ~15-19 mm
ECRM 295-1D	0.0203	.	0.0041	0.0018	.	.	48.36	(0.0003)	.	.	.	0.0007	0.0025	38 mm Ø x 25 or 30 mm
IARM 239B	0.008	.	0.0008	.	.	.	.	.	(0.004)	.	.	.	(0.003)	31 mm Ø x 2 mm
13X NSA 7A	(0.009)	.	.	.	.	.	.	.	.	.	.	.	.	42 mm Ø x 15 mm last
HRT FE2004-H	0.005	.	.	0.0021	.	.	.	.	.	.	.	.	.	32 mm Ø x 20 mm
13X PH 7F	0.012	.	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm



**MANGANESE STAINLESS STEEL**

# = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

# Number	Mn	Ni	Cr	C	P	S	Si	Cu	Mo	Al	Co	N	Nb	V	W
1 IARM 294A	21.6	2.9	19.7	0.017	0.026	0.0028	0.43	0.34	1.8	(0.01)	0.021	0.78	(0.03)	0.046	(0.01)
1 IARM 295A	19.7	1.84	18.0	0.021	0.028	0.0041	0.36	0.113	0.97	(0.01)	0.021	0.62	0.018	0.046	0.016
1 ECRM 294-1D	18.68	0.429	17.98	0.0657	0.0271	0.00031	0.283	0.0242	0.0861	(0.0095)	0.0288	0.566	(0.00117)	0.0694	(0.00114)
1 IARM 214A	18.3	2.33	12.36	0.018	0.033	0.002	1.00	0.36	0.44	(0.002)	0.021	0.27	0.23	0.04	0.02
1 VS RG20/1	15.77	0.673	14.35	0.064	(0.02)	(0.01)	0.81	0.265	0.089	.	.	.	0.175	0.166	0.007
1 VS RG22/1	13.41	3.94	13.25	0.054	(0.02)	(0.008)	0.63	0.358	0.121	.	.	.	0.38	0.125	0.137
2 BS 193	12.11	1.82	18.48	0.104	0.018	0.002	0.66	0.088	0.21	(0.003)	0.028	0.37	0.014	0.107	(0.007)
2 CT ISO035A	12.04	1.81	18.48	0.102	0.023	0.002	0.59	0.17	0.28	<0.004	0.037	0.33	0.004	0.058	0.002
1 13X NSC3AB	11.00	3.19	24.1	0.74	0.019	0.010	1.39	0.287	0.059	0.035	0.019	0.51	2.56	0.158	0.034
1 IARM 296A	10.6	1.71	11.2	0.074	0.027	0.002	0.38	0.12	0.60	(0.005)	0.018	0.23	0.043	0.056	(0.01)
2 BS 190	9.72	6.74	19.57	0.022	0.015	0.001	0.46	0.072	0.15	(0.004)	0.044	0.255	(0.004)	0.11	0.015
2 CT ISO129A	9.31	6.86	19.62	0.030	0.002	<0.001	0.40	0.152	0.25	0.014	0.102	0.264	0.025	0.144	0.03
1 13X NSC6A	8.85	6.52	20.47	0.0266	0.0049	0.0055	0.523	0.0064	(0.002)	(0.009)	.	0.235	.	0.0052	.
1 VS RG23/1	8.74	1.98	18.5	0.045	(0.02)	(0.004)	0.49	0.099	0.401	.	.	.	0.24	0.69	0.3
2 BS 181A	8.16	8.15	16.52	0.071	0.019	0.001	4.03	0.18	0.21	0.022	0.072	0.148	0.017	0.094	0.04
1 BS 181B	8.07	8.18	16.17	0.070	0.021	0.0009	3.94	0.206	0.173	0.0119	0.044	0.158	0.026	0.044	0.016
1 13X NSC2Q	8.02	3.63	20.95	0.574	.	0.014	1.02	1.01	0.339	0.37	.	0.299	2.03	0.293	0.063
1 13X 21800A	8.00	8.32	16.81	0.0765	0.032	0.0011	4.03	0.431	0.325	0.012	0.0943	0.125	0.007	0.0619	.
1 NM 303	7.21	1.59	12.68	0.16	0.035	0.050	0.40	0.68	0.17	.	0.063	.	.	0.071	.
1 SRM 1297	7.11	5.34	16.69	0.066	0.038	0.0033	0.397	0.442	0.331	.	0.127	.	.	0.080	.
1 13X NSC1Q	6.79	5.10	19.46	0.269	0.0103	(0.007)	0.93	0.438	0.240	0.034	0.015	0.087	1.48	0.540	0.104
1 VS RG21/1	6.39	7.52	15.53	0.169	(0.02)	(0.008)	1.95	0.17	0.88	.	.	.	0.48	1.71	(0.2)
3 CZ SL-5A	5.8	4.94	11.7	0.37	0.021	0.014	0.36	2.90	4.12	0.035	0.26	.	0.20	0.21	0.78
2 BS 191	5.71	5.34	16.33	0.098	0.024	0.023	3.73	0.33	0.36	(0.002)	0.11	0.117	0.024	0.083	0.033
1 VS RG19/1	5.63	17.73	24.5	0.064	(0.02)	(0.009)	0.90	(0.2)	0.166	.	.	.	0.108	0.407	0.206
1 IARM FeN50-18	5.27	11.90	21.0	0.030	0.026	(0.0013)	0.24	0.28	2.01	(0.006)	0.081	0.26	0.18	0.121	0.023
1 13X NSA10A	5.23	12.98	20.67	0.0180	0.0206	0.0007	0.375	0.170	2.636	.	0.060	0.342	0.143	0.151	(0.061)
2 BS 180A	5.05	13.19	21.09	0.018	0.012	0.001	0.32	0.067	2.04	0.012	0.039	0.334	0.20	0.20	0.02
1 IARM 292A	5.0	1.47	21.35	0.030	0.018	0.001	0.75	0.29	0.097	0.010	0.031	0.245	0.009	0.084	0.01
1 BS 180B	4.65	11.9	21.5	0.022	0.017	0.0008	0.46	0.201	2.20	(0.007)	0.111	0.315	0.131	0.149	0.050
2 HRT FE2017-H	4.43	15.45	20.15	0.015	0.022	0.002	0.34	0.21	3.17	.	.	0.311	0.131	.	.
1 IARM 17D	4.15	11.83	21.06	0.041	0.026	0.0018	0.416	0.412	1.52	0.0032	0.23	0.311	0.14	0.118	0.056
1 13X NSC7B	3.55	7.50	23.9	0.397	0.019	0.0098	0.88	0.220	0.435	0.204	0.297	0.429	0.82	0.167	0.041
1 13X NSC5C	2.06	4.42	21.6	0.524	.	0.024	1.18	0.84	0.472	0.24	0.093	0.265	2.31	0.102	0.050

Number	As	B	Ca	O	Pb	Sb	Sn	Ta	Te	Ti	Zr	Units
IARM 294A	.	(0.003)	.	(0.003)	.	.	(0.006)	(0.003)	.	(0.002)	(0.002)	31 mm Ø x 2 mm
IARM 295A	.	0.002	.	(0.003)	.	.	0.004	.	.	0.0019	(0.001)	31 mm Ø x 2 or 18 mm
ECRM 294-1D	0.0037	(<0.00005)	(0.00026)	.	(0.000128)	(0.00053)	(0.0014)	.	(<0.00008)	(0.0008)	(0.0001)	40 mm Ø x 20 mm
IARM 214A	.	(0.001)	.	0.0026	.	.	0.008	.	.	0.002	.	31 mm Ø x 2 mm
VS RG20/1	.	.	.	.	.	.	.	.	.	0.093	.	45 mm Ø x ~30 mm
VS RG22/1	.	.	.	.	.	.	.	.	.	0.33	.	45 mm Ø x ~30 mm
BS 193	.	0.0007	0.0020	(0.004)	.	.	0.004	.	.	0.003	.	32 mm Ø x ~7 or 19+ mm
CT ISO035A	.	.	Fe: 65.91	.	(<0.0001)	.	0.003	.	.	0.001	<0.001	30-35 mm Ø x ~19 mm
13X NSC3AB	.	.	.	.	.	.	(0.0035)	.	.	(0.009)	.	40 mm Ø x ~15 mm
IARM 296A	.	(0.001)	.	(0.003)	.	.	0.007	.	.	(0.002)	.	31 mm Ø x 2 mm
BS 190	.	0.0005	.	0.0045	.	.	0.003	.	.	0.002	.	38 mm Ø x ~7 or 19+ mm
CT ISO129A	.	.	Fe: 62.62	.	.	.	.	.	.	.	.	30-35 mm Ø x ~16 mm
13X NSC6A	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 13 mm HIP
VS RG23/1	.	.	.	.	.	.	.	.	.	0.21	.	45 mm Ø x ~30 mm
BS 181A	.	0.0009	.	0.0010	.	.	0.005	.	.	0.007	last	38 mm Ø x ~7 mm
BS 181B	(0.002)	(0.0008)	(0.001)	0.0010	(0.0005)	(0.0007)	(0.004)	Fe:62.9	17025	0.0051	(0.0004)	38 mm Ø x ~7 or 19+ mm
13X NSC2Q	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x ~15 mm
13X 21800A	.	(0.001)	.	.	.	.	.	.	.	.	.	38 mm Ø x ~15 mm
NM 303	.	.	.	.	.	.	.	.	.	.	.	35 mm Ø x 20 mm
SRM 1297	.	.	.	.	.	.	.	.	.	.	.	32 mm Ø x 19 mm
13X NSC1Q	.	.	.	.	.	.	0.0026	.	.	0.004	.	40 mm Ø x ~15 mm
VS RG21/1	.	.	.	.	.	.	.	.	.	0.18	.	45 mm Ø x ~30 mm
CZ SL-5A	0.005	.	.	.	.	.	0.004	0.07	.	0.004	.	39 mm Ø x 25 mm
BS 191	.	(0.0006)	.	0.002	.	.	(0.006)	0.002	.	0.012	.	38 mm Ø x ~7 or 19+ mm
VS RG19/1	.	.	.	.	.	.	.	.	.	0.14	.	45 mm Ø x ~30 mm
IARM FeN50-18	.	.	.	(0.006)	.	.	(0.007)	.	.	(0.002)	.	31 mm Ø x 2 or 18 mm
13X NSA10A	.	0.0031	.	.	.	.	.	.	.	.	.	38 mm Ø x ~15 mm
BS 180A	.	(0.0023)	.	0.003	.	.	(0.002)	.	last	(0.002)	.	37 mm Ø x ~7-10 mm last
IARM 292A	.	0.0011	.	0.0024	.	.	0.004	(0.006)	.	0.005	.	31 mm Ø x 2 mm
BS 180B	(0.004)	0.0011	0.0009	0.0043	17025	(0.0007)	0.0040	(0.003)	Fe:58.5	(0.005)	(0.0009)	38 mm Ø x ~7 or 19+ mm
HRT FE2017-H	.	.	.	.	.	.	.	.	.	.	.	30 mm x 30 mm x 10 mm
IARM 17D	0.005	0.001	(0.002)	0.003	(0.0002)	(0.001)	0.0044	(0.003)	.	0.010	(0.002)	31 mm Ø x 2 or 18 mm
13X NSC7B	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x ~15 mm
13X NSC5C	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x ~15 mm

**CRM NICKEL BINARIES** analysis listed in mass % -40 mm Ø x ~15 mm

Number	Ni	C	Mn	P	S	Si	Cu	Cr	Al	Co	N	Mg	Mo	Nb	Ti	W
14X FeNi50C	51.5	0.0245	0.057	0.0168	0.16	0.151	0.089	0.066	0.319	0.416	.	.	.	.	.	.
14X FeNi45C	45.88	0.0082	0.0222	0.026	0.0015	0.77	0.089	0.076	0.98	0.572	.	.	.	.	.	.
14X FeNi40C	40.1	0.012	0.031	0.0148	1.03	0.050	0.081	0.64	.	1.057	.	.	.	.	.	.
14X 94100A	41.00	0.0055	0.443	0.0051	0.0027	0.103	0.0628	0.0265	2.00	0.0208	0.0016	0.0021	0.0053	(0.01)	0.0011	0.0017
14X FeNi10A	10.12	0.095	0.272	0.015	0.027	0.061	0.029	0.070	0.025	.	0.0055	.	.	.	.	.
14X FeNi8A	8.10	0.097	0.330	0.015	0.029	0.097	0.030	0.250	0.029	.	0.0061	.	.	.	.	.
14X FeNi6A	6.08	0.100	0.330	0.0155	0.028	0.075	0.028	0.073	0.025	.	0.0055	.	.	.	.	.



## SULFUR AND PHOSPHORUS IN STAINLESS AND HIGH ALLOY STEEL

# = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	S	P	Ni	Cr	C	Mn	Si	Cu	Al	Co	Mo	N	Nb	Ti	V
2	CT 416	0.36	0.018	0.24	13.15	0.088	0.52	0.63	0.004	.	0.019	0.065	0.020	.	.	0.025
2	BS 150	0.33	0.020	0.19	18.61	0.048	1.71	0.43	0.042	0.002	0.024	1.97	0.029	0.003	.	0.054
1	SRM 1223	0.329	0.018	0.232	12.64	0.127	1.08	0.327	0.081	.	.	0.053	.	.	.	0.068
2	BS 90F	0.328	0.023	0.30	13.01	0.085	0.53	0.58	0.12	(0.006)	0.021	0.14	0.037	0.011	.	0.076
1	<b>BS 303</b>	0.326	0.028	8.17	17.23	0.044	1.80	0.415	0.627	0.0019	0.071	0.410	0.023	0.008	0.017	0.056
1	13X 30300A	0.312	0.0205	8.60	17.62	0.041	1.83	0.422	0.025	.	0.0255	0.334	0.034	.	.	0.091
2	CT 303	0.31	0.029	9.08	17.78	0.070	1.64	0.58	0.49	.	0.16	0.41	.	.	.	0.044
1	IARM 355A	0.31	0.0186	0.427	17.81	0.0274	0.47	0.435	0.083	0.0016	0.047	0.337	0.0439	0.0095	0.0020	0.038
2	BS 154	0.302	0.027	0.25	17.58	0.030	0.40	1.26	0.063	(0.002)	0.019	0.31	0.039	0.005	.	0.046
2	13X 12549K	0.29	0.092	1.26	11.70	0.16	0.34	0.43	0.10	.	0.52	1.49	.	0.23	.	.
2	BS 153	0.280	0.018	0.140	17.38	0.026	0.41	0.53	0.052	0.002	0.017	0.30	0.021	0.002	(0.004)	0.045
2	BS 152	0.275	0.022	0.14	13.41	0.320	0.36	0.44	0.050	(0.002)	0.015	0.061	0.020	0.006	.	0.051
3	CZ SP-1A	0.26	0.024	8.6	17.7	0.047	1.87	0.33	0.52	0.004	0.095	0.42	.	0.012	0.02	0.058
1	IARM 352A	0.21	0.0182	0.269	13.11	0.341	1.13	0.357	0.148	(0.0025)	(0.016)	0.38	0.029	(0.012)	0.0015	0.028
1	13X 43020A	0.189	0.0246	0.517	16.07	0.147	1.439	0.415	0.0687	0.0047	0.0191	0.226	0.0212	0.0102	.	0.0542
1	IMZ 154	0.16	0.040	9.86	17.71	0.076	2.18	0.89	0.33	(0.16)	0.105	2.58	.	.	1.00	0.073
1	NCS HS41751A	0.16	0.035	8.07	17.41	0.075	1.70	0.71	0.26	.	0.13	0.33	0.077	.	.	0.068
2	BS 155	0.145	0.014	0.13	16.64	1.00	0.35	0.40	0.035	(0.001)	0.019	0.46	0.032	0.002	.	0.10
1	13X 12536T	0.090	0.0449	12.12	16.09	0.146	0.374	0.546	0.0793	0.108	0.280	2.48	0.0084	0.060	0.444	0.0513
1	SRM C1154a	0.051	0.06	13.08	19.31	0.100	1.44	0.53	0.44	.	0.38	0.068	.	.	.	0.135
1	VS LG58	0.0280	0.0135	4.26	23.4	0.48	0.99	0.292	0.388	.	.	2.41	.	0.214	0.039	0.264
1	13X 19004C	0.0135	0.074	17.90	22.77	0.075	2.01	0.35	0.0112	0.030	0.0501	3.43	.	0.152	.	0.041

Number	Ag	As	B	O	Pb	Sn	Ta	W	Units
CT 416	0.0002	.	.	.	<0.001	0.005	.	.	30-35 mm Ø x ~16 mm
BS 150	.	.	.	0.012	.	(0.003)	.	0.01	35 mm Ø x ~7 or 19+ mm
SRM 1223	.	.	.	.	.	.	.	.	32 mm Ø x 19 mm
BS 90F	.	.	.	0.011	.	0.005	.	0.032	38 mm Ø x ~7 to 19 mm last
<b>BS 303</b>	.	.	0.0013	0.0058	.	0.0091	.	0.023	44 mm Ø x ~7 or 19+ mm <b>17025</b>
13X 30300A	.	.	0.0035	.	.	.	.	.	~40 mm Ø x ~15 mm
CT 303	0.0003	.	.	.	0.001	0.007	.	.	30-35 mm Ø x ~16 mm
IARM 355A	.	(0.004)	(0.0011)	(0.010)	(0.0002)	(0.005)	.	(0.018)	31 mm Ø x 2 or 18 mm
BS 154	.	.	.	0.008	.	(0.005)	.	(0.01)	38 mm Ø x ~7 or 19+ mm
13X 12549K	.	.	.	.	.	.	.	.	40 mm Ø x 15 mm
BS 153	.	(0.004)	.	.	(0.001)	0.002	.	(0.002)	35 mm Ø x ~7 or 19+ mm
BS 152	.	.	.	.	.	0.003	.	<0.01	41 mm Ø x ~7 or 19+ mm
CZ SP-1A	.	0.006	0.0007	.	.	0.01	.	0.03	~39 mm Ø x 25 mm
IARM 352A	.	(0.005)	(0.0007)	(0.005)	.	0.0046	.	(0.005)	31 mm Ø x 2 or 18 mm
13X 43020A	.	.	(0.0032)	.	.	.	.	0.0108	~40 mm Ø x ~15 mm
IMZ 154	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
NCS HS41751A	.	.	.	.	.	.	.	.	38 mm Ø x 38 mm
BS 155	.	.	.	0.0048	.	(0.003)	.	.	36 mm Ø x ~7 or 19+ mm
13X 12536T	.	.	0.0214	.	.	0.0068	0.104	.	~40 mm Ø x ~15 mm
SRM C1154a	.	.	.	.	0.017	.	.	.	32 mm Ø x 19 mm
VS LG58	.	.	.	.	.	.	.	0.21	~47 mm Ø x ~30 mm
13X 19004C	.	.	(0.001)	.	.	(0.001)	0.011	.	~40 mm Ø x ~15 mm

## SELENIUM IN STAINLESS AND HIGH ALLOY STEEL

# = Class, where 1 = CRM and 2 = RM

#	Number	Se	Ni	Cr	C	Mn	P	S	Si	Cu	Al	Co	Mo	N	Nb	Ti
2	BS 151	0.328	0.24	13.19	0.090	0.41	0.021	0.018	0.65	0.11	(0.002)	0.018	0.088	0.022	0.005	(<0.003)
2	BS 186A	0.229	35.86	0.16	0.040	0.72	0.008	0.0053	0.19	0.016	(0.001)	0.028	0.0032	0.0026	(<0.002)	(<0.003)
1	IARM 253A	0.21	9.17	17.90	0.041	1.50	0.140	0.0089	0.50	0.223	0.003	0.088	0.348	0.0373	0.016	0.002
1	IARM 24B	0.19	35.86	0.121	0.053	0.82	0.009	0.0010	0.28	0.052	0.002	0.036	0.011	0.0017	<0.01	0.002
1	IARM 353A	0.17	0.265	17.01	0.98	0.95	0.019	0.025	0.49	0.13	0.0018	0.032	0.50	0.027	(0.011)	0.0015
2	CT ISO124A	0.167	48.07	0.079	0.011	0.73	0.007	0.006	0.40	0.015	.	0.012	0.009	.	.	.
2	BS 156	0.142	0.35	16.87	1.06	1.15	0.022	0.007	0.47	0.09	(<0.002)	0.047	0.50	0.041	0.005	0.001
1	IARM 253B	0.13	9.11	17.64	0.051	1.61	0.13	0.011	0.46	0.44	(0.004)	0.145	0.59	0.031	0.021	0.0027

Number	B	Fe	O	Sn	Ta	V	W	Zr	Units
BS 151	.	.	0.009	0.005	.	0.046	0.010	.	50 mm Ø x ~7 or 19+ mm
BS 186A	.	.	.	(0.002)	.	0.0012	(0.01)	.	38 mm Ø x ~7, ~12 or 19 mm
IARM 253A	0.0003	.	0.009	0.01	.	0.106	0.10	.	31 mm Ø x 2 or 18 mm
IARM 24B	(0.001)	62.6	0.003	0.0018	<0.005	<0.005	<0.04	<0.005	31 mm Ø x 2 or 18 mm
IARM 353A	(0.0006)	.	(0.005)	0.0056	(0.004)	0.116	0.041	(0.002)	31 mm Ø x 2 mm
CT ISO124A	.	50.65	.	.	.	.	.	.	44-47 mm Ø x ~11 or ~19 mm
BS 156	.	.	0.0045	(0.004)	.	0.13	0.11	.	41 mm Ø x ~7 or 19+ mm
IARM 253B	0.0007	.	0.007	(0.012)	(0.003)	0.092	(0.05)	.	31 mm Ø x 2 or 18 mm

## STAINLESS STEEL WITH NI &lt; 5.0 %

## CONTINUED ON THE NEXT PAGE

# = Class, 1=CRM, 2=RM, and 3=RM with no uncertainties \*\* Provisional Analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
3	CZ SL-4A	1.38	2.85	0.038	0.017	2.28	0.75	2.04	26.3	0.11	0.92	.	1.11	0.8	0.54	0.35
2	BS 156	1.06	1.15	0.022	0.007	0.47	0.09	0.35	16.87	0.047	0.50	0.041	0.005	0.001	0.13	0.11
1	BS 938	1.047	0.59	0.0266	<0.0025	0.49	0.02	0.187	16.72	0.021	0.46	0.051	0.0029	0.0012	0.057	0.0016
1	IARM T3d	1.040	0.697	0.0195	0.0012	0.614	0.184	0.256	16.36	0.0212	0.488	0.0492	0.0074	0.0035	0.058	0.046
1	13X 44004B	1.012	0.378	0.0232	0.0018	0.440	0.0587	0.197	16.50	0.0167	0.468	0.0308	0.008	(0.004)	0.0484	0.0156
2	BS 155	1.00	0.35	0.014	0.005	0.40	0.035	0.13	16.64	0.019	0.46	0.032	0.002	.	0.10	.
1	NCS HS41752	0.97	0.46	0.023	0.0016	0.48	0.082	0.192	17.61	.	0.057	.	.	.	0.088	.
1	ECRM 291-1D	0.90	0.81	0.017	0.0088	0.91	0.071	0.56	17.15	0.0233	2.10	0.1142	.	.	0.39	.
1	VS LG40/1	0.66	0.318	(0.02)	(0.006)	0.289	(0.15)	0.271	13.67	.	0.039	.	.	.	0.038	.
1	VS LG39/1	0.406	0.64	(0.02)	(0.007)	0.94	(0.12)	0.42	13.11	.	0.136	.	.	.	0.135	.
2	HRT FE2018-H	0.37	0.73	0.026	(0.003)	0.33	0.29	0.56	16.34	.	1.04	0.0134	.	.	0.064	.
1	13X 14122A	0.356	0.480	0.0177	0.0021	0.449	0.066	0.632	15.91	0.0224	0.855	0.0290	0.006	.	0.101	0.004
1	13X 40900A	0.035	0.716	0.0032	0.0059	0.616	0.134	0.231	10.98	0.053	0.102	0.007	0.032	0.530	0.099	.
2	BS SS4952	0.347	0.41	0.016	0.003	0.66	0.045	0.23	13.15	0.030	0.049	0.027	0.004	0.002	0.089	(0.007)
1	IARM 154C	0.339	0.423	0.0174	0.0043	0.37	0.120	0.215	12.41	0.016	0.036	0.054	0.014	0.0015	0.043	(0.005)
2	BS SS4951	0.333	0.58	0.016	0.0012	0.62	0.033	0.15	13.55	0.013	0.009	0.0127	0.006	0.002	0.032	.
2	BS 152	0.320	0.36	0.022	0.275	0.44	0.050	0.14	13.41	0.015	0.061	0.020	0.006	.	0.051	<0.01
1	IRSID 1825	0.305	0.650	0.019	0.022	0.336	0.100	0.308	12.90	0.026	0.052	.	.	.	0.052	.
1	13X 42027A	0.294	0.356	0.0139	0.0005	0.544	0.035	0.163	15.25	0.0191	0.990	0.402	0.004	(0.002)	0.048	0.019
1	ECRM 272-1D	0.2815	0.600	0.0156	0.0196	0.420	0.0192	0.2445	11.927	0.0145	0.0030	0.0508	0.0028	0.00096	0.167	.
1	SS 469	0.279	0.598	0.015	0.020	0.421	(0.02)	0.246	11.93	(0.01)	.	.	.	.	(0.02)	.
1	VS LG38/1	0.255	0.73	(0.02)	(0.01)	0.81	(0.16)	0.551	11.75	.	0.344	.	.	.	0.190	.
1	IMZ 168	0.24	1.36	0.019	0.012	1.12	0.093	0.17	13.91	(0.019)	0.026	(0.057)	.	(0.003)	0.053	.
1	IARM 205D	0.232	0.736	0.0209	0.0028	0.257	0.122	0.841	12.18	0.043	1.002	0.0484	0.013	0.0022	0.319	1.07
1	BS 422	0.232	0.640	0.0169	0.0013	0.404	0.080	0.676	11.25	0.0293	0.896	0.050	0.045	0.0011	0.274	0.95
1	SS 472	0.227	1.02	0.032	0.029	1.05	(0.02)	1.95	15.82	(0.02)	0.661	.	.	.	(0.02)	.
1	13X 42200A	0.220	0.651	0.0182	0.0012	0.314	0.136	0.738	11.41	0.0114	1.042	0.0585	0.0203	.	0.246	1.177
1	NCS HS41749	0.21	0.39	0.023	0.012	0.56	1.15	1.52	12.27	.	0.158	.	.	.	0.074	.
1	13X 42000A	0.208	0.679	0.0241	0.0253	0.496	0.202	0.295	12.56	0.0161	0.0398	0.0273	.	.	0.046	.
1	13X 14923A	0.205	0.501	0.0197	0.0031	0.330	0.0563	0.452	11.26	0.0207	0.819	0.0321	0.005	.	0.295	.
1	VS LG41/1	0.200	0.91	(0.02)	(0.008)	0.64	(0.12)	1.53	15.90	.	0.277	.	.	.	0.303	.
1	IMZ 171	0.195	0.42	0.020	0.014	0.21	0.116	0.59	11.44	0.024	1.23	0.057	.	(0.001)	0.26	.
1	NCS HS41748	0.194	0.62	0.016	0.011	0.54	0.008	0.077	12.70	.	0.010	.	.	.	0.048	.
2	HRT FE2015-H	0.19	0.52	0.021	0.002	0.37	0.07	0.25	12.87	.	0.07	0.045	.	.	0.055	.
1	13X 12548M	0.188	0.577	0.027	0.219	0.425	0.230	1.075	12.96	0.353	1.318	0.0500	0.586	.	0.044	0.031
2	HRT FE2010-H	0.18	0.60	0.024	0.004	0.39	0.08	1.94	15.95	0.023	0.13	.	.	.	0.044	0.024
1	SS 70	0.18	0.38	0.024	0.020	0.35	(0.06)	0.40	16.35	.	.	.	.	.	0.17	3.52
1	IARM 20B	0.18	0.35	0.019	0.004	0.40	0.069	1.94	12.42	0.030	0.32	0.0434	0.010	0.004	0.086	2.59
1	IARM 20C	0.18	0.30	0.018	0.007	0.35	0.060	1.93	12.15	0.031	0.12	0.0222	0.010	(0.003)	0.054	.
1	IMZ 167	0.175	1.16	0.016	0.0025	0.755	0.106	0.16	13.07	(0.021)	0.024	0.053	.	(0.002)	(0.02)	2.75
1	SS 473	0.172	0.494	0.019	0.030	0.604	(0.02)	(0.06)	9.06	(0.01)	0.95	.	.	.	0.020	.
1	13X 41800A	0.172	0.328	0.0176	0.0006	0.316	0.104	2.05	12.30	0.0357	0.068	0.028	(0.006)	.	0.020	2.75
2	BS 183A	0.172	0.35	0.016	0.0040	0.37	0.093	1.85	12.14	0.036	0.12	0.0256	0.006	0.002	0.090	2.60
1	IARM Fe418-18	0.168	0.429	0.016	(0.0005)	0.32	0.22	2.00	12.4	0.029	0.104	0.031	(0.019)	.	0.046	2.63
1	13X 15024X	0.166	0.610	0.0284	0.0294	0.750	0.332	2.99	14.65	0.1059	0.299	0.0156	0.039	.	0.150	0.039
1	13X 43100A	0.166	0.378	0.0199	0.0050	0.335	0.134	2.10	16.39	0.0239	0.0768	0.075	0.006	.	0.0577	0.004
2	13X 12549K	0.166	0.34	0.092	0.29	0.43	0.10	1.26	11.70	0.52	1.49	.	0.03	.	0.040	0.015
1	IARM 12C	0.155	0.55	0.022	0.0032	0.34	0.33	2.23	15.78	0.048	0.125	0.056	0.020	(0.002)	0.040	0.015
1	SS 470	0.153	0.235	0.024	0.035	0.335	(0.02)	0.369	17.68	(0.02)	.	.	.	.	(0.02)	.
2	BS 92B	0.150	0.42	0.021	0.003	0.42	0.13	2.12	15.92	0.04	0.17	0.073	(0.006)	.	0.07	0.02
1	SRM 1219	0.149	0.42	0.026	0.001	0.545	0.162	2.16	15.64	.	0.164	0.078	.	.	0.056	.
1	BS 431	0.146	0.579	0.0232	0.0047	0.393	0.282	2.25	15.8	0.050	0.092	0.049	0.034	0.0007	0.062	0.012
1	IARM 335A	0.138	0.85	0.016	0.0005	0.39	0.086	4.27	15.30	0.063	2.72	0.085	0.015	(0.002)	0.094	0.008
1	BS 355	0.136	0.862	0.0171	0.0003	0.374	0.173	4.18	15.43	0.053	2.73	0.081	0.0103	0.0007	0.106	0.0069
1	13X 41001A	0.136	0.464	0.0142	0.0037	0.298	0.056	0.0939	12.06	0.0143	0.0102	0.0316	.	.	0.079	.
1	IARM Fe410-18	0.136	0.117	0.0014	0.29	0.046	0.280	0.280	12.2	0.012	0.046	0.030	0.0021	.	0.065	(0.008)
1	NCS HS28747	0.132	0.453	0.027	0.0068	0.502	0.126	1.79	16.44	0.051	0.153	0.030	.	(0.002)	0.075	.
1	BS 410C	0.131	0.381	0.0206	0.0051	0.366	0.084	0.352	12.78	0.0185	0.055	0.039	0.056	0.0006	0.042	0.0131
1	BS 002I	0.128	0.420	0.021	0.008	0.354	0.040	0.100	12.00	0.015	0.016	0.029	(0.001)	(0.003)	0.029	0.005
1	IARM 10C	0.128	0.35	0.026	0.29	0.37	0.155	0.24	12.25	0.022	0.08	0.015	0.003	0.002	0.024	0.011
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	SRM 1223	0.127	1.08	0.018	0.329	0.327	0.081	0.232	12.64	.	0.053	.	.	.	0.068	.
1	ECRM 296-1D	0.1166	0.676	0.0178	0.0026	0.242	0.1498	2.790	11.82	0.0218	1.700	0.0214	.	0.0012	0.363	.
1	BS 416	0.116	0.64	0.0237	0.35	0.232	0.154	0.371	13.41	0.0241	0.030	0.043	(0.006)	0.0012	0.100	0.0034
1	13X T5035U	0.115	0.674	0.0415	0.0456	0.636	0.204	2.38	14.00	0.199	0.399	0.0584	0.500	.	0.160	0.048
1	13X 64152A	0.114	0.666	0.0123	0.0020	0.224	0.0622	2.50	11.34	0.0185	1.567	0.0339	.	.	0.275	.
1	13X 41600A	0.111	0.627	0.0253	0.302	0.442	0.160	0.331	13.23	0.0216	0.0499	0.0245	0.0053	.	0.0888	(0.003)
1	IARM 291A	0.11	0.71	0.016	0.009	0.23	0.060	2.62	11.3	0.021	1.61	0.035	0.022	0.0011	0.29	(0.01)
2	CT 410	0.11	0.48	0.015	0.023	0.27	0.079	0.34	12.04	0.023	0.053	0.036	0.001	0.001	0.025	0.004
1	IMZ 156	0.101	0.84	0.031	0.008	1.11	0.071	0.64	16.96	(0.033)	0.035	.	.	(0.032)	0.073	.
1	SS 471	0.095	0.417	0.018	0.023	0.326	(0.02)	0.96	23.85	(0.02)	.	.	.	.	(0.03)	.
1	NCS HS11721-4	0.093	0.531	0.029	0.026	0.506	0.169	0.632	17.43	0.176	0.089	0.023	.	0.288	0.241	.
1	IMZ 158	0.091	1.34	0.015	0.007	2.23	0.097	0.24	25.51	.	0.025	.	.	0.12	0.078	.
2	BS 151	0.090	0.41	0.021	0.018	0.65	0.11	0.24	13.19	0.018	0.088	0.022	0.005	<0.003	0.046	0.010
1	13X 15023W **	0.09	1.76	0.015	0.005	0.35	0.03	0.96	11.2	0.05	0.98	0.01	1.43	.	0.03	0.039
1	13X 14742A	0.084	0.714	0.0214												



## STAINLESS STEEL WITH C &gt; 0.05 %

## CONTINUED ON THE NEXT PAGE

# = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	VS LG76	0.445	0.342	0.021	0.0076	0.455	0.098	13.39	13.77		0.263	0.031		0.020	0.041	2.38
1	VS LG74	0.373	0.962	0.024	0.0049	2.49	0.093	23.66	18.30	0.031	0.104	0.030		0.030		0.052
1	KUT S21	0.37	0.19	0.017	0.021	1.26	0.11	22.3	3.99		4.12			0.50		
2	CZ CM-19A	0.361	0.783	0.0440	0.0182	1.588	0.986	15.27	13.12	0.222	1.023	(0.021)	0.091	0.254	1.235	0.311
1	VS LG79	0.313	1.28	0.017	0.0036	0.703	0.065	8.72	19.23		1.18		0.47	0.049		1.16
2	CZ SP-3C	0.30	0.43	0.026	0.011	0.84	0.185	5.31	16.42	0.041	0.26		(0.04)	(0.17)	0.19	0.12
1	DSZU C016	0.281	3.26	0.0192	0.0174	1.16	0.054	7.47	21.9		0.52	0.010		0.72	0.036	0.014
3	CZ SP-3B	0.27	0.29	0.023	0.008	0.72	0.62	5.65	15.1	0.02	0.24			0.13	0.10	0.12
1	KUT S19	0.26	0.32	0.012	0.021	2.32	0.19	12.8	7.00		0.11		0.81	0.048		
1	SRM C1153a	0.225	0.544	0.030	0.019	1.00	0.226	8.76	16.70	0.127	0.24				0.176	
1	13X 18001B	0.207	0.463	0.0090	0.0786	0.203	0.149	6.13	15.92	0.0231	0.816		0.0347	0.612		0.0996
1	KUT H6/1	0.20	0.49	0.021	0.024	0.67	0.10	0.15	18.9					0.10		(0.12)
2	CZ SP-3D	0.171	0.34	0.021	0.015	0.71	0.73	5.36	16.44	0.033	0.25		(0.04)	0.088	0.11	0.12
2	13X NSB1D	0.17	0.44		0.015	0.58		10.0	19.1		0.11	0.04				
1	IARM 339A	0.16	1.71	0.004	0.009	0.64	0.021	12.9	17.0	0.007	2.79	0.0060	(0.005)	(0.002)	0.007	(0.0119)
1	13X 18002D	0.159	0.722	0.0245	0.0487	0.352	0.116	7.92	17.77	0.0514	0.209		0.072		0.0542	
2	CZ CM-18A	0.143	1.792	0.0182	0.0119	0.903	2.393	20.44	20.59	0.097	2.282	0.0848			0.113	0.097
1	SS 468/1	0.143	1.70	0.014	0.020	1.41		8.90	17.96	0.018						
1	SRM C1152a	0.142	0.95	0.023	0.0064	0.64	0.097	10.86	17.76	0.22	0.44				0.033	
1	VS LG32/5	0.138	0.54	0.0057	0.039	0.185	0.019	7.10	19.75		0.110			0.92	0.317	0.205
1	13X NSA2J	0.132	1.03	0.0252	0.0275	0.739	0.259	10.08	17.82		2.013	0.131	0.155		0.139	
1	IARM 289A	0.126	1.67	0.006	0.0019	0.58	0.016	7.12	17.0	0.054	(0.005)	0.0032	0.008	0.028	0.01	0.01
1	IARM 241D	0.125	1.94	(0.003)	0.0023	1.00	0.242	8.98	18.12	0.022	(0.02)	(0.008)	0.028	0.018	0.031	(0.012)
1	DSZU C018	0.125	1.09	0.0268	0.0099	0.53	0.163	9.33	17.54		0.189	0.009		0.54	0.048	0.066
1	13X NSB3G	0.121	0.632			0.471		9.26	15.22		0.630	0.198				
1	KUT H5	0.12	0.48	0.017	(0.003)	0.70	0.22	0.20	21.8					0.03		0.10
1	13X 18003C	0.113	1.000	0.0545	0.0245	0.805	0.0433	10.08	19.56	0.100	0.401	0.090	1.042		0.0750	
1	IRSID 1819	0.112	0.903	0.023	0.0112	0.616	0.064	7.10	17.31	0.117	0.110	0.0288				
1	13X 17002E	0.112	0.801	0.0409	0.0250	0.486	0.1012	7.87	17.45	0.0702	0.204	0.061	0.487		0.0587	
1	NCS HS28743	0.110	0.841	0.024	0.0082	0.780	0.089	18.02	23.71	0.102	0.115	0.057	0.016	(0.003)	0.077	
1	IMZ 166A	0.108	1.99	0.019	0.005	2.51	0.025	21.93	25.53	0.030	(0.025)	0.077		0.003	0.038	
1	13X 12855N	0.107	0.918	0.0020	0.0063	0.863	0.340	11.79	16.29	0.155	2.96	0.0078	0.098	0.083		0.199
1	13X 14828A	0.104	1.52	0.0268	0.0067	2.19	0.409	11.25	19.3	0.143	0.301	0.037	0.016		0.080	0.0167
1	VS LG81	0.104	0.29	0.0121	0.0014	0.231	0.088	22.5	11.51		1.22		0.004	2.93	0.040	0.012
1	VS LG77	0.101	0.34	0.0149	0.0021	0.44	0.116	4.32	15.67		0.020	0.054	0.109		0.022	0.006
1	IMZ 164	0.100	1.77	0.019	0.002	0.82	0.26	6.75	20.96	0.035	3.48	0.249	0.049	(0.003)	0.053	(0.025)
2	13X 17003A	0.10	0.85	0.037	0.035	0.78	0.08	11.9	11.89	0.07	0.27		0.34			
1	VS LG73	0.098	1.26	0.019	0.0073	0.570	0.140	17.74	22.60	0.247	0.061	0.0319		0.0022		0.102
1	KUT S20	0.097	1.50	0.011	0.025	1.80	0.44	18.2	2.06		3.15		1.22	(0.01)		
1	VS LG80	0.097	0.709	0.025	0.0029	2.15	0.166	19.38	24.7		0.086	0.064		0.015	0.032	0.029
2	BS 253	0.094	0.58	0.018	<0.001	1.81	0.14	10.89	20.68	0.15	0.21	0.146	0.017	0.005	0.050	0.03
1	IARM 234C	0.092	1.93	0.0090	(0.0027)	0.88	3.41	9.00	18.15	0.034	0.012	(0.01)	0.053	0.026	0.055	(0.006)
1	SS 462	0.092	0.74	0.010	0.018	0.46		12.53	12.37							
1	DSZU C015	0.087	0.420	0.0118	0.059	0.214	0.070	12.15	15.36		0.89	0.020		0.177	0.021	0.023
1	SS 464/1	0.086	0.791	0.020	0.028	0.57		20.05	25.39	0.054						
1	13X 17004B	0.084	0.497	0.018	0.039	1.23	0.0449	16.04	21.37	0.055	0.455	0.0086	0.179	0.034		
1	IMZ 165	0.082	0.98	0.017	0.007	1.42	0.040	19.01	23.28	0.029	0.025	0.105		(0.002)	0.042	
1	SS 467/1	0.082	0.788	0.018	0.019	0.52		9.21	18.09				0.99			
1	13X 12854M	0.081	1.84	0.038	0.028	0.89	0.205	11.38	15.64	0.344	2.00	0.0097	0.33	0.052		0.141
1	VS LG35/5	0.078	0.81	0.042	0.0094	1.01	0.066	8.23	18.44		0.39			0.73	0.041	0.107
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	13X 17001C	0.0769	1.543	0.055	0.0134	0.215	0.0161	6.31	14.83	0.0979	0.0967		0.546			
1	KUT S26	0.076	0.99	0.027	0.026	0.67	0.14	3.31	18.9		2.59		0.07	0.11		
1	NCS HS41750	0.075	1.43	0.031	0.012	0.33	0.276	6.35	16.31		0.107	0.058		(0.001)	0.064	
1	ECRM 270-1D	0.0742	0.540	0.0196	0.0007	1.517	0.1076	10.86	20.88	0.0685	0.2099	0.1417		(0.0019)	0.0256	(0.0244)
1	VS LG78	0.074	1.60	0.017	0.0017	0.58	0.053	35.4	14.71		0.061	0.0062	0.004	1.31	0.020	3.16
1	BS 192	0.074	0.835	0.025	0.0005	0.387	0.412	7.11	16.44	0.104	0.430	0.0290	0.168	0.076	0.124	0.05
2	BS 83G	0.073	1.66	0.024	0.004	0.56	0.114	19.15	24.50	0.153	0.085	0.026	0.061	(0.003)	0.077	0.007
1	NM 301	0.073	1.38	0.037	0.021	0.39	0.41	7.89	18.0	0.17	0.36				0.07	
1	VS LG72	0.072	1.32		0.0050	0.334	0.306	12.4	16.36	0.090	2.07	0.0073		0.57		0.077
1	NM 302	0.072	1.06	0.031	0.018	0.49	0.40	10.12	16.92	0.19	2.03				0.066	
1	13X 12534X	0.0716	0.589	0.0192	0.0086	0.811	0.0586	8.50	17.71	0.0602	2.04		0.201	0.348	0.110	0.010
1	IARM 316A	0.070	0.61	0.023	0.0011	1.50	0.19	10.81	21.07	0.118	0.250	0.16	(0.003)	(0.002)	0.042	0.022
1	IARM 18D	0.069	8.1	0.032	0.0025	3.68	0.421	8.39	16.7	0.086	0.325	0.170	(0.031)	0.012	0.064	(0.026)
1	13X 12853L	0.069	1.156	0.0053	0.0062	0.994	0.092	12.31	17.13	0.0415	2.718	0.0086	0.180	0.0455		0.089
1	VS LG63	0.068	0.356	0.010	0.0050	0.285	0.024	22.15	10.13		1.65		0.113	2.98	0.086	0.43
1	KUT S25	0.067	1.90	0.045	0.015	1.49	0.07	13.8	15.6		1.77		0.07	0.46		
1	SRM 1171	0.067	1.81	(0.019)	(0.013)	0.536	0.1205	11.18	17.50	(0.097)	0.167			0.346		(0.012)
1	BS 9841	0.067	1.69	0.024	0.024	0.54	0.356	19.55	24.30	0.116	0.57	0.064	0.070	(0.002)	0.070	0.06
1	SS 465/1	0.066	1.380	0.021	0.012	0.405	0.098	9.24	17.31	0.053	0.092			0.40	0.102	
1	BS 192A	0.066	0.768	0.021	<0.002	0.300	0.334	7.01	16.44	0.114	0.28	0.029	0.208	0.083	0.077	0.048
1	IMZ 152	0.065	1.42	0.010	0.0025	0.52	0.061	9.48	18.04		0.017					0.030
1	IMZ 152A	0.065	1.38	0.0115	0.0072	0.55	0.065	8.47	17.10	(0.006)	0.010	0.083	(0.003)	(0.003)	0.013	(0.004)
1	VS LG71	0.064	1.33	0.032	0.0072	0.602	0.204	10.40	17.63	0.188	0.161			0.473		0.048
2	CT 304	0.063	0.78	0.026	0.023	0.56	0.34	9.60	18.57	0.20	0.33		0.043		0.037	
2	BS 82E	0.062	1.61	0.027	0.001	0.58	0.26	12.49	22.38	0.12	0.31	0.072	0.062	0.003	0.064	0.041
1	13X 31008A	0.062	1.232	0.030	0.0040	0.510	0.157	19.35	24.45	0.078	0.337	0.063	0.012		0.079	0.166
1	KUT H7/1	0.062	0.35	0.018	0.022	0.42	0.085	0.10	9.07							

## STAINLESS STEEL WITH C &gt; 0.05 %

## CONTINUED FROM THE PREVIOUS PAGE

Number	Al	As	B	Bi	Ca	Ce	O	Pb	Sb	Sn	Ta	Zr	Units
VS LG76	0.034	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
VS LG74	0.035	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
KUT S21	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm last
CZ CM-19A	0.0788	.	(0.091)	.	(0.0036)	.	.	.	.	0.0283	.	.	-37 mm Ø x -25 mm
VS LG79	0.059	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
CZ SP-3C	0.095	(0.03)	1.67	.	.	.	.	.	.	(0.02)	.	.	-39 mm Ø x 25 mm
DSZU C016	0.007	.	.	.	0.0004	.	.	.	.	.	.	.	40 mm Ø x 25 mm
CZ SP-3B	0.08	.	0.88	.	.	.	.	.	.	0.01	.	.	-39 mm Ø x 25 mm
KUT S19	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm
SRM C1153a	.	.	.	.	.	.	.	0.006	.	.	.	.	32 mm Ø x 19 mm
13X 18001B	0.0157	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
KUT H6/1	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm
CZ SP-3D	0.037	(0.03)	2.45	.	.	.	.	.	.	(0.04)	.	.	-39 mm Ø x 25 mm
13X NSB1D	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 15 mm
IARM 339A	0.004	(0.001)	0.0006	.	0.0014	.	0.016	.	.	(0.002)	(0.005)	(0.003)	31 mm Ø x 2 or 18 mm
13X 18002D	0.0617	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
CZ CM-18A	0.0344	.	.	.	.	.	.	.	.	.	.	.	-37 mm Ø x -25 mm
SS 468/1	.	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm
SRM C1152a	.	.	.	.	.	.	.	0.0047	.	.	.	.	32 mm Ø x 19 mm
VS LG32/5	0.156	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -25 mm
13X NSA2J	.	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
IARM 289A	0.01	.	0.0003	.	.	.	0.0104	.	.	(0.002)	<0.005	.	31 mm Ø x 2 mm
IARM 241D	0.022	(0.001)	0.0016	.	(0.0012)	.	(0.005)	(0.0003)	.	(0.0022)	(0.007)	(0.005)	31 mm Ø x 2 or 18 mm
DSZU C018	0.086	.	.	.	0.0003	.	.	.	.	.	.	.	40 mm Ø x 25 mm
13X NSB3G	.	.	.	.	.	.	.	.	.	.	.	.	42 mm Ø x 15 mm
KUT H5	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm
13X 18003C	0.0292	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
IRSID 1819	.	.	(0.0004)	.	.	.	.	.	.	.	.	.	47 mm x 47 mm x 30 mm
13X 17002E	(0.030)	.	0.0012	.	.	.	.	.	.	.	(0.012)	.	-40 mm Ø x -15 mm
NCS HS28743	0.0056	0.0042	.	.	.	.	.	0.0004	.	0.0025	.	.	38 mm Ø x 35 mm
IMZ 166A	0.036	(0.0026)	.	.	.	.	.	.	.	(0.0035)	.	.	40 mm Ø x 40 mm
13X 12855N	0.048	.	0.0098	.	.	.	.	.	0.093	.	0.122	.	-40 mm Ø x -15 mm
13X 14828A	0.008	.	.	.	.	.	.	.	.	0.0128	.	.	-40 mm Ø x -15 mm
VS LG81	0.409	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
VS LG77	.	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
IMZ 164	0.040	(0.005)	.	.	.	.	.	(0.002)	.	(0.003)	.	.	40 mm Ø x 40 mm
13X 17003A	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 15 mm
VS LG73	.	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
KUT S20	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm
VS LG80	0.025	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
<b>BS 253</b>	0.016	0.005	.	.	.	.	0.044	.	.	0.006	<b>25(pre-17025)</b>	.	38 mm Ø x -7 or 19+ mm
IARM 234C	0.035	(0.001)	0.0023	.	(0.0017)	.	(0.005)	(0.001)	.	0.0017	(0.003)	(0.006)	31 mm Ø x 2 or 18 mm
SS 462	.	0.007	.	.	.	.	.	0.0005	.	.	.	.	38 mm Ø x 19 mm
DSZU C015	(0.008)	.	.	.	0.0017	.	.	.	.	.	.	.	40 mm Ø x 25 mm
SS 464/1	.	(0.003)	.	.	.	.	.	0.0004	.	.	.	.	38 mm Ø x 19 mm
13X 17004B	0.043	.	0.0066	.	.	.	.	.	.	.	0.057	.	-40 mm Ø x -15 mm
IMZ 165	0.038	(0.003)	.	.	.	.	.	(0.001)	.	0.003	.	.	40 mm Ø x 40 mm
SS 467/1	.	0.004	.	.	.	.	.	0.004	.	.	0.0017	.	38 mm Ø x 19 mm
13X 12854M	.	.	0.0101	0.0052	.	.	.	.	0.068	.	0.020	0.0146	-40 mm Ø x -15 mm
VS LG35/5	0.087	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -25 mm
Number	Al	As	B	Bi	Ca	Ce	O	Pb	Sb	Sn	Ta	Zr	Units
13X 17001C	0.0312	.	0.0085	.	.	.	.	.	.	.	0.0124	.	-40 mm Ø x -15 mm
KUT S26	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm
NCS HS41750	0.009	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 35 mm
ECRM 270-1D	(0.0023)	(0.0034)	Ce: 0.0487	La: 0.0154	.	.	.	.	(0.0007)	(0.0035)	.	(0.002)	38 mm Ø x 25 mm
VS LG78	0.15	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
<b>BS 192</b>	1.17	(0.005)	(0.0003)	.	0.0007	.	0.0014	<b>25(pre-17025)</b>	.	0.008	(0.001)	.	38 mm Ø x -7 or 19+ mm
BS 83G	(0.004)	.	(0.001)	.	.	.	0.0064	.	.	0.003	.	.	38 mm Ø x -7 or 19+ mm
NM 301	.	.	.	.	.	.	.	.	.	.	.	.	35 mm Ø x 20 mm
VS LG72	0.089	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x 28 mm
NM 302	.	.	.	.	.	.	.	.	.	.	.	.	35 mm Ø x 20 mm
13X 12534X	0.0485	.	.	.	.	.	.	.	.	.	0.031	.	-40 mm Ø x -15 mm
IARM 316A	0.006	0.007	(0.0003)	.	0.0017	0.064	0.0052	(0.0001)	.	0.006	(0.003)	.	31 mm Ø x 2 or 18 mm
IARM 18D	(0.006)	.	(0.0011)	.	.	.	.	.	.	(0.007)	.	.	31 mm Ø x 18 mm
13X 12853L	0.18	.	0.0018	.	.	.	.	.	.	.	0.034	.	-40 mm Ø x -15 mm
VS LG63	0.45	.	.	.	.	.	.	.	.	.	.	.	-47 mm Ø x -30 mm
KUT S25	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm
SRM 1171	.	.	.	.	.	.	.	.	.	.	.	.	31 mm Ø x 19 mm
<b>BS 9841</b>	<0.006	(0.003)	0.0026	<b>25(pre-17025)</b>	.	.	(0.011)	(0.001)	(0.006)	0.006	.	(0.002)	44 mm Ø x -7 or 19+ mm
SS 465/1	0.026	.	0.0006	.	.	.	.	<0.001	.	.	.	.	38 mm Ø x 19 mm
<b>BS 192A</b>	0.98	(0.0035)	(0.0003)	.	(0.0006)	.	(0.0006)	.	.	0.008	<b>25(pre-17025)</b>	.	38 mm Ø x -7 or 19+ mm
IMZ 152	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
IMZ 152A	(0.004)	(0.002)	0.0022	.	.	.	.	.	.	(0.001)	.	.	38 mm Ø x 20 mm
VS LG71	0.072	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
CT 304	.	.	.	.	.	.	.	<0.001	.	0.017	.	.	30-35 mm Ø x -16 mm Ag: 7ppm
BS 82E	0.006	.	0.0024	.	0.0014	.	.	.	.	0.006	.	.	38 mm Ø x -7 to 19 mm
13X 31008A	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -15 mm
KUT H7/1	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm
CT 316	.	.	.	.	.	.	.	0.001	.	0.006	.	.	30-35 mm Ø x -19 mm Ag: 5ppm
VS LG36/5	0.080	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -25 mm
<b>BS 321D</b>	0.103	0.0040	0.0012	.	(0.0003)	.	0.0009	(0.0003)	(0.001)	0.0091	<b>17025</b>	(0.001)	44 mm Ø x -7 or 19+ mm Fe, Mg
13X NSB2D	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 15 mm
<b>BS 9842</b>	0.014	(0.002)	0.0025	.	0.0010	.	(0.0044)	.	.	0.005	<b>25(pre-17025)</b>	.	38 mm Ø x -7 or 19+ mm
BS 82D	(0.002)	.	0.0040	.	0.0007	.	0.007	.	.	0.004	.	last	38 mm Ø x -7 mm
SRM 1172	.	.	.	.	.	.	.	.	.	.	<0.001	.	32 mm Ø x 19 mm
VS LG82	0.076	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
BS 87F	0.004	0.005	(0.0006)	.	0.0007	.	0.005	.	.	0.004	.	.	41 mm Ø x -7 or 19+ mm
BS 86F	(0.007)	(0.003)	0.0026	.	(0.001)	.	.	(0.001)	.	0.004	.	.	44 mm Ø x -7 or 19+ mm
DSZU C017	0.28	.	.	.	0.0031	.	.	.	.	.	.	.	40 mm Ø x 25 mm
IARM Fe304H-18	(0.005)	0.0076	.	.	.	.	(0.008)	.	.	(0.014)	.	.	31 mm Ø x 2 or 18 mm
BS 347B	0.002	(0.003)	0.0036	.	(0.0005)	.	0.005	.	.	0.006	<0.004	.	38 mm Ø x -7 or 19+ mm
BS 347A	(0.002)	(0.003)	(0.0004)	.	(0.0002)	.	0.0047	.	.	0.007	<0.004	.	38 mm Ø x 19+ mm

## STAINLESS STEEL WITH C &lt; 0.05 %

## CONTINUED ON THE NEXT PAGE

# = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

analysis listed in mass %

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	ECRM 269-1D	0.0499	1.262	0.0313	0.0010	0.441	0.366	8.044	18.150	0.1116	0.397	0.0460	0.0242	0.0006	0.0991	0.0306
1	IARM 8H *	0.049	1.81	0.0250	(0.002)	0.40	0.192	9.08	17.14	0.083	0.237	0.027	0.48	0.0027	0.049	(0.016)
1	IARM 6i	0.049	1.76	0.0208	(0.023)	0.31	0.202	9.20	17.76	0.052	0.133	(0.013)	(0.018)	0.60	0.048	(0.023)
1	ECRM 289-1D	0.0489	1.016	0.0114	0.0027	0.531		24.68	14.63	0.065	1.102			2.01	0.260	
1	IMZ 150A	0.048	1.35	0.0064	0.0095	0.59	0.090	12.75	18.89	0.125	0.12		0.0026	0.021	(0.027)	0.11
1	IARM 4F	0.047	1.17	0.0195	0.0015	0.494	0.146	20.1	24.5	0.067	0.142	0.056	0.007	0.0031	0.146	0.012
1	13X 14211R	0.047	0.787	0.0093	0.008	1.73	0.336	12.64	24.48	0.034	0.395	0.1115	0.150	0.206	0.039	2.99
1	13X 32100A	0.0463	1.52	0.0298	0.0011	0.498	0.415	9.32	17.39	0.105	0.282	0.023	0.0191	0.376	0.106	0.021
1	IARM Fe303-18	0.046	1.55	0.033	0.35	0.47	0.61	8.12	17.2	0.140	0.42	0.069	0.015		0.072	0.029
1	<b>BS 188B</b>	0.046	0.247	0.016	(0.0007)	0.266	0.120	24.81	14.32	0.274	1.30	0.0021	0.099	2.20	0.264	0.043
1	IARM 4G	0.0454	1.36	0.027	0.0008	0.630	0.320	19.2	24.9	0.085	0.580	0.058	0.008	0.029	0.092	0.017
1	IARM 6J	0.045	1.52	0.028	(0.002)	0.62	0.383	9.00	17.74	0.191	0.387	0.0109	0.010	0.34	0.081	0.026
1	<b>BS 303</b>	0.044	1.80	0.028	0.326	0.415	0.627	8.17	17.23	0.071	0.410	0.023	0.008	0.017	0.056	0.023
1	IARM 4E	0.044	1.07	0.0224	0.0006	0.514	0.234	20.18	24.25	0.066	0.32	0.038	0.024	(0.003)	0.052	0.046
1	13X 18004C	0.0430	1.57	0.0060	0.0063	1.21	0.048	12.26	21.62	0.168	0.562	0.0225	0.748	0.095	0.152	0.004
3	CZ SL-3A	0.043	1.73	0.024	0.002	0.53	0.22	19.6	24.6	0.06	0.38	0.065	0.013	0.003	0.066	0.03
1	IARM 8i	0.0424	1.395	0.0352	0.0118	0.38	0.441	9.01	17.08	0.301	0.416	0.052	0.60	(0.008)	0.057	0.060
1	13X 14216P	0.0424	0.663	0.0048	0.0070	1.566	0.231	12.06	23.44	0.248	0.209	0.0152	0.248		0.0722	2.25
1	IARM 8G	0.042	1.468	0.0327	0.0126	0.36	0.390	9.02	17.20	0.162	0.359	0.046	0.53	0.0024	0.062	0.032
1	VS LG70	0.042	0.834	0.042	0.0020	0.382	0.062	9.17	17.10	0.209	0.096	0.0134		0.305		0.0053
1	NILAB 500HA D	0.041	1.541	0.024	0.012	0.720	0.182	11.00	16.93	0.139	2.73	0.1154	0.023		0.074	
1	13X 12538J	0.04	0.78			0.64		6.07	23.72		1.53					
1	NCS HS28741	0.039	1.07	0.037	0.016	0.425	0.399	8.19	18.31	0.208	0.027	0.069		(0.002)	0.106	
1	13X 14207L	0.0388	0.597	0.0061	0.0060	1.448	0.186	12.43	19.63	0.0089	0.573	0.0099	0.258	0.0119	0.0043	2.99
1	IRSID 1821	0.037	1.72	(0.025)	(0.004)	0.542	0.058	10.42	17.04	0.266	2.04	0.0125		0.297		
1	IMZ 153A	0.037	1.49	0.021	0.0073	0.73	0.102	13.57	16.45	0.015	2.61	0.107	0.034	0.036	0.020	
1	ECRM 292-1D	0.0367	1.744	0.0175	0.0055	0.402	0.0391	10.09	18.00	0.0255	0.0464	0.0640	0.571			
2	BS 184A	0.035	0.06	0.007	0.001	0.080	0.041	8.34	12.66	0.036	2.20	0.0045	(0.006)	0.051	0.014	0.032
1	SS 462/1	0.0345	0.722	0.0053	0.0041	0.463	0.0112	12.85	11.888		0.0304					
1	SRM C1151a	0.034	2.37	0.017	0.038	0.29	0.385	7.25	22.59	0.033	0.79				0.040	
1	13X 31400A	0.033	1.60	0.026	0.0006	2.23	0.210	18.76	24.38	0.129	0.240	0.0288	0.018		0.092	0.015
1	<b>BS 9812</b>	0.031	0.485	0.018	0.004	0.43	1.65	6.61	14.82	0.110	0.76	0.0195	0.645	(0.005)	0.088	0.025
1	13X NSA9B	0.030	1.52	0.0237	0.0009	0.290	0.154	5.75	22.39	0.033	3.27	0.184	0.021		0.060	0.033
1	13X 30403B	0.0277	1.820	0.0321	0.0266	0.288	0.497	8.13	18.30	0.178	0.313	0.083	0.0201	0.0013	0.0700	0.035
2	HRT FE2014-H	0.027	1.91	0.023	(0.002)	0.39	0.25	9.92	17.16		0.41	(0.018)		0.31		
1	VS LG75	0.027	0.728	0.0046	0.0026	0.298	0.029	24.5	14.80	0.190	0.052	0.0044		1.76		4.14
1	<b>BS 9811</b>	0.027	0.380	0.016	0.0010	0.36	1.63	6.55	14.87	0.055	0.744	0.0196	0.62	(0.003)	0.086	0.013
1	SRM 1155a	0.0260	1.593	0.0271	(0.0020)	0.521	0.2431	12.471	17.803	0.225	2.188	(0.0428)	0.0082	0.0039	0.0725	0.0809
1	13X 32900A	0.0251	1.478	0.0276	0.0269	0.556	0.354	5.57	24.91	0.0724	1.310	0.097		0.0139	0.0938	0.017
1	<b>BS 317L</b>	0.025	1.17	0.029	0.0017	0.67	0.23	13.51	18.2	0.14	3.07	0.055	0.031	0.0034	0.091	0.017
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	IARM 162D	0.0240	1.82	0.0296	0.0271	0.570	0.52	8.15	18.31	0.074	0.573	0.097	0.0090	0.013	0.063	0.028
1	IARM Fe304L-18	0.024	1.39	0.034	0.029	0.43	0.54	8.17	18.34	0.156	0.462	0.081	0.013	0.0056	0.076	0.056
1	NCS HS28764	0.024	0.985	0.032	0.024	0.454	0.203	11.68	18.78	0.105	3.23	0.036	0.145		0.059	0.046
1	IARM 153C	0.0225	1.60	0.0289	0.0288	0.349	0.442	11.10	18.22	0.251	3.00	0.086	0.015	0.004	0.058	0.043
1	ECRM 297-1D	0.0223	0.897	0.0137	0.0101	0.344	0.204	12.33	18.37	0.0413	0.290	0.0152	(0.0089)	0.0072	0.0535	(0.0057)
1	NCS HS28746	0.021	1.87	0.031	0.0009	0.510	0.340	8.24	17.19	0.191	0.069	0.011		0.184	0.096	
1	<b>BS 9942</b>	0.021	1.84	0.025	0.006	0.49	0.305	13.55	18.21	0.086	3.30	0.071	0.005	(0.002)	0.072	0.032
1	<b>BS 9941</b>	0.021	1.78	0.027	0.024	0.33	0.424	13.68	18.48	0.178	3.24	0.036	0.015	(0.002)	0.062	0.068
1	IARM Fe316L-18	0.021	1.70	0.033	0.029	0.438	0.550	10.12	16.7	0.209	2.02	0.067	(0.027)	(0.003)	(0.067)	(0.06)
1	IRSID 1820	0.021	1.61	(0.021)	0.0079	0.428	0.045	9.07	19.51	0.151	0.115	0.064				
1	<b>BS 2205A</b>	0.021	1.48	0.029	0.0006	0.53	0.300	5.26	22.73	0.071	3.17	0.157	0.010	(0.002)	0.083	(0.02)
1	NCS HS28742	0.021	0.940	0.034	0.0028	0.414	0.043	8.11	18.2	0.216	0.025	0.059		0.006	0.089	
1	13X NSA8B	0.0206	0.596	0.0248	0.0007	0.285	0.589	7.48	25.49	0.0448	3.49	0.232	0.026		0.0583	0.599
1	13X NSA13A	0.020	0.761	0.0249	0.0005	0.257	0.156	6.73	25.27	0.032	3.73	0.269	0.028		0.0712	0.035
1	SS 463/1	0.019	1.400	0.025	0.019	0.270	0.276	10.20	18.46	0.116	0.265	0.063				
1	13X NSA12A	0.0192	1.272	0.0267	0.0007	0.492	1.485	24.84	19.63	0.090	4.20	0.0662	0.0088		0.0660	0.047
1	IARM 212D	0.019	1.21	0.024	0.0007	0.34	0.125	5.53	22.60	0.049	3.27	0.182	(0.009)	(0.002)	0.063	0.014
1	13X FV520BA	0.0181	0.655	0.0221	0.0016	0.342	1.462	5.29	13.73	0.030	1.334	0.0197	0.301		0.080	0.020
2	HRT FE2000-H	0.018	2.02	0.022	(0.003)	0.36	0.15	5.98	22.15	0.048	3.27	0.20	0.010	0.005	0.042	0.063
1	IARM Fe2205-18	0.018	1.18	0.023	(0.0013)	0.46	0.208	5.57	22.6	0.104	3.20	0.17	0.011	(0.003)	0.063	0.024
1	NCS HS28745	0.018	1.17	0.042	0.0057	0.317	0.334	10.34	16.61	0.185	2.05	0.070		(0.002)	0.070	
1	SS 476	0.0171	1.755	0.0302	0.0234	0.323	0.302	10.17	16.88	0.162	2.04	0.0794	0.0107		0.066	0.041
1	<b>BS 304B</b>	0.017	1.72	0.022	0.023	0.540	0.257	8.68	18.3	0.220	0.42	0.081	0.074	(0.0018)	0.097	(0.01)
1	IARM 239C	0.017	0.87	0.023	(0.0010)	0.38	1.49	6.14	25.8	0.039	3.33	0.228	(0.006)	(0.004)	0.083	(0.05)
1	IARM FeZ100-18	0.017	0.52	0.026	(0.0009)	0.24	0.55	7.1	25.5	0.123	3.61	0.22	(0.005)		0.090	0.56
1	<b>BS 179C</b>	0.0164	0.878	0.0236	0.0003	0.373	1.53	6.10	25.9	0.0386	3.34	0.236	0.009	(0.0005)	0.080	0.056
1	<b>BS 179B</b>	0.0161	0.890	0.0243	0.0002	0.371	1.56	6.17	25.9	0.0394	3.34	0.239	0.008	(0.0008)	0.079	0.053
1	ECRM 287-1D	0.016	1.48	0.027	0.0014	0.569	0.203	10.35	18.61	0.148	0.247	0.019				
1	13X 34700A	0.016	1.290	0.028	(0.0006)	0.483	0.163	9.38	17.19	0.131	0.393	0.0166	0.330		0.123	0.146
1	13X NSA11A	0.0159	0.640	0.0186	<0.001	0.275	0.187	23.89	20.18	0.0981	6.16	0.203	0.150		0.0513	0.038
3	CZ SL-2A	0.015	1.84	0.025	0.027	0.64	0.50	11.0	16.9	0.09	2.03	0.04		0.06	0.075	0.03
1	<b>BS 316F</b>	0.015	1.													



## STAINLESS STEEL WITH C &lt; 0.05 %

## CONTINUED FROM THE PREVIOUS PAGE

analysis listed in mass %

Number	Al	As	B	Ca	O	Pb	Sb	Sn	Ta	Units
ECRM 269-1D	.	0.0061	.	.	.	.	.	0.0099	.	35 mm Ø x 25 mm
IARM 8H	(0.005)	.	(0.0002)	.	.	.	.	(0.008)	(0.01)	31 mm Ø x 2 or 18 mm
IARM 61	0.084	(0.005)	0.0034	(0.0004)	0.0012	.	.	(0.0060)	.	31 mm Ø x 2 mm
ECRM 289-1D	0.199	.	0.0044	.	.	.	.	0.111	.	38 mm Ø x 30 mm
IMZ 150A	0.022	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
IARM 4F	0.015	(0.003)	(0.0012)	(0.002)	(0.004)	.	(0.001)	(0.005)	(0.007)	31 mm Ø x 2 or 18 mm
13X 14211R	0.089	.	.	.	.	.	.	.	0.0152	~40 mm Ø x ~15 mm
13X 32100A	0.0247	.	0.0025	.	.	.	.	0.0115	.	~38 mm Ø x ~15 mm
IARM Fe303-18	.	0.007	(0.0012)	.	(0.006)	.	.	(0.015)	.	31 mm Ø x 2 or 18 mm
<b>BS 188B</b>	0.168	0.0045	0.0047	(0.00003)	0.0006	(0.0001)	(0.0006)	0.0051	.	38 mm Ø x ~7 or 19+ mm Fe: 55.8 <b>17025</b>
IARM 4G	0.008	(0.005)	0.0032	(0.001)	(0.003)	(0.0005)	(0.001)	0.008	(0.008)	31 mm Ø x 2 mm
IARM 6J	0.0195	.	0.0024	.	(0.001)	.	.	(0.009)	(0.01)	31 mm Ø x 2 mm
<b>BS 303</b>	0.0019	.	0.0013	(0.0015)	0.0058	.	(0.002)	0.0091	.	44 mm Ø x ~7 or 19+ mm <b>17025</b> Fe:[70.7]
IARM 4E	0.004	(0.005)	0.0011	.	0.0021	.	.	0.0060	0.005	31 mm Ø x 2 mm
13X 18004C	0.011	.	.	.	.	.	.	(0.0025)	.	~40 mm Ø x ~15 mm
CZ SL-3A	0.007	.	0.002	.	.	.	.	0.006	.	~39 mm Ø x 25 mm
IARM 8i	(0.0030)	.	(0.0005)	.	(0.004)	.	.	(0.012)	.	31 mm Ø x 2 or 18 mm
13X 14216P	.	.	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm
IARM 8G	0.0030	(0.007)	(0.0005)	(0.0005)	(0.003)	.	.	0.0107	(0.004)	31 mm Ø x 2 mm
VS LG70	0.029	.	.	.	.	.	.	.	.	~45 mm Ø x ~28 mm
NILAB 500HA D	.	.	.	.	.	.	.	.	.	38 mm Ø x 20 mm
13X 12538J	.	.	.	.	.	.	.	.	.	40 mm Ø x 15 mm
NCS HS28741	.	0.0035	.	.	.	0.0001	.	0.0051	.	38 mm Ø x 35 mm
13X 14207L	0.0226	.	.	.	.	.	.	.	0.082	~40 mm Ø x ~15 mm
IRSD 1821	.	.	.	.	.	.	.	.	.	47 mm x 47 mm x 30 mm
IMZ 153A	0.036	.	.	0.0024	.	.	.	.	.	38 mm Ø x 20 mm
ECRM 292-1D	(0.002)	(0.008)	.	(0.0006)	(0.0003)	.	.	.	(0.001)	38 mm Ø x 25 or 30 mm
BS 184A	1.00	.	(0.0004)	(0.0003)	(0.0003)	.	.	(0.002)	(0.002)	38 mm Ø x ~7 or 19+ mm
SS 462/1	.	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm
SRM C1151a	.	.	.	.	.	0.0039	.	.	.	32 mm Ø x 19 mm
13X 31400A	0.022	.	.	0.0024	.	.	.	.	.	~40 mm Ø x ~15 mm
<b>BS 9812</b>	(0.002)	(0.005)	(0.0003)	0.0012	(0.007)	.	.	0.004	.	50 mm Ø x ~7 or 19+ mm <b>25(pre-17025)</b>
13X NSA9B	.	.	0.0018	.	.	.	.	.	.	~40 mm Ø x ~15 mm
13X 30403B	0.0056	.	.	0.0027	.	.	.	0.0139	.	~40 mm Ø x ~15 mm
HRT FE2014-H	.	.	.	.	.	.	.	.	.	35 mm Ø x 20 mm
VS LG75	0.113	.	.	.	.	.	.	.	.	~45 mm Ø x ~28 mm
<b>BS 9811</b>	(0.003)	(0.003)	(0.0003)	0.0014	(0.0060)	.	.	0.004	.	38 mm Ø x ~7 or 19+ mm <b>25(pre-17025)</b>
SRM 1155a	<0.01	(0.007)	(0.002)	.	(0.003)	<0.005	.	(0.0069)	.	32 mm Ø x 19 mm
13X 32900A	0.007	.	0.0028	0.0033	.	.	.	.	.	~40 mm Ø x ~15 mm
<b>BS 317L</b>	0.0044	(0.003)	0.0012	0.0017	(0.006)	(0.0002)	(0.002)	0.0049	(0.002)	37 mm Ø x ~7 or 19+ mm <b>17025</b>
Number	Al	As	B	Ca	O	Pb	Sb	Sn	Ta	Units
IARM 162D	(0.0026)	0.0072	0.0027	(0.003)	0.005	.	(0.0019)	0.0102	(0.005)	31 mm Ø x 2 mm
IARM Fe304L-18	(0.003)	0.007	(0.0012)	.	(0.006)	.	.	(0.013)	.	31 mm Ø x 2 mm
NCS HS28764	.	0.013	.	.	.	.	.	.	.	40 mm Ø x 30 mm
IARM 153C	(0.003)	0.0061	0.0009	(0.0026)	0.006	(0.001)	(0.002)	0.010	(0.006)	31 mm Ø x 2 or 18 mm
ECRM 297-1D	0.0195	0.0040	1.146	(0.0002)	.	.	.	.	.	40 mm Ø x 30 mm
NCS HS28746	0.086	0.0032	.	.	.	0.0002	.	0.0065	.	38 mm Ø x 35 mm
<b>BS 9942</b>	0.004	(0.004)	0.0014	0.0014	(0.0023)	.	.	0.006	.	44 mm Ø x ~7 or 19+ mm <b>25(pre-17025)</b>
<b>BS 9941</b>	0.004	(0.010)	0.0025	(0.0003)	(0.0058)	.	.	0.007	.	38 mm Ø x ~7 or 19+ mm <b>25(pre-17025)</b>
IARM Fe316L-18	(0.006)	.	.	.	(0.005)	.	.	(0.013)	.	31 mm Ø x 18 mm
IRSD 1820	.	.	(0.0013)	.	.	.	.	.	.	47 mm x 47 mm x 30 mm
<b>BS 2205A</b>	(0.004)	0.0072	0.0022	0.0007	0.0046	.	.	0.0058	.	38 mm Ø x ~7 or 19+ mm <b>17025</b> Fe: 66.2
NCS HS28742	.	0.0025	.	.	.	0.0001	.	(0.0001)	.	38 mm Ø x 35 mm
13X NSA8B	.	.	0.0017	0.0011	.	.	.	.	.	~38 mm Ø x ~15 mm
13X NSA13A	(0.007)	.	0.0030	.	.	(0.0008)	.	0.0046	.	~40 mm Ø x ~15 mm
SS 463/1	.	.	0.0022	.	.	.	.	.	.	38 mm Ø x 19 mm
13X NSA12A	0.0169	.	0.0020	.	.	.	.	.	.	~40 mm Ø x ~15 mm
IARM 212D	(0.005)	(0.01)	0.001	(0.001)	0.0034	(0.001)	.	(0.003)	(0.003)	31 mm Ø x 2 mm last of stock
13X FV520BA	.	.	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm
HRT FE2000-H	.	.	0.0013	.	.	.	.	.	.	40 mm Ø x 20 mm
IARM Fe2205-18	(0.007)	.	.	.	(0.004)	.	.	(0.006)	.	31 mm Ø x 2 or 18 mm
NCS HS28745	.	0.0055	.	.	.	0.0001	.	0.0073	.	38 mm Ø x 35 mm
SS 476	.	0.0053	.	0.0028	.	.	.	0.0059	.	38 mm Ø x 19 mm
<b>BS 304B</b>	0.0036	0.0051	(0.0004)	0.0009	0.0038	(0.0008)	.	0.0057	.	38 mm Ø x ~7 or 19+ mm <b>17025</b> Fe: 69.6
IARM 239C	0.007	(0.004)	0.0014	.	.	.	.	(0.003)	(0.004)	31 mm Ø x 2 or 18 mm
IARM Fe2100-18	(0.017)	.	0.002	.	(0.003)	.	.	(0.006)	.	31 mm Ø x 2 or 18 mm
<b>BS 179C</b>	0.0078	0.0034	0.0015	(0.0003)	0.0038	(0.00002)	0.0005	0.0018	(0.0006)	38 mm Ø x ~7 or 19+ mm <b>17025</b> Fe:[61.6]
<b>BS 179B</b>	0.0070	0.0036	0.0015	(0.0004)	0.0037	(0.00002)	0.0005	0.0019	(0.0006)	38 mm Ø x 19+ mm <b>17025</b> Fe:[61.5]
ECRM 287-1D	.	.	0.924	.	.	.	.	.	.	38 mm Ø x 25 or 30 mm
13X 34700A	0.023	.	0.0008	.	.	.	.	.	.	~38 mm Ø x ~15 mm
13X NSA11A	(0.021)	.	.	.	.	.	.	.	.	~38 mm Ø x ~15 mm
CZ SL-2A	0.005	0.008	0.002	.	.	.	.	0.01	.	~39 mm Ø x 25 mm
<b>BS 316F</b>	(0.002)	0.0067	0.0019	0.0018	0.0055	(0.0002)	.	0.0092	Fe:68.1	38 mm Ø x ~7 or 19+ mm <b>17025</b>
IARM 319A	(0.010)	(0.004)	0.0020	.	0.0025	.	.	0.0055	(0.002)	31 mm Ø x 2 mm
SS 466/2	0.0018	0.0020	0.0039	.	.	.	.	.	.	38 mm Ø x 19 mm
IARM 163E *	0.0039	(0.008)	0.0019	(0.002)	0.007	.	(0.002)	0.012	.	31 mm Ø x 2 mm * Provisional Analysis, last
HRT FE2016-H	.	.	.	.	.	.	.	.	.	30 mm Ø x 20 mm
SS 461/1	0.069	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm
13X 30600A	0.020	.	.	.	Mg:0.0016	.	.	.	.	~32 mm Ø x ~20 mm
BS SS1961	0.067	0.004	0.0022	.	(0.002)	.	.	0.004	.	38 mm Ø x 12 mm last
JK 27B	.	.	0.00072	0.0022	.	.	.	0.0068	.	~37 mm Ø x 25 mm
BS SS1962	0.062	0.002	0.0018	.	(0.001)	.	.	0.004	.	38 mm Ø x ~7 or 19+ mm
IARM 354A	(0.05)	(0.002)	0.0023	(0.0003)	(0.0012)	(0.004)	(0.0002)	(0.002)	.	31 mm Ø x 2 or 18 mm
CT IS0123A	0.027	.	0.0021	.	.	.	.	.	.	44-47 mm Ø x ~16 mm Fe: 74.72
13X 46500A	0.069	.	0.0016	.	.	.	.	0.0030	.	~32 mm Ø x ~20 mm
ECRM 284-3D	.	0.00131	0.00020	.	.	.	.	0.00074	.	39 mm Ø x 28 mm
Number	Al	As	B	Ca	O	Pb	Sb	Sn	Ta	Units



RM TRACE ELEMENTS IN STAINLESS STEEL

certified analysis						informational analysis										40 mm Ø x 20 mm		
Number	As	Pb	Sb	Sn	Zn	C	Mn	P	Si	Cu	Ni	Cr	Mo	N	B	Ca	V	
DSZU C25	0.093	0.038	0.094	0.095	0.034	0.3	0.1	0.02	0.3	0.7	1.6	13	0.1	0.10	0.03	0.004	0.03	
DSZU C22	0.051	0.023	0.050	0.051	0.019	0.4	0.1	0.02	0.2	0.5	1.5	13	0.1	0.04	0.03	0.002	0.03	
DSZU C33	0.021	0.0046	0.015	0.020	0.019	0.1	1.1	0.03	1.0	0.3	16	17	1.2	0.14	0.02	0.0004	0.03	
DSZU C24	0.014	0.0017	0.010	0.011	0.0035	0.4	0.1	0.02	0.2	0.3	1.5	13	0.1	0.12	0.007	0.003	0.03	
DSZU C23	0.008	0.0008	0.006	0.010	0.0028	0.4	0.1	0.02	0.3	0.2	1.4	13	0.1	0.10	0.004	0.002	0.03	
DSZU C26	0.0077	0.0025	0.0019	0.0042	0.0189	0.3	0.1	0.02	0.3	0.7	1.6	13	0.1	0.025	0.0003	0.0009	0.03	
DSZU C21	0.005	0.0002	0.0011	0.003	0.0026	0.4	0.1	0.02	0.3	0.2	1.2	13	0.1	0.03	0.002	0.001	0.03	

last of stock

STAINLESS STEEL XRF SETS

AVAILABLE IN SETS OR INDIVIDUALLY

~7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	V	W	
<b>SET BS SS-17</b>																
15-5PH	BS 185A	0.033	0.49	0.022	0.002	0.38	3.41	4.43	14.46	0.026	0.30	0.027	0.32	0.048	(0.014)	
17-4PH	BS 17-4PHA	0.018	0.85	0.023	0.022	0.40	3.30	4.69	15.40	0.072	0.34	0.022	0.204	0.043	.	
17-7PH	BS 192	0.075	0.84	0.025	0.001	0.38	0.41	7.10	16.42	0.104	0.42	0.029	0.17	0.13	0.04	
253 MA	BS 253	0.094	0.58	0.018	<0.001	1.81	0.14	10.89	20.68	0.15	0.21	0.146	0.017	0.050	0.03	
255	BS 179C	0.0164	0.878	0.0236	0.0003	0.373	1.53	6.10	25.9	0.0386	3.34	0.236	0.009	0.080	0.056	
2205 (318)	BS 2205	0.0199	1.029	0.0227	0.0005	0.564	0.196	5.27	22.92	0.041	3.26	0.169	0.0052	0.0560	0.0309	
303	BS 303	0.044	1.80	0.028	0.326	0.415	0.627	8.17	17.23	0.071	0.410	0.023	0.008	0.056	0.023	
304 L	BS 304B	0.017	1.72	0.022	0.023	0.540	0.257	8.68	18.3	0.220	0.42	0.081	0.074	0.097	(0.01)	
309	BS 82E	0.062	1.61	0.027	0.001	0.58	0.26	12.49	22.38	0.12	0.31	0.072	0.062	0.064	0.041	
310	BS 83G	0.073	1.66	0.024	0.004	0.56	0.114	19.15	24.50	0.153	0.085	0.026	0.061	0.077	0.007	
316	BS 316F	0.015	1.46	0.029	0.026	0.55	0.437	10.09	16.79	0.126	2.10	0.061	0.011	0.062	0.045	
317 L	BS 317L	0.025	1.17	0.029	0.0017	0.67	0.23	13.51	18.2	0.14	3.07	0.055	0.031	0.091	0.017	
321	BS 85D	0.048	1.69	0.024	0.024	0.54	0.45	9.98	17.09	0.97	0.59	(0.02)	0.062	0.132	(0.07)	
330	BS 86F	0.054	1.30	0.021	0.0011	1.22	0.23	34.99	18.74	0.098	0.24	0.035	0.19	0.061	(0.03)	
347	BS 347B	0.051	1.57	0.028	0.026	0.51	0.15	9.16	17.24	0.05	0.38	0.056	0.71	0.04	(0.005)	
355	BS 355	0.136	0.862	0.0171	0.0003	0.374	0.173	4.18	15.43	0.053	2.73	0.081	0.0103	0.106	0.0069	
PH13-8 Mo	BS 184A	0.035	0.06	0.007	0.001	0.080	0.041	8.34	12.66	0.036	2.20	0.0045	(0.006)	0.014	0.032	
<b>SET BS 400-SS-16</b>																
182PM	BS 150	0.048	1.71	0.020	0.33	0.43	0.042	0.19	18.61	0.024	1.97	0.029	0.003	0.054	0.01	
410	BS 410C	0.131	0.381	0.0206	0.0051	0.366	0.084	0.352	12.78	0.0185	0.055	0.039	0.0056	0.0006	0.0131	
416	BS 90F	0.085	0.53	0.023	0.328	0.58	0.12	0.30	13.01	0.021	0.14	0.037	0.011	0.076	0.032	
416 Se	BS 151	0.090	0.41	0.021	0.018	0.65	0.11	0.24	13.19	0.018	0.088	0.022	0.005	0.046	0.010	
420	BS 98	0.309	0.48	0.019	0.0014	0.72	0.098	0.21	13.35	0.020	0.034	0.0181	0.003	0.075	0.009	
420F	BS 152	0.32	0.36	0.022	0.275	0.44	0.050	0.14	13.41	0.015	0.061	0.020	0.006	0.051	<0.01	
422	BS 97	0.216	0.71	0.021	0.0004	0.39	0.066	0.76	11.82	0.041	1.05	0.030	0.007	0.21	0.95	
430	BS 91E	0.066	0.42	0.017	0.002	0.52	0.05	0.17	16.58	0.02	0.035	0.032	(0.004)	0.09	0.01	
430F	BS 153	0.026	0.41	0.018	0.280	0.53	0.052	0.140	17.38	0.017	0.30	0.021	0.002	0.045	(0.002)	
431	BS 92B	0.150	0.42	0.021	0.003	0.42	0.13	2.12	15.92	0.04	0.17	0.073	(0.006)	0.07	0.02	
440C	BS 93E	1.02	0.52	0.022	0.0010	0.90	0.12	0.35	17.33	0.048	0.50	0.0359	0.005	0.24	0.11	
440F	BS 155	1.00	0.35	0.014	0.145	0.40	0.035	0.13	16.64	0.019	0.46	0.032	0.002	0.10	.	
440F Se	BS 156	1.06	1.15	0.022	0.007	0.47	0.09	0.35	16.87	0.047	0.50	0.041	0.005	0.13	0.11	
446	BS 94C	0.057	0.45	0.024	0.002	0.62	0.056	0.43	25.90	0.042	0.20	0.065	0.032	0.12	(0.03)	
450	BS 95A	0.035	0.58	0.026	0.004	0.46	1.50	6.42	14.72	0.081	0.73	0.0255	0.55	0.052	0.02	
455	BS 96A	0.009	0.04	0.007	0.004	0.06	2.07	8.38	11.62	0.03	0.021	.	0.26	0.07	.	

Number	Al	B	Ca	Se	Sn	Ti
--------	----	---	----	----	----	----

SET BS SS-17

BS 185A	0.002	0.0017	(0.0002)	.	0.007	(0.001)
BS 17-4PHA	.	0.0016	.	.	.	Ta: (0.002)
BS 192	1.15	(0.0004)	0.0007	.	0.009	0.078
BS 253	0.016	.	.	.	0.006	0.005
BS 179C	0.0078	0.0015	(0.0003)	.	0.0018	(0.0005)
BS 2205	0.0080	0.0016	0.0014	.	0.0050	0.0019
BS 303	0.0019	0.0013	(0.0015)	.	0.0091	0.017
BS 304B	0.0036	(0.0004)	0.0009	69.6	0.0057	(0.0018)
BS 82E	0.006	0.0024	0.0014	.	0.006	0.003
BS 83G	(0.004)	(0.001)	O: 0.0064	.	0.003	(0.003)
BS 316F	(0.002)	0.0019	0.0018	.	0.0092	0.011
BS 317L	0.0044	0.0012	0.0017	.	0.0049	0.0034
BS 85D	0.13	(0.001)	0.0004	.	0.0062	0.48
BS 86F	(0.007)	0.0026	(0.001)	.	0.004	(0.006)
BS 347B	0.002	0.0036	(0.0005)	.	0.006	(0.002)
BS 355	0.0192	0.0039	(0.0002)	.	0.0038	0.0007
BS 184A	1.00	(0.0004)	(0.0003)	.	(0.002)	0.051

SET BS 400-SS-16

BS 150	0.002	.	.	.	(0.003)	(0.002)
BS 410C	0.0079	(0.0001)	0.0022	.	0.0023	0.0006
BS 90F	(0.006)	.	.	.	0.005	(0.002)
BS 151	(0.002)	.	.	0.328	0.005	(0.003)
BS 98	0.003	.	(0.0005)	.	0.006	0.002
BS 152	(0.002)	.	.	.	0.003	(0.002)
BS 97	0.018	.	.	.	(0.003)	(0.002)
BS 91E	(0.002)	.	0.0008	.	0.004	(0.002)
BS 153	(0.004)	.	.	.	0.002	(0.004)
BS 92B	(0.002)	.	(0.0009)	.	0.006	(0.002)
BS 93E	0.009	.	.	.	0.003	0.007
BS 155	(0.001)	.	.	.	(0.003)	(0.002)
BS 156	(0.002)	.	.	0.142	(0.004)	0.001
BS 94C	0.004	.	0.0008	.	0.006	.
BS 95A	0.002	0.0010	0.0008	.	0.008	(0.003)
BS 96A	0.08	(0.0017)	.	.	.	1.18

## HIGH ALLOY STEEL

# = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V
3	CZ SP-8B	2.37	0.86	0.022	0.012	1.40	0.075	2.72	37.6	0.13	0.075	0.10	.	0.04	0.13	0.13
2	CZ SP-4C	0.34	1.66	0.020	0.010	1.75	0.056	37.1	22.1	0.011	0.065	0.105	(0.04)	0.022	0.031	0.059
1	IARM 242A	0.24	0.018	0.002	0.0004	0.02	0.007	11.1	3.00	0.004	13.5	1.21	0.0003	0.004	0.009	0.01
1	SRM 1246	0.082	0.91	0.018	0.001	0.18	0.49	30.8	20.1	0.30	0.076	0.36	(0.018)	(0.09)	0.32	(0.040)
2	23X DS5E	0.080	1.04	.	.	1.98	0.30	36.6	8.64	0.083	0.50	0.30	.	.	0.17	.
1	NCS HS41747	0.071	0.807	0.015	0.0006	0.36	0.038	32.27	20.72	0.299	0.050	0.297	.	.	0.49	.
3	HH 5157A	0.067	0.95	0.012	0.003	0.43	0.33	29.31	21.48	0.45	.	.	.	.	0.55	.
2	DSZU C103	0.064	0.287	0.027	(0.006)	0.34	0.066	5.21	27.04	5.28	.	0.013	.	(0.002)	0.29	0.035
1	IARM 24B	0.053	0.82	0.009	0.0010	0.28	0.052	35.86	0.121	0.002	0.036	0.011	0.0017	<0.01	0.002	<0.005
1	SS 479	0.0529	0.680	0.0029	0.0030	0.553	0.0052	24.87	19.922	(0.013)	(0.002)	(0.003)	0.0057	0.625	0.0306	0.0052
1	<b>BS CD4MCU</b>	0.045	0.568	0.025	0.021	0.71	2.93	5.62	24.46	0.0063	(0.03)	1.98	0.229	(0.004)	0.021	0.108
1	SRM 1230	0.044	0.64	0.023	0.0007	0.43	0.14	24.2	14.8	0.24	0.15	1.18	.	.	2.12	0.23
3	HH 5179A	0.042	0.87	0.012	0.003	0.38	0.26	34.13	22.20	0.30	.	.	.	.	0.46	.
2	BS 186A	0.040	0.72	0.008	0.0053	0.19	0.016	35.86	0.16	(0.001)	0.028	0.0032	0.0026	(0.002)	(0.003)	0.0012
2	DSZU C102	0.038	0.265	0.025	(0.006)	1.27	0.031	0.19	24.41	4.98	.	0.022	.	(0.005)	0.25	0.089
3	HH 5196A	0.036	1.05	0.011	0.002	0.45	0.24	31.46	20.66	0.31	.	.	.	.	1.13	.
3	HH 5300A	0.026	0.86	0.013	0.003	0.35	0.28	33.56	18.18	0.45	.	.	.	.	0.54	.
1	SRM 1158	0.025	0.468	0.004	0.005	0.194	0.039	36.03	0.062	0.008	0.010	.	.	.	.	0.001
2	DSZU C101	0.024	0.198	0.013	(0.006)	0.32	0.055	0.34	21.77	5.06	0.026	.	.	(0.011)	0.31	0.023
2	BS 187A	0.022	0.52	0.017	0.0025	0.26	3.10	33.06	19.75	(0.009)	0.32	2.06	0.0157	0.57	(0.002)	0.10
1	13X 17005E	0.0217	0.209	0.0040	0.0431	1.739	0.120	20.06	24.65	0.049	0.0265	0.599	0.0097	0.101	0.0073	.
2	CT IS0139A	0.021	1.00	0.001	0.0005	0.015	<0.001	41.69	0.004	.	0.066	<0.001	.	.	.	.
1	SRM 1247	0.021	0.38	0.018	0.002	0.32	1.75	43.5	23.4	0.060	0.089	2.73	(0.017)	(0.46)	0.75	(0.048)
1	<b>BS CD4MCU-A</b>	0.021	0.38	(0.008)	0.0072	0.31	2.92	5.18	24.6	(0.009)	(0.005)	1.92	0.0112	(0.009)	0.021	(0.006)
2	CT IS0141A	0.0199	0.31	0.001	<0.001	0.28	<0.001	47.16	<0.001	0.001	0.030	<0.001	<0.001	.	0.014	0.024
2	CT IS0136A	0.018	0.44	0.001	<0.001	0.198	<0.001	44.92	0.002	.	0.009	<0.001	.	.	.	.
1	IARM 157D	0.0154	0.626	0.016	0.0005	0.28	0.196	23.9	20.31	0.020	0.102	6.08	0.203	0.149	0.009	0.050
1	<b>BS 189A</b>	0.0147	0.639	0.019	(0.001)	0.30	0.184	23.8	20.4	0.0129	0.100	6.04	0.198	(0.13)	0.0065	0.054
1	NILAB 501HA D	0.014	0.858	0.020	0.003	0.61	0.761	17.69	19.79	0.003	0.159	6.14	0.2243	0.007	.	0.044
1	KUT S22	0.014	0.34	0.009	0.008	0.61	(0.02)	28.2	1.00	.	.	0.82	.	.	0.13	.
1	ECRM 379-1D	0.0121	1.804	0.0166	0.0006	0.393	0.984	30.83	26.79	(0.00246)	0.0390	3.290	0.0550	(0.0028)	(0.0014)	0.0663
1	NCS HS41753a	0.012	0.973	0.021	0.013	0.480	1.26	24.28	19.16	.	0.180	4.25	0.041	0.812	0.004	0.075
2	CT IS0124A	0.011	0.73	0.007	0.006	0.40	0.015	48.07	0.079	.	0.012	0.009	.	.	.	.
1	14X 93603A	0.0101	0.339	0.0050	0.0045	0.153	0.0460	35.79	0.024	0.0404	0.0974	0.0145	0.0057	.	0.0011	.
1	SRM 1159	0.007	0.30	0.003	0.003	0.32	0.038	48.2	0.06	.	0.022	0.01	.	.	.	.
1	IARM 98B	0.007	0.18	0.002	0.0007	0.17	0.028	29.4	0.012	0.07	17.0	0.010	0.0024	0.002	0.03	(0.003)
1	<b>BS 160A</b>	0.0064	0.180	0.0007	(0.0002)	0.158	0.026	29.6	0.0138	0.088	17.0	0.0100	0.0026	0.0014	0.026	0.0008
1	<b>BS 161A</b>	0.004	0.031	0.004	0.0007	0.032	0.22	18.40	0.12	0.14	9.22	4.82	(0.002)	(0.004)	0.65	0.031
1	IARM 26D	0.038	0.224	0.013	(0.0008)	(0.05)	0.047	24.6	14.29	0.29	0.040	1.23	0.0035	(0.007)	2.17	0.223
2	CT IS0138A	0.002	0.48	0.001	0.006	<0.010	<0.001	39.98	<0.001	.	0.64	<0.001	.	.	0.34	.
1	ECRM 285-2D	0.0018	0.0168	0.0053	0.0025	0.0117	0.0094	18.07	0.0236	0.1067	7.76	4.99	0.0007	.	0.520	.

Number	As	B	Ca	Ce	Mg	O	Se	Sn	Ta	W	Zr	Units
CZ SP-8B	0.05	0.03	.	.	.	.	.	0.06	.	0.05	.	-39 mm Ø x 25 mm
CZ SP-4C	.	.	.	.	.	.	.	.	.	(0.01)	.	-39 mm Ø x 25 mm
IARM 242A	.	(0.0005)	.	.	.	0.0006	.	(0.001)	0.008	<0.01	.	31 mm Ø x 2 mm
SRM 1246	(0.004)	<0.001	Ga: (0.004)	.	.	(0.003)	.	.	.	(0.004)	.	35 mm Ø x 19 mm
23X DS5E	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 15 mm
NCS HS41747	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 30 mm
HH 5157A	.	.	.	.	.	.	.	.	.	.	.	44 mm Ø x 12 mm
DSZU C103	.	.	.	.	.	.	.	.	.	(0.004)	(0.001)	38 mm Ø x 18 mm
IARM 24B	<0.005	(0.001)	.	.	.	0.003	0.19	0.0018	<0.005	<0.04	<0.005	31 mm Ø x 2 or 18 mm
SS 479	(0.002)	<0.0005	.	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm
<b>BS CD4MCU</b>	0.0040	0.0028	(0.001)	.	(0.0003)	0.019	<b>17025</b>	(0.03)	.	0.024	(0.002)	36 mm Ø x 26 mm
SRM 1230	.	0.0055	.	.	.	.	.	.	.	.	.	32 mm Ø x 19 mm
HH 5179A	.	.	.	.	.	.	.	.	.	.	.	41 mm Ø x 12 mm
BS 186A	.	.	.	.	.	.	0.229	(0.002)	.	(0.01)	.	38 mm Ø x -7, -12 or 19 mm
DSZU C102	.	.	.	.	.	.	.	.	.	(0.020)	(0.003)	38 mm Ø x 18 mm
HH 5196A	.	.	.	.	.	.	.	.	.	.	.	44 mm Ø x 12 mm
HH 5300A	.	.	.	.	.	.	.	.	.	.	.	41 mm Ø x 12 mm
SRM 1158	.	.	.	.	.	.	.	.	.	.	.	32 mm Ø x 19 mm
DSZU C101	.	.	.	.	.	.	.	.	.	(0.011)	(0.003)	38 mm Ø x 18 mm
BS 187A	.	0.0022	.	(0.025)	.	0.0029	.	0.003	<0.002	(0.02)	.	41 mm Ø x -7 mm
13X 17005E	.	0.0030	.	.	.	.	.	.	0.015	.	.	-40 mm Ø x -15 mm
CT IS0139A	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
SRM 1247	(0.003)	0.002	Ga: (0.011)	.	.	(0.005)	.	.	.	(0.005)	.	35 mm Ø x 19 mm
<b>BS CD4MCU-A</b>	0.0022	(0.0008)	(0.001)	.	(0.0003)	0.0061	<b>17025</b>	0.0024	.	(0.009)	(0.002)	44 mm Ø x 19+ mm
CT IS0141A	.	.	.	.	0.0002	.	.	.	.	.	.	30-35 mm Ø x -16 mm
CT IS0136A	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
IARM 157D	.	0.0007	.	.	.	.	.	0.0036	.	0.036	.	31 mm Ø x 2 or 18 mm
<b>BS 189A</b>	0.0039	(0.0002)	(0.0004)	.	.	0.0024	<b>17025</b>	0.0035	.	0.037	(0.001)	38 mm Ø x -7 or 19+ mm
NILAB 501HA D	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 20 mm
KUT S22	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 or 40 mm
ECRM 379-1D	(0.0018)	0.00190	0.0033	.	(0.0006)	(0.0027)	.	0.0021	.	(0.0091)	(0.00033)	38 or 45 mm Ø x 25 mm
NCS HS41753a	.	.	.	.	.	.	.	.	.	0.058	.	Sb: 0.00057
CT IS0124A	.	.	.	.	.	.	0.167	.	.	.	.	37 mm Ø x 35 mm
14X 93603A	.	.	.	.	0.0019	.	.	.	.	.	(0.0009)	44-47 mm Ø x -11 or -19 mm
SRM 1159	.	.	.	.	.	.	.	.	.	.	.	Fe: 50.65
IARM 98B	<0.002	0.001	<0.0005	.	0.0040	0.0021	.	0.002	<0.05	(0.02)	<0.01	31 mm Ø x 2 mm
<b>BS 160A</b>	0.0011	0.0010	(0.0004)	.	0.0032	0.0022	<b>17025</b>	0.0024	Ta, W: (0.0001)	0.0048	.	38 mm Ø x -7 or 19+ mm
<b>BS 161A</b>	(0.002)	0.0023	(0.0008)	.	(0.0004)	.	.	(0.0015)	(0.03)	(0.008)	(0.002)	38 mm Ø x -12 or 19 mm
IARM 26D	.	0.0063	.	.	.	.	.	0.0039	.	0.036	.	last
CT IS0138A	.	.	.	.	.	.	.	.	.	.	.	25(pre-17025)
ECRM 285-2D	.	0.0009	.	.	.	.	.	.	.	.	0.0050	30-35 mm Ø x -16 mm
												Fe: 58.53
												38 mm Ø x 25 or 30 mm

## HIGH ALLOY STEEL XRF SET

Part Number:	BS HAS-12	RM except CRM as noted, available as set or individually											* Provisional Analysis					~7 mm Ø discs		
Number Grade	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	B	Co	N	Nb	Sn	Ti	V	W	O	
<b>BS 189A</b> AL6XN CRM	0.0147	0.639	0.019	(0.001)	0.30	0.184	23.8	20.4	6.04	0.0129	(0.0002)	0.100	0.198	(0.13)	0.0035	0.0065	0.054	0.037	0.0024	
		<b>17025</b>																		
BS 179A Alloy 255	0.017	1.04	0.021	0.001	0.44	1.94	5.84	25.45	3.24	(0.009)	(0.001)	0.58	0.184	0.030	0.005	0.006	0.070	(0.2)	.	
<b>BS 183B</b> Greek Ascology CRM	0.181	0.344	0.018	0.0042	0.41	0.074	1.96	12.45	0.33	0.0009	(0.0007)	0.032	0.044	(0.0075)	0.0046	(0.0016)	0.165	3.5	(0.0054)	
		<b>17025</b>																		
BS 186A Invar 36	0.040	0.72	0.008	0.0053	0.19	0.016	35.86	0.16	0.0032	(0.001)	.	0.028	0.0026	(<0.002)	(0.002)	(<0.003)	0.0012	(0.01)	.	
BS 187A Carp. 20Cb3	0.022	0.52	0.017	0.0025	0.26	3.10	33.06	19.75	2.06	(0.009)	0.0022	0.32	0.0157	0.57	0.003	(0.002)	0.10	(0.02)	.	
<b>BS 188B</b> A-286 CRM	0.046	0.247	0.016	(0.0007)	0.266	0.120	24.81	14.32	1.30	0.168	0.0047	0.274	0.0021	0.099	0.0051	2.20	0.264	0.043	0.0006	
		<b>17025</b>																		
BS 190 Nitronic® 40	0.022	9.72	0.015	0.001	0.46	0.072	6.74	19.57	0.15	(0.004)	0.0005	0.044	0.255	(0.004)	0.003	0.002	0.11	0.015	0.0045	
BS 180A Nitronic® 50	0.018	5.05	0.012	0.001	0.32	0.067	13.19	21.09	2.04	0.012	(0.0024)	0.039	0.334	0.20	(0.002)	(0.002)	0.20	0.02	0.003	
BS 181A Nitronic® 60	0.071	8.16	0.019	0.001	4.03	0.18	8.15	16.52	0.21	0.022	0.0009	0.072	0.148	0.017	0.005	0.007	0.094	0.04	0.0010	
BS 193 18Cr-12Mn	0.104	12.11	0.018	0.002	0.66	0.088	1.82	18.48	0.21	(0.003)	0.0007	0.028	0.37	0.014	0.004	0.003	0.107	(0.007)	.	
BS 182 17Cr-15Mn	0.037	15.09	0.022	(0.003)	0.46	0.56	1.11	16.67	0.99	.	.	0.032	(0.40)	(0.005)	(0.003)	(0.003)	0.059	(0.01)	.	
BS 191 16Cr-6Mn-4Si	0.098	5.71	0.024	0.023	3.66	0.33	5.34	16.33	0.36	(0.002)	(0.0006)	0.11	0.117	0.024	(0.006)	0.012	0.083	0.033	.	

## CRM

## CAST IRON SETS

AVAILABLE IN SETS ONLY, as grouped

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Sn	Ti	V	Ce	La	Mg	N
30 mm Ø x 28 mm																	
NCS HS11712a-6	4.02	1.41	0.021	0.026	0.163	1.83	1.89	0.112	0.019	0.726	0.057	0.238	0.509	<0.0001	<0.0001	0.104	0.013
NCS HS11712a-7	3.94	1.38	0.085	0.0048	0.918	1.10	1.37	1.05	0.214	0.168	0.134	0.114	0.390	<0.0001	<0.0001	0.056	0.0063
NCS HS11712a-5	3.52	0.311	0.420	0.019	1.17	0.389	1.03	0.766	.	0.629	0.013	0.161	0.324	<0.0001	<0.0001	0.021	0.0047
NCS HS11712a-4	3.16	0.462	0.396	0.017	1.96	0.921	0.778	1.40	0.0073	0.428	0.024	0.065	0.166	<0.0001	<0.0001	0.025	0.0073
NCS HS11712a-2	2.22	0.301	0.043	0.058	2.44	0.458	0.341	2.13	0.060	0.087	0.044	0.065	0.055	0.0010	0.010	0.0085	0.024
NCS HS11712a-3	2.55	0.878	0.071	0.045	1.50	0.641	0.519	0.417	0.034	0.354	0.021	0.027	0.085	0.027	0.0061	0.024	0.024
NCS HS11712a-1	1.75	0.080	0.580	0.119	3.40	0.025	0.030	2.48	0.248	0.031	0.0031	0.038	0.021	<0.0001	<0.0001	0.0006	0.015
30 mm Ø x 30 mm																	
NCS HS19701-7	4.13	2.06	0.306	0.111	1.85	.	0.026	0.157	.	.	0.043	0.399	0.821	.	.	.	.
NCS HS19701-6	3.93	1.46	0.168	0.124	0.99	.	0.094	0.387	.	(0.112)	0.0018	0.105	0.506	.	.	.	.
NCS HS19701-5	3.67	0.596	0.072	0.117	0.183	.	0.502	0.171	.	(0.68)	0.0022	0.066	0.335	.	.	.	.
NCS HS19701-4	3.70	0.857	0.087	0.076	0.451	.	0.032	0.117	.	(0.031)	0.0017	0.030	0.158	.	.	.	.
NCS HS19701-3	3.29	1.22	0.045	0.056	0.689	.	0.046	0.030	.	.	0.009	0.043	0.071	.	.	.	.
NCS HS19701-2	2.99	0.329	0.033	0.038	0.937	.	0.194	0.080	.	.	0.024	0.216	0.044	.	.	.	.
NCS HS19701-1	2.46	0.072	0.011	0.019	0.099	.	0.183	0.511	.	.	0.005	0.0059	0.0090	.	.	.	.

**RM GRAY IRON** as cast (not chill cast) CONTAINS FREE GRAPHITE OBS regularly requires extension of preburn time to analyze correctly

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	Sb	Sn	Ti	V	mm Ø x mm H
BS 20G	3.33	0.58	0.028	0.029	3.02	0.54	0.38	0.086	0.008	0.004	0.022	0.19	<(0.001)	0.12	0.012	0.018	47 x 19+
BS 20W	3.27	0.62	0.045	0.036	2.64	0.29	0.082	0.092	0.004	0.004	0.005	0.054	<(0.001)	0.086	0.015	0.007	47 x 13
BS 20R	3.25	0.62	0.047	0.034	2.72	0.35	0.096	0.094	0.005	0.004	0.006	0.053	<(0.001)	0.104	0.015	0.007	47 x 19+
BS 20E	3.24	0.80	0.042	0.044	2.29	0.23	0.156	0.088	0.006	(0.003)	0.006	0.042	<(0.002)	0.093	0.017	0.007	47 x 19+
BS 20P	3.22	0.63	0.032	0.044	2.62	0.067	0.143	0.079	0.008	(0.004)	0.018	0.033	<(0.001)	0.099	0.018	0.017	44 x 19+

**DUCTILE / NODULAR IRON**

# = Class, where 1 = CRM and 2 = RM

\* Provisional Analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Ce	Co	Mg	Mo	Ti	V
1	SCRM 666/12	3.599	0.106	.	.	1.763	0.0581	1.709	0.102	.	.	.	<b>0.083</b>	0.0979	0.1069	0.0486
1	SCRM 667/13	3.04	0.222	.	.	2.866	0.497	1.303	0.294	.	0.110	.	<b>0.070</b>	.	.	0.103
1	BS 285BH	3.43	0.732	0.0470	0.0128	1.93	0.321	1.38	1.05	0.0168	.	0.0034	<b>0.052</b>	0.238	0.0429	0.122
1	BS 286CI	3.27	0.714	0.20	(0.012)	2.00	0.363	1.43	0.349	0.012	(0.03)	0.027	<b>0.052</b>	0.258	0.052	0.150
1	BS 285BG	3.44	0.731	0.0469	0.0126	1.93	0.321	1.39	1.05	0.0165	.	0.0038	<b>0.051</b>	0.238	0.0427	0.122
1	BS 286CH	3.27	0.714	0.20	(0.012)	2.00	0.363	1.43	0.349	0.012	(0.03)	0.027	<b>0.051</b>	0.258	0.052	0.150
1	BS 285BF	3.43	0.732	0.0472	0.0127	1.93	0.320	1.386	1.047	0.0164	.	0.0033	<b>0.050</b>	0.238	0.0424	0.122
1	BS 286CG	3.27	0.714	0.20	(0.012)	2.00	0.363	1.43	0.349	0.012	(0.03)	0.027	<b>0.050</b>	0.258	0.052	0.150
1	BS 286CF	3.27	0.714	0.20	(0.012)	2.00	0.363	1.43	0.349	0.012	(0.03)	0.027	<b>0.049</b>	0.258	0.052	0.150
1	BS 285BD	3.45	0.730	0.0471	0.0126	1.93	0.322	1.39	1.047	0.0160	.	0.0036	<b>0.048</b>	0.238	0.0427	0.121
1	BS 286CE	3.27	0.714	0.20	(0.012)	2.00	0.363	1.43	0.349	0.012	(0.03)	0.027	<b>0.048</b>	0.258	0.052	0.150
1	BS 286CD	3.27	0.714	0.20	(0.012)	2.00	0.363	1.43	0.349	0.012	(0.03)	0.027	<b>0.047</b>	0.258	0.052	0.150
1	SCRM 670/23	3.585	0.318	0.0464	0.0098	2.234	0.976	0.907	0.498	.	0.0123	.	<b>0.047</b>	0.0109	0.111	0.0257
1	BS 286CC	3.27	0.714	0.20	(0.012)	2.00	0.363	1.43	0.349	0.012	(0.03)	0.027	<b>0.046</b>	0.258	0.052	0.150
1	BS 291GJ	3.33	0.497	0.034	0.014	2.30	0.231	0.098	0.070	0.043	.	0.0039	<b>0.045</b>	0.031	0.028	0.033
1	BS 291GI	3.33	0.497	0.034	0.014	2.30	0.231	0.098	0.070	0.043	.	0.0039	<b>0.044</b>	0.031	0.028	0.033
1	BS 291GH	3.33	0.497	0.034	0.014	2.30	0.231	0.098	0.070	0.042	.	0.0039	<b>0.043</b>	0.031	0.028	0.033
1	BS 291GG	3.33	0.497	0.034	0.014	2.30	0.231	0.098	0.070	0.041	.	0.0039	<b>0.042</b>	0.031	0.028	0.033
1	BS 285CK *	3.30	0.70	0.050	0.009	1.95	0.30	1.28	1.00	0.021	.	0.005	<b>0.042</b>	0.19	0.045	0.13
1	BS 291GF	3.33	0.497	0.034	0.014	2.30	0.231	0.098	0.070	0.040	.	0.0039	<b>0.041</b>	0.031	0.028	0.033
1	BS 285CJ *	3.30	0.70	0.050	0.009	1.95	0.30	1.28	1.00	0.022	.	0.005	<b>0.041</b>	0.19	0.045	0.13
1	BS 285CI *	3.30	0.70	0.050	0.009	1.95	0.30	1.28	1.00	0.021	.	0.005	<b>0.040</b>	0.19	0.045	0.13
1	BS 285CH *	3.30	0.70	0.050	0.009	1.95	0.30	1.28	1.00	0.021	.	0.005	<b>0.039</b>	0.19	0.045	0.13
1	BS 285CG *	3.30	0.70	0.050	0.009	1.95	0.30	1.28	1.00	0.021	.	0.005	<b>0.038</b>	0.19	0.045	0.13
1	BS 285CF *	3.30	0.70	0.050	0.009	1.95	0.30	1.28	1.00	0.021	.	0.005	<b>0.037</b>	0.19	0.045	0.13
1	BS 285CE *	3.30	0.70	0.050	0.009	1.95	0.30	1.28	1.00	0.020	.	0.005	<b>0.036</b>	0.19	0.045	0.13
1	BS 285CD *	3.30	0.70	0.050	0.009	1.95	0.30	1.28	1.00	0.020	.	0.005	<b>0.035</b>	0.19	0.045	0.13
2	BAS SIMO 1/5	2.72	0.330	0.031	0.014	3.94	0.005	0.035	0.889	0.029	.	0.004	<b>0.034</b>	0.738	0.008	0.004
1	BS 285CC *	3.30	0.70	0.050	0.009	1.95	0.30	1.28	1.00	0.020	.	0.005	<b>0.034</b>	0.19	0.045	0.13
1	BS 285CB *	3.30	0.70	0.050	0.009	1.95	0.30	1.28	1.00	0.019	.	0.005	<b>0.033</b>	0.19	0.045	0.13
1	SRM C1137a	2.86	0.52	0.087	0.017	1.15	0.192	2.17	0.643	(0.007)	0.016	.	<b>0.032</b>	0.86	(0.04)	0.019
1	BS 285CA *	3.30	0.70	0.050	0.009	1.95	0.30	1.28	1.00	0.019	.	0.005	<b>0.032</b>	0.19	0.045	0.13
1	BAS SIMO 2/2	2.14	0.434	0.025	0.007	4.75	0.010	0.0189	0.856	0.013	0.006	0.0029	<b>0.026</b>	0.484	0.005	0.009
1	SCRM 669/15	3.09	0.52	0.041	0.0108	2.41	0.217	0.48	0.260	.	0.040	.	<b>0.023</b>	0.057	0.058	0.50
1	SCRM 668/14	3.77	0.702	0.045	0.0220	1.72	0.65	0.096	0.99	.	0.023	.	<b>0.009</b>	0.0179	0.086	0.195
1	SRM C2424	2.68	0.268	0.041	0.024	3.37	0.125	0.061	0.13	<(0.01)	0.0046	(0.05)	<b>0.006</b>	0.019	0.050	0.083

Number	As	B	Ca	Fe	La	Nb	Pb	Sb	Sn	W	Zr	Units
SCRM 666/12	.	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
SCRM 667/13	.	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
BS 285BH	0.0007	0.0084	0.0010	90.54	.	0.0040	0.0009	(0.2)	0.0017	0.0612	0.0055	~35 mm Ø x ~30 mm
BS 286CI	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	.	(0.01)	0.0025	(0.003)	~35 mm Ø x ~30 mm
BS 285BG	0.0008	0.0084	0.0010	90.54	.	0.0039	0.0009	(0.2)	0.0017	0.0611	0.0055	~35 mm Ø x ~30 mm
BS 286CH	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	.	(0.01)	0.0025	(0.003)	~35 mm Ø x ~30 mm
BS 285BF	0.0009	0.0084	0.0010	90.54	.	0.0039	0.0008	(0.2)	0.0018	0.0608	0.0054	~35 mm Ø x ~30 mm
BS 286CG	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	.	(0.01)	0.0025	(0.003)	~35 mm Ø x ~30 mm
BS 286CF	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	.	(0.01)	0.0025	(0.003)	~35 mm Ø x ~30 mm
BS 285BD	0.0010	0.0084	0.0009	90.54	.	0.0039	0.0007	(0.2)	0.0017	0.0608	0.0055	~35 mm Ø x ~30 mm
BS 286CE	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	.	(0.01)	0.0025	(0.003)	~35 mm Ø x ~30 mm
BS 286CD	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	.	(0.01)	0.0025	(0.003)	~35 mm Ø x ~30 mm
SCRM 670/23	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	.	(0.01)	0.0025	(0.003)	48 mm x 42 mm x 12 mm
BS 286CC	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	.	(0.01)	0.0025	(0.003)	~35 mm Ø x ~30 mm
BS 291GJ	0.0052	0.017	0.0010	93.14	N:0.0053	0.0036	0:0.0009	(0.006)	0.049	(0.003)	(0.0018)	~34 mm Ø x ~28 mm
BS 291GI	0.0052	0.017	0.0010	93.14	N:0.0053	0.0036	0:0.0009	(0.006)	0.049	(0.003)	(0.0018)	~34 mm Ø x ~28 mm
BS 291GH	0.0052	0.017	0.0010	93.14	N:0.0053	0.0036	0:0.0009	(0.006)	0.049	(0.003)	(0.0018)	~34 mm Ø x ~28 mm
BS 291GG	0.0052	0.017	0.0010	93.14	N:0.0053	0.0036	0:0.0009	(0.006)	0.049	(0.003)	(0.0018)	~34 mm Ø x ~28 mm
BS 285CK *	0.002	0.008	0.002	[90.9]	.	0.005	0.001	0.013	0.002	0.048	0.006	~33 mm Ø x ~30 mm
BS 291GF	0.0052	0.017	0.0010	93.14	N:0.0053	0.0036	0:0.0009	(0.006)	0.049	(0.003)	(0.0018)	~34 mm Ø x ~28 mm
BS 285CJ *	0.002	0.008	0.002	[90.9]	.	0.005	0.001	0.013	0.002	0.048	0.006	~33 mm Ø x ~30 mm
BS 285CI *	0.002	0.008	0.002	[90.9]	.	0.005	0.001	0.013	0.002	0.048	0.006	~33 mm Ø x ~30 mm
BS 285CH *	0.002	0.008	0.002	[90.9]	.	0.005	0.001	0.013	0.002	0.048	0.006	~33 mm Ø x ~30 mm
BS 285CG *	0.002	0.008	0.002	[90.9]	.	0.005	0.001	0.013	0.002	0.048	0.006	~33 mm Ø x ~30 mm
BS 285CF *	0.002	0.008	0.002	[90.9]	.	0.005	0.001	0.013	0.002	0.048	0.006	~33 mm Ø x ~30 mm
BS 285CE *	0.002	0.008	0.002	[90.9]	.	0.005	0.001	0.013	0.002	0.048	0.006	~33 mm Ø x ~30 mm
BS 285CD *	0.0											

CAST IRON WITH MAGNESIUM - continued on the next page

# = Class, where 1 = CRM and 2 = RM

\* Provisional Analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Te	Al	Ce	Co	Mo	Ti	V
1	CZ 20034 17b	4.38	0.501	0.089	0.0040	0.178	0.111	2.34	0.200	0.009	.	(0.002)	(0.003)	0.043	0.030	0.016	0.086
1	CZ 20034 17a	4.30	0.494	0.115	0.0034	0.170	0.082	2.38	0.200	0.007	.	(0.002)	(0.003)	0.043	0.030	0.016	0.086
1	CZ 20034 17c	4.08	0.503	0.104	0.0033	0.150	0.037	2.32	0.178	0.007	.	(0.002)	(0.003)	0.043	0.030	0.015	0.076
1	Y 2863-11	4.03	0.61	0.613	0.026	0.79	0.96	0.46	1.65	0.0075	.	.	.	.	0.94	0.29	0.079
2	CZ SPL17 43A	3.98	1.322	0.190	0.008	1.63	0.385	0.411	0.032	(0.04)	.	0.024	0.017	0.045	0.152	0.065	0.152
2	CZ SPL17 42A	3.94	0.764	0.294	0.0040	1.94	0.199	0.492	0.145	(0.06)	.	0.087	0.039	0.010	0.021	0.126	0.093
1	Y 451045	3.90	0.12	0.023	0.0027	2.29	0.022	0.45	0.028	0.033	.	.	.	.	0.0030	0.016	0.0014
1	SCRM 668/14	3.77	0.702	0.045	0.0220	1.72	0.65	0.096	0.99	0.009	.	.	0.023	.	0.0179	0.086	0.195
1	Y 2863-12	3.77	0.158	0.053	0.057	0.150	0.55	0.192	2.31	0.0024	.	.	.	.	0.44	0.030	0.229
1	CZ 02033 2f	3.77	0.091	0.159	0.009	1.23	0.89	0.658	0.022	0.053	.	0.024	0.018	(0.003)	(0.002)	0.021	0.010
1	VS ChG 25/1	3.75	0.67	0.013	0.0048	1.46	0.81	0.406	0.214	0.0096	.	.	.	.	0.271	0.0087	0.0070
1	CZ 02033 3c	3.68	0.333	0.026	0.007	2.15	0.421	0.040	0.100	0.006	(0.005)	0.024	0.013	0.026	0.490	0.021	0.016
1	SCRM 666/12	3.599	0.106	.	.	1.763	0.0581	1.709	0.102	0.0838	.	.	.	.	0.0979	0.1069	0.0486
1	VS ChG 27/1	3.59	1.20	0.039	0.019	1.97	0.351	0.030	0.139	.	.	0.011	.	.	0.131	0.060	0.070
2	Y 4510058B-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.042	.	.	0.022	.	0.180	0.044	0.174
2	Y 4510058C-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.039	.	.	0.022	.	0.180	0.044	0.174
2	Y 4510058D-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.036	.	.	0.022	.	0.180	0.044	0.174
2	Y 4510058E-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.032	.	.	0.022	.	0.180	0.044	0.174
2	CZ SPL17 31A	3.54	0.041	0.025	0.006	2.10	0.005	0.538	0.019	0.070	.	0.005	(0.004)	0.022	0.004	0.007	0.008
2	CZ SPL17 34A	3.48	0.980	0.105	0.008	2.29	0.230	0.493	0.102	0.026	.	0.010	0.008	0.025	0.072	0.044	0.073
1	CZ 20034 15c	3.47	0.060	0.054	0.0028	1.68	1.123	0.728	0.078	0.040	.	0.010	0.030	0.026	(0.002)	0.036	0.019
2	CZ SPL17 32A	3.39	0.288	0.037	0.007	2.74	0.306	0.015	0.060	0.024	.	0.029	(0.004)	(0.002)	0.116	0.044	0.005
1	CZ 02033 3b	3.38	0.260	0.012	0.012	1.74	0.400	0.049	0.235	0.012	.	0.026	0.006	0.012	0.456	0.023	0.009
2	CZ SPL17 40A	3.38	0.042	0.021	0.0035	1.98	0.010	0.045	0.031	0.007	.	0.096	0.012	0.027	0.005	0.015	0.014
1	VS ChG 28	3.29	0.414	0.025	0.015	2.22	1.29	0.166	0.127	0.010	.	0.015	.	.	0.0024	0.0041	0.0020
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Te	Al	Ce	Co	Mo	Ti	V
1	VS ChG 28/1	3.28	0.420	0.039	0.008	2.14	1.30	0.177	0.177	0.014	.	0.0097	.	.	.	0.019	0.013
1	CZ 02033 3d	3.24	0.317	0.008	0.006	2.12	0.396	0.025	0.236	0.016	.	0.055	0.006	0.014	0.453	0.016	0.072
1	CZ 02033 1f	3.23	0.693	0.043	0.005	2.68	0.018	0.373	0.035	0.070	(0.007)	0.073	0.036	0.024	0.182	0.041	0.014
1	CZ 20034 13c	3.15	0.704	0.0261	0.0044	2.23	0.089	1.299	0.124	0.064	.	0.022	0.011	0.024	0.360	0.015	0.043
1	CZ 20034 14c	3.14	0.275	0.0162	0.0081	2.49	0.585	0.030	0.045	0.017	.	0.007	0.019	0.009	0.646	0.018	0.013
1	CZ 20034 13a	3.13	0.691	0.0244	0.0046	2.19	0.021	1.266	0.122	0.053	.	0.017	0.011	0.024	0.364	0.014	0.048
1	CZ 20034 13b	3.12	0.692	0.0243	0.0041	2.12	0.021	1.313	0.125	0.054	.	0.019	0.011	0.024	0.364	0.012	0.048
1	BS CC-11A	3.07	1.23	0.020	0.011	1.90	0.007	0.046	0.048	0.014	0.026	0.0055	0.018	(0.007)	0.0063	0.0091	0.0066
1	VS ChM5/1	3.04	0.311	0.056	0.016	1.37	.	.	.	0.045	.	0.013	.	.	.	.	.
1	SCRM 667/13	3.04	0.222	.	.	2.866	0.497	1.303	0.294	0.070	.	.	0.110	.	.	.	0.103
1	VS ChG 24/1	3.04	0.280	0.237	0.007	2.40	0.104	0.85	0.030	0.021	.	0.027	0.021	.	0.028	0.089	0.026
1	VS ChM6/1	3.03	0.54	0.055	0.0074	2.75	.	.	.	0.072	.	0.022	.	.	.	.	.
1	VS ChM8/1	3.02	0.83	0.055	0.0034	3.39	.	.	.	0.105	.	0.041	.	.	.	.	.
2	CZ SPL17 36A	3.02	0.057	0.026	0.010	2.13	0.007	0.011	0.014	0.012	.	(0.003)	0.0007	(0.004)	0.004	0.021	0.021
1	BS CC-11B	2.97	1.17	0.020	0.008	1.94	0.0210	0.173	0.189	0.025	0.019	0.028	0.045	(0.022)	0.018	0.031	0.0179
1	VS ChM13	2.96	1.05	0.043	0.009	2.98	0.062	1.65	0.273	0.09	.	0.065	.	.	.	0.018	0.0096
1	VS ChG 26/1	2.96	0.132	0.104	0.0058	2.89	0.022	1.41	0.050	0.052	.	0.041	0.017	.	0.070	0.016	0.159
1	SCRM 669/14	2.955	0.526	.	.	2.201	0.194	0.473	0.214	0.0224	.	.	0.0415	.	0.0550	0.0499	0.532
1	VS ChG 26	(2.9)	0.126	0.123	0.0041	2.98	0.014	1.52	0.050	0.044	.	0.038	.	.	0.075	0.0026	0.040
1	VS ChM10	2.89	0.43	0.067	0.017	1.13	0.082	0.85	0.067	0.024	.	0.005	.	.	.	0.028	0.079
1	SRM C1137a	2.86	0.52	0.087	0.017	1.15	0.192	2.17	0.643	0.032	.	(0.007)	0.016	.	0.86	(0.04)	0.019
2	CZ SPL17 33A	2.75	0.710	0.060	0.007	3.10	0.730	0.389	0.239	0.021	.	0.054	0.026	0.015	0.220	0.130	0.356
1	SRM C2424	2.68	0.268	0.041	0.024	3.37	0.125	0.061	0.13	0.006	.	(<0.01)	0.0046	(0.05)	0.019	0.050	0.083
1	VS ChM9	2.61	1.28	0.075	0.021	1.59	0.095	0.38	0.083	0.011	.	0.016	.	.	.	0.027	0.068
1	VS ChM11	2.26	0.77	0.032	0.011	2.32	0.067	1.75	0.122	0.066	.	0.035	.	.	.	0.014	0.0044
1	Y 2863-7	1.98	3.42	0.067	0.0061	3.10	0.089	4.47	0.150	0.050	.	.	0.019	.	0.052	0.060	0.87
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Te	Al	Ce	Co	Mo	Ti	V

BS: 28-34 mm Ø x 17-35 mm      CKD 24x: 37 mm x 37 mm x ~15-20 mm      SCRM: 48 mm x 42 mm x 12 mm      VS: ~40 mm Ø x ~40 mm  
 CZ: 40 mm Ø x 18 mm      SRM: 32 mm Ø x 19 mm      Y: 30 mm Ø x 30 mm

## CAST IRON WITH MAGNESIUM - continued from the previous page

sizes shown below

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other
CZ 20034 17b	0.008	(0.0002)	(0.001)	.	.	.	.	(0.002)	.	.	(0.002)	0.004	.	.
CZ 20034 17a	0.007	(0.0002)	(0.001)	.	.	.	.	(0.002)	.	.	(0.002)	0.004	.	.
CZ 20034 17c	0.0005	(0.0006)	(0.002)	.	.	.	.	(0.002)	.	.	(0.002)	0.004	.	.
Y 2863-11	(0.022)	0.053	.	.	.	.	0.33	(0.0057)	(0.174)	.	(0.108)	0.010	.	.
CZ SPL17 43A	.	0.0014	(0.002)	.	.	.	0.008	0.014	(0.004)	.	0.067	0.038	Zn:0.013	.
CZ SPL17 42A	.	0.0036	(0.002)	.	.	.	0.045	0.020	0.015	.	0.027	0.020	Zn:0.013	.
Y 451045	.	.	.	.	.	.	.	.	.	.	.	.	.	last
SCRM 668/14	.	.	.	.	.	.	.	.	.	.	.	.	.	.
Y 2863-12	(0.0097)	0.0078	.	.	.	.	0.21	(0.056)	(0.471)	.	(0.307)	0.13	.	.
CZ 02033 2f	.	0.0020	(0.002)	.	.	.	.	0.005	0.028	.	0.014	(0.003)	(0.005)	Zn: 0.018
VS ChG 25/1	.	.	.	.	.	.	.	.	0.067	.	.	0.011	.	.
CZ 02033 3c	(0.007)	0.0044	(0.002)	.	.	.	.	0.005	.	.	0.009	(0.003)	.	.
SCRM 666/12	.	.	.	.	.	.	.	.	.	.	.	.	.	.
VS ChG 27/1	.	.	.	.	.	.	.	.	0.036	.	.	0.125	.	.
Y 4510058B-18	0.0021	0.024	.	.	.	.	.	.	.	.	.	.	.	.
Y 4510058C-18	0.0021	0.024	.	.	.	.	.	.	.	.	.	.	.	.
Y 4510058D-18	0.0021	0.024	.	.	.	.	.	.	.	.	.	.	.	.
Y 4510058E-18	0.0021	0.024	.	.	.	.	.	.	.	.	.	.	.	last
CZ SPL17 31A	.	(0.0004)	.	.	.	.	.	.	.	.	(0.003)	(0.005)	.	.
CZ SPL17 34A	.	0.0076	(0.005)	.	.	.	0.014	(0.006)	0.007	.	0.051	0.016	Zn:0.007	.
CZ 20034 15c	(0.003)	0.0057	0.008	.	.	.	.	.	0.056	.	0.006	0.004	.	.
CZ SPL17 32A	.	(0.0005)	(0.007)	.	.	.	.	0.022	0.023	.	(0.012)	(0.008)	Zn:0.011	.
CZ 02033 3b	.	0.0042	0.001	.	.	.	.	0.009	.	.	0.019	.	.	.
CZ SPL17 40A	.	0.0008	.	.	.	.	.	.	.	.	(0.004)	.	Zn:(0.002)	.
VS ChG 28	.	.	.	.	.	.	.	.	0.015	.	0.0017	.	.	.

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other
VS ChG 28/1	.	.	.	.	.	.	.	.	.	.	0.0017	.	.	.
CZ 02033 3d	(0.018)	0.0071	(0.002)	.	.	.	.	0.005	0.007	.	0.009	.	.	.
CZ 02033 1f	.	0.0043	(0.001)	.	.	.	.	0.009	.	.	0.030	0.022	(0.008)	.
CZ 20034 13c	(0.002)	.	.	.	.	.	.	.	(0.002)	.	0.014	(0.003)	(0.02)	.
CZ 20034 14c	0.035	0.0123	.	.	.	.	.	.	0.020	.	0.025	(0.003)	0.013	Zn: 0.010
CZ 20034 13a	(0.002)	.	.	.	.	.	.	.	(0.002)	.	0.014	(0.003)	0.029	.
CZ 20034 13b	(0.002)	.	.	.	.	.	.	.	(0.002)	.	0.014	(0.003)	0.023	.
<b>BS CC-11A</b>	0.0018	0.0008	(0.005)	(0.0009)	93.6	(0.004)	(0.007)	(0.002)	(0.01)	Zn:0.0032	(0.004)	(0.017)	(0.0025)	<b>17025</b>
VS ChM5/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.
SCRM 667/13	.	.	.	.	.	.	.	.	.	.	.	.	.	.
VS ChG 24/1	.	.	.	.	.	.	.	.	0.011	.	0.081	.	.	.
VS ChM6/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.
VS ChM8/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.
CZ SPL17 36A	.	0.022	(0.007)	.	.	.	.	0.016	.	.	(0.002)	.	Zn:(0.002)	.
<b>BS CC-11B</b>	0.0074	0.0033	(0.016)	(0.002)	93.2	(0.008)	0.043	0.014	0.026	Zn:0.008	0.021	0.028	0.0165	<b>17025</b>
VS ChM13	.	.	.	.	.	.	.	.	.	.	.	.	.	.
VS ChG 26/1	.	.	.	.	.	.	.	.	0.0055	.	0.034	.	.	.
SCRM 669/14	.	.	.	.	.	.	.	.	.	.	.	.	.	.
VS ChG 26	.	.	.	.	.	.	.	.	.	.	0.031	.	.	.
VS ChM10	.	.	.	.	.	.	.	.	.	.	.	.	.	.
SRM C1137a	.	.	.	.	.	.	.	.	.	.	.	.	.	.
CZ SPL17 33A	.	0.0064	(0.002)	.	.	.	0.032	0.010	0.019	.	0.039	0.079	Zn:0.009	.
SRM C2424	.	(0.002)	.	.	.	0.0011	.	.	.	.	.	.	.	.
VS ChM9	.	.	.	.	.	.	.	.	.	.	.	.	.	.
VS ChM11	.	.	.	.	.	.	.	.	.	.	.	.	.	.
Y 2863-7	(0.021)	0.100	.	.	.	.	0.041	(0.0025)	(0.010)	.	(0.0073)	.	.	.

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other
--------	----	---	----	----	----	----	----	----	----	----	----	---	----	-------

BS: 28-35 mm Ø x 17-35 mm

CZ: 40 mm Ø x 18 mm  
SCRM: 48 mm x 42 mm x 12 mmSRM: 32 mm Ø x 19 mm  
Y: 30-35 mm Ø x 18-30 mmVS ChM: ~39 mm Ø x ~39 mm  
VS ChG: ~34 mm x ~35 mm X ~22 mm

**RM CAST IRON WITH YOUR CHOICE OF MAGNESIUM LEVELS** each unit: 2 pcs mushroom 43 mm Ø x 5 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Al	Ce	Co	Sn	Ti	V	Zn	Other
CTIF 6134	3.70	0.25	0.030	<0.01	1.60	0.020	2.00	0.040	*	.	<0.03	.	.	.	.	.	.
CTIF 8532	3.7	0.288	0.05	.	2.6	0.0443	0.888	0.04	*	.	<0.025	.	0.0303	0.02	0.07	.	.
CTIF 6135	3.6	0.38	0.0130	(0.003)	0.9	0.0219	1.98	0.04	*	(0.006)	.	0.037	.	0.007	0.0155	.	.
CTIF 4500	3.38	0.60	0.059	(0.002)	1.97	.	1.45	0.014	*	0.033	0.023	0.065	.	.	.	.	.
CTIF 5781	3.35	0.26	0.030	(0.0025)	2.50	0.0061	0.83	0.040	*	.	.	(0.004)	.	0.0208	0.0150	.	.
CTIF 4497	3.12	0.605	0.043	(<0.002)	2.66	0.048	1.90	0.040	*	.	.	.	0.094	0.031	0.44	.	.
CTIF 7160	3.1	0.57	0.05	(0.001)	2.4	0.08	1.0	(0.1)	*	(0.02)	0.02	0.09	.	0.013	0.018	.	As: 0.009
CTIF 5037	3.04	0.76	0.043	(0.0025)	3.40	.	0.64	0.014	*	.	.	.	.	0.029	.	.	.
CTIF 3601B	3.0	0.35	0.037	(0.005)	2.1	0.019	1.08	0.029	*	.	<0.01	.	.	0.016	(0.005)	<0.05	Pb:(<0.002)
CTIF 8018	3.0	0.7	0.07	(0.0015)	3.0	0.08	0.127	0.09	*	0.02	(<0.02)	.	0.07	0.06	0.39	.	Sb:(0.01)
CTIF 6736	2.8	0.65	0.012	(0.002)	1.6	0.0258	1.7	0.03	*	.	.	.	.	0.008	(0.03)	.	.
CTIF 5783	2.55	0.2	0.0266	(0.003)	2.3	0.110	1.23	0.05	*	.	.	0.0074	.	0.015	0.0127	.	As: 0.0016

Magnesium level available in the below samples. X = available

For Mg Range	Order Suffix	3601B	4497	4500	5037	5781	5783	6134	6135	6736	7160	8018	8532
<0.005	<0.005	X	.	.	.	X	X	.	.	.	.	X	X
0.005 - 0.009	0.005	X	.	.	X	X	X	.	.	X	.	X	X
0.010 - 0.014	0.01	.	.	.	X	X	X	.	.	X	X	X	X
0.015 - 0.024	0.02	X	.	.	X	X	X	.	X	X	X	X	X
0.025 - 0.034	0.03	.	.	.	X	.	X	.	X	X	X	X	X
0.035 - 0.044	0.04	.	.	.	X	.	X	.	X	X	X	X	X
0.045 - 0.054	0.05	.	.	.	X	.	X	.	X	X	X	X	X
0.055 - 0.064	0.06	.	X	.	.	.	X	.	X	X	X	X	X
0.065 - 0.074	0.07	.	X	X	.	.	X	.	X	X	X	X	X
0.075 - 0.084	0.08	.	X	X	.	.	X	X	X	X	X	X	X
0.085 - 0.094	0.09	.	X	X	.	.	X	X	X	X	X	X	X
0.095 - 0.104	0.10	.	.	.	.	.	X	X	X	X	X	X	X
0.105 - 0.114	0.11	.	.	.	.	.	X	X	X	X	X	X	X
0.115 - 0.124	0.12	.	.	.	.	.	X	X	X	X	X	X	X
0.125 - 0.134	0.13	.	.	.	.	.	X	X	X	X	X	X	X
0.135 - 0.144	0.14	.	.	.	.	.	X	X	X	X	X	X	X
0.145 - 0.154	0.15	.	.	.	.	.	.	.	.	.	X	.	.
0.155 - 0.164	0.16	.	.	.	.	.	.	.	.	.	X	.	.
0.165 - 0.174	0.17	.	.	.	.	.	.	.	.	.	X	.	.
0.175 - 0.184	0.18	.	.	.	.	.	.	.	.	.	X	.	.

The above cast iron samples can be ordered with your choice of Magnesium. Examples:  
 to order CTIF 6736 with Mg 0.035 - 0.044 then order as part number CTIF 6736 0.04  
 to order CTIF 8018 with 0.08 % Mg, order as part number CTIF 8018 0.08

**CRM WHITE IRON** analysis listed in mass %

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	Nb	Ti	V
<b>BS WI-2</b>	3.61	0.80	0.22	0.056	0.52	0.0124	0.254	0.229	0.0118	0.219	0.128	0.089	0.215
SRM CII45	2.92	0.187	0.215	0.191	0.271	0.46	0.62	0.63	0.058	0.48	.	0.012	0.112
VS ChG 8/6	(2.7)	1.51	0.040	0.013	3.93	.	.	(0.2)	.	.	.	.	(0.3)
VS ChG 10/6	(2.7)	0.86	0.103	0.0072	2.86	.	.	(0.2)	.	.	.	.	(0.3)
VS ChG 11/6	(2.7)	0.312	0.23	0.039	1.79	.	.	(0.2)	.	.	.	.	(0.3)
VS ChG 9/6	(2.7)	0.155	0.38	0.071	0.80	.	.	(0.2)	.	.	.	.	(0.3)
<b>BS WI-1</b>	1.75	0.24	0.051	0.114	1.90	0.027	0.053	0.048	0.0074	0.0103	0.027	0.020	0.008

**17025**

**17025**

Number	Al	As	B	Bi	Ca	Fe	Mg	Pb	Sb	Sn	W	Zr	Units
<b>BS WI-2</b>	0.0192	0.0016	0.0008	.	(0.00013)	[93.6]	(0.0002)	0.013	0.023	0.0042	0.023	0.0045	~35 mm Ø x ~30 mm
SRM CII45	(0.04)	(0.03)	(0.02)	(<0.01)	.	.	.	0.0012	(0.04)	(0.10)	.	(0.002)	32 mm Ø x 19 mm
VS ChG 8/6	.	(0.003-0.006)	.	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~40 mm
VS ChG 10/6	.	(0.003-0.006)	.	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~40 mm
VS ChG 11/6	.	(0.003-0.006)	.	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~40 mm
VS ChG 9/6	.	(0.003-0.006)	.	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~40 mm
<b>BS WI-1</b>	0.075	0.0067	0.0032	.	0.0005	[95.5]	0.0009	0.115	.	0.0081	0.185	0.0034	~35 mm Ø x ~30 mm



## CAST IRON WITH C &gt; 2.75%

CONTINUED ON THE NEXT PAGE

# = Class, 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
2	CZ SPL17 35A	4.55	0.096	0.024	0.011	0.078	0.004	0.024	0.022	(0.002)	0.023	0.003	.	(0.002)	(0.002)	0.009	.
2	MBH FEPIGH	4.5	0.10	0.048	0.11	1.64	0.011	0.040	0.087	0.17	0.019	0.027	no uncertainties	.	0.41	0.12	.
1	CZ 02033 4e	4.45	0.034	0.023	0.006	0.090	0.005	0.049	0.030	(0.003)	0.033	0.002	.	(0.001)	0.011	0.015	.
1	CZ 02033 4d	4.19	0.112	0.050	0.041	0.259	0.084	0.063	0.056	0.007	(0.003)	0.024	.	(0.001)	0.009	0.012	0.009
1	SCRm 659/9	4.174	1.010	0.0215	0.0372	1.361	.	.	.	.	.	.	.	.	.	.	.
1	Y 2582-7	4.13	2.06	0.306	0.111	1.85	.	0.26	0.157	.	.	.	.	.	0.399	0.821	.
1	DSZU CH04	4.01	1.77	0.074	0.018	0.73	0.55	0.273	0.100	0.014	(0.05)	(0.004)	(0.005)	(0.002)	0.025	(0.004)	.
1	DSZU CH05	3.99	2.23	0.119	0.039	0.46	0.61	0.85	1.63	(0.002)	(0.07)	0.109	(0.3)	(0.01)	0.070	0.200	.
1	CZ 02033 4b	3.95	0.145	0.041	0.046	0.252	0.062	0.023	0.049	0.003	0.005	0.005	.	0.001	0.006	0.004	0.008
1	VS ChG 2/9	3.93	0.456	0.513	0.078	0.387	0.082	.	0.060	.	.	.	.	.	0.080	0.049	.
1	DSZU CH06	3.88	0.85	0.050	0.050	0.28	1.03	1.23	(2.8)	0.025	(0.07)	0.29	(0.05)	(0.03)	0.33	0.205	.
1	CZ 20034 16c	3.87	1.311	0.173	0.0243	0.95	0.345	0.376	0.332	0.004	0.006	0.195	.	0.125	0.057	0.027	0.017
1	CZ 20034 16a	3.80	1.292	0.171	0.0266	1.00	0.332	0.390	0.374	0.007	0.010	0.203	.	0.125	0.0763	0.021	0.019
1	11X C6W	3.80	0.967	0.088	0.064	0.81	0.952	0.072	0.396	0.021	0.046	1.32	0.010	0.030	0.195	0.045	0.0045
1	CZ 20034 16b	3.78	1.327	0.170	0.0236	1.00	0.332	0.388	0.378	0.007	0.010	0.202	.	0.121	0.070	0.029	0.020
1	VS ChG 32	3.74	1.90	0.061	0.018	0.60	0.171	.	0.031	.	.	0.113	.	0.060	0.040	0.294	.
1	SCRm 674/1	3.71	1.437	0.0180	0.078	0.484	.	0.161	0.0296	0.0061	0.0066	0.0497	.	0.0164	0.0131	0.0125	.
1	Y 2582-4	3.70	0.857	0.087	0.076	0.451	.	0.032	0.117	.	.	(0.031)	.	0.030	0.158	.	.
2	CZ SPL17 39A	3.70	0.812	0.160	0.045	1.90	0.298	0.032	0.488	0.008	(0.002)	0.203	.	(0.003)	(0.074)	0.232	0.035
1	Y 2582-5	3.67	0.596	0.072	0.117	0.183	.	0.502	0.171	.	.	(0.68)	.	.	0.066	0.335	.
1	VS ChG 1/9	3.61	1.12	0.184	0.038	1.13	0.041	.	0.017	.	.	.	.	.	0.014	0.006	.
1	CZ 02033 7b	3.61	0.304	0.021	0.020	1.82	0.036	1.28	0.536	0.022	0.050	0.96	.	.	0.015	0.007	.
1	CZ 02033 7c	3.55	0.389	0.028	0.026	1.73	0.016	1.26	0.542	0.040	0.048	0.966	.	(0.004)	0.026	0.067	.
1	DSZU CH03	3.54	0.40	0.023	0.034	0.57	0.194	0.187	0.612	0.035	(0.05)	(0.019)	(0.010)	(0.004)	0.059	0.009	.
1	VS ChG 3/9	3.54	0.387	0.037	0.053	0.516	0.123	.	0.100	.	.	.	.	.	0.125	0.096	.
1	VS ChG 27	3.53	1.21	0.044	0.029	1.82	0.348	0.022	0.162	0.008	.	0.147	.	0.115	0.056	0.160	.
1	VS ChG 5/9	3.51	0.60	0.104	0.036	0.84	0.037	.	0.307	.	.	.	.	.	(0.1)	0.441	.
1	11X HPC4Q	3.48	1.19	1.63	0.102	1.70	0.078	2.03	0.788	.	.	0.101	.	.	.	0.029	.
1	Y 2863-5	3.47	0.78	0.564	0.070	0.89	0.365	0.62	1.53	.	.	0.67	.	.	0.133	0.129	.
1	11X C3AD	3.45	0.896	0.539	0.180	1.06	0.351	4.34	1.669	0.0104	0.240	0.235	0.021	0.166	0.127	0.605	0.007
1	CZ SPL17 41A	3.41	0.512	0.199	0.068	1.92	0.151	0.104	0.125	(0.003)	0.031	0.041	.	0.066	0.048	0.011	(0.001)
1	VS CHL1/1	3.39	0.53	0.048	0.029	1.32	0.344	0.410	0.264	.	0.017	0.036	.	.	0.061	0.073	.
2	CZ SPL17 38A	3.39	0.401	0.067	0.036	2.37	0.510	0.306	0.141	0.034	0.021	0.101	0.008	0.032	0.012	0.061	0.028
1	11X C10D	3.38	0.754	0.104	0.086	1.89	0.643	0.873	0.429	0.024	0.059	0.288	.	0.035	0.0474	0.1048	.
1	VS ChG 35	3.34	1.23	0.102	0.021	0.617	0.090	2.15	0.233	.	.	0.027	.	.	0.022	0.043	.
1	KUT 120	3.34	0.59	0.059	0.18	1.84	.	.	.	.	.	.	.	.	.	.	.
1	Y 2863-3	3.32	1.27	0.115	0.049	2.27	0.62	2.01	0.49	.	.	0.313	.	.	0.176	0.45	.
1	KUT 121	3.32	0.61	0.135	0.17	(1.86)	.	.	.	.	.	.	.	.	.	.	.
1	KUT 205	3.32	0.80	0.025	(0.010)	1.88	0.81	0.61	0.64	.	.	1.79	.	(0.035)	.	.	.
1	KUT 206	3.32	0.75	0.027	(0.010)	1.84	1.01	0.21	0.12	.	.	2.14	.	(0.107)	.	.	.
1	KUT 122	3.31	0.61	0.22	0.20	1.72	.	.	.	.	.	.	.	.	.	.	.
1	KUT 123	3.30	0.69	0.31	0.074	(1.87)	.	.	.	.	.	.	.	.	.	.	.
1	NCS HS11784	3.30	0.528	0.78	0.031	2.68	0.015	0.024	0.812	(0.0012)	.	0.142	(0.0012)	0.0005	0.084	0.020	.
1	Y 2582-3	3.29	1.22	0.045	0.056	0.689	0.046	0.030	.	.	.	.	.	.	0.043	0.071	.
1	VS ChG 4/9	3.24	1.42	0.030	0.024	0.455	0.199	.	0.155	.	.	.	.	.	0.10	0.169	.
1	11X HPC3K	3.24	1.00	0.232	0.078	1.37	0.132	1.52	1.19	.	.	0.172	.	.	.	0.042	.
2	BAS NCRM3	3.24	0.67	0.125	0.090	0.29	1.21	3.64	3.95	.	.	0.78	.	.	.	0.02	.
1	NCS HS11782	3.21	1.09	0.088	0.035	1.64	0.042	0.014	0.061	.	.	0.0048	.	.	0.027	0.0079	.
1	KUT 125	3.20	0.73	0.70	0.019	(1.87)	.	.	.	.	.	.	.	.	.	.	.
2	MBH FEPIGM	3.2	0.066	0.045	0.064	0.69	0.008	0.029	0.057	0.060	0.016	0.014	no uncertainties	0.25	0.081	.	.
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
1	VS ChG 31	3.19	0.97	0.047	0.043	1.60	0.281	.	0.156	.	.	0.0069	.	0.013	0.0063	0.0035	.
1	NCS HS11785	3.19	0.482	0.79	0.030	2.52	0.021	0.031	0.817	(0.0030)	.	0.139	(0.0009)	0.0010	0.076	0.018	.
1	DSZU CH02	3.18	1.09	0.007	0.0116	1.35	0.038	0.658	0.59	0.026	(0.06)	0.224	(0.4)	(0.014)	0.161	(0.005)	.
1	11X C2V	3.17	1.23	0.256	0.077	1.180	0.191	1.803	1.126	0.104	0.116	0.116	0.0160	0.0627	0.0870	0.328	0.0115
1	VS ChM 12	3.17	1.00	0.030	0.007	3.10	0.062	1.65	0.039	0.050	.	.	.	.	0.013	0.0027	.
1	SCRm 671/1	3.165	0.811	0.108	0.0503	0.868	.	0.0627	0.0609	0.030	0.098	0.0259	.	0.0103	0.0407	0.0122	.
1	KUT 126	3.16	0.81	1.41	0.016	1.90	.	.	.	.	.	.	.	.	.	.	.
1	KUT 202	3.16	0.81	0.024	(0.010)	1.77	0.24	2.07	2.36	.	.	.	.	(0.21)	.	.	.
1	SCRm 657/9	3.157	0.112	0.101	0.0401	3.209	.	.	.	.	.	.	.	.	.	.	.
1	KUT 204	3.15	0.80	0.023	(0.009)	1.79	0.64	1.09	1.22	.	.	1.38	.	(0.215)	.	.	.
1	KUT 127	3.14	0.79	1.55	0.014	1.81	.	.	.	.	.	.	.	.	.	.	.
1	CZ 02033 6c	3.11	1.25	0.097	0.019	3.25	0.273	0.021	1.33	0.024	0.005	0.006	.	0.131	0.107	0.192	.
2	CZ SPL17 37A	3.07	0.211	0.025	0.023	3.30	0.149	0.106	0.328	0.039	0.031	0.325	.	0.073	0.008	0.122	(0.001)
1	VS ChG 30	3.06	2.10	0.090	0.035	1.97	0.576	.	0.24	.	.	0.0061	.	0.015	0.012	0.0074	.
2	BAS NCRM1	3.05	1.22	0.300	0.156	0.95	2.17	0.57	0.55	.	.	1.02	.	.	.	0.03	.
1	VS CHL3/1	3.04	0.250	0.067	0.024	2.39	0.60	1.08	0.533	.	0.016	0.262	.	.	0.043	0.103	.
1	11X C9E	3.03	1.87	0.045	0.020	1.39	0.433	2.66	1.48	0.072	0.169	0.166	0.077	0.047	0.116	0.437	0.0091
1	DSZU CH08	3.02	0.79	0.056	0.058	2.05	1.60	2.52	2.13	0.29	(0.07)	0.96	(0.3)	(0.008)	0.315	0.34	.
1	VS ChG 39	3.01	0.82	0.304	0.088	1.45	0.414	1.09	1.08	.	.	0.113					

## CAST IRON WITH C &gt; 2.75%

## CONTINUED FROM THE PREVIOUS PAGE

analysis in mass % except \* = mg/kg

Number	As	B	Bi	Ca*	Ce	La	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
CZ SPL17 35A	.	(0.0002)	.	.	.	.	.	.	(0.002)	.	.	.	(0.005)	.	40 mm Ø x 18 mm last
MBH FEPIGH	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø -15 mm
CZ 02033 4e	.	.	(0.002)	.	.	.	.	.	.	(0.002)	.	.	.	.	40 mm Ø x 18 mm
CZ 02033 4d	(0.012)	(0.0001)	(0.002)	.	.	.	.	.	.	0.007	.	.	.	.	40 mm Ø x 18 mm
SCRm 659/9	.	.	.	.	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
Y 2582-7	0.043	.	.	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm
DSZU CH04	.	(0.0007)	.	(7)	.	.	(0.0001)	.	(0.007)	.	.	.	(<0.0002)	.	-30 mm x -35 mm x -19mm
DSZU CH05	.	(0.03)	.	(20)	.	.	(0.001)	.	.	.	.	.	.	.	-30 mm x -35 mm x -19mm
CZ 02033 4b	.	.	.	.	.	.	.	.	0.004	(0.001)	.	.	.	.	40 mm Ø x 18 mm
VS ChG 2/9	(0.003)	.	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -40 mm
DSZU CH06	.	(0.02)	.	(10)	.	.	.	.	.	.	.	.	0.1	.	-35 mm x -35 mm x -19mm
CZ 20034 16c	(0.003)	0.020	.	.	.	.	.	.	0.015	0.010	.	.	0.015	(0.002)	40 mm Ø x 18 mm
CZ 20034 16a	.	0.005	0.018	.	.	.	.	.	0.006	0.011	.	.	0.019	(0.002)	40 mm Ø x 18 mm
11X C5W	0.0544	0.0043	0.007	Cd:(0.0003)	Ag:0.0042	.	.	0.0070	0.007	0.058	0.006	0.013	0.0242	.	-40 mm Ø x -15 mm
CZ 20034 16b	0.005	0.018	.	.	.	.	.	.	0.007	0.011	.	.	0.019	(0.002)	40 mm Ø x 18 mm
VS ChG 32	.	.	0.361	.	.	.	.	.	.	.	.	.	.	.	-37 mm x -37 mm x -24 mm
SCRm 674/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
Y 2582-4	0.0017	.	.	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm
CZ SPL17 39A	.	0.0195	0.008	.	.	.	.	.	0.017	0.037	.	.	.	.	40 mm Ø x 18 mm
Y 2582-5	0.0022	.	.	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm
VS ChG 1/9	(0.003)	.	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -40 mm
CZ 02033 7b	.	.	.	.	.	.	.	.	.	.	.	.	0.045	.	40 mm Ø x 18 mm
CZ 02033 7c	.	0.0008	(0.002)	.	.	.	.	.	.	.	.	(0.006)	0.037	.	40 mm Ø x 18 mm
DSZU CH03	(0.004)	(0.001)	.	(20)	.	.	(0.0001)	.	(0.01)	.	.	.	(0.006)	.	-30 mm x -35 mm x -16mm
VS ChG 3/9	(0.003)	.	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -40 mm
VS ChG 27	.	.	.	.	.	.	.	.	.	0.029	.	.	.	.	-35 mm x -35 mm x -22 mm
VS ChG 5/9	(0.003)	.	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -40 mm
11X HPC4Q	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
Y 2863-5	.	0.060	.	.	.	.	.	.	.	.	.	.	0.158	.	30 mm Ø x 18-30 mm
11X C3AD	0.086	0.0253	0.0124	.	.	.	.	0.0075	0.0170	0.243	0.028	.	0.040	.	-40 mm Ø x -15 mm
CZ SPL17 41A	.	(0.0004)	(0.007)	.	.	.	.	.	0.010	0.016	.	.	0.012	.	40 mm Ø x 18 mm
VS ChL1/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -38 mm
CZ SPL17 38A	.	0.0027	(0.002)	.	.	.	.	.	(0.003)	0.018	.	.	(0.005)	.	40 mm Ø x 18 mm
11X C10D	0.019	0.0030	.	Cd:(0.0004)	.	.	.	0.0057	0.006	0.040	.	.	0.308	.	-40 mm Ø x -15 mm
VS ChG 35	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-34 mm Ø x -37 mm
KUT 120	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
Y 2863-3	.	0.056	.	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm
KUT 121	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
KUT 205	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
KUT 206	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
KUT 122	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
KUT 123	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
NCS HS11784	0.0041	.	0.0083	.	.	.	.	.	0.0002	0.0007	.	.	.	.	31 mm Ø x 28 mm
Y 2582-3	0.009	.	.	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm
VS ChG 4/9	(0.003)	.	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -40 mm
11X HPC3K	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
BAS NCRM3	.	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
NCS HS11782	0.0065	.	.	.	.	.	.	.	.	.	.	.	.	.	31 mm Ø x 28 mm
KUT 125	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
MBH FEPIGM	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø -15 mm

  

Number	As	B	Bi	Ca*	Ce	La	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
VS ChG 31	.	.	0.068	.	.	.	.	.	.	.	.	.	.	.	-37 mm x -37 mm x -24 mm
NCS HS11785	0.0049	.	0.013	.	.	.	.	.	0.0002	0.0005	.	.	.	.	31 mm Ø x 28 mm
DSZU CH02	.	(0.016)	(10)	.	.	.	(0.002)	.	.	.	.	.	.	.	-35 mm Ø x -18 mm
11X C2V	0.0541	0.0098	0.0084	.	.	.	.	0.0096	0.0133	0.115	0.0157	.	0.0228	.	-40 mm Ø x -15 mm
VS ChM 12	.	.	.	.	.	.	(0.08)	.	.	.	.	.	.	.	-38 mm Ø x -38 mm
SCRm 671/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 12 mm
KUT 126	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
KUT 202	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
SCRm 657/9	.	.	.	.	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
KUT 204	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
KUT 127	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
CZ 02033 6c	.	0.0024	.	.	.	.	.	.	.	(0.003)	0.044	.	0.007	.	40 mm Ø x 18 mm
CZ SPL17 37A	.	0.0124	(0.002)	.	.	.	.	.	(0.002)	.	.	.	0.026	.	40 mm Ø x 18 mm
VS ChG 30	.	.	0.082	.	.	.	.	.	.	.	.	.	.	.	-37 mm x -37 mm x -24 mm
BAS NCRM1	.	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
VS ChL3/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -38 mm
11X C9E	0.53	0.0047	.	.	.	.	.	.	(0.0023)	0.145	.	0.0097	0.31	(0.0017)	-40 mm Ø x -15 mm
DSZU CH08	.	(0.08)	(10)	.	.	.	.	.	.	.	.	.	.	.	-35 mm x -35 mm x -19mm
VS ChG 39	.	.	.	.	0.008	.	.	.	.	.	.	.	.	.	-34 mm Ø x -37 mm
BAS LARM2	0.044	.	.	.	.	.	.	.	0.007	.	.	.	.	.	40 mm x 37 mm x 10 mm
BAS LARM4	.	.	.	.	0.008	.	.	.	0.018	.	.	.	.	.	40 mm x 37 mm x 10 mm
BAS LARM1	.	0.006	0.011	.	0.005	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
BAS LARM5	0.018	0.0012	0.0010	.	.	.	.	.	0.0005	.	.	.	.	.	40 mm x 37 mm x 10 mm
BAS LARM3	0.092	0.003	0.022	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm last
Y 2863-4	.	0.041	.	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm
BAS LARM5/1	.	0.0016	0.0012	.	.	.	.	.	<0.001	.	.	.	.	.	40 mm x 37 mm x 10 mm
BAS NCRM2	.	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
KUT 124	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
CZ 02033 6b	.	.	.	.	.	.	.	.	.	0.049	.	.	.	.	40 mm Ø x 18 mm
SCRm 662/4	.	.	.	.	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
VS ChG 36	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-34 mm Ø x -37 mm
CZ 20034 12b	0.024	0.047	0.006	.	.	.	.	.	0.009	0.046	.	.	0.007	(0.002)	40 mm Ø x 18 mm
SRM C1145a	(0.03)	(0.02)	.	.	.	.	.	.	0.0012	(0.04)	.	.	.	(0.002)	32 mm Ø x 19 mm
VS ChG 34	.	.	0.223	.	.	.	.	.	.	.	.	.	.	.	-37 mm x -37 mm x -24 mm
CZ 20034 12a	0.022	0.036	0.005	.	.	.	.	.	0.007	0.046	.	.	0.011	(0.002)	40 mm Ø x 18 mm
NCS HS11786	0.0075	.	0.015	.	.	.	.	.	0.0003	0.0008	.	.	.	.	31 mm Ø x 28 mm
11X CSY	0.0203	0.0058	0.005	.	.	.	.	0.0094	0.0108	0.030	0.0072	(0.0022)	0.0072	(0.0024)	-40 mm Ø x -15 mm
KUT 201	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm

  

Number	As	B	Bi	Ca*	Ce	La	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
--------	----	---	----	-----	----	----	----	---	----	----	----	----	---	----	-------

## CAST IRON WITH C &lt; 2.75%

# = Class, 1 = CRM and 2 = RM

analysis in mass % except \* = mg/kg

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
1	VS ChL4/1	2.69	1.37	0.054	0.027	1.99	0.161	0.725	0.92	.	0.017	0.116	.	.	0.11	0.258	.
1	SRM C1291	2.67	1.14	0.028	0.032	1.34	0.26	4.34	2.78	.	.	0.32	.	.	.	0.031	.
1	VS ChG 6/9	2.65	0.83	0.54	0.027	0.53	0.34	.	0.241	.	.	.	.	.	0.028	0.130	.
1	DSZU CH01	2.61	0.258	0.012	0.0045	1.95	0.097	0.072	0.88	0.079	(0.06)	0.070	(0.010)	(0.05)	0.132	0.134	.
1	VS ChG 40	2.59	1.56	0.059	0.019	1.60	0.98	1.61	1.47	.	.	0.229	.	.	0.18	0.325	.
1	11X C8V	2.60	0.394	1.00	0.204	1.643	0.310	0.275	0.148	0.086	0.126	0.148	0.0217	0.1063	0.235	0.064	0.0068
1	SCRM 661/4	2.56	0.30	0.84	0.068	2.96	.	.	(1)	.	.	.	.	.	.	.	.
1	SCRM 656/9	2.537	0.820	0.060	0.108	2.504	.	.	.	.	.	.	.	.	.	.	.
1	Y 2863-2	2.50	1.83	0.069	0.026	3.14	0.020	3.73	0.136	.	.	0.096	.	.	0.066	0.61	.
1	VS ChG 37	2.49	0.92	0.038	0.046	2.03	0.512	0.90	0.82	.	.	0.55	.	.	0.092	0.227	.
1	SCRM 673/1	2.455	0.123	0.317	0.0112	1.702	.	0.103	0.0423	0.0287	0.053	0.0092	.	0.0206	0.0718	0.052	.
1	CZ 20034 11b	2.44	0.382	0.271	0.140	3.67	0.130	0.082	1.178	0.067	0.005	1.144	.	0.074	0.041	0.182	.
1	VS ChG 38	2.43	0.302	0.386	0.084	2.30	1.20	0.162	1.98	.	.	0.046	.	.	0.105	0.119	.
1	CZ 02033 5b	2.42	0.812	0.033	0.073	1.32	0.031	0.188	0.061	0.062	.	0.089	.	.	0.007	0.005	.
1	VS ChL2/1	2.38	1.03	0.054	0.023	0.55	0.97	0.114	0.077	.	0.013	0.012	.	.	0.009	0.050	.
1	CZ 20034 11a	2.37	0.343	0.271	0.163	3.31	0.086	0.084	1.219	0.046	0.005	1.130	.	0.070	0.028	0.184	.
1	SCRM 652/4	2.34	1.19	0.071	0.129	0.878	.	.	(1)	.	.	.	.	.	.	.	.
1	DSZU CH07	2.33	1.36	0.090	0.064	3.01	0.35	0.403	0.34	0.036	.	0.66	(0.08)	(0.07)	0.150	0.52	.
1	CZ 02033 5c	2.30	0.704	0.027	0.091	1.40	0.013	0.188	0.085	0.103	0.013	0.104	.	(0.002)	0.008	0.054	.
1	11X C4S	1.954	0.565	0.1014	0.096	2.98	0.095	3.21	1.382	0.006	0.0210	0.177	0.0233	0.0140	0.080	0.0165	0.0037
1	SCRM 675	1.92	1.81	0.045	0.072	1.29	0.012	0.210	0.080	0.007	0.023	0.034	.	0.0062	0.007	0.178	0.0006
1	SCRM 655/4	1.90	0.44	0.180	0.076	2.110	.	.	(1)	.	.	.	.	.	.	.	.
1	Y 2863-1	1.78	2.41	0.021	0.009	3.62	0.022	4.77	0.031	.	.	0.038	0.0052	.	0.068	1.13	.

  

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
	Number	As	B	Bi	Ca*	Ce	Mg	N	Pb	Sb	Se	Te	W	Zr	Units		
	VS ChL4/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~38 mm
	SRM C1291	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	32 mm Ø x 19 mm
	VS ChG 6/9	(0.003)	.	.	.	.	.	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~40 mm
	DSZU CH01	.	(0.03)	.	(10)	.	(0.0005)	.	.	.	.	.	(0.02)	.	.	.	~30 mm x ~35 mm
	VS ChG 40	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	~34 mm Ø x ~37 mm
	11X C8V	0.0812	0.0366	0.014	.	.	.	0.0065	0.0052	0.069	0.0210	0.0049	0.0258	0.0064	.	.	~40 mm Ø x ~15 mm
	SCRM 661/4	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
	SCRM 656/9	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
	Y 2863-2	.	0.0025	.	.	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm
	VS ChG 37	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	~34 mm Ø x ~37 mm
	SCRM 673/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
	CZ 20034 11b	0.005	0.0032	0.007	.	.	.	.	0.007	0.011	.	.	(0.005)	0.007	.	.	40 mm Ø x 18 mm
	VS ChG 38	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	~34 mm Ø x ~37 mm
	CZ 02033 5b	.	0.014	0.020	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 18 mm
	VS ChL2/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~38 mm
	CZ 20034 11a	0.005	0.0018	0.011	.	.	.	.	0.017	0.013	.	.	(0.005)	0.007	.	.	40 mm Ø x 18 mm
	SCRM 652/4	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
	DSZU CH07	.	(0.13)	.	(10)	.	(0.01)	.	.	.	.	.	.	.	.	.	~35 mm x ~35 mm x ~19mm
	CZ 02033 5c	.	0.0078	0.007	.	.	.	.	.	.	(0.002)	(0.010)	.	(0.009)	.	.	40 mm Ø x 18 mm
	11X C4S	0.0235	0.0351	0.0070	.	.	.	0.0126	0.034	0.0055	0.009	.	0.099	.	.	.	~40 mm Ø x ~15 mm
	SCRM 675	0.035	.	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
	SCRM 655/4	.	.	.	.	.	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
	Y 2863-1	.	0.0024	.	.	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm

ALLOYED CAST IRON, CHART 1 of 2

# = Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
2	DSZU CH021	3.93	3.66	0.064	0.009	0.52	0.369	5.86	9.07	0.168	4.42	.	.	0.093	0.61	.	.
1	VS CHG41/1	3.88	1.23	0.037	0.090	1.77	0.56	5.84	8.7	.	0.50	.	.	0.21	0.25	.	.
2	BAS NCRM5	3.70	0.27	0.025	0.015	1.15	0.204	6.74	10.44	.	0.10	.	.	.	0.06	.	.
1	SRM C1292	3.47	0.55	0.049	0.016	0.59	0.36	5.04	11.4	.	0.25	.	.	.	0.041	.	.
2	BAS CRRM5/2	3.43	0.30	0.029	0.018	0.20	0.22	0.36	30.35	0.15	0.63	.	.	0.009	0.11	.	.
1	Y 451052-1	3.31	1.54	0.369	0.0047	0.098	0.449	2.57	1.17	.	1.47	.	.	.	.	.	0.952
1	<b>BS PM15</b>	3.54	0.416	0.0198	0.0127	0.912	0.142	0.203	5.33	0.0025	1.22	(0.00001)	0.0034	0.0029	14.79	(0.0002)	0.111
1	VS CHG 48	3.44	0.100	0.0070	0.0039	0.923	0.90	0.280	22.79	0.049	0.591	.	0.0018	0.0022	0.0016	0.072	.
1	VS CHG44/1	3.25	1.91	0.018	0.029	1.28	2.46	0.210	25.4	.	0.028	.	.	0.43	0.106	.	.
1	11X 15309T	3.18	1.53	0.034	0.021	1.22	0.056	0.152	24.9	0.097	0.066	.	0.0047	0.013	0.098	.	.
1	Y 451052-7	3.13	0.201	0.024	0.116	2.48	0.154	0.129	31.26	.	0.086	.	.	0.033	0.087	.	.
2	58A SC01141	3.08	0.62	0.045	0.036	0.56	0.77	1.21	15.32	.	2.70	.	.	0.020	0.28	.	.
1	SRM C1290	3.04	0.66	0.030	0.013	0.971	0.065	0.917	30.5	.	(0.041)	.	.	.	0.442	.	.
1	Y TSK205	3.03	0.16	0.041	0.088	1.65	0.35	0.37	30.35	.	0.22	.	.	.	0.077	.	0.108
1	Y 451054-2	3.00	1.42	0.133	0.016	0.56	0.324	1.43	7.23	.	2.48	.	.	0.015	0.88	.	.
1	NCS HS11788	2.97	1.62	0.191	0.010	3.29	0.51	17.77	2.56	(0.0023)	0.0013	.	0.0003	0.043	0.017	.	.
1	Y 451052-2	2.96	1.24	0.211	0.0077	0.491	1.57	1.99	9.75	.	2.17	.	.	0.300	0.669	.	.
2	BAS NIRM5/1	2.95	1.01	0.103	0.005	1.50	0.21	21.7	0.51	.	.	.	.	.	0.055	.	.
2	58A ZS01036	2.95	0.719	0.077	0.024	0.970	0.448	0.806	13.89	.	0.683	.	0.048	0.035	0.135	.	.
2	BAS NIRM2/2	2.94	2.01	0.096	0.007	1.43	5.93	13.69	1.48	.	.	.	.	.	0.044	.	.
2	BAS CRRM4/2	2.93	0.58	0.049	0.042	0.45	0.53	0.58	21.93	<0.005	1.15	.	.	0.008	0.11	.	.
2	11X 20003K	2.91	1.53	0.174	0.007	3.03	0.52	17.8	2.53	.	.	.	.	.	.	.	.
1	11X S/1 Cr3J	2.91	0.861	0.072	0.023	1.07	9.01	14.53	1.61	.	.	.	.	.	.	.	.
2	DSZU CH022	2.90	1.76	0.033	0.018	0.43	2.53	2.19	14.85	0.053	2.65	.	.	0.078	0.45	.	.
2	11X 20001J	2.90	0.58	0.005	0.143	1.01	0.01	21.4	1.50	.	.	.	.	.	.	.	.
1	11X 15294W	2.76	0.451	0.082	0.029	0.36	0.103	0.309	29.3	(0.147)	0.091	0.012	0.036	.	0.132	.	.
1	Y 451054-3	2.73	1.09	0.105	0.036	0.99	0.451	1.20	12.97	.	2.08	.	.	0.045	0.66	.	.
1	VS CHG45	(2.7)	1.01	0.096	0.047	2.96	0.040	0.60	32.65	.	0.198	.	.	0.011	0.111	.	.
1	VS CHG42/1	2.69	2.78	0.068	0.034	0.411	1.37	0.26	14.8	.	1.87	.	.	0.131	0.48	.	.
2	BAS NCRM4	2.66	0.40	0.203	0.012	2.13	0.68	5.34	7.94	.	0.57	.	.	.	0.11	.	.
1	NCS HS11787	2.65	1.08	0.067	0.037	2.07	0.306	19.84	1.98	(0.085)	0.0014	.	0.0054	0.022	0.0096	.	.
1	11X 15310B	2.63	0.97	0.070	0.029	0.99	2.37	4.59	20.7	0.018	0.92	.	.	0.034	0.096	.	.
1	11X 0331-2M	2.62	1.85	0.050	(0.09)	3.14	6.68	15.1	1.54	0.137	0.067	0.019	0.0271	0.198	0.051	.	.
1	11X 15295S	2.58	1.02	0.059	0.048	0.783	0.213	0.326	28.5	0.122	0.363	0.008	0.026	0.008	0.270	.	.
1	Y TSK201	2.56	1.07	0.253	0.023	0.66	1.53	2.44	10.14	.	2.56	.	.	.	0.42	.	0.029
2	BAS NIRM6/1	2.53	4.07	0.225	0.049	2.68	0.11	26.9	1.02	.	0.51	.	.	.	.	.	.
2	BAS NIRM3	2.51	0.51	0.208	0.096	2.21	1.00	17.8	2.43	.	.	.	.	.	.	.	.
1	VS CHG 47	2.43	0.949	0.099	0.083	2.73	0.0104	0.149	14.45	0.0056	0.0019	.	0.093	0.041	0.129	.	.
1	VS CHG45/1	1.96	0.59	0.021	0.0091	3.08	0.056	0.95	33.8	.	0.209	.	.	.	0.21	.	.
1	VS CHG43/1	0.87	1.02	0.063	0.076	4.44	0.171	0.439	23.7	.	0.107	.	.	0.033	0.040	.	.

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
	Number	B	Ce	Co	Nb	W	Zr		Units								Other
	DSZU CH021	.	.	.	.	.	.	.	35 mm x 35 mm x 16 mm								
	VS CHG41/1	.	.	.	.	.	.	.	-37 mm Ø x -22 mm								
	BAS NCRM5	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm								
	SRM C1292	.	.	.	.	.	.	.	32 mm Ø x 19 mm								
	BAS CRRM5/2	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm								
	Y 451052-1	0.177	.	.	0.018	0.015	.	.	30 mm Ø x 18-30 mm								
	<b>BS PM15</b>	.	.	0.0330	0.014	0.109	(0.0005)	0.109	38 mm Ø x 19+ mm	<b>17025</b>	Fe:[73.0]	As:0.0040	N:0.111	O:0.0129			
	VS CHG 48	As:0.0021	.	0.044	.	.	.	Sb:0.0017	-35 mm Ø x -17 mm								
	VS CHG44/1	.	.	.	.	.	.	.	-37 mm Ø x -22 mm								
	11X 15309T	.	.	0.76	0.056	0.022	.	.	-40 mm Ø x -15 mm								
	Y 451052-7	0.015	.	.	0.010	0.175	.	.	30 mm Ø x 18-30 mm								
	58A SC01141	.	.	.	.	.	.	.	-35 mm Ø x -30 mm								
	SRM C1290	.	.	.	.	.	.	.	32 mm Ø x 19 mm								
	Y TSK205	.	.	.	.	.	.	.	35 mm Ø x 18-30 mm								
	Y 451054-2	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm								
	NCS HS11788	0.0008	.	(0.0063)	.	(0.0002)	.	.	31 mm Ø x 28 mm	As: 0.014							
	Y 451052-2	0.142	.	.	0.182	1.99	.	.	30 mm Ø x 18-30 mm								
	BAS NIRM5/1	.	0.016	.	0.15	.	.	.	48 mm x 42 mm x 12 mm								
	58A ZS01036	.	.	0.024	0.025	0.172	.	.	-32 mm Ø x -30 mm	As: (0.003)							
	BAS NIRM2/2	.	0.018	.	.	.	.	.	48 mm x 42 mm x 12 mm								
	BAS CRRM4/2	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm								
	11X 20003K	.	.	.	.	.	.	.	40 mm Ø x 15 mm								
	11X S/1 Cr3J	.	.	.	.	.	.	.	-40 mm Ø x -15 mm								
	DSZU CH022	.	.	.	.	.	.	.	35 mm x 35 mm x 16 mm								
	11X 20001J	.	.	.	.	.	.	.	40 mm Ø x 15 mm								
	11X 15294W	.	.	0.128	.	0.265	.	.	-40 mm Ø x -15 mm								
	Y 451054-3	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm								
	VS CHG45	.	.	.	.	.	.	.	-36 mm x -36 mm Ø x -18 mm	last							
	VS CHG42/1	.	.	.	.	.	.	.	-37 mm Ø x -22 mm								
	BAS NCRM4	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm								
	NCS HS11787	0.0007	.	(0.0054)	.	(0.0002)	.	.	31 mm Ø x 28 mm	As: 0.0075							
	11X 15310B	.	.	0.157	.	0.188	.	.	-40 mm Ø x -15 mm								
	11X 0331-2M	.	.	0.179	0.134	0.004	0.0022	.	-40 mm Ø x -15 mm								
	11X 15295S	.	.	1.55	0.091	0.202	(0.0012)	.	-40 mm Ø x -15 mm								
	Y TSK201	.	.	.	.	.	.	.	35 mm Ø x 18-30 mm								
	BAS NIRM6/1	.	0.006	.	.	.	.	.	48 mm x 42 mm x 12 mm								
	BAS NIRM3	.	0.007	.	0.09	.	.	.	40 mm x 37 mm x 10 mm								
	VS CHG 47	As:0.014	.	0.0042	.	.	.	Sb:0.040	-35 mm Ø x -17 mm								
	VS CHG45/1	.	.	.	.	.	.	.	-37 mm Ø x -22 mm				</				

## ALLOYED CAST IRON, CHART 2 of 2

# = Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
1	Y 451052-3	2.40	1.06	0.115	0.015	0.821	0.953	1.55	13.30	.	0.869	.	.	0.171	0.482	.	.
2	BAS CRRM3/2	2.37	0.92	0.073	0.087	1.21	1.09	1.35	18.78	0.102	1.58	.	.	0.015	0.042	.	.
2	DSZU CH023	2.33	0.43	0.023	0.073	0.98	0.054	0.715	23.45	0.255	1.46	.	.	0.38	0.288	.	.
1	Y 451054-4	2.31	0.725	0.071	0.046	1.40	0.739	0.914	17.60	.	1.44	.	.	0.084	0.46	.	.
1	Y TSK200	2.11	0.82	0.319	0.022	0.17	1.86	3.22	4.97	.	3.50	.	.	.	0.60	.	0.021
2	DSZU CH024	2.01	1.22	0.102	0.037	2.18	0.88	0.222	27.84	0.096	3.86	.	.	0.099	0.164	.	.
1	Y 451052-4	2.00	0.803	0.090	0.025	1.16	0.738	1.07	18.28	.	0.598	.	.	0.087	0.380	.	.
2	BAS NIRM4	1.97	2.37	0.051	0.008	3.03	0.52	20.2	3.56	.	.	.	.	.	.	0.014	.
1	NCS HS11789	1.97	1.08	0.048	0.076	2.58	6.39	17.80	2.51	0.061	0.062	0.015	0.014	0.011	0.0093	.	.
2	BAS CRRM2/1	1.92	1.11	0.097	0.079	1.18	1.59	1.61	14.13	0.054	2.44	.	.	0.070	0.063	.	.
1	VS ChG 46	1.87	0.067	0.0106	0.108	3.24	0.0109	5.44	8.58	.	0.63	.	.	.	0.109	.	.
2	BAS NIRM1/1	1.83	6.74	0.058	0.015	3.26	0.20	11.8	0.300	.	.	.	.	.	.	0.021	.
2	DSZU CRRM1/1	1.83	1.45	0.132	0.099	1.53	2.01	2.03	11.18	0.117	3.05	.	.	0.096	0.040	.	.
1	Y 451054-5	1.83	0.466	0.043	0.091	1.80	0.904	0.517	23.40	.	0.739	.	.	0.068	0.26	.	.
1	Y TSK202	1.81	1.16	0.201	0.057	2.00	1.10	1.91	15.42	.	2.20	.	.	.	0.33	.	0.075
2	DSZU CH025	1.80	0.387	0.030	0.026	2.70	1.23	1.77	35.14	0.351	0.302	.	.	0.117	0.044	.	.
2	BAS CRRM1/2	1.70	1.43	0.16	0.099	1.84	1.97	2.03	11.28	0.140	3.06	.	.	0.054	0.063	.	.
2	DSZU CH026	1.62	0.305	0.050	0.032	1.14	0.288	3.63	35.87	0.059	0.96	.	.	0.013	0.067	.	.
1	Y 451052-5	1.48	0.579	0.041	0.058	1.37	0.583	0.708	22.55	.	0.359	.	.	0.056	0.314	.	.
2	BAS NIRM8/2	1.45	1.58	0.105	0.014	5.61	0.23	35.3	2.47	.	0.77	.	.	.	.	0.033	.
1	Y 451054-6	1.45	0.254	0.024	0.123	2.38	1.15	0.216	28.96	.	0.213	.	.	0.084	0.13	.	.
1	VS ChG44	1.24	0.87	(1.2)	0.076	1.50	2.27	0.175	25.44	.	0.035	.	.	0.104	0.079	.	.
1	Y TSK203	1.23	0.68	0.117	0.044	0.46	0.75	1.55	19.93	.	1.58	.	.	.	0.22	.	0.094
1	Y 451052-6	1.16	0.302	0.033	0.086	1.44	0.845	0.289	25.76	.	0.150	.	.	0.019	0.146	.	.
1	Y TSK204	0.91	0.34	0.078	0.063	1.00	0.53	0.97	25.37	.	0.95	.	.	.	0.14	.	0.114

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
	Number	B	Ce	Co	Nb	W	Units			Other							
	Y 451052-3	0.102	.	.	0.149	1.57	30 mm Ø x 18-30 mm										
	BAS CRRM3/2	.	.	.	.	.	40 mm x 37 mm x 10 mm										
	DSZU CH023	.	.	.	.	.	35 mm x 35 mm x 16 mm										
	Y 451054-4	.	.	.	.	.	30 mm Ø x 18-30 mm										
	Y TSK200	.	.	.	.	.	35 mm Ø x 18-30 mm										
	DSZU CH024	.	.	.	.	.	35 mm x 35 mm x 16 mm										
	Y 451052-4	0.086	.	.	0.071	1.05	30 mm Ø x 18-30 mm										
	BAS NIRM4	.	0.011	.	0.37	.	40 mm x 37 mm x 10 mm										
	NCS HS11789	0.0008	.	(0.0075)	.	(0.0002)	31 mm Ø x 28 mm As: 0.0076 Bi: 0.067										
	BAS CRRM2/1	.	.	.	.	.	40 mm x 37 mm x 10 mm										
	VS ChG 46	.	.	.	.	Sb:0.140	~35 mm Ø x ~17 mm										
	BAS NIRM1/1	.	0.022	.	.	.	40 mm x 37 mm x 10 mm										
	BAS CRRM1/1	.	.	.	.	.	40 mm x 37 mm x 10 mm last										
	Y 451054-5	.	.	.	.	.	30 mm Ø x 18-30 mm										
	Y TSK202	.	.	.	.	.	35 mm Ø x 18-30 mm										
	DSZU CH025	.	.	.	.	.	35 mm x 35 mm x 16 mm										
	BAS CRRM1/2	.	.	.	.	.	40 mm x 37 mm x 10 mm										
	DSZU CH026	.	.	.	.	.	35 mm x 35 mm x 16 mm										
	Y 451052-5	0.076	.	.	0.022	0.694	30 mm Ø x 18-30 mm										
	BAS NIRM8/2	.	0.013	.	.	.	48 mm x 42 mm x 12 mm										
	Y 451054-6	.	.	.	.	.	30 mm Ø x 18-30 mm										
	VS ChG44	.	.	.	.	.	~36 mm x ~36 mm Ø x ~18 mm last										
	Y TSK203	.	.	.	.	.	35 mm Ø x 18-30 mm										
	Y 451052-6	0.055	.	.	0.014	0.370	30 mm Ø x 18-30 mm										
	Y TSK204	.	.	.	.	.	35 mm Ø x 18-30 mm										
	Number	B	Ce	Co	Nb	W	Units			Other							

**RM CAST IRON MUSHROOMS CONTINUED ON THE NEXT PAGE**

typical analysis

each unit is one pair of 43 mm Ø x 5 mm mushroom discs

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
CTIF F019	4.04	1.05	1.05	0.032	0.057	.	.	.	.	.	.	.	.	.	.
CTIF F012	3.71	1.86	0.44	0.038	0.004	0.77	.	.	0.008	.	.	0.011	.	.	.
CTIF F08	3.6	1.04	0.37	0.107	0.021	0.215	0.30	0.30	.	.	0.005	0.05	0.055	0.014	.
CTIF FCR7	3.59	1.07	0.365	0.099	0.0427	0.704	0.947	33.65	.	.	2.62	.	.	.	.
CTIF F06	3.49	0.55	0.715	0.87	0.106	0.120	0.128	0.45	.	.	0.202	0.039	0.080	0.110	.
CTIF F010	3.5	0.67	1.05	0.20	0.101	0.114	0.118	0.38	.	.	0.20	.	0.1	0.08	.
CTIF NH3	3.47	0.85	0.175	0.36	0.024	0.031	2.53	1.76	.	.	0.73	.	.	.	.
CTIF F011	3.45	1.57	0.685	0.052	0.103	0.211	0.235	0.34	.	(0.013)	0.225	0.066	0.078	0.113	.
CTIF F018	3.43	1.24	0.590	1.34	0.136	0.049	0.140	0.170	.	.	0.179	0.046	0.057	0.102	.
CTIF NH7-1	3.43	0.95	0.63	0.035	0.022	0.105	5.53	9.02	.	.	.	.	.	.	.
CTIF FCR5	3.43	0.35	0.62	0.052	0.0175	1.02	2.69	28.5	.	.	3.27	.	.	.	.
CTIF FT2-1	3.39	1.415	0.78	0.045	0.095	0.01	0.070	0.030	.	.	.	.	0.100	0.405	.
CTIF NiMo1	3.22	2.585	0.200	0.0590	(0.0030)	0.376	2.165	0.0353	.	0.0205	0.457	0.0020	0.0190	0.0169	.
CTIF FL7	3.22	2.550	0.100	1.34	0.048	0.351	0.232	0.043	.	.	0.335	0.0291	0.0525	0.0796	.
CTIF FT3	3.2	1.55	0.345	0.063	0.051	0.015	0.092	0.685	.	.	.	.	0.2	0.016	.
CTIF NH7-2	3.2	1.20	0.91	0.034	0.0120	0.108	5.53	8.87	.	.	.	.	.	.	.
CTIF F05	3.2	0.7	0.2	1.30	0.027	0.12	0.172	0.3	.	.	0.41	0.109	0.04	0.14	.
CTIF NH9	3.13	1.24	0.65	0.087	0.029	0.203	4.11	11.70	.	.	0.059	.	.	.	.
CTIF NR Cu1	3.12	1.465	0.172	0.090	0.99	4.95	18.02	0.994	(0.095)	.	.	.	.	.	.
CTIF FL6	3.1	1.4	0.6	0.012	0.18	0.079	1.03	0.167	.	0.028	0.50	0.005	0.15	0.033	.
CTIF FL10	3.1	1.3	0.85	0.323	0.066	0.104	0.10	(0.07)	(0.03)	.	0.0335	0.028	0.045	0.048	(0.02)
CTIF FFA 1	3.090	0.0300	0.100	0.0022	0.0009	0.0622	0.0450	0.0710	.	0.0097	0.0109	.	0.0010	0.0010	.
CTIF NR 8S	3.05	1.41	4.39	0.124	0.071	14.20	0.191	.	.	.	.	.	.	.	.
CTIF F017	3.01	2.48	0.475	0.470	0.168	(0.006)	0.021	(0.016)	.	0.032	.	0.024	0.032	0.018	.
CTIF FAL 1	3.0	1.0	0.2	0.04	<0.001	0.2	0.06	0.04	2.1	.	0.015	.	0.01	.	.
CTIF NR 3L	2.99	3.05	0.72	0.088	0.052	0.26	21.58	2.97	.	.	.	.	.	.	.
CTIF NH1	2.98	1.35	0.90	0.060	0.105	1.99	1.38	0.83	.	.	1.45	.	.	.	.
CTIF NH8	2.98	0.80	0.57	0.052	0.076	0.065	8.16	5.03	.	.	0.125	.	.	.	.
CTIF NR 3S	2.92	2.91	0.77	0.024	0.025	0.33	24.63	3.05	.	.	.	.	.	.	.
CTIF FT1	2.9	2.12	0.71	0.12	0.025	0.012	0.11	0.057	.	.	.	0.067	0.19	0.525	.

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
CTIF NR 8L	2.89	1.70	5.19	0.054	0.030	0.075	13.33	0.165	.	.	.	.	.	.	.
CTIF NH4	2.84	0.49	0.28	0.12	0.022	0.09	3.60	2.46	.	.	0.30	.	.	.	.
CTIF F04	2.81	1.51	0.64	0.58	0.009	0.31	0.32	0.17	.	.	0.095	0.013	0.075	0.049	.
CTIF FCR2	2.86	1.07	0.740	0.137	0.055	0.135	1.87	11.8	.	.	3.88	.	.	.	.
CTIF FL5	2.8	2.3	0.4	0.02	(0.005)	0.5	0.05	0.35	.	0.010	0.01	0.07	0.01	0.01	.
CTIF FCR Ni3	2.74	0.69	0.47	0.036	0.011	.	11.05	31.65	.	.	.	.	.	.	.
CTIF NH6	2.70	2.28	0.355	0.066	0.036	0.115	7.06	6.60	.	.	0.11	.	.	.	.
CTIF F09	2.7	1.5	0.7	0.02	0.015	0.31	0.355	0.18	.	.	0.13	0.144	0.017	0.022	.
CTIF FL4	2.6	2.91	0.5	0.288	0.137	0.0168	0.061	0.45	.	.	0.090	0.011	0.0296	0.116	.
CTIF NR 1S	2.58	3.02	1.54	0.19	0.0015	0.11	20.60	2.00	.	.	.	.	.	.	.
CTIF NR 1L	2.50	3.00	1.34	0.125	0.10	0.49	25.87	1.74	.	.	.	.	.	.	.
CTIF NH2	2.50	1.81	1.04	0.047	0.058	1.02	1.78	1.26	.	.	1.01	.	.	.	.
CTIF NR Cu2	2.48	2.07	1.078	0.113	0.049	6.50	15.85	2.05	.	.	.	.	.	.	.
CTIF NR 4S	2.47	4.87	1.71	0.145	0.066	0.63	18.30	1.50	.	.	.	.	.	.	.
CTIF FCR4	2.47	1.40	2.05	0.097	0.066	1.32	0.571	24.2	.	.	2.16	.	.	.	.
CTIF FCR1	2.46	0.48	0.63	0.019	0.007	0.031	1.30	18.71	.	.	1.41	.	.	.	.
CTIF F07	2.45	0.675	0.70	0.84	0.085	0.125	0.15	0.455	.	.	0.26	.	0.065	0.13	.
CTIF NR 4L	2.41	5.89	1.495	0.155	0.010	0.758	15.90	1.403	.	.	.	.	.	.	.
CTIF NR 2S	2.32	1.43	0.530	0.062	0.0210	0.210	36.3	0.51	.	.	.	.	.	.	.
CTIF NH5	2.31	0.31	0.24	0.115	0.04	0.035	4.90	2.85	.	.	0.017	.	.	.	.
CTIF FL3	2.3	2.1	0.27	0.729	(0.013)	0.102	0.553	0.107	.	.	0.106	0.111	0.05	0.049	.
CTIF NR 4G	2.24	5.60	1.72	0.11	(0.002)	0.64	21.30	1.40	.	.	.	.	.	.	.
CTIF NR 2G	2.25	1.47	0.380	0.0476	(0.003)	0.232	36.34	0.395	.	.	.	.	.	.	.
CTIF FL2	2.18	3.61	0.0400	0.049	0.082	0.0497	0.0238	0.440	(0.006)	0.0263	(0.004)	0.140	0.0750	0.201	.
CTIF FL1	2.1	3.2	0.80	0.118	0.0765	0.0195	0.245	0.06	.	(0.022)	0.038	0.305	0.020	0.015	.
CTIF FCR Ni2	2.02	1.50	0.61	0.185	0.024	.	13.05	29.00	.	.	.	.	.	.	.
CTIF NR Cu3	1.94	3.12	0.60	0.046	0.016	8.05	13.3	3.50	.	.	.	.	.	.	.
CTIF NR 6S	1.82	2.44	0.99	0.019	0.031	0.03	30.75	1.06	.	.	.	.	.	.	.
CTIF NR 5L	1.77	2.99	1.207	0.037	0.083	0.48	33.89	0.27	.	.	.	.	.	.	.
CTIF NR 6L	1.76	2.07	0.70	0.031	0.063	0.020	30.37	3.49	.	.	.	.	.	.	.
CTIF NR 5S	1.67	1.97	1.23	0.035	.	0.50	27.05	0.24	.	.	.	.	.	.	.
CTIF FCR6	1.44	0.76	1.47	0.201	0.086	0.480	0.188	30.84	.	.	0.455	.	.	.	.
CTIF FCR Ni1	1.27	1.63	0.71	0.41	0.06	0.02	16.50	26.20	.	.	.	.	.	.	.

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
--------	---	----	----	---	---	----	----	----	----	----	----	----	----	---	---



## CAST IRON MUSHROOMS

## CONTINUED FROM THE PREVIOUS PAGE

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
CTIF F019	.	.	.	.	.	.	.	.	.	0.0005	.
CTIF F012	.	.	.	.	.	.	.	.	.	.	.
CTIF F08	.	.	.	.	.	.	.	.	.	.	.
CTIF FCR7	.	.	.	.	.	.	.	.	.	.	.
CTIF F06	.	.	.	.	.	.	.	.	.	.	.
CTIF F010	.	.	.	.	.	.	.	.	.	.	.
CTIF NH3	.	.	.	.	.	.	.	.	.	.	.
CTIF F011	.	.	.	.	.	.	.	.	.	.	.
CTIF F018	.	.	.	.	.	0.0040	.	.	.	.	.
CTIF NH7-1	.	.	.	.	.	.	.	.	.	.	.
CTIF FCR5	.	.	.	.	.	.	.	.	.	.	.
CTIF FT2-1	.	.	.	.	.	.	.	.	.	.	.
CTIF NiMo1	.	.	.	.	.	.	.	.	.	.	.
CTIF FL7	(0.0266)	(0.010)	.	(0.010)	.	0.0035	.	.	.	.	.
CTIF FT3	.	.	.	.	.	.	.	.	.	.	.
CTIF NH7-2	.	.	.	.	.	.	.	.	.	.	.
CTIF F05	.	.	.	.	.	.	.	.	.	.	.
CTIF NH9	.	.	.	.	.	.	.	.	.	.	.
CTIF NR Cu1	.	.	.	.	.	.	.	.	.	.	.
CTIF FL6	.	0.008	.	.	.	.	.	.	.	.	.
CTIF FL10	(0.022)	.	(0.012)	(0.004)	.	.	(0.018)	(0.002)	(0.032)	(0.001)	(0.029)
CTIF FFA 1	0.0109	.	.	.	.	0.0125	.	.	.	.	.
CTIF NR 8S	.	.	.	.	.	.	.	.	.	.	.
CTIF F017	.	.	.	.	.	.	.	.	.	.	.
CTIF FAL 1	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 3L	.	.	.	.	.	.	.	.	.	.	.
CTIF NH1	.	.	.	.	.	.	.	.	.	.	.
CTIF NH8	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 3S	.	.	.	.	.	.	.	.	.	.	.
CTIF FT1	.	.	.	.	.	.	.	.	.	.	.

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
CTIF NR 8L	.	.	.	.	.	.	.	.	.	.	.
CTIF NH4	.	.	.	.	.	.	.	.	.	.	.
CTIF F04	.	.	.	.	.	.	.	.	.	.	.
CTIF FCR2	.	.	.	.	.	.	.	.	.	.	.
CTIF FL5	.	(0.002)	.	(0.0005)	.	.	.	.	.	.	.
CTIF FCR Ni3	.	.	.	.	.	.	.	.	.	.	.
CTIF NH6	.	.	.	.	.	.	.	.	.	.	.
CTIF F09	.	.	.	.	.	.	.	.	.	.	.
CTIF FL4	(0.05)	.	.	(0.003)	.	0.007	.	.	.	.	.
CTIF NR 1S	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 1L	.	.	.	.	.	.	.	.	.	.	.
CTIF NH2	.	.	.	.	.	.	.	.	.	.	.
CTIF NR Cu2	.	.	.	.	.	(0.0079)	.	.	.	.	.
CTIF NR 4S	.	.	.	.	.	.	.	.	.	.	.
CTIF FCR4	.	.	.	.	.	.	.	.	.	.	.
CTIF FCR1	.	.	.	.	.	.	.	.	.	.	.
CTIF F07	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 4L	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 2S	.	.	.	.	.	.	.	.	.	.	.
CTIF NH5	.	.	.	.	.	.	.	.	.	.	.
CTIF FL3	.	.	.	.	.	0.008	.	.	.	.	.
CTIF NR 4G	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 2G	.	.	.	.	.	.	0.27	.	.	.	.
CTIF FL2	.	.	.	(0.0135)	.	.	.	.	.	.	.
CTIF FL1	.	.	.	.	.	.	.	.	.	.	.
CTIF FCR Ni2	.	.	.	.	.	.	.	.	.	.	.
CTIF NR Cu3	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 6S	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 5L	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 6L	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 5S	.	.	.	.	.	.	.	.	.	.	.
CTIF FCR6	.	.	.	.	.	.	.	.	.	.	.
CTIF FCR Nil	.	.	.	.	.	.	.	.	.	.	.

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
--------	----	---	----	----	----	---	----	----	----	----	----

**CARBON STEEL**

# = Class, where 1 = CRM and 2 = RM

\* Provisional Analysis

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
1 VS UG128	0.816	0.405	0.014	0.0139	0.324	0.0235	0.032	0.038	0.0078	.	.	0.0088	0.0046	.
1 <b>BS 54J</b>	0.78	0.77	0.0090	0.0108	0.552	0.080	0.037	0.177	0.0021	0.0042	0.0138	0.0060	0.0014	0.0024
1 VS UG129	0.728	.	.	0.013	.	.	.	.	0.0014	.	.	.	.	.
1 NM 309	0.57	0.80	0.037	0.046	0.20	.	0.034	0.081	.	.	.	.	.	.
1 IARM Fe1050-18	0.499	0.79	0.0045	0.027	0.223	0.179	0.068	0.100	(0.003)	0.0056	0.018	0.0097	0.0270	.
1 NM 306A	0.46	0.71	0.085	0.043	0.28	.	0.023	0.13	.	.	.	.	.	.
1 <b>BS 1040</b>	0.402	0.79	0.010	0.032	0.229	0.241	0.067	0.123	(0.0019)	0.0069	0.021	0.0111	0.030	(0.0017)
1 IARM Fe1020-18	0.226	0.56	0.0100	0.0031	0.207	0.030	0.026	0.853	.	.	.	0.0070	.	.
1 <b>BS 1030A</b>	0.34	0.763	0.0059	0.016	0.28	0.189	0.141	0.112	0.0021	0.0061	0.029	0.0082	0.0261	(0.0011)
1 SS 452/1	0.323	1.30	0.035	0.017	0.055	0.22	0.19	0.067	.	.	0.054	.	.	0.054
1 VS UG121	(0.3)	0.55	0.014	0.027	0.244	0.180	0.078	0.126	0.023	.	.	0.0068	0.0018	.
1 <b>BS 1026A</b>	0.270	0.76	0.0064	0.021	0.180	0.094	0.081	0.123	0.0091	(0.005)	0.053	0.0100	0.0257	0.0009
1 IARM Fe1020-18	0.226	0.547	0.006	0.024	0.235	0.198	0.078	0.125	(0.003)	0.0065	0.0252	0.0098	0.036	.
1 IMZ 112A	0.212	0.471	0.0055	0.0188	0.257	0.068	0.055	0.099	0.017	0.080	0.054	0.0058	0.043	0.072
2 BS 57F	0.196	0.554	0.009	0.027	0.202	0.197	0.070	0.120	(0.002)	0.007	0.018	0.0077	0.063	.
2 BS 2971	0.187	1.01	0.015	0.024	0.237	0.065	0.111	0.152	0.022	.	0.040	0.0084	(0.002)	.
1 VS UG132	0.180	0.466	0.0075	0.0030	0.201	0.039	0.024	0.035	.	.	.	0.0054	.	.
1 12X 10180D	0.179	0.807	0.014	0.025	0.286	0.066	0.053	0.0251	(0.003)	0.007	0.0026	0.007	.	.
1 IMZ 71A	0.126	0.493	0.0126	0.0075	0.494	0.90	0.036	0.505	0.019	0.025	0.018	0.0065	0.055	0.023
1 NM 308	0.11	0.47	0.013	0.008	0.067	.	0.009	0.032	.	.	.	.	.	.
1 VS UG122	(0.1)	0.433	(0.02)	(0.02)	0.396	0.288	0.378	0.72	.	.	.	0.0038	0.0040	.
1 VS UG120	0.096	0.685	0.027	(0.02)	0.96	0.447	0.634	0.75	0.011	.	.	(0.008)	0.0078	.
1 DSZU C041a	0.085	1.35	0.021	0.0092	0.59	0.046	0.032	0.035	0.029	0.010	0.0038	(0.008)	0.0033	(0.003)
1 IARM Fe1215-18	0.043	0.96	0.059	0.29	(0.006)	0.164	0.055	0.051	.	0.0055	0.016	0.0109	0.0020	.
1 <b>BS XCAS</b>	0.024	0.471	0.008	0.0064	0.339	0.020	0.031	0.035	(0.027)	0.0086	0.0069	0.0055	0.020	(0.006)
1 <b>BS XCAS-2</b>	0.021	0.58	0.0055	0.0059	0.40	0.047	0.099	0.039	0.073	0.016	0.013	0.0139	0.018	0.020
1 DSZU C040A	0.013	0.012	0.0023	0.0029	0.060	0.007	0.005	0.007	0.039	(0.002)	(0.001)	0.0068	(0.001)	(0.002)

Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Alloy	Units	Others
VS UG128	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~20 mm	.
<b>BS 54J</b>	0.0025	<0.0005	97.6	(0.002)	(0.0011)	(0.0006)	(0.005)	0.0020	1080	38 mm Ø x ~7 or 19+ mm	<b>17025</b>
VS UG129	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~20 mm	.
NM 309	.	.	.	.	.	.	.	.	1060 + P	40 mm Ø x 20 mm	.
IARM Fe1050-18	(0.0030)	(0.0005)	98.0	(0.0013)	0.0026	0.0015	0.0103	0.0008	1050	31 mm Ø x 2 or 18 mm	.
NM 306A	.	.	.	.	.	.	.	.	1045 + P	40 mm Ø x 20 mm	.
<b>BS 1040</b>	(0.006)	0.0003	98.0	(0.0012)	0.0023	0.0022	0.009	0.0018	1040	28 mm Ø x ~7 or 19+ mm	<b>17025</b> Ca:0.0011 H:0.0002
VS UG131	.	.	.	.	.	.	.	.	.	~39 mm Ø x ~25 mm	.
<b>BS 1030A</b>	(0.005)	(0.0003)	98.0	(0.0007)	0.0047	0.0014	(0.015)	0.0014	1030	38 mm Ø x ~7 or 19+ mm	<b>17025</b> Zn:0.0033
SS 452/1	0.015	.	.	.	.	.	0.094	0.031	.	38 mm Ø x 19 mm	.
VS UG121	.	.	.	.	.	.	.	.	.	~45 mm Ø x ~25 mm	.
<b>BS 1026A</b>	(0.005)	(0.0003)	98.3	0.0008	0.0042	0.0013	0.0068	(0.0006)	1026	38 mm Ø x ~7 or 19+ mm	<b>17025</b> Ca:0.0025
IARM Fe1020-18	0.0044	.	98.5	(0.0012)	(0.007)	0.0018	0.0080	.	1020	31 mm Ø x 2 or 18 mm	.
IMZ 112A	0.023	0.0010	.	0.0123	Pb:0.008	0.021	0.162	0.0138	1023	38 mm Ø x 20 mm	Zn: 0.0020
BS 57F	(0.006)	.	Ca:(0.0003)	.	(0.006)	.	0.008	.	1020	44 mm Ø x 17 or 19+ mm	.
BS 2971	0.003	.	.	.	.	.	(0.005)	.	LF-2	44 mm Ø x ~7 or 19+ mm	.
VS UG132	.	.	.	.	.	.	.	.	.	~39 mm Ø x ~25 mm	.
12X 10180D	0.0068	.	.	.	.	.	0.0033	.	1018	~40 mm Ø x ~15 mm	.
IMZ 71A	0.016	0.0009	.	0.0100	.	0.013	0.015	0.0041	1010 - 1013	35 mm Ø x 20 mm	Zr: 0.0065
NM 308	.	.	.	.	.	.	.	.	1010	40 mm Ø x 20 mm	.
VS UG122	.	.	.	.	.	.	.	.	.	~45 mm Ø x ~25 mm	.
VS UG120	.	.	.	.	.	.	.	.	.	~45 mm Ø x ~25 mm	.
DSZU C041a	(0.004)	(0.0005)	.	(0.002)	.	.	(0.004)	0.0049	.	40 mm Ø x 25 mm	.
IARM Fe1215-18	0.0043	.	.	0.0012	.	0.0018	0.0083	0.0007	1215	~38 mm Ø x ~3 or ~19 mm	.
<b>BS XCAS</b>	0.0016	(0.0002)	99.0	(0.0015)	0.008	0.0006	0.0017	0.0010	1008	38 mm Ø x 30 mm	<b>17025</b>
<b>BS XCAS-2</b>	(0.004)	0.021	98.6	(0.003)	0.0066	(0.0016)	(0.0015)	0.011	1009 + Al	~37 mm D x ~30 mm	<b>17025</b> Ca: 0.0032
DSZU C040A	(0.0002)	0.00032	.	(0.0003)	Ca:0.0021	.	(0.0002)	0.0010	1005	40 mm Ø x 25 mm	.

**RESULFURIZED STEEL**

# = Class, where 1 = CRM and 2 = RM

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
1 IARM 307B	0.162	1.45	(0.012)	0.094	(0.30)	0.191	0.195	0.105	0.034	0.0101	0.045	(0.011)	(0.003)	.
2 CZ CM-22A	0.154	1.443	0.086	0.084	0.248	0.419	3.10	0.167	(0.004)	0.130	0.132	0.0065	0.653	0.59

  

Number	As	Nb	Sn	Ti	Alloy	Units
IARM 307B	.	(0.0013)	0.010	(0.003)	1118	31 mm Ø x 2 or 18 mm
CZ CM-22A	0.057	0.019	0.069	0.0038	.	~39 mm Ø x ~25 mm

## LOW ALLOY AND TOOL STEEL, CHART 1 of 2

# = Class, 1 = CRM and 2 = RM

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
1 IARM Fe15V-18	3.51	0.39	0.022	0.010	0.89	0.084	0.123	5.5	.	0.018	1.24	.	15.6	0.080
2 BS 37D	1.54	0.28	0.021	0.015	0.29	0.063	0.21	11.07	.	0.07	1.09	0.016	0.80	0.16
1 IARM FeM4-18	1.42	0.298	0.013	0.062	0.60	0.104	0.127	4.16	.	0.080	5.07	0.042	3.97	5.55
1 IARM FeM62-18	1.32	0.27	0.016	0.015	0.37	0.115	0.129	3.86	(0.006)	0.105	10.2	0.045	2.02	6.31
1 BS E52100	0.99	0.371	0.011	0.004	0.270	0.090	0.066	1.54	0.019	0.0067	0.0209	0.0057	0.0046	(0.0015)
2 BS 36C	0.96	0.46	0.023	0.027	0.31	0.18	0.19	5.01	.	0.03	0.99	.	0.11	(0.04)
2 BS TM1	0.86	0.23	0.007	0.012	0.46	0.054	0.057	3.72	.	0.45	8.4	.	1.05	1.7
1 IARM FeM2-18	0.853	0.337	0.025	(0.0010)	0.26	0.098	0.182	4.23	(0.014)	0.28	4.92	0.0148	1.90	5.81
1 IARM FeM1-18	0.85	0.318	0.013	(0.0003)	0.44	0.091	0.104	3.67	0.007	0.226	8.0	0.037	1.19	1.98
1 IARM FeL6-18	0.718	0.605	0.013	0.0017	0.264	0.027	1.34	0.71	0.020	0.007	0.237	0.0064	0.008	.
1 BS 33F	0.569	0.295	0.0134	0.0009	0.76	0.039	0.211	1.31	0.019	0.017	0.202	0.0124	0.25	2.28
2 BS TS7	0.529	0.70	0.015	0.010	0.27	0.05	0.10	3.18	.	0.043	1.34	.	0.35	0.19
1 BS TS-7A	0.527	0.74	0.013	0.016	0.84	0.127	(0.031)	3.35	0.061	(0.005)	1.52	0.0124	0.265	(0.0014)
1 IARM FeS7-18	0.51	0.271	0.021	0.0032	0.47	0.128	0.170	3.28	(0.015)	0.0106	1.39	0.0102	0.233	(0.016)
1 BS D-6A	0.47	0.78	0.0076	0.0010	0.232	0.136	0.60	0.99	0.038	0.013	1.00	0.0031	0.123	0.0019
1 12X 41400B	0.452	0.764	0.0095	0.041	0.32	0.161	0.156	0.999	0.0137	.	0.177	0.0124	.	.
1 BS 4140C	0.43	0.922	0.010	0.026	0.29	0.260	0.131	0.94	0.0215	0.0078	0.169	0.0064	0.0026	(0.003)
2 PV 1017I	0.424	0.798	0.014	0.027	0.177	0.108	0.091	1.013	.	.	0.099	.	.	.
2 BS TH11	0.423	0.31	0.016	0.005	0.88	0.041	0.11	5.04	.	(0.008)	1.27	.	0.46	(0.01)
1 BS 300A **	0.416	0.716	0.0049	0.0008	1.71	0.118	1.87	0.798	0.098	0.0087	0.38	0.0023	0.070	<0.01
1 IARM Fe4140-19	0.401	(0.9)	0.008	0.022	0.22	0.23	0.14	1.1	0.031	0.009	0.17	0.0110	0.0030	(0.003)
1 IARM 170B	0.400	0.821	(0.005)	(0.004)	0.21	(0.005)	0.197	0.009	0.230	(0.005)	(0.003)	.	(0.002)	.
2 BS 34D	0.395	0.38	0.017	0.005	1.06	0.049	0.10	5.15	.	0.031	1.24	.	0.94	0.10
1 BS 8740	0.39	0.86	0.011	0.023	0.25	0.16	0.55	0.49	0.037	0.0086	0.27	0.0073	0.0024	0.0023
2 BS 68C	0.38	0.60	0.018	0.008	0.305	0.178	0.166	1.77	1.06	0.011	0.36	0.0045	0.007	.
1 IARM Fe5140H-18	0.37	0.93	0.014	0.022	0.187	0.253	0.266	0.67	0.13	0.0081	0.031	0.007	(0.0024)	(0.003)
2 BS TH12	0.372	0.40	0.020	0.005	0.92	0.064	0.16	5.02	.	0.07	1.41	.	0.62	1.06
1 BS 4130A	0.318	0.56	0.016	0.0183	0.270	0.249	0.152	0.97	0.025	0.0068	0.206	0.0060	0.0029	0.0025
1 BS 4330MOD	0.316	0.92	0.0052	0.0010	0.269	0.105	1.83	0.848	0.031	0.034	0.478	0.0031	0.083	(0.001)
1 IARM 378A	0.274	1.38	0.018	0.037	0.307	0.299	0.142	0.187	(0.0029)	0.013	0.031	(0.02)	0.0844	(0.006)
2 BS 9325	0.25	0.91	0.008	0.007	0.32	0.13	3.29	1.48	0.030	0.010	0.31	0.0089	0.004	.
1 IARM 169B	0.232	0.75	(0.004)	(0.004)	(0.32)	(0.005)	(0.010)	0.010	0.36	(0.003)	(0.004)	.	(0.002)	(0.003)
1 BS 8822A	0.212	0.852	0.020	0.031	0.287	0.030	0.569	0.562	(0.010)	0.0042	0.378	0.0086	0.0028	<0.005
1 IARM Fe8620-18	0.211	0.857	0.012	0.026	0.23	0.197	0.446	0.536	0.0246	0.0085	0.197	0.007	0.0061	(0.004)
1 BS 4820B	0.199	0.67	0.0081	0.0113	0.269	0.221	3.32	0.116	0.038	0.012	0.251	0.0075	0.0016	(0.003)
2 BS 1931	0.194	0.84	0.007	0.018	0.235	0.116	0.42	0.50	0.021	0.012	0.268	0.0079	0.002	.
1 IARM Fe4820-18	0.192	0.541	(0.011)	0.0018	0.26	0.167	3.51	0.144	0.022	0.0107	0.287	0.007	0.0015	(0.004)
2 BS 61C	0.187	0.76	0.014	0.026	0.21	0.030	0.55	0.505	0.033	0.012	0.169	0.0050	<0.002	.
2 PV 102/1	0.186	1.226	0.024	0.018	0.184	0.109	0.140	0.092	.	.	0.030	.	.	.
2 BS 8620A	0.184	0.80	0.008	0.079	0.21	0.15	0.44	0.48	0.016	0.010	0.16	0.0107	0.004	.
1 BS 1982	0.128	0.441	0.012	0.026	0.255	0.177	0.197	2.09	0.021	0.010	0.89	0.0097	0.003	.
2 BS 58D	0.127	0.45	0.010	0.005	0.32	0.156	3.02	1.35	0.042	0.009	0.14	0.0147	0.005	.
1 IARM FeE9310-18	0.121	0.62	0.009	0.0128	0.256	0.158	3.07	1.09	0.036	0.009	0.086	0.0070	0.0030	.
1 IARM FeDP1080-18	0.110	1.88	0.014	(0.006)	0.11	0.042	0.554	0.554	(0.002)	0.069	0.445	(0.009)	(0.0043)	(0.030)
1 BS 3310	0.104	0.54	0.0092	0.0144	0.257	0.199	3.49	1.55	0.035	0.0096	(0.052)	0.0075	0.0029	(0.003)
2 HRT FE2003-H	0.104	0.46	0.013	0.002	0.43	0.05	0.26	8.66	(0.004)	0.013	0.93	.	0.217	.
1 IARM FeF9-18	0.104	0.459	(0.011)	0.0036	0.345	0.093	0.148	8.72	.	0.013	0.94	0.0323	0.214	0.0030
1 IARM Fe91-18	0.099	0.453	0.015	(0.002)	0.27	0.041	0.187	8.24	(0.006)	0.013	0.94	0.046	0.198	(0.003)
1 IARM FeP92-18	0.092	0.737	(0.005)	(0.005)	0.20	0.074	0.82	9.4	(0.005)	0.036	0.52	(0.0036)	0.188	1.97
1 IARM FeT23-18	0.068	0.82	0.012	0.006	0.18	0.046	0.53	2.47	.	0.085	0.261	(0.003)	0.238	1.60

  

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Alloy	Units	Others			
IARM Fe15V-18	.	.	.	.	.	.	0.0054	0.0027	CPM15V	38 mm Ø x 2 or 19 mm				
BS 37D	.	.	.	.	0.0031	.	0.004	.	D-2	37 mm Ø x ~7 or 19+ mm				
IARM FeM4-18	0.0058	.	79.0	.	.	.	0.0050	.	M-4	~38 mm Ø x ~3 or ~19 mm				
IARM FeM62-18	(0.003)	.	.	(0.017)	(0.003)	.	.	.	M-62	31 mm Ø x 2 or 18 mm				
BS E52100	0.0033	Ca:0.0006	96.6	(0.0010)	0.0009	0.0011	0.0049	(0.0010)	E52100	38 mm Ø x ~7 or 19+ mm				17025
BS 36C	.	.	.	.	.	.	.	.	A-2	38 mm Ø x ~7 or 19+ mm				
BS TM1	.	.	.	.	.	.	.	.	M-1	41 mm Ø x ~7 or 19+ mm				
IARM FeM2-18	(0.008)	.	81.4	(0.021)	(0.0016)	.	(0.007)	(0.0016)	M-2	31 mm Ø x 2 or 18 mm				
IARM FeM1-18	.	.	.	.	.	.	0.0041	0.0044	M-1	~38 mm Ø x ~3 or ~19 mm				Zr: 0.0013
BS 33F	(0.003)	(0.0007)	94.0	(0.002)	0.0024	(0.01)	(0.004)	(0.002)	S-1 MOD	38 mm Ø x ~7 to 19+ mm				17025
IARM FeL6-18	0.0033	(0.0008)	.	(0.003)	0.0012	.	.	0.0033	L-6	38 mm Ø x 2 or 19 mm				
BS TS-7	.	.	.	.	.	.	.	.	S-7	38 mm Ø x ~7 or 19+ mm				
BS TS-7A	(0.005)	0.0021	92.3	<0.01	(0.005)	<0.01	(0.004)	(0.003)	S-7	36 mm Ø x 25 mm				17025
IARM FeS7-18	(0.005)	.	(93.6)	(0.005)	0.0023	(0.0016)	(0.006)	0.0014	S-7	31 mm Ø x 2 or 18 mm				Ca: 0.0004
BS D-6A	0.0101	0.0004	95.6	<0.01	0.0009	0.0014	(0.009)	0.0024	D-6	38 mm Ø x 19 mm				17025
														Ca: 0.0011 last
12X 41400B	0.015	.	.	.	.	.	0.0099	.	4140	~38 mm Ø x ~20 mm				Zn: 0.0012
BS 4140C	0.0052	(0.0007)	96.8	0.0019	0.0011	0.0021	0.0095	0.0009	4140	38 mm Ø x ~7 or 19+ mm				Ca: 0.0010 17025
PV 1017I	.	.	.	.	.	.	.	.	42CrMo4	40 mm Ø x 25 mm				
BS TH11	.	.	.	.	.	.	.	.	H-11	48 mm Ø x ~7 or 19+ mm				
BS 300A **	0.0029	(0.00032)	93.8	(0.002)	<0.01	0.0011	0.0065	0.0095	300M	38 mm Ø x ~7 or 19+ mm				17025
IARM Fe4140-19	(0.005)	.	.	(0.002)	.	(0.004)	0.010	0.0009	4140	31 mm Ø x 2 or 18 mm				
IARM 170B	.	(0.0004)	.	(0.004)	.	.	(0.002)	(0.19)	CLA7	31 mm Ø x 2 or 18 mm				
BS 34D	.	.	.	.	.	.	.	.	H-13	41 mm Ø x ~7 or 19+ mm				
BS 8740	0.0051	0.0003	96.91	(0.0007)	(0.001)	0.0017	0.008	0.0012	8740	48 mm Ø x ~7 or 19+ mm				17025
BS 68C	(0.004)	.	.	.	.	.	0.008	.	P-20 + Al	37 mm Ø x ~7 or 19+ mm				
IARM Fe5140H-18	(0.011)	.	.	(0.002)	.	.	0.0089	0.0015	5140H	31 mm Ø x 2 or 18 mm				
BS TH12	.	.	.	.	.	.	.	.	H-12	38 mm Ø x ~7 or 19+ mm				
BS 4130A	(0.005)	0.0002	97.2	0.0014	0.0017	0.0018	0.0093	0.0009	4130	38 mm Ø x ~7 or 19+ mm				Ca:0.0010 17025
BS 4330MOD	0.0038	(0.0009)	95.1	0.007	(0.001)	(0.0007)	0.0062	0.0027	4330MOD	44 mm Ø x ~7 or 19+ mm				Zr:0.0016 17025
IARM 378A	.	(0.0006)	.	(0.003)	.	.	0.0236	(0.003)	A615-75	31 mm Ø x 2 or 18 mm				
BS 9325	0.004	Ca:0.0049	.	.	0.0010	.	0.009	.	9325	38 mm Ø x ~7 mm last				
IARM 169B	.	0.0003	.	(0.004)	.	.	(0.002)	0.23	CLA6	31 mm Ø x 2 or 18 mm				
BS 8822A	0.0027	0.0004	96.9	0.0024	0.0068	(0.0016)	(0.003)	0.0015	8822	37 mm Ø x 25 mm				Pb:0.0005 Ta:0.007 17025
IARM Fe8620-18	0.009	.	.	.	.	.	0.0072	0.0015	8620	31 mm Ø x 2 or 18 mm				
BS 4820B	0.0055	Ca:0.0004	94.8	0.0022	(0.0015)	0.0028	0.0098	0.0013	4820	38 mm Ø x ~7 to 19+ mm				17025
BS 1931	0.007	.	.	.	(0									

## LOW ALLOY AND TOOL STEEL, CHART 2 of 2

# = Class, where 1 = CRM and 2 = RM

\* Provisional Analysis

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
2 HRT FE2019-H	1.54	0.39	0.025	(0.003)	0.51	0.08	0.14	11.89	0.015	.	0.86	.	0.80	.
2 CZ LA-4D	1.143	1.266	0.028	0.0091	0.181	0.066	0.367	1.83	0.067	0.037	0.136	0.0064	0.103	0.025
1 ECRM 268-1D	1.134	0.293	0.0209	0.0154	0.373	0.123	0.143	4.57	.	0.0290	3.20	2.03	8.47	3.70
1 VS UG127	0.962	0.93	0.020	0.029	0.427	0.145	0.151	0.188	0.0051	.	.	0.0155	0.141	.
1 VS UG126	0.856	0.78	0.0128	0.0077	0.348	0.030	0.029	0.591	0.0015	.	.	0.0123	0.075	.
1 VS UG130	0.80	0.228	0.0078	0.0071	0.226	0.252	0.104	0.258	.	.	.	.	.	.
2 CZ CM-1D	0.735	1.80	0.0218	0.026	0.341	0.186	0.547	0.456	0.024	0.029	0.100	0.0124	0.089	0.063
1 12X LA5D	0.681	0.855	0.040	0.016	0.53	0.107	0.409	0.291	0.177	0.151	0.206	.	0.603	(0.004)
1 12X LA4C	0.657	0.374	0.050	0.0258	0.482	0.265	0.485	0.526	0.183	0.099	0.405	0.0116	0.372	0.091
1 NCS HS13752	0.51	0.99	0.027	0.011	0.21	.	.	0.67	.	.	0.27	.	0.09	.
1 DSZU C051	0.443	0.795	0.0162	0.029	0.293	0.140	0.041	0.048	(0.010)	(0.003)	.	.	(0.002)	.
1 IMZ 54/1	0.43	0.14	(0.009)	0.010	0.17	(0.034)	4.01	0.12	.	.	(0.007)	.	0.19	.
2 CZ LA-5C	0.439	1.87	0.017	0.0088	0.394	0.138	2.59	3.815	0.081	0.088	0.86	0.024	0.536	0.631
1 12X 15260X	0.404	1.67	0.034	0.086	0.390	0.119	0.499	2.48	0.57	0.085	0.093	.	0.417	.
1 SS 214/2	0.39	1.61	0.032	0.043	0.18	0.21	0.15	0.09	.	.	0.26	.	.	.
1 DSZU C045a	0.374	0.382	0.012	0.0032	0.267	0.191	0.147	1.45	0.86	0.010	0.184	0.0063	0.004	(0.005)
2 HRT FE2021-N	0.33	0.31	0.0178	0.0014	0.28	0.070	0.193	2.81	0.014	0.011	2.7	0.007	0.52	0.027
1 BS 1763 *	0.27	1.50	0.017	0.025	0.68	0.18	0.53	0.56	0.052	0.12	0.55	<0.05	0.29	0.023
1 BS 9325B	0.254	0.504	0.032	0.0067	0.38	0.166	3.13	1.22	0.027	0.0073	0.203	0.0112	0.0080	0.0036
2 CZ CM-8B	0.185	1.95	0.015	0.014	0.112	0.081	0.032	1.22	0.0028	0.007	0.011	0.0075	0.0078	(0.009)
1 IRSID 1658	0.180	0.618	0.014	0.032	0.160	0.345	0.241	0.147	0.029	.	0.046	.	(0.002)	.
2 HRT FE2019-N	0.17	1.27	0.015	(0.001)	0.30	0.03	0.33	0.75	0.068	(0.003)	0.40	0.0040	(0.003)	.
1 VS RG31	0.169	0.291	0.0048	0.006	0.39	0.46	2.08	1.31	.	.	0.306	.	0.207	0.39
1 DSZU C042a	0.132	0.488	0.0091	0.0062	0.286	0.137	0.195	0.995	0.018	0.009	0.31	(0.01)	0.189	(0.006)
1 12X 12746V	0.048	1.19	0.034	0.064	0.156	0.646	0.226	0.374	0.459	0.142	0.658	0.0208	0.105	.
1 VS UG102	0.045	1.78	0.0082	.	0.222	0.172	0.277	0.0143	0.036	.	0.209	.	.	.

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Units	Others				
HRT FE2019-H	.	.	.	0.071	.	.	.	0.012	40 mm Ø x 20 mm					
CZ LA-4D	0.010	.	.	0.0046	.	.	0.014	0.0154	~39 mm Ø x ~25 mm	Pb:0.040				
ECRM 268-1D	0.0062	0.0009	.	.	.	0.0017	0.0078	.	38 mm Ø x 25 mm					
VS UG127	.	.	.	.	.	.	.	0.0094	~38 mm Ø x ~20 mm	Bi:0.011	Pb:0.0049			
VS UG126	.	.	.	.	.	.	.	.	~38 mm Ø x ~20 mm	Bi:0.0055	Pb:0.009			
VS UG130	0.0093	.	.	.	.	.	.	.	~39 mm Ø x ~25 mm					
CZ CM-1D	.	0.0017	.	0.050	.	0.0112	0.0144	0.054	~39 mm Ø x ~25 mm					
12X LA5D	0.0101	.	.	0.0039	.	.	0.0142	0.080	~40 mm Ø x ~15 mm	Zr:0.0013				
12X LA4C	0.018	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm	Zn:0.006				
NCS HS13752	.	.	.	.	.	.	.	0.006	38 mm Ø x 38 mm					
DSZU C051	(0.002)	.	.	(0.001)	.	.	(0.004)	(0.001)	40 mm Ø x 25 mm					
IMZ 54/1	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm					
CZ LA-5C	0.026	.	.	0.057	Pb:0.015	0.018	0.031	0.048	~37 mm Ø x 25 mm					
12X 15260X	0.044	.	.	0.183	.	Pb:0.0012	0.0021	0.0064	~40 mm Ø x ~15 mm	Zr:0.0054				
SS 214/2	.	.	.	.	.	.	.	.	42 mm Ø x 19 mm					
DSZU C045a	0.010	(0.0004)	.	0.003	.	.	0.012	0.004	40 mm Ø x 25 mm	Ca:(0.002)				
HRT FE2021-N	0.004	0.0006	Ce:0.0011	0.007	.	0.001	0.004	0.001	36 mm Ø x 20 mm	Zn:0.002	Zr:0.0012			
BS 1763 *	0.072	0.003	[94.6]	0.14	<0.05	<0.05	0.015	0.31	37 mm Ø x 19 or 20 mm	Zr:0.027				
BS 9325B	0.0033	(0.0003)	94.0	(0.002)	0.011	<0.05	(0.002)	0.0010	38 mm Ø x 30 mm	17025	Pb:0.0019	Ta:0.0020		
CZ CM-8B	0.0035	0.0023	.	(0.002)	.	(0.004)	0.0126	0.0008	~39 mm Ø x 25 mm					
IRSID 1658	0.034	.	.	.	.	.	0.022	(0.002)	40 mm Ø x 30 mm					
HRT FE2019-N	.	0.0016	.	0.029	.	.	.	0.004	40 mm x 40 mm x 20 mm			Ca:0.0014		
VS RG31	.	.	.	.	.	.	.	0.21	~45 mm Ø x ~28 mm					
DSZU C042a	0.0069	(0.0005)	.	0.0025	.	.	0.0079	0.0029	40 mm Ø x 25 mm					
12X 12746V	0.051	.	.	.	.	.	0.264	0.088	~40 mm Ø x ~15mm					
VS UG102	.	.	.	0.071	.	.	.	.	~45 mm Ø x ~25 mm	Ca:0.0018				

## SILICON STEEL

# = Class, where 1 = CRM and 2 = RM

Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	N	V	W
2 CZ CM-12C	3.7	0.038	0.275	0.0103	0.0110	0.175	0.046	0.081	0.145	0.0044	0.012	0.0056	0.027	(0.004)
1 ECRM 191-3C	3.226	0.0027	0.153	0.0097	0.0005	0.0097	0.0124	0.0242	0.81	.	0.00127	0.00105	0.00043	.
1 DSZU C047A	1.94	0.789	0.411	0.022	0.0107	0.150	0.311	4.76	0.054	0.105	0.76	0.022	1.21	2.37
2 CZ CM-20A	1.74	0.63	0.594	0.0383	0.020	0.237	1.007	0.97	0.076	0.124	0.365	0.0086	0.225	0.104
1 SS 405/1	1.71	0.032	1.28	0.018	0.069	0.013	0.22	0.15	.	.	(0.002)	.	0.28	.
1 SS 409/1	1.46	0.082	0.44	0.025	0.021	0.048	3.06	0.94	.	0.014	0.65	.	0.09	.
1 IMZ 52/1	1.38	0.41	0.25	0.012	(0.009)	0.094	2.35	0.12	.	.	(0.041)	.	.	.
2 CZ LA-3G	1.29	0.626	0.68	0.047	0.035	0.236	1.01	1.377	0.047	0.127	0.326	0.011	0.232	0.105

Number	As	B	Nb	Pb	Sb	Sn	Ti	Zr	Units	Others
CZ CM-12C	0.0030	0.0033	0.0066	.	.	(0.005)	0.0128	.	~39 mm Ø x ~25 mm	Ca:0.0010
ECRM 191-3C	0.0014	0.00024	.	.	.	0.0013	0.0020	.	~30 mm Ø x ~39 mm	Mg:0.0036
DSZU C047A	(0.0095)	0.0006	0.020	.	.	0.0104	0.0096	.	40 mm Ø x 25 mm	Ca:0.0022
CZ CM-20A	0.073	0.0071	0.074	0.015	0.025	0.033	0.175	0.083	~37 mm Ø x ~25 mm	Zn:0.007
SS 405/1	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm	
SS 409/1	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm	
IMZ 52/1	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm	
CZ LA-3G	0.051	0.0039	0.071	0.0098	0.024	0.031	0.143	0.068	~39 mm Ø x ~25 mm	Ca:0.0016

## LOW NICKEL STAINLESS STEEL

# = Class, where 1 = CRM and 2 = RM

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
2 BS 93E	1.02	0.52	0.022	0.0010	0.90	0.12	0.35	17.33	0.009	0.048	0.50	0.0359	0.24	0.11
2 BS 98	0.309	0.48	0.019	0.0014	0.72	0.098	0.21	13.35	0.003	0.020	0.034	0.0181	0.075	0.009
2 DSZU C116	0.296	0.464	0.0214	0.0118	0.295	0.082	0.209	12.71	(0.006)	0.021	0.029	0.022	0.029	(0.01)
2 BS 97	0.216	0.71	0.021	0.0004	0.39	0.066	0.76	11.82	0.018	0.041	1.05	0.030	0.21	0.95
1 BS 183B	0.181	0.344	0.018	0.0042	0.41	0.074	1.96	12.45	0.0009	0.032	0.33	0.044	0.165	3.5
1 13X 12548N	0.175	0.510	0.023	0.189	0.193	0.264	1.10	12.70	(0.02)	0.388	1.42	0.102	0.025	0.038
1 BS 183C	0.173	0.368	0.015	0.0040	0.427	0.060	1.87	12.72	0.0020	0.027	0.189	0.039	0.109	2.83
1 BS 431A	0.159	0.53	0.019	0.0036	0.31	0.111	2.21	15.78	(0.0012)	0.041	0.172	0.058	0.079	0.021
2 DSZU C115	0.145	0.341	0.0278	0.0026	0.389	0.122	1.66	11.73	0.011	0.028	0.368	0.039	0.250	1.98
2 DSZU C119	0.128	0.229	0.027	0.0068	0.51	0.069	0.244	25.38	0.017	(0.01)	0.084	0.010	0.052	0.046
2 DSZU C117	0.071	0.200	0.0240	0.0122	0.393	0.091	0.52	16.89	0.012	0.019	0.044	0.008	0.027	(0.04)
2 BS 91E	0.066	0.42	0.017	0.002	0.52	0.05	0.17	16.58	(0.002)	0.02	0.035	0.032	0.09	0.01
1 IARM Fe174PH-18	0.041	0.47	0.024	(<0.0040)	0.52	3.33	4.73	15.10	0.007	0.047	0.315	0.0436	0.051	0.015
1 13X 41500A	0.038	0.596	0.021	0.0101	0.402	0.129	3.52	13.00		0.099	0.504	0.0504	0.091	.
1 13X 41008B	0.034	0.684	0.013	0.0070	0.761	0.267	0.338	12.36	0.028	0.053	0.042	0.0088	0.061	.
1 13X 40800A	0.032	0.804	0.034	0.030	0.80	0.299	0.58	12.32	0.042	0.033	0.268	0.0054	0.034	0.005
2 DSZU C118	0.018	1.23	0.0057	0.0098	0.142	0.344	3.45	19.69	(0.004)	0.093	0.337	0.028	0.109	0.32
1 IARM Fe155PH-18	0.015	0.616	0.021	(0.0004)	0.430	3.35	4.79	15.13	0.014	0.024	0.129	0.0494	0.055	0.019
1 IARM Fe409-20	0.010	0.387	0.021	(0.0007)	0.52	0.0655	0.110	11.28	0.017	0.019	0.011	0.010	0.075	0.0036

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Alloy	Units				
BS 93E	.	.	.	0.005	0.0040	.	0.003	0.007	440C	41 mm Ø x	-7 or -17 mm	last of stock		
BS 98	(0.003)	(0.0002)	.	0.003	0.0038	.	0.006	0.002	420	38 mm Ø x	-7 mm	last of stock		
DSZU C116	.	.	.	(0.01)	.	.	(0.005)	(0.002)		40 mm Ø x	20 mm			
BS 97	.	.	.	0.007	.	.	(0.003)	(0.002)	422	35 mm Ø x	-7 or 19+ mm			
BS 183B	(0.005)	(0.0007)	80.4	(0.0075)	(0.0054)	0.0009	0.0046	(0.0016)	Greek Ascoloy	38 mm Ø x	-7 or 19+ mm	17025		
13X 12548N	(0.003)	.	.	0.49	.	0.019	0.0064	0.0027	Resulfurized	-40 mm Ø x	-15 mm			
BS 183C	0.0041	(0.0008)	81.1	0.0054	(0.005)	0.0007	0.0039	(0.002)	Greek Ascoloy	38 mm Ø x	-7 or 19+ mm	17025	Ca: 0.0006	
BS 431A	0.0033	0.0002	80.5	0.0062	0.0067	0.0012	0.0047	0.0010	431	38 mm Ø x	-7 or 19+ mm	17025	Zr: 0.0012	
DSZU C115	.	.	.	0.015	.	.	0.006	(0.0020)		40 mm Ø x	20 mm			
DSZU C119	.	.	.	(0.02)	.	.	(0.006)	1.02		40 mm Ø x	20 mm			
DSZU C117	.	.	.	(0.02)	.	.	(0.005)	0.59		40 mm Ø x	20 mm			
BS 91E	.	.	.	(0.004)	.	.	0.004	(0.002)	430	41 mm Ø x	-7 or 19+ mm			
IARM Fe174PH-18	.	.	.	(0.0015)	0.0035	.	0.0069	.	17-4 PH	31 mm Ø x	2 or 18 mm			
13X 41500A	.	.	.	0.040	.	.	.	0.0012	415	-40 mm Ø x	-15 mm			
13X 41008B	.	.	.	0.019	.	.	0.0081	.	410	-40 mm Ø x	-15 mm	Zr:0.047		
13X 40800A	0.004	.	.	0.020	.	(0.002)	0.0028	0.84	408	-40 mm Ø x	-15 mm			
DSZU C118	.	.	.	0.116	.	.	0.026	0.117		40 mm Ø x	20 mm			
IARM Fe155PH-18	(0.0026)	(0.0005)	75.03	0.273	0.0028	.	0.0021	.	15-5PH	31 mm Ø x	2 or 18 mm			
IARM Fe409-20	0.0026	.	.	0.0041	.	0.0011	0.0053	0.141	409	38 mm Ø x	2 or 19 mm			

Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Alloy	Units				
--------	----	---	----	----	---	----	----	----	-------	-------	--	--	--	--

## STAINLESS AND HIGH ALLOY STEEL

# = Class, where 1 = CRM and 2 = RM

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
1 IARM FeAl100-18	0.222	(0.013)	(0.004)	(<0.0010)	(0.039)	(0.010)	11.2	2.98	(0.007)	13.4	1.19	(0.0010)	(0.007)	(0.006)
1 IMZ 303	0.105	1.23	0.038	0.011	0.74	0.018	8.26	19.56	0.100	0.017		0.0113	0.037	
2 DSZU C120	0.078	0.158	0.0138	0.0030	0.35	0.122	8.46	30.8	(0.02)	(0.03)	(0.03)	0.042	0.041	(0.01)
1 IARM Fe309-18	0.066	1.61	0.029	(0.002)	0.30	0.430	12.2	22.42		0.248	0.357		0.073	0.063
1 <b>BS 309</b>	0.062	1.61	0.028	0.0011	0.24	0.349	12.16	22.40	(0.0025)	0.200	0.193		0.073	(0.031)
1 <b>BS 347C</b>	0.051	1.67	0.022	0.022	0.677	0.110	10.08	17.27	(0.003)	0.072	0.27		0.039	0.097
2 CZ SP-1B	0.050	1.67	0.039	0.30	0.505	0.47	8.32	17.42	(0.003)	0.161	0.40		0.063	0.060
2 PV 112/1	0.047	1.577	0.018	0.023	0.515	0.102	11.14	17.56			2.03			
2 HRT FE2021-H	0.041	1.19	0.021	0.002	0.34	0.17	12.7	15.6	0.007	0.044	1.11		0.088	0.59
1 13X 33425A	0.039	0.997	0.028	0.0052	0.85	0.204	20.90	22.3	0.017	0.092	2.52		0.0106	(0.014)
2 BS 95A	0.035	0.58	0.026	0.004	0.46	1.50	6.42	14.72	0.002	0.081	0.73		0.0255	0.052
1 13X 32180A	0.031	2.11	0.007	0.0093	0.485	0.49	10.16	18.92	0.043	0.040	0.245		0.0067	0.026
1 <b>BS 2507</b>	0.026	0.79	0.023	(0.0005)	0.32	0.222	6.94	25.3	(0.004)	0.040	3.75		0.0273	0.064
2 TL 200ID	0.0244	0.679	0.022	0.0006	0.27	0.612	7.5	25.58		0.046	3.49		0.279	0.079
1 IARM FeKovar-18	0.024	0.26	(0.004)	(0.0055)	(0.09)	0.077	29.0	0.068		17.3	0.062			(0.020)
2 PV 111/1	0.0226	1.538	0.019	0.026	0.485	0.105	8.57	18.49			0.173			
1 <b>BS 186B</b>	0.022	0.288	(0.0027)	0.0016	0.254	0.057	36.1	0.11	0.0080	0.041	0.025		0.0033	(0.002)
1 <b>BS 160B</b>	0.022	0.27	0.0033	0.0032	0.112	0.059	29.13	0.06	(0.005)	17.24	0.047		0.0006	0.0039
2 TL 2003D	0.0193	1.068	0.0274	0.0169	0.5020	0.2773	9.231	18.25		0.1270	0.2871		0.0556	0.0711
1 IARM FeN40-18	0.019	9.13	0.025	0.0012	0.31	0.421	6.42	19.45		0.122	0.343		0.348	0.086
1 <b>BS 254</b>	0.019	0.95	0.026	0.0009	0.312	0.612	18.47	20.2	<0.01	0.08	6.07		0.210	0.062
1 BS 179A	0.017	1.04	0.021	0.001	0.44	1.94	5.84	25.45	(0.009)	0.58	3.24		0.184	0.070
2 TL 2002D	0.0149	1.30	0.022	0.0206	0.53	0.438	11.0	16.7		0.087	2.05		0.0341	0.068
1 ECRM 298-2D	0.0140	0.788	0.0210	0.0006	0.331	0.105	6.87	24.91	0.0148	0.0482	3.78		0.277	0.070
1 SS 477	0.0102	1.623	0.0209	0.00039	0.473	1.340	25.07	20.38	0.0303	0.0875	4.23		0.0562	0.0527
2 BS 96A	0.009	0.04	0.007	0.004	0.06	2.07	8.38	11.62	0.08	0.03	0.021			0.07
1 IARM 99D	(0.006)	(0.013)	(0.004)	0.0011	(0.03)	(0.045)	18.4	(0.12)	0.117	9.24	4.8		0.0014	(0.037)
1 <b>BS 161B</b>	0.0031	0.010	(0.004)	0.0007	0.0107	0.010	18.56	0.034	0.073	9.28	4.87		0.0011	0.0011
1 BS M250 *	0.002	0.025	0.003	<0.005	<0.05	0.004	18.7	0.005	0.093	7.93	4.92		<0.005	<0.005

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Alloy	Units				
IARM FeAl100-18	.	.	.	0.070	(0.0009)	.	(0.004)	(0.008)	Aermet 100	31 mm Ø x 2 or 18 mm				
IMZ 303	.	.	.	.	.	.	.	0.60		40 mm Ø x 37 mm				
DSZU C120	.	.	.	0.015	.	.	0.004	0.005		40 mm Ø x 20 mm				
IARM Fe309-18	0.0065	.	.	0.021	.	0.0018	0.012	.	309	-38 mm Ø x -3 or -19 mm				
<b>BS 309</b>	0.0048	(0.0004)	62.6	0.0090	0.0027	(0.0017)	0.0089	0.0020	309, 309H	38 mm Ø x -7 or 19+ mm			<b>17025</b>	Ca: 0.0010
<b>BS 347C</b>	(0.003)	0.0018	69.1	0.58	0.0053	(0.002)	0.0034	(0.004)	347	44 mm Ø x -7 or 19+ mm			<b>17025</b>	
CZ SP-1B	(0.003)	0.0007	.	(0.012)	.	.	0.013	(0.002)		-37 mm Ø x -25 mm				
PV 112/1	.	.	.	.	.	.	.	0.394	316 Ti	40 mm Ø x 25 mm				
HRT FE2021-H	0.004	0.0021	.	0.57	.	0.003	0.005	0.004	X8CrNiMoVNb16-13	50 mm Ø x 20 mm				
13X 33425A	(0.0021)	.	.	0.047	.	(0.002)	0.0106	0.178		-40 mm Ø x -15 mm				
BS 95A	.	0.0010	.	0.55	.	.	0.008	(0.003)	450	38 mm Ø x -7 or 19+ mm				
13X 32180A	(0.003)	(0.0011)	.	(0.0021)	.	(0.0011)	0.0116	0.81	ER321	-40 mm Ø x -15 mm				
<b>BS 2507</b>	0.0046	0.0021	62.3	(0.011)	0.0038	0.0008	0.0050	0.0028	2507	38 mm Ø x -7 or 19+ mm			<b>17025</b>	
TL 200ID	.	.	.	0.024	.	.	.	.	Super Duplex	40 mm Ø x 20 mm				
IARM FeKovar-18	.	.	53.3	.	.	.	0.0021	.	Kovar	31 mm Ø x 2 or 18 mm				
PV 111/1	.	.	.	.	.	.	.	.	304 L	40 mm Ø x 25 mm				
<b>BS 186B</b>	0.0022	(0.0006)	63.0	(0.002)	0.0011	(0.0007)	0.0025	0.0028	Invar 36	43 mm Ø x -7 or 19+ mm			<b>17025</b>	Zr: 0.0020
<b>BS 160B</b>	<0.005	0.0003	53.0	0.0015	0.0010	(0.0009)	0.0020	(0.003)	Kovar	38 mm Ø x -7 or 19+ mm			<b>17025</b>	Ca: 0.0004
TL 2003D	.	.	.	0.0150	.	.	.	.	304 L	40 mm Ø x 20 mm				
IARM FeN40-18	.	.	.	0.032	.	.	0.0081	.	Nitronic 40	-38 mm Ø x -3 or -19 mm				
<b>BS 254</b>	(0.006)	0.0018	52.9	(0.03)	0.0038	0.0014	0.0063	0.0019	254 SMO	38 mm Ø x -7 or 19+ mm			<b>17025</b>	Zr: 0.0026
BS 179A	(0.003)	(0.001)	.	0.030	.	.	0.005	0.006	Ferralium 255	31 mm Ø x -7 or 19+ mm				
TL 2002D	.	.	.	.	.	.	.	0.0098	316 MOD	40 mm Ø x 20 mm				
ECRM 298-2D	0.0028	0.0024	.	0.0011	.	0.0006	0.0029	0.0023	1.4410	38 mm Ø x 25 mm				
SS 477	0.00399	0.00198	.	Mg:0.00053	.	0.00078	0.00453	.		38 mm Ø x 19 mm				
BS 96A	.	(0.0017)	.	0.26	.	.	.	1.18	455	38 mm Ø x -7 or 19+ mm				
IARM 99D	.	0.0026	.	(0.011)	.	.	.	0.67	Maraging 300	31 mm Ø x 2 or 18 mm				
<b>BS 161B</b>	.	0.0027	66.6	(0.0034)	0.0005	.	(0.0011)	0.67	Maraging 300	41 mm Ø x -7 or 19+ mm			<b>17025</b>	
BS M250 *	.	0.003	[67.9]	.	<0.005	.	.	0.42	Maraging 250	38 mm Ø x -7 or 19+ mm				

Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Alloy	Units
--------	----	---	----	----	---	----	----	----	-------	-------



## CRM CAST IRON

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Ce	La	Mg	Se	Te
MBH-FEPIGH-21	4.42	0.127	0.050	0.141	1.60	0.0113	0.040	0.088	0.20	0.018	.	.	.	.	.
NCS AH11112	3.95	0.511	0.055	0.014	2.30	0.487	0.141	0.251	0.014	.	.	.	0.032	.	.
NCS HS11799	3.95	0.511	0.055	0.014	2.30	0.487	0.141	0.251	0.014	.	0.012	0.0064	0.032	.	.
VS Chg 56	(3.8)	(0.2)	(0.8)	(0.01)	(0.5)	(0.4)	(0.1)	(0.1)	(0.01)	(0.005)	.	.	.	.	.
VS Chg 57	(3.8)	(0.2)	1.17	(0.03)	(0.6)	(0.3)	(0.3)	(0.4)	(0.06)	(0.01)	.	.	.	.	.
NCS HS11798	3.78	0.606	0.053	0.020	2.73	0.526	0.856	0.700	0.042	.	0.0097	0.0042	(0.034)	.	.
SCRM 660/11	3.62	0.444	0.137	0.115	1.74	.	.	.	.	.	.	.	.	.	.
NCS HS92744c	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	.	.	0.022	.	0.042	.	.
NCS HS92746a	3.59	0.226	0.046	0.012	2.25	0.263	0.501	0.097	0.014	.	.	.	0.029	.	.
SCRM 658/12	3.33	0.55	0.243	0.076	2.03	.	.	.	.	.	.	.	.	.	.
MBH-FEPIGM-21	3.22	0.077	0.051	0.053	0.71	0.0117	0.028	0.057	0.060	0.015	.	.	.	.	.
NCS AH11353	3.15	0.47	0.020	0.0006	2.30	0.029	0.59	0.025	0.023	0.015	.	.	0.029	.	.
Y 2863-9A	3.04	1.43	0.049	0.015	1.53	0.269	1.59	0.72	.	0.042	.	.	.	.	.
BS CC-23	2.96	0.73	0.53	0.082	0.43	0.307	0.56	0.467	0.060	0.090	(0.0006)	(0.0008)	(0.0006)	.	(0.03)
CKD 242A	1.84	0.060	0.039	0.036	3.06	0.055	0.039	0.029	0.036	0.002	(0.00)	(0.00)	0.000	(0.000)	(0.08)

  

Number	As	B	Bi	Fe	Mo	Nb	Pb	Sb	Sn	Ti	V	W	Zn	Zr	Units in mm
MBH-FEPIGH-21	0.0015	.	.	.	0.027	0.019	.	.	0.0075	0.42	0.108	(0.004)	.	0.0039	-40 Ø x ~15
NCS AH11112	.	.	.	.	0.474	.	.	.	0.055	0.117	0.312	.	.	.	31 Ø x 30
NCS HS11799	.	.	.	.	0.474	.	.	.	0.055	0.117	0.312	.	.	.	31 Ø x 30
VS Chg 56	0.18	(0.001)	.	.	(0.01)	(0.002)	.	0.014	.	(0.06)	(0.02)	(0.004)	.	.	-37 Ø x ~17
VS Chg 57	0.095	(0.002)	.	.	(0.01)	(0.004)	.	(0.001)	(0.01)	(0.08)	(0.04)	(0.01)	.	.	-37 Ø x ~17
NCS HS11798	.	.	.	.	0.359	.	.	0.025	0.032	0.117	0.018	.	.	.	31 Ø x 30
SCRM 660/11	.	.	.	.	.	.	.	.	.	.	.	.	.	.	48 x 42 x 12
NCS HS92744c	0.0021	0.024	.	.	0.180	.	.	.	.	0.044	0.174	.	.	.	35 Ø x 30
NCS HS92746a	(0.003)	0.0086	.	.	0.214	.	.	.	.	0.040	0.033	.	.	.	35 Ø x 30
SCRM 658/12	.	.	.	.	.	.	.	.	.	.	.	.	.	.	48 x 42 x 12
MBH-FEPIGM-21 (0.0018)	.	.	.	.	0.0157	0.014	.	.	0.0061	0.258	0.071	(0.003)	.	0.0022	-40 Ø x ~15
NCS AH11353	0.008	0.004	.	.	0.002	0.003	.	0.0005	0.003	0.027	0.032	0.003	.	.	30 Ø x 25
Y 2863-9A	(0.041)	0.153	.	.	1.38	0.11	(0.093)	(0.116)	(0.124)	0.212	0.41	.	.	.	30 Ø x 18-30
BS CC-23	0.016	0.067	.	(92.8)	0.267	(0.002)	0.008	0.17	0.052	0.091	0.195	(0.002)	17025	0.057	-32 Ø x ~17 17025
CKD 242A	0.015	0.008	(0.015)	(92.9)	1.13	0.013	(0.012)	0.007	0.010	0.19	0.37	(0.007)	(0.00)	(0.000)	37x37x ~18-20 last

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
1.0812		ECRM 191-2D	15-5PH		BS 9621	314		IMZ 166A
1.2344		ECRM 271-1D	15-5PH		BS 9622	316 H		13X NSA2
1.4410		ECRM 298-2D	15-5PH		IARM Fe155PH-18	316 H		CT 316
1.4435, 1.4436		JK 27B	15-5PH		ECRM 273-1D	316 H		IARM 339A
1.4765		ECRM 299-1D	16MnCr5		PV 102/1	316 H		NILAB 500HAD
1.5415		HRT FE2012-N	17-4PH		13X PH2	316 L	17025	BS 316F
1.6587		HRT FE2013-N	17-4PH		BS 17-4PHA	316 L		CZ SL-2A
1.7149	20MnCrS5	ECRM 187-2D	17-4PH	17025	BS 17-4PHB	316 L		IARM Fe316L-18
1.7160		ECRM 194-1D	17-4PH	17025	BS 17-4PHC	316 L		IARM 163E
1.8550		ECRM 129-3D	17-4PH		IARM Fe174PH-18	316 L		SRM 1155A
1.8519		HRT FE2010-N	17-4PH		SRM C2400	316 L		SS 466/2
1.8928		ECRM 194-2D	17-7PH		13X PH17700	316 MOD		TL 2002
1005	17025	BS 1005	17-7PH 25(preceded 17025)		BS 192	316 Ti		IRSID 1821
1005		DSZU C040a	17-7PH 25(preceded 17025)		BS 192A	316 Ti		PV 112/1
1005		ECRM 064-2D	17-7PH		IARM 152C	316 Ti		VS LG72
1005		RM Fe 1/5	17-7PH		IARM Fe177PH-18	317 L	17025	BS 317L
1005		SRM 1765	182FM		BS 150	317 L	25(pre-17025)	BS 9941
1005		SRM 1766	18Cr2Ni12Mn		CT ISO035A	317 L	25(pre-17025)	BS 9942
1005		SS 111/1	201		BS 191	317 L		IARM 153C
1008	17025	BS XCAS	201		SRM 1297	318	17025	BS 2205
1008		ECRM 057-2D	20Cb3		BS 187A	318		BS 2205A
1009	17025	BS 1009	20Cb3		CT 20 Cb-3	321		13X 32100
1009 + Al	17025	BS XCAS-2	20MoCr4		ECRM 197-1D	321	17025	BS 85D
100C6		IRSID 1747	2101		IARM 292A	321	17025	BS 321D
1010		IMZ 111	21Cr6Ni9Mn		CT ISO129A	321		IARM 61
1010		NM 308	2205		13x NSA9	321		IARM 6J
1011		IMZ 73	2205	17025	BS 2205	321		SRM 1171
1012, 1013		IMZ 71A	2205	17025	BS 2205A	321		SS 465/1
1016	17025	BS 1016	2205		IARM 212D	321 - Ti		IMZ 152
1017		IMZ 112B	2205		HRT FE2000-H	32750		13X NSA13
1017		IRSID 1664	2205		IARM Fe2205-18	3310		BS 3310
1018		12X 10180B	2304		IARM 317A	347		13X 34700
1018		12X 10180C	2507	17025	BS 2507	347		BS 347A
1018	17025	BS 1018	2507		IARM 301B	347		BS 347B
1018		ECRM 087-1D	253 MA	25(pre-17025)	BS 253	347		BS 347C
1018		IARM 28K	253 MA		IARM 316A	347		IARM 8G
1020	17025	BS 1020	254 SMO	17025	BS 254	347		IARM 8H
1020		BS 57F	254 SMO		NILAB 501HAD	347		IARM 8i
1020		IARM Fe1020-18	255, Duplex		IARM 239B	347 H		BS 87F
1023		IMZ 112A	255, Duplex		IARM 239C	348		SRM 1172
1026	17025	BS 1026	300M		12X 44220	355	17025	BS 355
1026	17025	BS 1026A	300M	17025	BS 300A	355		IARM 335A
1026		IARM 359A	300M		IARM 340A	35MV7		IRSID 1750
1030	17025	BS 1030	301		IARM 289A	405		SRM 1295
1030	17025	BS 1030A	301		IARM 289B	408		13X 40800A
1030		IARM 209D	301		IRSID 1819	409		13X 40900
1033		IRSID 1663	302		IARM 241D	409		13X 40930
1035	17025	BS 1035	302 HQ		IARM 234C	409		IARM Fe409-20
1035		IARM 360A	303		13X 30300	409 + Cr		NCS HS20743
1039		IRSID 1637	303	17025	BS 303	410		13X 41008
1040	17025	BS 1040	303		CT 303	410	25(pre-17025)	BS 0021
1040		IARM 210D	303		CZ SP-1A	410, F6NM	25(pre-17025)	BS 0022
1040		IRSID 1657	303		IARM Fe303-18	410	17025	BS 410C
1042		IRSID 1656	303 Se		IARM 253A	410		CT 410
1042		NM EN-8	303 Se		IARM 253B	410		IARM Fe410-18
1043		IRSID 1652	304 H		13X NSB1	410 + Mo		ECRM 296-1D
1045	17025	BS 1045	304 H + Ca	17025	BS CA304-4	410 + Mo		IMZ 161
1045		BS 56E	304 H		CT 304	410 H		13X 41001
1045		IARM 200D	304 H		IARM Fe304H-18	4130	17025	BS 4130
1045		IPT 503	304 H		SS 468/1	4130		IARM 143F
1045 + P		NM 306A	304 L		13X 30403	4130		SRM 1225
1050		IARM Fe1050-18	304 L	17025	BS 304B	4130 H		IPT 501
1060		IARM 373A	304 L		IARM 162D	4140		12X 41400
1060 + P		NM 309	304 L		IARM Fe304L-18	4140	25(pre-17025)	BS 1962
1069		ECRM 059-2D	304 L		ECRM 287-1D	4140	17025	BS 4140C
1070	17025	BS 54H	304 L		ECRM 292-1D	4140		IARM 30H
1078		ECRM 056-2D	304 L		IARM 162C	4140		IARM 30J
1078		SRM 1224	304 L		PV 111/1	4140		IARM Fe4140-19
1080		BS 54J	304 L		TL 2003D	4140 Bi		BS 4140A
1090		SS 602/2	304 L		SS 463/1	4140 Bi		BS 4140B
1095		BS 64C	305		ECRM 297-1D	41L40MOD	17025	BS 70B
1095		SRM 1227	306		13X 30600A	41L40MOD	17025	BS 70C
1117	25(preceded 17025)	BS 3993	308		DSZU C017	4150 Bi & S		BS 4150MOD
1117		BS 65C	309		BS 82E	4150 S	17025	BS 4150MOD-A
1117		IARM 29E	309	17025	BS 309	4150 S	17025	BS 42
1118		IARM 307A	309		IARM Fe309-18	4150 S		BS 42A
1118		IARM 307B	310		13X 31008	415		13X 41500A
1141		BS 66B	310		BS 83G	416		BS 90F
1141		IARM 348A	310	25(pre-17025)	BS 9841	416	17025	BS 416
1144	17025	BS 1144	310	25(pre-17025)	BS 9842	416		CT 416
1144	17025	BS 1144A	310		CZ SL-3A	416		SRM 1223
1144		IARM 199C	310		IARM 4E	416 H		13X 41600
11L17	17025	BS 75F	310		IARM 4F	416 Se		BS 151
11L17	17025	BS 75G	310		IARM 4G	418		IARM Fe418-18
1215		BS 66K	310		SS 464/1	41CAD7		IRSID 1749
1215	17025	BS 66L	3115		BS XCCT	41L40	17025	BS 70B
1215		IARM Fe1215-18	314		IMZ 165	41L50	17025	BS 72B
12L14		BS 74B				42		CT ISO138A
12L14	17025	BS 74C				42		CT ISO139A
12L14	17025	BS 74D				42CrMo4		PV 101/1
12Mn18Cr		BS 193				420		BS 98
1345		BS XCCV				420		BS SS4951
13-8PH		13X PH13800				420		BS SS4952
13-8PH		BS 184A				420		ECRM 272-1D
13-8PH		CT X92834				420		IARM 154C
13-8PH		IARM 21D				420		SS 469
1429		ECRM 058-2D				420 F		BS 152
1513		IMZ 76				420 F S		IARM 352A
1526 MOD		SRM 1269				422		13X 42200
1541		IARM 349A				422		BS 97
1541		IPT 504				422	17025	BS 422
1541		IRSID 1648				422		IARM 205D
1544		IRSID 1644				430		BS 91E
15-5PH		BS 185A				430	17025	BS 430
						430		IARM 11D

Please use the Adobe Acrobat "search" function to find the complete chemistry of these samples listed within this catalog.

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
430		NCS HS20742	A-6		IARM 40B	Invar 42		14X 94100
430 F		BS 153	A-6		IARM 40C	ISO 898-1		SS 457/2
430 F S		BS 154	A615-75		IARM 378A		17025	BS 160A
430 F S		IARM 355A	A706-60		IARM 380A		17025	BS 160B
431	17025	BS 431	A706-60		IARM 380B			IARM 98B
431		BS 92B	A706-80		IARM 381A			IARM FeKovar-18
431		IARM 12C	Aermet 100		CT ISO045A		17025	BS 43A
431		HRT FE2010-H	Aermet 100		IARM 242A		17025	BS 39B
431		SRM 1219	Aermet 100		IARM FeA100-18			IARM FeL6-18
4320		BS 3961	AL6XN	17025	BS 189A			LDX2101
4330 MOD		BS 4330MOD	AL6XN		IARM 157D			13X 32101
4330 MOD		IARM 330B	C-.5Mo		BS 3952		17025	BS 2971
4340	17025	BS 4340	C-.5Mo		IARM 229B			BS LF2B
4340	17025	BS 4340A	C-250		IARM 308A			SS 601/2
4340		IARM 31G	C-350		IARM 309A			BS LF3
439 MOD		NCS HS11721-4	CA6NM		HRT FE2009-H			BS TM1
440 C		13X 44004	CA6NM		IARM 327A			CT M1
440 C		BS 93E	CD3MN		ECRM 298-2D			IARM 304A
440 C	17025	BS 93F	CD4MCU	17025	BS CD4MCU			IARM FeM1-18
440 C		IARM 13D	CD4MCU	17025	BS CD4MCU-A			CT M10
440 F		BS 155	CD6MN		VS LG58			IARM 324A
440 F Se		BS 156	CF-3		IRSID 1820			13X 64152
440 F Se		IARM 353A	CLA6		IARM 169B			IARM 291A
441		NCS HS11721-4	CLA7		IARM 170B			BS 32D
446		BS 94C	CLA11		IARM 180A			CT M2
450		BS 95A	CLA5		IARM 168A			IARM 44C
450	17025	BS 450	CLA9		IARM 172A			IARM FeM2-18
450	25(pre-17025)	BS 9811	CPM15V	17025	BS PM15			SRM 1157
450	25(pre-17025)	BS 9812	CPM15V		IARM Fe15V-18			IARM 320A
450		IARM 15C	D-2		BS 37G			IARM 251A
450		CT 450	D-2		CT D2			IARM FeM4-18
455		13X 45500	D-2		IARM 41D		17025	SS 487/1
455		BS 96A	D-3, D-4		ECRM 288-1D		17025	BS M-47
455		BS SS1962	D-6	17025	BS D-6			BS M-50
455		CT 455	D-6	17025	BS D-6A			IARM 306B
455		IARM 16C	D6-AC		IARM 299A			IARM FeM62-18
446		IARM 14C	DPI080		IARM FeDPI080-18			CT M7
4615		BS 3962	Duplex		13X NSA9			CT 250
4620		BS 4620	Duplex	17025	BS 2205			ECRM 285-2
4620	17025	BS 51F	Duplex		IMZ 163A		25(pre17025)	BS 161A
4620		IARM 33D	Duplex		IMZ 164		17025	BS 161B
465		13X 46500	Duplex		TL 2001			CT 300
465		IARM 354A	E52100		BS 53G			IARM 99D
465		CT ISO123A	E52100	17025	BS E52100		17025	BS PP20
4820	17025	BS 4820A	E52100		IARM 49E			IARM 305B
4820		BS 4820B	E52100 Bi		BS 53MOD			BS 68B
4820		IARM 155F	Elect./ Magnetic		SRM 1159		17025	BS 68E
4820		IARM Fe4820-18	Electrolytic		SRM 1265a			13X NSC6
5140H		IARM Fe5140H-18	ER321		13X 32180A			BS 190
5160		IMZ 116	F-1		RM Fe 2			IARM FeN40-18
6150	17025	BS 43A	F-11		BS 45A		17025	BS 180A
6150		BS 4941	F-11	17025	BS 45B			BS 180B
6150		IARM 34C	F-11		IARM 35L			IARM 17D
630		CT 630	F-11		IARM FeF11-21			IARM FeN50-18
6418		BS 6418	F-2		CT X27081			13X 21800
6418		BS 69B	F-22	17025	BS 46B			BS 181A
6526		BS 9-4-30	F-22	25(preceeded 17025)	BS 1982		17025	BS 181B
709		CT X67975	F-22		IARM 36C			IARM 18D
8620		12X 86200-21	F-22		SRM 1270			IARM 214A
8620		BS 1931	F-22 + Cr		HRT FE2009-N			IARM 295A
8620 + Bi		BS 8620A	F-5		BS 47A		17025	IARM 294A
8620	17025	BS 8620F	F-5		BS 47B			BS 35D
8620		IARM Fe8620-18	F-5		IARM 37C			CT O1
8620		IPT 502	F-51	17025	BS 2205		17025	CZ LA-4C
86L20	25(preceeded 17025)	BS 73B	F-51		BS 2205A		25(preceeded 17025)	BS 41
86L20		BS 73C	F-9	17025	BS 48B			BS 41A
8630	17025	BS 8630	F-9		IARM FeF9-18			IARM 45A
8740		BS 67B	F-91		13X 90901		17025	IARM 45B
8740	17025	BS 8740	F-91	17025	BS 9905A			BS 55G
8740		IARM 252C	F-91		HRT FE2003-H			BS 68C
8740		IARM 252D	F-91		IARM Fe91-18		17025	BS PP20
8740		IARM 252E	Ferrallium 255		BS 179A			BS 86F
8740		IARM 252F	Ferallium 255	17025	BS 179B			BS 54H
8822		BS 8822	Ferallium 255	17025	BS 179C			BS 33D
8822	17025	BS 8822A	F6NM 25(preceeded 17025)		BS 0022			BS 33E
904L		13X NSA12	Greek Ascoloy		BS 183A		17025	IARM 46B
904L		ECRM 295-1D	Greek Ascoloy	17025	BS 183B			BS 33F
9310		BS 58C	Greek Ascoloy	17025	BS 183C			BS 38C
9310		BS 58D	Greek Ascoloy		IARM 20C			IARM 47B
9310		BS 58E	H-10		BS 49		17025	BS TS7
9310		IARM FeE9310-18	H-11		BS TH11			BS TS-7A
9325	17025	BS 9325A	H-11		ECRM 276-2D			IARM 259A
9325		BS 9325B	H-11		IARM 255A			IARM FeS7-18
9-4-30		IARM 341A	H-11		IARM 255B			SRM 1772
A-10		BS A-10	H-11		IMZ 173			13X 42027A
A-11		BS 10V	H-12		BS TH12			IMZ 159
A-11	17025	BS A-11	H-13		BS 34D			IMZ 160
A-106 Gr B		SRM 1228	H-13	17025	BS H-13A			IMZ 169
A-193 B16		BS 4942	H-13		CT H13			BS 20E
A-193 B16	17025	BS 4942A	H-13		IARM 42C			IARM 268B
A-2		BS 36C	H-13		IMZ 174		17025	BS 30D
A-2		BS 36D	H-19	17025	BS H-19			IARM FeT1-18
A-2		CT A2	HC 250+v		SRM C1290		17025	IARM 281A
A-2		IARM 39B	High Perm		CT ISO124A			BS TS15
A-2		IARM 39C	High Perm		CT ISO136A			IARM FeT23-18
A-242		IPT 500	High Perm 49		CT ISO141A			IMZ 196
A-242 Mod		SRM C1285	HSLA 100		SRM 1271			14X 72305
A-286	17025	BS 188B	HY 130		SRM 1226			IRSID 1825
A-286		IARM 26D	HY 80		SRM 1286			13X NSA8
A-286		SRM 1230	Hy-Tuff		IARM 342A			IARM 319A
A-36		IARM 213C	Invar		14X 93603			IARM FeZ100-18
A-36		IARM 213D	Invar-36	17025	BS 186B			
A-485-1		BS A485-1	Invar-36 + Se		BS 186A			
A-6		BS 40B	Invar-36 + Se		IARM 24B			

## CARBON STEEL SPECIFICATIONS

Number	C	Mn	P	S
1005	<0.06	<0.35	<0.03	<0.05
1006	<0.08	0.25-0.40	<0.03	<0.05
1008	<0.10	0.30-0.50	<0.03	<0.05
1009	<0.15	<0.60	<0.03	<0.05
1010	0.08-0.13	0.30-0.60	<0.03	<0.05
1011	0.09-0.14	0.60-0.90	<0.03	<0.05
1012	0.10-0.15	0.30-0.60	<0.03	<0.05
1013	0.11-0.16	0.50-0.80	<0.03	<0.05
1015	0.13-0.18	0.30-0.60	<0.03	<0.05
1016	0.13-0.18	0.60-0.90	<0.03	<0.05
1017	0.15-0.20	0.30-0.60	<0.03	<0.05
1018	0.15-0.20	0.60-0.90	<0.03	<0.05
1019	0.15-0.20	0.70-1.00	<0.03	<0.05
1020	0.18-0.23	0.30-0.60	<0.03	<0.05
1021	0.18-0.23	0.60-0.90	<0.03	<0.05
1022	0.18-0.23	0.70-1.00	<0.03	<0.05
1023	0.20-0.25	0.30-0.60	<0.03	<0.05
1025	0.22-0.28	0.30-0.60	<0.03	<0.05
1026	0.22-0.28	0.60-0.90	<0.03	<0.05
1029	0.25-0.31	0.60-0.90	<0.03	<0.05
1030	0.28-0.34	0.60-0.90	<0.03	<0.05
1033	0.29-0.36	0.70-1.00	<0.03	<0.05
1034	0.32-0.38	0.50-0.80	<0.03	<0.05
1035	0.32-0.38	0.60-0.90	<0.03	<0.05
1037	0.32-0.38	0.70-1.00	<0.03	<0.05
1038	0.35-0.42	0.60-0.90	<0.03	<0.05
1039	0.37-0.44	0.70-1.00	<0.03	<0.05
1040	0.37-0.44	0.60-0.90	<0.03	<0.05
1042	0.40-0.47	0.60-0.90	<0.03	<0.05
1043	0.40-0.47	0.70-1.00	<0.03	<0.05
1044	0.43-0.50	0.30-0.60	<0.03	<0.05
1045	0.43-0.50	0.60-0.90	<0.03	<0.05
1046	0.43-0.50	0.70-1.00	<0.03	<0.05
1049	0.46-0.53	0.60-0.90	<0.03	<0.05
1050	0.48-0.55	0.60-0.90	<0.03	<0.05
1053	0.48-0.55	0.70-1.00	<0.03	<0.05
1055	0.50-0.60	0.60-0.90	<0.03	<0.05
1059	0.55-0.65	0.50-0.80	<0.03	<0.05
1060	0.55-0.65	0.60-0.90	<0.03	<0.05
1064	0.60-0.70	0.50-0.80	<0.03	<0.05
1065	0.60-0.70	0.60-0.90	<0.03	<0.05
1069	0.65-0.75	0.40-0.70	<0.03	<0.05
1070	0.65-0.75	0.60-0.90	<0.03	<0.05
1074	0.70-0.80	0.50-0.80	<0.03	<0.05
1078	0.72-0.85	0.30-0.60	<0.03	<0.05
1080	0.75-0.88	0.60-0.90	<0.03	<0.05
1084	0.83-0.93	0.60-0.90	<0.03	<0.05
1085	0.80-0.94	0.70-1.00	<0.03	<0.05
1086	0.80-0.93	0.30-0.50	<0.03	<0.05
1090	0.85-0.98	0.60-0.90	<0.03	<0.05
1095	0.90-1.03	0.30-0.50	<0.03	<0.05
Number	C	Mn	P	S

## CARBON STEEL SPECIFICATIONS

Number	C	Mn	P	S	Si
1513	0.10-0.16	1.10-1.40	<0.03	<0.05	.
1522	0.18-0.24	1.10-1.40	<0.04	<0.05	.
1524	0.19-0.25	1.35-1.65	<0.04	<0.05	.
1526	0.22-0.29	1.10-1.40	<0.04	<0.05	.
1527	0.22-0.29	1.20-1.50	<0.04	<0.05	.
1533	0.30-0.37	1.10-1.40	<0.04	<0.05	.
1534	0.30-0.37	1.20-1.50	<0.04	<0.05	.
1541	0.36-0.44	1.35-1.65	<0.04	<0.05	.
1544	0.40-0.47	0.80-1.10	<0.04	<0.05	.
1545	0.43-0.50	0.80-1.10	<0.04	<0.05	.
1546	0.44-0.52	1.00-1.30	<0.04	<0.05	.
1548	0.44-0.52	1.10-1.40	<0.04	<0.05	.
1552	0.47-0.55	1.20-1.50	<0.04	<0.05	.
1553	0.48-0.55	0.80-1.10	<0.04	<0.05	.
1566	0.60-0.70	0.85-1.15	<0.04	<0.05	.
1570	0.65-0.75	0.80-1.10	<0.04	<0.05	.
1580	0.75-0.88	0.80-1.10	<0.04	<0.05	.
1590	0.85-0.98	0.80-1.10	<0.04	<0.05	.
LF2	<0.30	0.60-1.35	<0.035	<0.04	0.15-0.30
Number	C	Mn	P	S	Si

## RESULFURIZED STEEL SPECIFICATIONS

Number	C	Mn	P	S
1108	0.08-0.13	0.50-0.80	<0.04	0.08-0.13
1109	0.08-0.13	0.60-0.90	<0.04	0.08-0.13
1110	0.08-0.13	0.30-0.60	<0.04	0.08-0.13
1116	0.14-0.20	1.10-1.40	<0.04	0.16-0.23
1117	0.14-0.20	1.00-1.30	<0.04	0.08-0.13
1118	0.14-0.20	1.30-1.60	<0.04	0.08-0.13
1119	0.14-0.20	1.00-1.30	<0.04	0.24-0.33
1123	0.20-0.27	1.20-1.50	<0.04	0.06-0.09
1132	0.27-0.34	1.35-1.65	<0.04	0.09-0.13
1137	0.32-0.39	1.35-1.65	<0.03	0.08-0.13
1139	0.35-0.43	1.35-1.65	<0.04	0.13-0.20
1140	0.37-0.44	0.70-1.00	<0.03	0.08-0.13
1141	0.37-0.45	1.35-1.65	<0.03	0.08-0.13
1144	0.40-0.48	1.35-1.65	<0.03	0.24-0.33
1145	0.41-0.49	0.70-1.00	<0.04	0.08-0.13
1146	0.42-0.49	0.70-1.00	<0.04	0.08-0.13
1151	0.48-0.55	0.70-1.00	<0.04	0.08-0.13
1152	0.48-0.55	0.70-1.00	<0.04	0.06-0.09
1211	<0.13	0.60-0.90	0.07-0.12	0.10-0.15
1212	<0.13	0.70-1.00	0.07-0.12	0.16-0.23
1213	<0.13	0.70-1.00	0.07-0.12	0.24-0.33
1215	<0.09	0.75-1.05	0.04-0.09	0.26-0.35
Number	C	Mn	P	S

These are specifications,  
not samples for sale.

## LOW ALLOY STEEL SPECIFICATIONS

Number	C	Mn	P	S	Si	Ni	Cr	Mo	Pb	Other
1330	0.28-0.33	1.60-1.90	<0.035	<0.04	0.15-0.35	.	.	.	.	.
1335	0.33-0.38	1.60-1.90	<0.035	<0.04	0.15-0.35	.	.	.	.	.
1340	0.38-0.43	1.60-1.90	<0.035	<0.04	0.15-0.35	.	.	.	.	.
1345	0.43-0.48	1.60-1.90	<0.035	<0.04	0.15-0.35	.	.	.	.	.
3140	0.38-0.43	0.70-0.90	<0.04	<0.04	0.15-0.35	1.10-1.40	0.55-0.75	.	.	.
4023	0.20-0.25	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4027	0.25-0.30	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4028	0.25-0.30	0.70-0.90	<0.035	0.035-0.050	0.15-0.35	.	.	0.20-0.30	.	.
4037	0.35-0.40	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4047	0.45-0.50	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4118	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.40-0.60	0.08-0.15	.	.
4120	0.18-0.23	0.80-1.20	<0.035	<0.04	0.15-0.35	.	0.40-0.60	0.15-0.25	.	.
4121	0.18-0.23	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.45-0.65	0.15-0.25	.	.
4130	0.28-0.33	0.40-0.60	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4135	0.33-0.38	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4137	0.35-0.40	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4140	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
41L40	0.38-0.43	0.75-1.00	<0.035	0.02-0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	0.15-0.35	.
4142	0.40-0.45	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4145	0.43-0.48	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4147	0.45-0.50	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4150	0.48-0.53	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
41L50	0.48-0.53	0.75-1.00	<0.035	0.02-0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	0.15-0.35	.
4320	0.17-0.22	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	0.40-0.60	0.20-0.30	.	.
4340	0.38-0.43	0.60-0.80	<0.035	<0.04	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30	.	.
4615	0.13-0.18	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4617	0.15-0.20	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4620	0.17-0.22	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4715	0.13-0.18	0.70-0.90	<0.035	<0.04	0.15-0.35	0.70-1.00	0.45-0.65	0.45-0.65	.	.
4720	0.17-0.22	0.50-0.70	<0.035	<0.04	0.15-0.35	0.90-1.20	0.35-0.55	0.15-0.25	.	.
4815	0.13-0.18	0.40-0.60	<0.035	<0.04	0.15-0.35	3.25-3.75	.	0.20-0.30	.	.
4820	0.18-0.23	0.50-0.70	<0.035	<0.04	0.15-0.35	3.25-3.75	.	0.20-0.30	.	.
50B46	0.44-0.49	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.20-0.35	.	.	B: 0.0005-0.003
5120	0.17-0.22	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
51L20	0.17-0.22	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	0.15-0.35	.
5130	0.28-0.33	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	.	.	.
5132	0.30-0.35	0.60-0.80	<0.035	<0.04	0.15-0.35	.	0.75-1.00	.	.	.
5140	0.38-0.43	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
5150	0.48-0.53	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
5160	0.56-0.64	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
51B60	0.56-0.64	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	B: >0.0005
6150	0.48-0.53	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	.	.	V: >0.15
8615	0.13-0.18	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8617	0.15-0.20	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8620	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
86L20	0.18-0.21	0.70-0.90	<0.035	0.02-0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	0.15-0.35	.
8622	0.20-0.25	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8630	0.28-0.33	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8637	0.35-0.40	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8640	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8645	0.43-0.48	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8720	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.20-0.30	.	.
8740	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.20-0.30	.	.
8822	0.20-0.25	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.30-0.40	.	.
9259	0.56-0.64	0.75-1.00	<0.035	<0.04	0.70-1.10	.	0.45-0.65	.	.	.
9260	0.56-0.64	0.75-1.00	<0.035	<0.04	1.80-2.20	.	.	.	.	.
E4340	0.38-0.43	0.65-0.85	<0.025	<0.025	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30	.	.
E51100	0.98-1.10	0.25-0.45	<0.025	<0.025	0.15-0.35	.	0.90-1.15	.	.	.
E52100	0.98-1.10	0.25-0.45	<0.025	<0.025	0.15-0.35	.	1.30-1.60	.	.	.
E9310	0.08-0.13	0.45-0.65	<0.025	<0.025	0.15-0.35	3.00-3.50	1.00-1.40	0.08-0.15	.	.
F-11	0.10-0.20	0.30-0.60	<0.04	<0.04	0.50-1.00	.	1.00-1.50	0.44-0.65	.	.
F-22	<0.15	0.30-0.60	<0.03	<0.03	<0.50	.	2.00-2.50	0.90-1.10	.	.
F-5	<0.15	0.30-0.60	<0.03	<0.03	<0.50	.	4.00-6.00	0.45-0.65	.	.
F-9	<0.15	0.30-0.60	<0.03	<0.03	0.50-1.0	.	8.00-10.00	0.90-1.10	.	.
F-91	0.08-0.12	0.30-0.60	<0.02	<0.01	0.20-0.50	<0.40	8.00-9.50	0.85-1.05	.	Al: <0.04 N: 0.03-0.07
F-91	continued									Nb: 0.06-0.10 V: 0.18-0.25
LF2	<0.30	0.60-1.35	<0.035	<0.04	0.15-0.30	.	.	.	.	.
LF3	<0.20	<0.90	<0.035	<0.04	0.20-0.35	3.25-3.75	.	.	.	.

Number	C	Mn	P	S	Si	Ni	Cr	Mo	Pb	Other
--------	---	----	---	---	----	----	----	----	----	-------

These are specifications,  
not samples for sale.

## TOOL STEEL SPECIFICATIONS

\* notes optional chemistry

Number	C	Mn	P	S	Si	Ni	Cr	Co	Mo	V	W	Other
A-2	0.95-1.05	<1.00	<0.03	<0.03	<0.50	.	4.75-5.50	.	0.90-1.40	0.15-0.50	.	.
A-4	0.95-1.05	1.80-2.20	<0.03	<0.03	<0.50	.	0.90-2.20	.	0.90-1.40	.	.	.
A-6	0.65-0.75	1.80-2.50	<0.03	<0.03	<0.50	.	0.90-1.20	.	0.90-1.40	.	.	.
A-7	2.00-2.85	<0.80	<0.03	<0.03	<0.50	.	5.00-5.75	.	0.90-1.40	3.90-5.15	0.50-1.50	.
A-8	0.50-0.60	<0.50	<0.03	<0.03	0.75-1.10	.	4.75-5.50	.	1.15-1.65	.	1.00-1.50	.
A-9	0.45-0.55	<0.50	<0.03	<0.03	0.95-1.15	1.25-1.75	4.75-5.50	.	1.30-1.80	0.80-1.40	.	.
A-10	1.25-1.50	1.60-2.10	<0.03	<0.03	1.00-1.50	1.55-2.05	.	.	1.25-1.75	.	.	.
A-11	2.45	0.50	.	.	0.90	.	5.25	.	1.30	9.75	.	.
D-2	1.40-1.60	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	<1.00	0.70-1.20	<1.10	.	.
D-3	2.00-2.35	<0.60	<0.03	<0.03	<0.60	.	11.00-13.50	.	.	<1.00	<1.00	.
D-4	2.05-2.40	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	.	0.70-1.20	<1.00	.	.
D-5	1.40-1.60	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	2.50-3.50	0.70-1.20	<1.00	.	.
D-7	2.15-2.50	<0.60	<0.03	<0.03	<0.60	.	11.50-13.50	.	0.70-1.20	3.80-4.40	.	.
H-10	0.35-0.45	0.25-0.70	<0.03	<0.03	0.80-1.20	.	3.00-3.75	.	2.00-3.00	0.25-0.75	.	.
H-11	0.33-0.43	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.10-1.60	0.30-0.60	.	.
H-12	0.30-0.40	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.25-1.75	<0.50	1.00-1.70	.
H-13	0.32-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.10-1.75	0.80-1.20	.	.
H-14	0.35-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	.	.	4.00-5.25	.
H-19	0.32-0.45	0.20-0.50	<0.03	<0.03	0.20-0.50	.	4.00-4.75	4.00-4.50	0.30-0.55	1.75-2.20	3.75-4.50	.
H-21	0.26-0.36	0.15-0.40	<0.03	<0.03	0.15-0.50	.	3.00-3.75	.	.	0.30-0.60	8.50-10.00	.
H-22	0.30-0.40	0.15-0.40	<0.03	<0.03	0.15-0.40	.	1.75-3.75	.	.	0.25-0.50	10.00-11.75	.
H-23	0.25-0.35	0.15-0.40	<0.03	<0.03	0.15-0.60	.	11.00-12.75	.	.	0.75-1.25	11.00-12.75	.
H-24	0.42-0.53	0.15-0.40	<0.03	<0.03	0.15-0.40	.	2.50-3.50	.	.	0.40-0.60	14.00-16.00	.
H-26	0.45-0.55	0.15-0.40	<0.03	<0.03	0.15-0.40	.	3.75-4.50	.	.	0.75-1.25	17.25-19.00	.
H-42	0.55-0.70	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.50-5.50	1.75-2.20	5.50-6.75	.
L-2	0.45-1.00	0.10-0.90	<0.03	<0.03	<0.50	.	0.70-1.20	.	<0.25	0.10-0.30	.	.
L-6	0.65-0.75	0.25-0.80	<0.03	<0.03	<0.50	1.25-2.00	0.60-1.20	.	<0.50	.	.	.
M-1	0.78-0.88	0.15-0.40	<0.03	<0.03	0.20-0.50	.	3.50-4.00	.	8.20-9.20	1.00-1.35	1.40-2.10	.
M-2	0.78-1.05	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.50-5.50	1.75-2.20	5.50-6.75	.
M-3.1	1.00-1.10	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.75-6.50	2.25-2.75	5.00-6.75	.
M-3.2	1.15-1.25	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.75-6.50	2.75-3.25	5.00-6.75	.
M-4	1.25-1.40	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.75	.	4.25-5.50	3.75-4.50	5.25-6.50	.
M-6	0.75-0.85	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	11.00-13.00	4.50-5.50	1.30-1.70	3.75-4.75	.
M-7	0.97-1.05	0.15-0.40	<0.03	<0.03	0.20-0.55	.	3.50-4.00	.	8.20-9.20	1.75-2.25	1.40-2.10	.
M-10	0.84-1.05	0.10-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	7.75-8.50	1.80-2.20	.	.
M-30	0.75-0.85	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.50-4.25	4.50-5.50	7.75-9.00	1.00-1.40	1.30-2.30	.
M-33	0.85-0.92	0.15-0.40	<0.03	<0.03	0.25-0.55	.	3.50-4.00	7.75-8.75	9.00-10.00	1.00-1.35	1.30-2.10	.
M-34	0.85-0.92	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.50-4.00	7.75-8.75	7.75-9.20	1.90-2.30	1.40-2.10	.
M-36	0.80-0.90	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	7.75-8.75	4.50-5.50	1.75-2.25	5.50-6.50	.
M-41	1.05-1.15	0.20-0.60	<0.03	<0.03	0.15-0.50	.	3.75-4.50	4.75-5.75	3.25-4.25	1.75-2.25	6.25-7.00	.
M-42	1.05-1.15	0.15-0.40	<0.03	<0.03	0.15-0.65	.	3.50-4.25	7.75-8.75	9.00-10.00	0.95-1.35	1.15-1.85	.
M-46	1.22-1.30	0.20-0.40	<0.03	<0.03	0.40-0.65	.	3.70-4.20	7.80-8.80	8.00-8.50	3.00-3.30	1.90-2.20	.
M-48	1.50	.	.	.	.	.	3.75	9.00	5.25	3.10	10.0	.
M-52	0.90	.	.	.	.	.	4.00	.	4.00	2.00	1.25	.
M-61	1.60	.	.	.	.	.	4.00	.	6.50	5.00	12.0	.
M-62	1.30	.	.	.	.	.	3.75	.	10.5	2.00	6.25	.
O-1	0.85-1.00	1.00-1.40	<0.03	<0.03	<0.50	.	0.40-0.60	.	.	<0.30	0.40-0.60	.
O-2	0.85-0.95	1.40-1.80	<0.03	<0.03	<0.50	.	<0.35	.	<0.30	<0.30	.	.
O-6	1.25-1.55	0.30-1.10	<0.03	<0.03	0.55-1.50	.	<0.30	.	0.20-0.30	.	.	.
O-7	1.10-1.30	<1.00	<0.03	<0.03	<0.60	.	0.35-0.85	.	<0.30	<0.40	1.00-2.00	.
P-20	0.28-0.40	0.60-1.00	<0.03	<0.03	0.20-0.80	.	1.40-2.00	.	0.30-0.55	.	.	.
P-21	0.18-0.22	0.20-0.40	<0.03	<0.03	0.20-0.40	4.00-4.25	0.20-0.30	.	.	0.15-0.25	.	Al: 1.05-1.25
P-6	0.05-0.15	0.35-0.70	<0.03	<0.03	0.10-0.40	3.25-3.75	1.25-1.75	.	.	.	.	.
S-1	0.40-0.55	0.10-0.40	<0.03	<0.03	0.15-1.20	.	1.00-1.80	.	<0.50	0.15-0.30	1.50-3.00	.
S-2	0.40-0.55	0.30-0.50	<0.03	<0.03	0.90-1.20	.	.	.	0.30-0.60	<0.50	.	.
S-4	0.50-0.65	0.60-0.95	<0.03	<0.03	1.75-2.25	.	<0.35	.	.	<0.35	.	.
S-5	0.50-0.65	0.60-1.00	<0.03	<0.03	1.75-2.25	.	<0.35	.	0.20-1.35	<0.35	.	.
S-6	0.40-0.50	1.20-1.50	<0.03	<0.03	2.00-2.50	.	1.20-1.50	.	0.30-0.50	0.20-0.40	.	.
S-7	0.45-0.55	0.20-0.80	<0.03	<0.03	0.20-1.00	.	3.00-3.50	.	1.30-1.80	0.20-0.30*	.	.
T-1	0.65-0.80	0.10-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	.	.	0.90-1.30	17.25-18.25	.
T-15	1.50-1.60	0.15-0.40	<0.03	<0.03	0.15-0.40	.	3.75-5.00	4.75-5.25	<1.00	4.50-5.25	11.75-13.00	.
T-4	0.70-0.80	0.10-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	4.25-5.75	0.40-1.00	0.80-1.20	17.50-19.00	.
T-5	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	3.75-5.00	7.00-9.50	0.50-1.25	1.80-2.40	17.50-19.00	.
T-6	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	4.00-4.75	11.00-13.00	0.40-1.00	1.50-2.10	18.50-21.00	.
T-8	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	4.25-5.75	0.40-1.00	1.80-2.40	13.25-14.75	.
W-1	0.70-1.50	0.10-0.40	<0.025	<0.025	0.10-0.40	<0.20	<0.15	.	<0.10	<0.10	<0.15	Cu: <0.20
W-2	0.85-1.50	0.10-0.40	<0.03	<0.03	0.10-0.40	<0.20	<0.15	.	<0.10	0.15-0.35	<0.15	Cu: <0.20
W-5	1.05-1.15	0.10-0.40	<0.03	<0.03	0.10-0.40	<0.20	0.40-0.60	.	<0.10	<0.10	<0.15	Cu: <0.20

Number	C	Mn	P	S	Si	Ni	Cr	Co	Mo	V	W	Other
--------	---	----	---	---	----	----	----	----	----	---	---	-------

These are specifications,  
not samples for sale.

## STAINLESS AND HIGH ALLOY STEEL SPECIFICATIONS

\* notes optional chemistry

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	N	Nb	Other
13-8PH	<0.05	<0.20	<0.01	<0.008	<0.10	.	7.50-8.50	12.25-13.25	2.00-2.50	<0.01	.	Al: 0.90-1.35
15-5PH	<0.07	<1.00	<0.04	<0.03	<1.00	2.50-4.50	3.50-5.50	14.00-15.50	.	.	0.15-0.45	
17-4PH	<0.07	<1.00	<0.04	<0.03	<1.00	3.00-5.00	3.00-5.00	15.00-17.50	.	.	0.15-0.45	
201	<0.15	5.5-7.5	<0.060	<0.03	<1.00	.	3.50-5.50	16.00-18.00	.	<0.25	.	
202	<0.15	7.5-10.0	<0.060	<0.03	<1.00	.	4.00-6.00	17.00-19.00	.	<0.25	.	
301	<0.15	<2.00	<0.045	<0.03	<1.00	.	6.00-8.00	16.00-18.00	.	.	.	
302	<0.15	<2.00	<0.045	<0.03	<1.00	.	8.00-10.00	17.00-19.00	.	.	.	
302B	<0.15	<2.00	<0.045	<0.03	2.00-3.00	.	8.00-10.00	17.00-19.00	.	.	.	
303	<0.15	<2.00	<0.20	>0.15	<1.00	.	8.00-10.00	17.00-19.00	<0.60*	.	.	Zr: <0.60*
304	<0.08	<2.00	<0.045	<0.03	<1.00	.	8.00-10.50	18.00-20.00	.	.	.	
304L	<0.03	<2.00	<0.045	<0.03	<1.00	.	8.00-12.00	18.00-20.00	.	.	.	
305	<0.12	<2.00	<0.045	<0.03	<1.00	.	10.00-13.00	17.00-19.00	.	.	.	
308	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-12.00	19.00-21.00	.	.	.	
309	<0.20	<2.00	<0.045	<0.03	<1.00	.	12.00-15.00	22.00-24.00	.	.	.	
310	<0.25	<2.00	<0.045	<0.03	<1.50	.	19.00-22.00	24.00-26.00	.	.	.	
314	<0.25	<2.00	<0.045	<0.03	1.50-3.00	.	19.00-22.00	23.00-26.00	.	.	.	
316	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
316	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
316L	<0.03	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
321	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-12.00	17.00-19.00	.	.	.	Ti: >5xC
347	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-13.00	17.00-19.00	.	.	>10xC	
348	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-13.00	17.00-19.00	.	.	>10xC	
384	<0.08	<2.00	<0.045	<0.03	<1.00	.	17.00-19.00	15.00-17.00	.	.	.	Ta: <0.10
385	<0.08	<2.00	<0.045	<0.03	<1.00	.	14.00-16.00	11.50-13.50	.	.	.	
403	<0.15	<1.00	<0.04	<0.03	<0.50	.	.	11.50-13.00	.	.	.	
405	<0.08	<1.00	<0.04	<0.03	<1.00	.	.	11.50-14.50	.	.	.	Al: 0.10-0.30
409	<0.08	<1.00	<0.04	<0.01	<1.00	.	<0.50	10.50-11.75	.	.	.	Ti: 6\mtC-0.75
410	<0.15	<1.00	<0.04	<0.03	<1.00	.	.	11.50-13.50	.	.	.	
414	<0.15	<1.00	<0.04	>0.03	<1.00	.	1.25-2.50	11.50-13.50	.	.	.	
416	<0.15	<1.25	<0.06	>0.15	<1.00	.	.	12.00-14.00	<0.60*	.	.	Zr: <0.60*
420	>0.15	<1.00	<0.04	<0.03	<1.00	.	.	12.00-14.00	.	.	.	
422	0.20-0.25	<1.00	<0.04	<0.03	<0.75	<0.50	0.50-1.00	11.00-12.50	0.75-1.25	.	.	V: 0.15-0.30
422	continued											W: 0.75-1.25
430	<0.12	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	.	.	.	
430F	<0.12	<1.25	<0.06	>0.15	<1.00	.	.	16.00-18.00	<0.60*	.	.	Zr: <0.60*
431	<0.20	<1.00	<0.04	<0.03	<1.00	.	1.25-2.50	15.00-17.00	.	.	.	
440A	0.60-0.75	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
440B	0.75-0.95	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
440C	0.95-1.20	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
450	<0.05	<1.00	<0.03	<0.03	<1.00	1.25-1.75	5.00-7.00	14.00-16.00	0.50-1.00	.	8\mtC	
455	<0.05	<0.50	<0.04	<0.03	<0.50	1.50-2.50	7.50-9.50	11.00-12.50	<0.50	.	0.10-0.50	Ti: 0.80-1.40
501	>0.10	<1.00	<0.04	<0.03	<1.00	.	.	4.00-6.00	0.40-0.65	.	.	
502	<0.10	<1.00	<0.04	<0.03	<1.00	.	.	4.00-6.00	0.40-0.65	.	.	
Duplex	<0.05	<3.00	<0.035	<0.03	<1.50	<2.50*	4.00-7.00	18.00-25.00	0.20-5.50	<0.40	.	

These are specifications,  
not samples for sale.