

INDEX

ALLOY LISTING 24
ALLOY SPECIFICATIONS 25
ALUMINUM BRASS 11
ALUMINUM BRONZE 16, 17, 18

BERYLLIUM ALLOY 4
BISMUTH BRASS 11
BISMUTH BRONZE 18
BRASS 9, 10, 11, 13, 14, 15
BRONZE 15, 16, 17, 18

CARTRIDGE BRASS 11, 12
CHROMIUM COPPER 4
CONVERTER COPPER 5
COPPER 2, 3, 4
COPPER ALLOYS 23
COPPER IN VARIOUS FORMS 2
COPPER WIRE 2

ENVIROBRASS 7

FEDERALLOY 7
FREE CUTTING BRASS 12

GILDING METAL 5
GLOBULE ARC 2
GUN METAL 5

HIGH TENSILE BRASS 15

LEADED BRASS 12, 13
LEADED BRONZE 20, 21, 22
LEADED TIN BRONZE 20, 21, 22

MAGNESIUM ALLOY 5
MANGANESE ALLOY 5
MANGANESE BRASS 13
MANGANESE BRONZE 18

NAVAL BRASS 13
NICKEL ALLOY 6, 7
NICKEL BRASS 14
NICKEL BRONZE 18

PHOSPHOR BRASS 14
PHOSPHOR BRONZE 19
PHOSPHORUS DEOXIDIZED 2

ROD 2, 4, 5, 13, 22

SEBILOY 7
SILICON BRASS 14
SILICON BRONZE 19
SILVER ALLOY 8

TIN BRONZE 20, 21, 22
TIN COPPER 8

WIRE 2

XRF 23

CRM PURITY COPPER DISCS AND RODS

listed in mg/kg IMN in SETS only, as grouped IMN CS: 40mm Ø x 25mm or 6mm Ø x 100mm VS: ~40-45mm Ø x ~25mm

Number	Ag	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	P	Pb	S	Sb	Se	Si	Sn	Te	Zn	Other	
AVAILABLE INDIVIDUALLY																				
VS M04-K3	299	310	124	285	98	115	419	296	551	261	495	70	332	287	93	489	289	293		
VS M04-K2.2	51.5	54.4	33.0	29.2	31.8	23.7	48.3	35.2	59.8	41.1	54.8	34	42.6	37.7	29.7	43	40	50.4		
VS M04-K2.1	50.9	51.9	32.8	29.2	28.2	30.5	56.8	55.1	72.2	41.9	50.3	41	45.9	62.6	.	55	34.9	49.1		
VS M04-7	50.7	50.5	27.6	26.5	30.6	41.3	84.8	53.0	75.6	39.0	26.8	36.6	60.8	.	13.3	45.4	27.0	68.1		
VS M04-5	30.1	11.0	5.2	1.0	1.0	0.8	5.1	6.4	4.4	0.93	1.9	2.9	8.3	6.1	3.1	2.0	2.9	16.9		
VS M04-6	21.0	19.8	10.7	10.0	9.2	11.1	40.4	20.0	32.4	14.0	60	19	22.4	10.6	21	14.6	8	32.4		
VS M04-K1	15.3	16.0	17.4	15.3	15.2	11.7	25.6	17.5	13.7	12.1	22.4	14.5	17.0	10.3	24.9	10.0	9.6	18.0		
VS M04-1	11.2	0.96	.	0.19	.	.	2.0	0.97	0.34	.	1.1	2.9	2.8	3.2	0.7	.	.	.		
VS M04-4	10.4	4.0	2.6	3.1	4.9	3.2	15.4	4.7	16.0	1.1	0.82	3.0	3.5	2.4	2.2	4.8	4.3	7.8		
VS M04-8 *	5.0	2.4	1.1	0.49	3.0	.	29.1	3.5	1.8	1.3	9.6	8.7	5.8	0.73	4.6	0.96	0.8	3.2		
VS M04-3 *	2.9	.	0.11	.	0.30	.	3.9	0.49	0.73	.	4.2	4.4	0.55	.	.	0.48	.	0.97	* SET ONLY	
VS M04-2 *	0.88	0.6	0.63	0.14	0.26	1.0	40.5	1.1	1.1	2.1	13.2	12.8	0.8	0.7	7.1	1.1	.	2.4	* SET ONLY	
AVAILABLE INDIVIDUALLY EXCEPT CS3 WHICH IS SET ONLY																				
IMN CS1	53.1	2.0	1.1	1.0	0.6	(0.3)	18.4	29.0	46.8	57.7	60.5	65.9	3.0	61.5	(3.0)	52.9	2.1	24.1	B:(1.1)	
IMN CS2	45.6	7.4	6.2	7.4	3.6	35.8	30.5	35.3	26.7	33.8	38.6	44.9	7.5	39.0	(9.4)	33.7	5.6	8.9	B:(2.8)	
IMN CS3	38.9	13.8	12.2	13.4	7.4	10.9	28.3	12.6	11.1	12.1	13.3	18.8	13.0	15.4	(22.2)	13.3	10.6	31.3	B:(4.2)	
IMN CS4	237	42.2	39.6	35.5	24.3	7.0	82.0	8.3	7.2	6.3	7.6	41.3	36.8	6.7	(46.5)	6.2	32.9	44.0	B:(21.7)	
IMN CS5	320	70.5	59.7	66.1	37.5	1.0	90.9	4.3	4.4	2.0	5.0	12.0	63.9	0.9	(54.8)	0.9	49.8	101	B:(35.2)	

Number	Ag	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	P	Pb	S	Sb	Se	Si	Sn	Te	Zn	Other
--------	----	----	----	----	----	----	----	----	----	---	----	---	----	----	----	----	----	----	-------

CRM ELECTROLYTIC COPPER ROD SET

available in SET/6 ONLY listed in mg/kg 3 or 6 mm Ø x 100 mm

Number	Ag	As	Bi	Fe	Ni	Pb	Sb	Sn	Zn	Cu
IMN CF1	45.0	6.7	12.5	42.0	29.0	33.0	24.0	21.0	57.0	Rem
IMN CF2	9.0	1.1	.	2.8	0.7	0.6	1.4	.	2.2	Rem
IMN CF3	3.2	1.8	.	20.0	6.4	8.9	2.2	3.2	3.4	Rem
IMN CF4	18.0	43.0	1.2	3.7	7.8	1.1	11.0	1.0	31.0	Rem
IMN CF5	12.0	2.3	0.25	98.0	3.0	3.2	1.9	1.3	4.7	Rem
IMN CF6	12.0	0.32	(0.012)	1.0	(0.4)	1.8	0.2	(0.06)	.	Rem

CRM COPPER

analysis listed in mg/kg 40 mm Ø x 30 mm

Number	Fe	P	Sn
BAM 391	0.90	3.3	(<0.1)
BAM 390	0.79	1.3	(<0.1)
BAM 392	0.80	7.0	(<0.1)

COPPER WIRE FOR GLOBULE ARC WORK

analysis listed in mg/kg wire form, intended for globule arc work ClC: CRM all others: RM 5 rods 3 mm Ø x 80 mm

Number	Ag	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	Pb	Sb	Se	Sn	Te	Zn	O	P	S	Si
38X C1B	13	0.8	0.1	<0.01	0.03	0.06	1.2	1.2	1.0	0.8	0.6	.	<0.3	0.3	0.45	.	.	.	last
38X C1C	11	0.19	0.10	<0.01	.	<0.005	1.7	(0.005)	0.27	(0.05)	0.10	(0.25)	(0.01)	(0.21)	<0.1	266	<0.05	2.0	<0.1

CHILL CAST PHOSPHORUS DEOXIDIZED COPPER

= Class, where 1 = CRM and 2 = RM, typical analysis

#	Number	P	Cu	Ag	Fe	Al	As	Co	Mn	Ni	Pb	Sb	Sn	Zn
2	CURM 09.01	0.151	99.82	0.011	0.0019	<0.0005	<0.001	<0.0003	<0.0003	<0.0003	<0.0005	<0.0005	<0.001	0.0008
2	CURM 09.02	0.078	99.90	0.0055	0.0042	<0.0005	<0.001	<0.0005	<0.0005	<0.0005	<0.001	<0.0005	<0.001	<0.001
1	SRM C1253a	0.0561	99.46	0.0494	0.0290	0.0176	0.0436	0.0454	0.0357	0.0491	0.0243	0.0139	0.0499	0.0329
1	SRM C1251a	0.0420	99.89	0.0080	0.0285	(<0.0020)	0.0016	0.00132	0.00046	0.00236	0.00235	0.00149	0.0016	0.0024
1	SRM C1252a	0.0125	99.87	0.0158	0.0072	(<0.0020)	0.0118	0.0087	0.0043	0.0128	0.0060	0.0042	0.0120	0.00694

Number	Au	Bi	Cd	Cr	Mg	S	Se	Si	Te	Units
CURM 09.01	.	<0.0003	<0.001	.	50 mm Ø x 10-12 mm
CURM 09.02	.	<0.0005	<0.002	.	50 mm Ø x 10-12 mm
SRM C1253a	0.0072	(0.0056)	0.0070	0.0260	(0.0150)	(0.0050)	0.0136	(0.0580)	0.0168	32 mm x 32 mm x 19 mm
SRM C1251a	0.00155	0.00037	(<0.0003)	(0.0003)	(0.0020)	(0.0035)	0.0011	(<0.0050)	0.0016	32 mm x 32 mm x 19 mm
SRM C1252a	0.00339	(0.0019)	0.00169	0.0019	(<0.0020)	(0.0070)	0.0056	(<0.0100)	0.00546	32 mm x 32 mm x 19 mm

CRM COPPER IN VARIOUS FORMS

analysis listed in mg/g each of the blow available in 3 forms A: disc 39 mm Ø x 30 mm B: Rod 8 mm Ø x 100 mm C: Chips 50 g

Number	Ag	Al	As	Au	Be	Bi	Cd	Co	Cr	Fe	Ind	Mg	Mn	Ni	P	Pb	S	Sb	Se	Si	Sn	Te	Ti	Zn	Zr	
ERM-EB075																										
10.8 2.3	3.18	1.46	1.08	1.79	2.69	2.64	1.4	9.3	1.83	7	1.35	2.18	2.59	4.8	25	2.93	1.69	2.6	2.13	1.78	3.2	6.51	.	.		
ERM-EB074																										
1.03 .	1.23	0.52	0.31	0.51	0.4	0.83	0.37	5.8	0.49	2.03	0.93	0.61	1.53	2.7	(3.3)	0.57	0.55	.	(1.5)	0.5	0.97	2.2	(8.8)	.		

COPPER

= class, where 1 = CRM and 2 = RM

39X: ~38-42 mm Ø x ~15-20 mm BS: 38 mm Ø x ~7 or 19+ mm
 BAM, BCR, ERM: 38-40 mm Ø x 27-30 mm CTIF: 40 mm Ø x 18 mm

IARM: 31 mm Ø x 2 or 18 mm
 IMN, VS: 40 mm Ø x 23-27 mm

#	Number	Al	As	Bi	Cd	Co	Cr	Fe	Mg	Mn	Ni	P	Pb	S
1	39X 17869AG	0.0186	0.0104	0.0401	0.0027	0.0084	0.0199	0.0365	0.0103	0.0325	0.0111	0.0245	0.0714	0.0069
1	BAM M376a	(0.0182)	0.0200	0.0200	0.0186	0.0208	(0.0400)	0.0235	(0.0124)	0.0206	0.0209	0.0203	0.0236	(0.0133)
1	39X 17871D	0.0150	.	0.052	0.0027	.	.	0.0019	.	.	0.0412	0.020	0.050	0.0052
1	BAM M385a	0.00133	0.00094	0.000564	0.000275	0.00074	0.00104	0.00442	(0.0032)	0.00099	0.00108	0.00100	0.00108	(0.00354)
1	39X 17870AJ	0.0047	0.0056	0.0476	0.0029	0.0042	0.0009	0.0416	0.020	0.0387	0.0079	0.0203	0.047	0.0037
1	39X 17866AH	0.0028	0.0435	0.0109	0.0410	0.0273	0.0316	0.0075	0.0041	0.0147	0.0511	0.0125	0.0501	0.052
1	BAM M386a	0.00269	0.00208	0.00095	0.00054	0.00049	0.00115	0.00593	0.00767	0.00111	0.00211	0.00065	0.00198	0.00159
1	IARM 279A	(0.002)	(0.002)	(0.001)	.	(0.002)	0.86	0.025	.	(0.002)	0.014	(0.005)	(0.01)	0.0015
1	BS Cu997	(0.002)	(0.0008)	.	.	(0.001)	(0.0003)	0.0032	(0.0005)	(0.001)	0.0004	0.0055	0.0008	(0.006)
1	IARM 278A	<0.002	(0.001)	(0.001)	.	(0.001)	(0.001)	0.004	.	(0.0004)	<0.005	0.011	(0.003)	0.002
1	IARM 70C	(0.0014)	(0.0009)	(0.002)	(0.0008)	(0.0014)	(0.0002)	(0.0016)	(0.0003)	(0.0002)	(0.0004)	(0.0014)	(0.0013)	0.0008
1	BAM 370	0.00126	0.00117	0.0016	.
1	39X 17867AE	0.0012	0.039	0.012	0.0061	0.0126	.	0.0097	0.0053	0.0016	0.0394	0.0242	0.0097	0.024
1	BAM M383d	0.00102	<0.0001	0.000082	0.000062	0.000130	0.000077	0.00224	0.00017	0.000097	0.00047	<0.0001	0.00078	0.00035
1	BS 110C	(0.0009)	(0.0001)	.	.	(0.001)	(0.0004)	(0.002)	(0.0005)	(0.0004)	(0.0005)	0.0016	(0.0003)	0.0008
1	BS 14500A	(0.0007)	.	Ca:(0.0004)	N:(0.0006)	(0.0005)	.	(0.001)	(0.00006)	(0.0004)	0.0026	0.010	0.0031	0.035
1	BS 14500	(<0.0006)	(<0.0005)	.	.	(<0.0001)	(<0.0001)	0.0041	(<0.0003)	0.00004	(<0.0003)	0.0075	0.0008	0.0033
1	BAM M384b	(0.00029)	0.00066	0.000681	0.00040	0.00104	(0.00023)	(0.00051)	0.00033	0.00081	0.00047	<0.0002	0.00016	(0.00038)
1	BAM M383b	<0.0002	0.00028	0.000185	0.000093	0.000102	<0.0001	0.00036	<0.0001	0.000018	0.000143	<0.0001	0.000101	(0.00036)
1	BS 110B	<0.0002	<0.0001	.	.	<0.0001	<0.0001	0.0005	<0.0001	<0.0001	<0.0002	<0.0006	0.00052	0.00030
1	BAM M382a	<0.0002	0.000073	0.000075	0.000050	0.000092	0.000024	0.00103	0.00019	0.00025	0.00027	<0.0002	0.00022	0.00067
1	39X 27866A	.	0.0383	0.0047	0.0139	0.0308	0.0012	0.0030	.	.	0.0487	0.0147	0.0054	0.0469
1	39X 27869A	.	0.0098	0.0376	0.0028	0.0036	(0.002)	0.0030	.	.	0.0190	0.0119	0.0225	0.0112
1	IMN CS5	.	0.00705	0.00597	0.00661	0.00375	0.00010	0.00909	.	0.00043	0.00044	0.00020	0.00050	0.00120
1	IMN CP5	.	0.0065	0.00094	0.00025	0.0034	0.0048	0.0077	.	0.0049	0.0039	0.0110	0.0013	0.0021
1	IMN CT6	.	0.0054	0.0040	.	0.011	.	0.014	.	.	0.011	0.011	0.0014	0.0069
1	IMN CS4	.	0.00422	0.00396	0.00355	0.00243	0.00070	0.00820	.	0.00083	0.00072	0.00063	0.00076	0.00413
1	IARM Cu101-18	.	0.00015	0.00005	.	.	.	0.00030	.	0.00003	0.00027	.	0.00012	0.00050
1	IARM Cu110-18	.	0.00013	.	.	.	(0.00009)	0.00034	0.00010	0.00006	(0.00006)	0.00160	(0.00005)	0.00060
1	BAM 372	.	0.00103	.	0.000163	0.00114	0.0012	.	.	.
1	IMN CS2	.	0.00074	0.00062	0.00074	0.00036	0.00358	0.00305	.	0.00353	0.00267	0.00338	0.00386	0.00449
1	IMN CS1	.	0.00020	0.00011	0.00010	0.00006	(0.00003)	0.00184	.	0.00290	0.00468	0.00577	0.00605	0.00659
1	IMN CS7 D	.	0.00009	<0.00005	(0.000002)	0.000009	0.00197	0.00049	.	0.00022	0.00044	(0.00024)	(0.00009)	0.00070
1	IMN CP6	.	0.000085	.	.	<0.0001	0.00003	0.00064	.	0.00006	0.00027	0.00017	0.00027	0.00075
1	IMN CS6	.	0.00002	<0.00005	(0.000006)	(0.00002)	0.00002	0.00208	.	0.00007	0.00008	(0.00015)	(0.00004)	0.00054
1	BAM 381	.	<0.0001	<0.0001	<0.00004	<0.00004	0.000013	0.00028	(0.000034)	0.000027	0.000073	.	0.00005	(0.00029)
1	BAM 369	.	.	0.00097	.	0.00104	0.00092	.	0.00036
1	BAM 371	0.0018	0.0013

Number Al As Bi Cd Co Cr Fe Mg Mn Ni P Pb S
 continued analysis listed in mass % except * which is mg/kg

Number	Sb	Se	Si	Sn	Te	Ti	Zn	Zr	Ag*	Au*	C*	Be*	Cu	In*	O*	Other
39X 17869AG	0.0375	0.0197	0.0117	0.070	0.0392	.	0.0261	.	399	22	Ge: 0.0047	.	26	.	.	.
BAM M376a	0.0202	0.0210	.	0.0247	0.0215	(0.00045)	0.0217	0.00422	163	.	(41)
39X 17871D	0.0141	0.0310	0.0014	0.105	0.0137	.	0.091	.	309	5	.	.	32	.	.	Ge*: (9)
BAM M385a	0.00149	0.00050	0.00073	0.00161	0.00081	0.00066	0.00092	(0.0018)	254
39X 17870AJ	0.0490	0.0111	0.0048	0.0100	0.040	.	0.0125	.	480	7	Ge: 0.0149	.	100	.	.	.
39X 17866AH	0.0095	0.0053	0.0111	0.0614	0.0065	.	0.0840	.	86	(4)	Ge: 0.0052	.	97	.	.	.
BAM M386a	0.00252	0.00097	(0.0012)	0.00216	0.00311	0.00347	0.00367	.	44.2
IARM 279A	(0.004)	.	0.020	0.021	.	.	(0.01)	0.012	(30)	.	(20)	.	99.1	(10)	XRF only	.
BS Cu997	(0.0002)	.	(0.0009)	0.0003	.	17025	0.0006	(0.007)	.	.	7	.	99.7	39	17025	.
IARM 278A	<0.005	.	(0.002)	(0.001)	0.53	.	(0.002)	.	(10)	.	(30)	.	99.5	(4)	.	.
IARM 70C	(0.003)	(0.001)	(0.0006)	0.0005	(0.001)	.	(0.002)	(0.001)	99.94	<1	.	.
BAM 370	0.0015	.	(0.0019)	0.00165
39X 17867AE	0.013	0.0061	0.0081	0.043	0.0072	B:0.0042	0.0381	.	148	11	Ge:0.0104	.	45	.	.	.
BAM M383d	0.00018	(0.00006)	.	0.00038	0.000047	0.00012	0.000108	<0.0001	.	As*:1.20
BS 110C	(0.0003)	.	(0.0009)	(0.0002)	.	17025	(0.004)	.	.	(20)	.	.	99.97	9	Ca*: (2)	.
BS 14500A	(0.005)	.	(0.002)	0.0028	0.51	17025	0.0053	(0.001)	.	(30)	.	.	99.6	17	.	.
BS 14500	(<0.001)	.	(<0.002)	0.0002	0.53	17025	0.004	.	(<2)	5	(<1)	.	99.4	7	.	.
BAM M384b	0.00058	(0.00029)	<0.0003	0.00021	0.00072	0.00029	0.00026	0.00013	11.3	(0.15)	.	.
BAM M383b	0.000169	0.000117	<0.0002	0.00008	0.00057	<0.0001	0.00093	<0.0001	106	(0.41)	last	.
BS 110B	<0.0005	.	<0.0004	<0.0002	<0.0002	17025	<0.0003	.	<2	.	7	<1	99.94	363	.	.
BAM M382a	0.000087	0.000077	.	0.00047	0.000072	0.000057	0.00076	29
39X 27866A	0.0052	0.0028	.	0.0448	0.0032	.	0.0287	.	57	16	.	.	437	.	Ge*: 29	.
39X 27869A	0.0362	0.0127	.	0.0106	0.0153	.	0.0065	.	349	80	.	.	90	.	Ge*: 123	.
IMN CS5	0.00639	0.00009	(0.00548)	0.00009	0.00498	.	0.0101	.	320	B*: (35.2)	.
IMN CP5	0.0027	0.0035	(0.0082)	0.00021	0.00078	.	0.0038	.	31	.	.	Rem	.	last	.	.
IMN CT6	0.011	0.011	.	0.013	0.012	.	0.030	.	39	B*: 60	.
IMN CS4	0.00368	0.00067	(0.00465)	0.00062	0.00329	.	0.00440	.	237	B*: (21.7)	.
IARM Cu101-18	0.00014	.	.	0.00020	.	.	0.00008	.	13.0
IARM Cu110-18	.	(0.00020)	.	(0.00020)	.	.	0.00010	.	13.0	.	(18)	.	.	10.0	.	.
BAM 372	.	0.00076
IMN CS2	0.00075	0.00390	(0.00094)	0.00337	0.00056	.	0.00089	.	45.6	B*: (2.8)	.
IMN CS1	0.00030	0.00615	(0.00030)	0.00529	0.00021	.	0.00241	.	53.1	B*: (1.1)	.
IMN CS7 D	0.00010	<0.00010	<0.00010	0.00005	<0.000005	.	0.00012	.	13.7	B*: <0.5	.
IMN CP6	0.00004	<0.0001	.	0.00007	.	.	0.00014	.	20	.						

CRM COPPER RODS analysis listed in mg/kg IMN: 6 mm Ø x 100 mm SRM: ~6.5 mm Ø x 103 mm

Number	Ag	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	O	P	Pb	S	Sb	Se	Sn	Te	Zn	Cu
SRM 494	50	2.6	0.35	.	0.5	2.0	.	3.7	11.7	.	.	26.5	15	4.5	2.00	70	0.58	400	99.91
IMN CS7R	13.7	0.9	<0.5	(0.02)	0.09	19.7	4.9	2.2	4.4	.	(2.4)	(0.9)	7.0	1.0	<1.0	0.5	<0.05	1.2	.
SRM 495	12.2	1.6	0.50	.	.	6.0	.	5.3	5.4	.	.	3.2	13	8.0	0.63	1.5	0.32	12	99.94
SRM 457	8.086	<2	0.22	<1	0.227	<2	2.4	<0.1	0.67	367	.	0.512	4	0.214	4.05	<0.1	0.296	<3	99.97

SRM 457 also contains Au:<0.05), Cd Si and Ti:<1) IMN CS7R also contains B:<0.5 and Si:<1.0

BERYLLIUM ALLOY

= class, where 1 = CRM and 2 = RM

17025

#	Number	Be	Co	Ag	Al	Cr	Cu	Fe	Ni	Pb	Si	Sn	Zn	Alloy	Notes
2	CTIF 4584	2.53	0.04	.	0.033	.	97.05	0.120	0.015	(0.002)	0.166	0.022	0.022		Typical Analysis
2	CTIF 4872	1.93	0.400	.	0.059	(0.04)	97.00	0.107	0.103	0.019	0.16	0.044	0.119	172	Typical Analysis
2	BS 172Be-1	1.89	0.206	.	(0.02)	0.0032	97.68	0.052	0.039	(0.002)	0.055	0.033	0.0070	172	last of stock
1	IARM Cu172-19	1.89	0.0017	0.0011	0.032	0.0017	(97.6)	0.071	0.237	.	0.045	0.0007	.	172	
1	36X CBC4E	1.869	0.215	.	0.0258	.	97.47	0.0274	0.0080	0.329	0.048	0.002	0.003	173	
1	36X CBC3D	1.840	0.209	.	0.019	.	97.77	0.046	0.007	0.0025	0.039	0.0021	0.004		
1	BS 172Be-2	1.83	(0.06)	.	0.032	0.015	97.7	0.127	0.165	0.041	(0.029)	0.015	0.0057	172	17025
2	CTIF 4766	1.58	0.64	.	0.027	(0.2)	96.83	0.165	0.203	0.053	0.11	0.100	0.070		Typical Analysis
2	CTIF CuBeCo6	1.54	(1.9)	1.37	0.135	0.0576	93.09	0.109	(1.4)	0.0397	0.26	0.0135	0.0330		Typical Analysis
2	CTIF 4583	0.84	(0.002)	.	0.029	.	96.35	(0.15)	2.02	0.084	0.08	0.25	0.094		Typical Analysis
1	36X CBC6A	0.507	1.045	0.0015	0.0490	.	97.11	0.0243	1.132	0.0014	0.0263	0.0041	0.0010		
1	36X CBC2F	0.439	2.22	0.0013	0.0097	.	97.15	0.0076	0.121	(0.0008)	0.0257	(0.0007)	0.0018		
1	BS 17500	0.43	2.31	(0.0012)	0.0210	0.0015	(97.1)	0.0262	0.095	0.0005	0.0641	(0.0002)	0.065	175	17025 , last
1	36X CBC5B	0.404	0.0084	0.0011	0.0104	.	97.61	0.0108	1.905	0.0015	0.004	0.0013	0.0010	175.1	
1	BS 17510	0.35	(0.024)	0.0014	0.042	(0.015)	97.6	0.042	1.70	0.0014	0.137	(0.004)	(0.005)	175.1	
2	CTIF 4873	0.10	0.86	.	0.069	0.080	98.60	0.135	0.050	(0.003)	0.071	(0.007)	(0.003)		Typical Analysis

w = wrought and c = cast; D = disc and M = mushroom

Number	As	C	Ca	Mg	Mn	O	P	S	Sb	Te	Zr	Form	Units
CTIF 4584	(0.002)	c	M 60 mm Ø x 5 mm
CTIF 4872	0.008	c	M 60 mm Ø x 5 mm
BS 172Be-1	(0.001)	(0.001)	.	.	0.0010	.	0.003	<0.0002	.	.	.	w	D 38 mm Ø x ~7 mm
IARM Cu172-19	.	.	.	0.112	0.0019	.	0.0036	0.0010	0.0007	.	.	w	D ~38 mm Ø x ~3 or ~19 mm
36X CBC4E	.	.	.	0.0035	.	.	0.0027	w	D ~38 mm Ø x ~15 mm
36X CBC3D	.	.	.	0.0040	w	D 41 mm Ø x 15 mm
BS 172Be-1	(0.00014)	(0.002)	(0.0008)	(0.01)	0.0070	(0.0008)	0.0014	(0.0003)	.	last	(0.0003)	w	D 38 mm Ø x ~7 or ~10 mm
CTIF 4766	0.007	c	M 60 mm Ø x 5 mm
CTIF CuBeCo6	0.0173	c	M 60 mm Ø x 5 mm
CTIF 4583	0.064	c	M 60 mm Ø x 5 mm
36X CBC6A	.	.	.	0.0070	.	.	0.0016	.	.	.	0.0553	w	D ~40 mm Ø x ~15 mm
36X CBC2F	.	.	.	0.0036	.	.	0.0067	0.001	.	.	(0.0006)	w	D ~40 mm Ø x ~15 mm
BS 17500	(0.0002)	0.0020	0.0054	0.0076	0.081	(0.0005)	0.0031	(0.0001)	0.0001	(0.0004)	.	w	D 38 mm Ø x ~10 mm last
36X CBC5B	.	.	.	0.0009	w	D ~40 mm Ø x ~15 mm
BS 17510	<0.005	(0.003)	<0.005	(0.007)	0.0020	.	(0.005)	<0.05	0.0024	.	0.0011	c	D 38 mm Ø x ~7 or 19+ mm
CTIF 4873	(0.002)	c	M 60 mm Ø x 5 mm

CHROMIUM COPPER

= class, where 1 = CRM and 2 = RM

#	Number	Cr	Ag	Al	Fe	Mn	Ni	Pb	Si	Sn	Zn	Zr	Cu
1	IARM Cu182-18	1.09	0.0008	0.0031	0.041	0.0007	0.0007	0.0019	(0.09)	(0.002)	0.010	0.063	98.8
1	IARM 158C	1.04	(0.01)	0.002	0.090	0.019	0.32	0.01	0.02	0.01	0.014	.	98.5
1	IARM 158B	0.85	(0.01)	0.002	0.090	0.019	0.32	0.01	0.02	0.01	0.014	.	98.5
1	BS 18150A	0.79	.	0.0023	0.007	0.0010	0.0019	0.0011	0.027	0.0144	0.0006	0.203	[98.9]
1	BS 18150	0.74	.	0.0009	0.0047	0.0010	0.0010	0.0005	0.019	0.0097	0.0006	0.113	[99.1]
2	HRT CU2019	0.73	.	.	(0.005)	.	.	.	0.030	0.011	.	0.17	98.97
1	36X 274B	0.333	0.0016	0.0011	0.0165	0.0004	2.59	0.0011	0.645	(0.0008)	(0.0009)	.	96.44

Number	As	C	Co	Mg	N	O	P	S	Sb	Units
IARM Cu182-18	.	.	0.00013	0.0019	.	.	0.0012	0.0018	.	38 mm Ø x 3 or 19 mm
IARM 158C	(0.001)	0.002	0.002	.	<0.0005	0.002	0.005	0.003	0.002	31 mm Ø x 2 or 18 mm
IARM 158B	(0.001)	0.002	0.002	.	<0.0005	0.002	0.005	0.003	0.002	31 mm Ø x 2 mm
BS 18150A	(0.0003)	0.0010	(0.0003)	.	.	(0.0008)	0.0045	0.0007	(0.0002)	38 mm Ø x ~7 or 19+ mm
BS 18150	(0.0004)	0.0009	(0.0002)	.	.	(0.0006)	0.0037	0.0007	(0.0001)	38 mm Ø x ~7 or 19+ mm
HRT CU2019	(0.005)	.	(0.006)	40 mm Ø x 20 mm
36X 274B	.	.	0.0042	.	.	.	0.0015	.	.	~40 mm Ø x ~15 mm

17025
17025

Need a larger size?
Most BS items are
available in any height.

CRM CONVERTER COPPER DISC AND ROD SETS

analysis listed in mass %

AVAILABLE IN SETS ONLY, AS GROUPED

10 mm Ø x 100 mm

Number	Ag	As	B	Bi	Co	Cu	Fe	Ni	P	Pb	S	Sb	Se	Sn	Te	Zn
IMN CT1	0.057	0.32	0.024	0.018	0.051	.	0.17	0.48	0.082	0.013	0.054	0.33	0.062	0.24	0.053	0.28
IMN CT2	0.042	0.22	0.033	0.013	0.033	.	0.10	0.29	0.059	0.086	0.036	0.24	0.041	0.14	0.036	0.19
IMN CT3	0.026	0.11	0.00093	0.0067	0.013	.	0.083	0.12	0.038	0.31	0.012	0.11	0.018	0.070	0.022	0.11
IMN CT4	0.016	0.050	0.0042	0.0043	0.011	.	0.045	0.049	0.020	0.88	0.0060	0.049	0.011	0.025	0.011	0.045
IMN CT5	0.0062	0.0056	(0.011)	0.0011	0.0061	.	0.016	0.0095	0.0059	(1.48)	0.0024	0.010	0.0069	0.0070	0.0064	0.0098
IMN CH6	0.18	.	.	.	0.18	Rem	0.028	0.40	.	0.50	0.19
IMN CH7	0.40	.	.	.	0.11	Rem	0.11	0.18	.	1.01	0.047
IMN CH8	0.039	.	.	.	0.020	Rem	0.0012	0.036	.	1.49	0.077
IMN CH9	0.010	.	.	.	0.0060	Rem	0.0060	0.010	.	1.97	0.015
IMN CG1	0.011	.	.	.	0.17	Rem	0.013	0.036	.	0.60	0.016
IMN CG2	0.25	.	.	.	0.098	Rem	0.015	0.011	.	0.30	0.026
IMN CG3	0.040	.	.	.	0.045	Rem	0.030	0.39	.	0.22	0.14
IMN CG4	0.10	.	.	.	0.057	Rem	0.25	0.23	.	0.11	0.12
IMN CG5	0.41	.	.	.	0.0079	Rem	0.069	0.10	.	0.053	0.18

CRM GILDING METAL

Number	Cu	Fe	Ni	P	Pb	Sn	Zn	method	Units
SRM 1114	96.4	0.01	0.021	0.009	0.012	0.02	3.4	wrought	31 mm Ø x 19 mm
SRM 1113	95.0	0.04	0.057	0.008	0.026	0.06	4.8	wrought	31 mm Ø x 19 mm
SRM 1112	93.3	0.07	0.10	0.009	0.057	0.12	6.3	wrought	31 mm Ø x 19 mm

CRM GILDING METAL SET

available individually or as a set

wrought 40 mm Ø x 25 mm

Number	Ag	Al	As	Be	Bi	Cd	Cu	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Te	Zn
IMN MI1	0.0038	0.0400	0.0720	0.000091	0.00063	0.0230	95.69	0.2500	0.0030	0.0059	0.0280	0.0060	0.0430	0.000044	0.0032	0.1500	0.0065	3.57
IMN MI2	0.0090	0.0550	0.0540	0.00085	0.00056	0.0160	93.35	0.1600	0.0081	0.0180	0.0220	0.0160	0.0490	0.0019	0.0120	0.1000	0.0110	6.19
IMN MI3	0.0200	0.0150	0.0340	0.0019	0.0026	0.0110	91.46	0.0860	0.0350	0.0730	0.0150	0.0420	0.0230	.	0.0310	0.0670	0.0031	8.01
IMN MI4	0.0260	0.0079	0.0031	0.0065	0.0026	0.0054	88.35	0.0410	0.0500	0.1400	0.0073	0.0700	0.0120	0.0006	0.0600	0.0130	0.0021	11.13
IMN MI5	0.0330	0.0021	0.0150	0.0072	0.0043	0.0012	94.71	0.0150	0.0690	0.2500	0.0026	0.0960	0.0019	0.0096	0.0820	0.0040	.	4.44

GUN METAL

C, CURM: 50 mm Ø x 10 - 12 mm

33X GM29: wrought 33 mm Ø x 19 mm

other 33X: chill cast ~40 mm Ø x ~15 mm

Number	Zn	Sn	Pb	Ni	Fe	Cu	Ag	Al	As	Bi	Co	Cr	Mn	P	S	Sb	Si
CRM																	
33X GM9A	13.81	2.93	6.91	0.710	0.090	75.1	0.0321	0.0052	0.0251	0.076	0.079	Cd:0.0072	.	0.0547	0.0153	0.184	(0.003)
33X GM4AD	5.90	3.02	5.27	1.482	0.0932	84.02	0.0206	0.0015	0.0228	0.0442	0.0077	.	0.00060	0.0034	0.034	0.0568	0.0010
33X GM8H	5.80	3.89	5.76	0.493	0.142	83.63	0.095	0.0052	0.0110	0.016	0.0151	0.0150	.	0.035	0.028	0.061	(0.003)
33X GM5P	5.66	4.48	5.18	0.728	0.127	83.39	0.0497	0.055	0.0498	0.018	0.0298	Cd:0.0048	Te:0.0075	0.0507	0.0411	0.072	0.0310
33X GM21B	4.96	4.50	7.53	0.197	0.693	78.86	0.701	0.173	0.333	0.459	Se:0.173	Cd:0.249	.	0.0697	0.0628	1.033	0.0213
33X GM20B	1.80	4.49	0.294	0.211	0.44	89.49	0.200	0.133	0.300	0.044	0.0211	Cd:0.020	0.040	0.060	.	2.41	.
33X GM7K	1.363	10.07	1.79	0.531	0.0178	85.69	0.0682	.	0.095	0.098	0.100	.	.	0.0050	0.0613	0.111	Te:0.0112
RM																	
CURM 71.31	4.27	4.38	6.44	2.07	0.098	82.30	0.052	0.045	0.11	0.027	last	<0.01	0.010	0.060	0.050	0.11	0.006
33X GM24A	3.67	3.85	3.35	0.0087	0.0083	88.88	0.0046	(0.0001)	0.0010	0.0009	.	(0.0013)	<0.0005	0.190	0.003	0.0012	0.0028
CURM 71.33	3.60	4.96	6.84	0.938	0.018	83.60	<0.002	<0.001	<0.001	<0.002	.	<0.0005	<0.0005	<0.001	<0.001	<0.002	<0.005
C71.34	1.55	8.20	2.47	<0.01	0.29	rem	0.025	0.007	0.18	0.029	last	0.03	0.05	0.020	0.16	0.071	0.04
CURM 71.34	1.54	8.19	2.48	<0.005	0.29	86.74	0.023	0.008	0.18	0.031	.	0.04	0.05	0.019	0.18	0.072	0.03

CRM MANGANESE ALLOY SET

available individually or as a set

40 mm Ø x 13 mm

Number	Ag	As	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn
IMN CK1	0.012	0.013	0.029	1.06	0.44	0.0011	0.0021	0.0049	0.049	0.13	0.24
IMN CK2	0.0094	0.010	0.11	1.51	0.38	0.0022	0.0062	0.0015	0.091	.	0.14
IMN CK3	0.0066	0.0095	0.17	1.78	0.27	0.0043	0.0098	0.0026	0.033	0.075	0.095
IMN CK4	0.0041	0.0055	0.26	1.91	0.13	0.0056	0.017	0.0041	0.0025	0.042	0.065
IMN CK5	.	0.0015	0.29	2.30	0.011	.	.	0.0051	0.011	0.0048	0.033
IMN CK6	0.0012	0.0039	0.40	2.64	0.073	0.013	.	0.0052	0.21	0.025	0.034

CRM MAGNESIUM ALLOY SET

available in set only 40 mm Ø x 25 mm

Number	Mg
IMN CCB-1	0.00405
IMN CCB-2	0.0339
IMN CCB-3	0.241
IMN CCB-4	0.509
IMN CCB-5	0.748

NICKEL ALLOY, chart 1 of 2

#	Number	Ni	Ag	Al	Bi	Co	Cr	Cu	Fe	Mn	Nb	P	Pb	S	Si	Sn	Zn
1	IARM 85C	31.3	<0.002	<0.01	.	0.016	0.002	67.3	0.63	0.65	.	(0.003)	0.004	(0.002)	0.01	0.005	0.057
1	36X 71500A	31.24	.	(0.001)	.	0.0163	.	66.74	0.888	0.850	.	0.0074	0.0114	0.0454	0.0096	0.0112	0.150
1	BS 715B	31.2	.	(0.0060)	.	(0.012)	(0.003)	67.3	0.59	0.745	.	0.0034	(0.003)	0.0034	0.0103	0.0036	0.053
1	BS 715C	31.2	.	(0.004)	.	(0.012)	(0.003)	67.4	0.59	0.706	.	0.0035	(0.003)	0.0036	0.011	0.0040	0.052
1	36X CN5P	31.03	.	.	.	0.0238	0.141	66.67	0.347	0.217	0.430	0.034	0.0120	0.088	0.689	0.0090	0.209
1	IARM Cu715-20	31.0	.	(0.004)	.	(0.004)	.	67.4	0.51	0.80	.	(0.009)	(0.001)	(0.002)	(0.09)	(0.004)	(0.007)
1	SRM 1276a	30.8	(0.004)	.	(<0.0001)	0.045	(0.0002)	67.5	0.56	1.01	.	0.006	0.004	(0.008)	(0.001)	0.023	0.038
2	BS 715A	30.22	.	(0.01)	.	.	.	68.0	0.61	0.82	.	0.006	(0.007)	0.001	0.10	0.008	0.10
1	IARM 236A	30.0	.	0.003	0.003	0.004	0.002	66.7	0.91	1.04	0.92	0.003	0.004	0.003	0.19	0.005	0.002
2	C62.11	29.8	.	.	.	<0.005	.	rem	0.60	0.52	.	.	<0.005	<0.005	0.36	0.04	0.097
2	CTIF CN33	29.75	.	(0.0105)	0.0212	.	.	66.95	1.66	0.490	0.062	0.021	0.053	0.013	0.500	(0.003)	0.385
1	36X CN8J	28.94	.	(0.030)	0.0518	0.121	1.38	65.78	1.65	0.951	0.585	0.019	0.037	0.0119	0.309	0.0502	0.107
1	C62.15	25.9	.	.	.	0.042	.	rem	2.36	0.23	.	.	0.016	0.023	0.014	0.03	0.04
1	36X CN4L	25.58	0.0093	0.040	0.0096	0.0305	0.0273	72.09	0.548	0.529	0.461	0.0140	0.0193	0.0075	0.448	0.0093	0.164
1	BAM 389	24.7	.	.	0.0044	0.0770	0.0153	74.3	0.107	0.415	.	0.0093	0.0098	.	.	0.0262	0.1125
2	C62.14	20.2	.	.	.	0.03	.	rem	1.49	0.24	.	.	0.01	0.083	0.022	0.12	0.12
1	IARM 298A	19.6	(0.009)	(0.003)	0.014	(0.016)	(0.005)	65.3	0.73	0.34	<0.01	(0.004)	4.0	(0.011)	0.019	4.0	5.8
1	C65.29	16.8	58.9	0.39	0.17	.	0.07	0.11	0.07	0.02	0.08	23.4
1	36X CN24A	15.41	0.0466	(0.0010)	.	0.0096	0.0065	52.56	0.127	23.60	.	0.0037	0.0056	.	.	(0.0023)	8.00
2	C65.28	15.3	56.9	0.13	0.57	.	0.07	0.06	0.03	0.01	0.15	26.7
1	36X CN11A	14.96	.	1.457	.	0.0049	0.380	77.56	0.992	4.34	0.124	(0.002)	(0.003)	0.0012	0.083	(0.002)	(0.006)
1	IARM CuH130-18	14.6	(0.0010)	2.76	(0.0020)	0.0037	(0.002)	80.9	0.84	0.449	.	(0.004)	(0.0020)	(0.0010)	0.024	(0.0010)	0.0015
1	36X CN13A	14.52	.	2.65	.	(0.001)	.	81.46	0.870	0.442	.	0.0011	(0.001)	(0.002)	0.012	(0.001)	0.0017
1	IARM CuH191-18	14.5	(0.0020)	1.60	(0.0020)	(0.002)	(0.0013)	(79.6)	0.96	3.79	.	(0.003)	(0.0030)	(0.002)	(0.017)	(0.0020)	0.0010
1	36X CN23A	14.38	0.042	0.007	.	0.0509	0.0029	70.22	0.140	0.0095	.	0.0299	0.115	.	.	0.102	14.88
2	C65.27	13.9	57.0	0.26	0.13	.	0.02	0.04	0.03	<0.002	0.01	28.7
1	36X CN12A	13.05	.	2.41	.	0.0056	.	83.79	0.105	0.402	0.0010	0.0011	0.0037	.	0.040	(0.0011)	0.157
1	CTIF CN1	12.3	.	(0.003)	.	.	.	85.0	1.1	0.8	(0.1)	.	0.0055	0.046	(0.05)	(0.005)	0.2
1	36X CN2K	11.45	0.0274	0.0009	.	0.197	0.0043	86.25	0.0404	(0.69)	0.0176	0.0408	0.0449	0.0100	0.049	0.0258	1.03
2	CTIF CN4	11.2	.	(0.02)	.	.	.	84.0	1.8	1.5	0.7	.	0.006	(0.001)	(0.01)	0.058	0.07
2	BS 706B	10.9	.	<0.003	.	0.005	.	87.00	1.56	0.61	.	0.009	0.006	0.009	<0.002	0.006	0.054
1	36X 70600A	10.65	0.0055	(0.0008)	.	0.0087	.	86.70	1.619	0.759	.	0.0062	0.0086	0.0136	.	0.0090	0.115
2	HRT CU2014	10.49	86.96	1.60	0.82	.	.	(0.005)	.	.	(0.005)	(0.01)
2	BS 706A	10.18	.	(0.002)	.	0.007	.	87.80	1.30	0.66	.	0.006	0.008	0.012	<0.005	0.011	0.13
2	CTIF CuNi 10	10.08	87.4	1.69	0.70	.	.	0.0027	(0.002)	.	(<0.01)	0.033

#	Number	Ni	Ag	Al	Bi	Co	Cr	Cu	Fe	Mn	Nb	P	Pb	S	Si	Sn	Zn
	Number	As	B	Be	C	Cd	Mg	Sb	Te	Ti	Zr	Units					
	IARM 85C	0.0009	.	.	0.008	.	0.01	31 mm Ø x 2 mm				
	36X 71500A	.	0.0049	.	0.0240	~40 mm Ø x ~15 mm				
	BS 715B	(0.001)	.	(0.0002)	0.0089	.	.	(0.001)	0:0.0020	(0.0002)	.	(0.0002)	38 mm Ø x ~7 or 19+ mm	17025			
	BS 715C	(0.001)	.	(0.0002)	0.0081	.	(0.005)	(0.0014)	0:0.0020	(0.001)	.	(0.001)	38 mm Ø x ~7 or 19+ mm	17025	Ca: (0.00005)		
	36X CN5P	.	0.0053	0.0035	(0.008)	.	0.0106	.	.	0.0203	.	.	~40 mm Ø x ~15 mm				
	IARM Cu715-20	.	.	.	(0.005)	.	(0.005)	.	.	0.073	.	.	31 mm Ø x 2 or 18 mm				
	SRM 1276a	(<0.001)	(0.0001)	.	.	0.0002	0.12	0.0004	0.005	(0.0002)	.	.	32 mm Ø x 19 mm	Se: 0.0005			
	BS 715A	(0.0014)	.	.	0.03	.	.	(0.003)	38 mm Ø x ~7 or 19+ mm				
	IARM 236A	.	.	.	0.010	.	.	<0.005	31 mm Ø x 2 or 18 mm	N: 2ppm, O: 0.002			
	C62.11	0.03	50 mm Ø x 10 - 12 mm				
	CTIF CN33	.	.	.	0.025	0.0060	0.043	.	0.0224	.	.	.	60 mm Ø x 5 mm				
	36X CN8J	.	0.005	.	0.013	(0.038)	.	.	~40 mm Ø x ~15 mm				
	C62.15	0.004	50 mm Ø x 10 - 12 mm				
	36X CN4L	.	.	.	(0.005)	.	0.008	~40 mm Ø x ~15 mm				
	BAM 389	0.0016	0.067	0.0046	.	0.0660	0.098	.	40 mm Ø x 30 mm				
	C62.14	0.002	50 mm Ø x 10 - 12 mm				
	IARM 298A	(0.004)	<0.005	<0.001	(0.013)	<0.001	0.0004	(0.04)	<0.005	.	<0.01	.	31 mm Ø x 2 or 18 mm				
	C65.29	0.01	50 mm Ø x 10 - 12 mm				
	36X CN24A	(0.0011)	.	.	0.0436	~17 mm Ø x ~17 mm				
	C65.28	0.01	50 mm Ø x 10 - 12 mm				
	36X CN11A	.	.	.	(0.001)	.	0.0241	40 mm Ø x ~17 mm				
	IARM CuH130-18	(0.0060)	(0.0009)	.	(0.006)	(0.0030)	0.0013	(0.0030)	.	(0.0010)	(0.0008)	.	31 mm Ø x 2 or 18 mm	CRM			
	36X CN13A	.	(0.002)	.	(0.003)	.	0.0039	~38 mm Ø x ~15 mm				
	IARM CuH191-18	.	(0.0030)	.	(0.004)	(0.0010)	0.0059	31 mm Ø x 2 or 18 mm	CRM			
	36X CN23A	0.047	.	.	.	0.0021	40 mm Ø x ~17 mm				
	C65.27	<0.01	50 mm Ø x 10 - 12 mm				
	36X CN12A	.	0.0055	.	0.0101	.	0.072	~40 mm Ø x ~15 mm				
	CTIF CN1N	.	.	.	(0.002)	60 mm Ø x 5 mm				
	36X CN2K	.	.	.	0.0013	0.0054	0.030	.	.	0.0350	.	.	~40 mm Ø x ~15 mm				
	CTIF CN4	.	.	.	(0.001)	60 mm Ø x 5 mm				
	BS 706B	<0.0005	.	.	(0.004)	.	.	<0.002	38 mm Ø x ~7 or 19+ mm				
	36X 70600A	.	0.0011	.	(0.0017)	~40 mm Ø x ~15 mm				
	HRT CU2014	38 mm Ø x 15 mm				
	BS 706A	<0.0005	.	.	0.004	.	.	0.0006	38 mm Ø x ~7 or 12 mm	last of stock			
	CTIF CuNi 10	.	.	.	(0.009)	40 mm Ø x 18 mm				

Number	As	B	Be	C	Cd	Mg	Sb	Te	Ti	Zr	Units
--------	----	---	----	---	----	----	----	----	----	----	-------

NICKEL ALLOY, chart 2 of 2

#	Number	Ni	Ag	Al	Bi	Co	Cr	Cu	Fe	Mn	Nb	P	Pb	S	Si	Sn	Zn
1	IARM 84C	9.8	(0.002)	.	.	(0.006)	.	89.4	0.28	(0.04)	.	(0.06)	0.047	(0.006)	(0.004)	0.13	0.13
1	34X 79830A	9.76	0.0028	0.0012	.	(0.0012)	.	45.88	0.079	0.311	.	0.0047	2.033	(0.0005)	.	0.1158	41.80
1	BS 706C	9.7	.	(0.001)	.	(0.003)	(0.0006)	87.9	1.68	0.60	.	(0.007)	0.0033	0.0014	0.0018	(0.0070)	0.084
1	36X SP1A	8.33	0.005	0.0020	0.0039	0.057	.	84.90	0.45	0.084	(0.031)	(0.003)	0.0115	0.005	0.004	5.75	0.344
2	CURM 62.12	7.94	.	.	.	0.081	.	89.42	0.45	1.59	.	.	0.053	0.034	0.109	0.111	0.180
2	CTIF CN2	7.80	.	(0.012)	.	.	.	88.40	1.68	1.19	(0.007)	.	0.055	0.028	0.26	(0.0065)	0.515
1	36X CN21A	5.50	0.0064	1.95	.	0.0079	0.0050	92.17	0.0316	0.0391	.	0.053	0.051	.	.	0.038	0.0203
2	HRT CU2012	2.30	97.0	0.013	0.002	0.63	0.035	.
1	37X 218B	1.892	.	0.0018	.	.	0.176	97.29	0.0209	0.0022	.	.	0.0014	.	0.564	0.0032	0.0054
1	36X CN22A	1.806	0.0196	6.09	.	0.0231	0.0144	91.80	0.088	(0.016)	.	0.0178	0.0260	.	.	0.0371	0.0175

Number	As	B	Be	C	Cd	Mg	Sb	Ti	Zr	Units
IARM 84C	.	.	.	(0.003)	.	.	(0.0012)	.	.	31 mm Ø x 2 or 18 mm
34X 79830A	0.0070	.	.	(0.0052)	.	.	0.0041	.	.	~38 mm Ø x ~15 mm
BS 706C	(0.001)	0:0.0016	N:(0.005)	(0.004)	.	(0.000003)	(0.0006)	.	(0.0000002)	38 mm Ø x ~7 or 19+ mm 17025
36X SP1A	.	0.0007	0.0177	(0.0004)	.	40 mm Ø x 15 mm
CURM 62.12	0.002	.	.	.	60 mm Ø x 10 mm
CTIF CN2	.	.	.	(0.008)	60 mm Ø x 5 mm
36X CN21A	0.0067	.	.	.	0.0021	40 mm Ø x ~17 mm
HRT CU2012	40 mm Ø x 20 mm
37X 218B	~38 mm Ø x ~15 mm
36X CN22A	0.0208	.	.	.	0.0083	40 mm Ø x ~17 mm

CRM NICKEL ALLOY SETS

analysis listed in mass %

NA: 28 mm Ø x 25 mm MN5: 35 mm Ø x 30 mm N: 35 mm Ø x 30 mm
NB: 40 mm Ø x 25 mm NC: 40 mm Ø x 12 mm

Number	Ni	Al	As	Bi	C	Cd	Co	Fe	Mg	Mn	P	Pb	S	Sb	Si	Sn	Zn	singles?
IMN NC1	23.17	.	0.0056	0.0011	0.0320	0.0142	0.0062	0.0501	0.0016	0.552	0.0147	0.0025	0.0709	0.0024	0.0854	0.0374	0.776	no
IMN NC2	24.21	0.0219	0.0104	0.0046	(0.0026)	0.0189	0.0115	0.290	0.0024	0.413	.	0.0021	0.0837	0.0049	0.196	0.0457	0.508	yes
IMN NC3	24.68	0.229	0.0167	0.0077	(0.0036)	0.0120	0.0282	0.106	0.0561	0.148	0.0312	0.0027	(0.0202)	0.0084	0.0609	0.0171	0.244	yes
IMN NC4	25.39	0.332	0.0251	0.0117	0.0500	0.0049	0.101	0.426	0.0170	0.0172	0.0113	0.0120	0.0022	0.0113	0.0197	0.0087	0.0099	yes
IMN NC5	25.82	0.0749	0.0427	0.0213	0.0050	0.0018	0.151	0.369	0.0861	0.0623	0.0222	0.0409	.	0.0161	0.0198	0.0044	0.0152	yes
IMN N1	25.38	0.0050	0.0056	.	0.0018	.	0.0019	.	.	0.0070	0.0089	0.019	yes
IMN N2	24.28	0.023	0.35	.	0.21	.	0.011	.	.	0.025	0.012	0.16	yes
IMN N3	22.57	0.055	0.77	.	0.50	.	0.020	.	.	0.062	0.023	0.33	yes
IMN N4	21.39	0.080	1.07	.	0.71	.	0.039	.	.	0.13	0.038	0.47	yes
IMN NA1	7.19	.	.	.	(0.020)	.	.	2.52	.	1.51	.	0.081	(0.081)	.	.	.	0.80	yes
IMN NA2	9.05	.	.	.	(0.023)	.	.	2.03	.	1.03	.	0.056	(0.065)	.	.	.	0.55	yes
IMN NA3	10.35	.	.	.	(0.019)	.	.	1.15	.	0.60	.	0.035	(0.036)	.	.	.	0.30	yes
IMN NA4	12.15	.	.	.	(0.012)	.	.	0.50	.	0.21	.	0.0066	(0.0069)	.	.	.	0.019	yes
IMN MN5-1	3.21	.	0.0007	0.00011	.	.	.	0.0041	.	.	(0.00027)	0.0062	.	0.00019	.	.	.	yes
IMN MN5-2	4.50	.	0.0011	0.00071	.	.	.	0.033	.	.	0.010	0.012	.	0.00078	.	.	.	yes
IMN MN5-3	5.29	.	0.0017	0.0012	.	.	.	0.062	.	.	0.016	0.016	.	0.0013	.	.	.	yes
IMN MN5-4	5.90	.	0.0038	0.0018	.	.	.	0.083	.	.	0.026	0.024	.	0.0019	.	.	.	yes

CRM SEBILOY / ENVIROBRASS / FEDERALLOY

Number	Sn	Zn	Bi	Se	As	Co	Fe	Ni	P	Pb	Sb	Cu
32X SEB2D	6.96	1.40	4.57	0.044	0.0160	0.0133	0.074	0.0449	0.036	0.104	0.0222	86.56
IARM 266A	6.9	3.48	2.37	0.001	0.004	(0.001)	0.035	0.46	0.032	0.010	0.010	(87)
32X SEB5C	5.18	5.30	1.056	0.471	.	0.0156	0.0430	0.317	0.072	0.268	0.0334	87.21
IARM 226A	5.1	4.8	1.7	0.93	0.003	0.001	0.054	0.54	0.005	0.040	0.004	86.7
IARM 227A	5.1	4.70	2.3	1.21	0.003	0.001	0.060	0.53	0.003	0.042	<0.01	85.9
IARM 265A	4.4	2.45	2.4	(0.002)	(0.005)	(0.001)	0.013	0.69	0.024	0.011	0.015	(90)
IARM 228A	4.1	4.1	1.53	0.67	0.003	0.001	0.052	0.45	0.032	0.026	0.010	89.0
IARM 263A	3.5	15.8	2.55	(0.002)	0.003	0.001	0.047	0.66	0.040	0.022	0.06	(78)
IARM 264A	3.03	5.33	3.6	(0.001)	(0.004)	(0.001)	0.048	0.54	0.027	0.057	0.074	(87.3)

Number	Ag	Al	B	C	Cd	Cr	Mn	N	O	S	Si	Units
32X SEB2D	0.0443	.	.	.	0.0255	.	In: 0.074	.	.	0.030	.	~40 mm Ø x ~15 mm
IARM 266A	(0.001)	0.002	.	(0.002)	.	(0.002)	(0.002)	.	.	(0.002)	0.002	31 mm Ø x 2 mm
32X SEB5C	.	(0.001)	.	.	0.0051	0.050	.	~40 mm Ø x ~15 mm
IARM 226A	0.004	0.002	.	0.003	.	(0.001)	0.002	<0.0005	(0.001)	0.005	0.002	31 mm Ø x 2 or 18 mm
IARM 227A	0.004	0.002	.	0.003	.	(0.001)	0.001	(0.0002)	0.0013	0.005	0.002	31 mm Ø x 2 or 18 mm
IARM 265A	(0.002)	0.003	.	.	.	(0.001)	(0.002)	.	.	(0.002)	0.003	31 mm Ø x 2 or 18 mm
IARM 228A	0.003	0.002	.	0.003	.	0.001	0.001	<0.0005	(0.002)	0.004	0.002	31 mm Ø x 2 or 18 mm
IARM 263A	(0.006)	(0.002)	.	<0.005	.	(0.002)	(0.002)	.	.	(0.002)	0.003	31 mm Ø x 2 or 18 mm
IARM 264A	(0.005)	0.003	.	(0.004)	.	(0.002)	(0.002)	.	.	0.0013	0.003	31 mm Ø x 2 or 18 mm

RM SILVER ALLOY

31 mm Ø x 2 or 18 mm

Number	Ag	C	P	S	Zr
IARM 159A	3.48	(0.002)	(<0.01)	(<0.01)	.
IARM 160A	3.03	0.003	(0.004)	(<0.003)	0.40
Al, Co, Cr, Fe, Mn, Ni, Pb, Si, Sn, and Zn: (<0.01)					

CRM SILVER ALLOY SET

available in set only 40 mm Ø x 25 mm

Number	Ag
IMN CCA-1	0.00720
IMN CCA-2	0.0539
IMN CCA-3	0.757
IMN CCA-4	1.524
IMN CCA-5	1.964

RM TIN COPPER

cast typical analysis

32X: 40 mm Ø x 15 mm

C: 50 mm Ø x 10-12 mm

Number	Sn	Al	As	Bi	Cu	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Si	Zn
C11.04	9.6	<0.005	<0.005	<0.0005	rem	<0.005	<0.001	<0.005	<0.005	0.05	0.01	<0.001	<0.005	<0.005	<0.005
C11.03	7.4	<0.005	<0.005	<0.0005	rem	<0.005	<0.001	<0.005	<0.005	0.04	0.01	<0.001	<0.005	<0.005	<0.005
C11.02	5.5	<0.005	<0.005	<0.0005	rem	<0.005	<0.001	<0.005	0.006	0.02	0.02	<0.001	<0.005	<0.005	<0.005
C11.01	3.4	<0.005	<0.005	<0.0005	rem	<0.005	<0.001	<0.005	0.006	0.009	0.01	<0.001	<0.005	<0.005	<0.005

CRM TIN COPPER SET

available in SET/5 or individually

40 mm Ø x 30 mm

Number	Ag	As	Bi	Cu	Fe	Ni	P	Pb	Sb	Sn	Zn
IMN CM1	0.010	0.0098	0.010	Rem	0.019	0.0086	0.0088	0.012	0.012	0.61	0.021
IMN CM2	0.0061	0.0068	0.0072	Rem	0.0064	0.0055	0.0058	0.0067	0.0068	0.84	0.0061
IMN CM3	0.0029	0.0036	0.0033	Rem	0.012	0.0031	0.0041	0.0038	0.0040	1.06	0.0060
IMN CM4	0.0011	0.0011	0.00093	Rem	0.0042	0.0011	0.0009	0.0023	0.0019	1.30	0.0020
IMN CM5	.	(0.015)	0.014	Rem	0.0094	0.014	0.015	0.019	0.018	1.14	0.013

CRM BRASS SETS

wrought IMN MG2 in SET only, all others OK individually

MB: 40 mm Ø x 18 mm

ME, MG, WR: 35-40 mm Ø x 25-30 mm

WC: 40 mm Ø x 12 mm

Number	Cu	Zn	Al	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	P	Pb	Sb	Si	Sn
IMN MG1	91.14	Rem	0.040	.	0.00058	.	.	.	0.0081	0.0013	0.048	(0.0019)	0.049	0.00077	.	0.0062
IMN MG2	90.08	Rem	(0.0026)	.	0.00039	.	.	.	0.0067	0.0007	0.0022	0.0012	0.0048	(0.00084)	.	0.018
IMN MG3	93.19	Rem	0.020	.	0.0014	.	.	.	0.062	0.0096	0.013	0.018	0.015	0.0026	.	0.033
IMN MG4	94.00	Rem	.	.	0.0017	.	.	.	0.091	0.024	0.0042	0.012	0.008	0.0045	.	0.023
IMN MG5	95.09	Rem	0.0011	.	0.0026	.	.	.	0.149	0.0036	0.0021	0.0069	0.0054	0.0061	.	0.013
IMN MG6	92.27	Rem	0.0067	.	0.00088	.	.	.	0.028	0.045	0.030	0.0026	0.031	0.0015	.	0.053
IMN WC1	75.10	Rem	0.0034	0.0043	0.0028	.	.	.	0.031	.	.	0.015	0.046	0.0034	0.26	0.0032
IMN WC2	75.05	Rem	0.0016	0.0024	0.0020	.	.	.	0.015	.	.	0.011	0.031	0.0023	0.41	0.0025
IMN WC3	75.28	Rem	0.0018	0.0011	0.00093	.	.	.	0.021	.	.	0.0058	0.0085	0.0010	0.89	0.0011
IMN WC4	75.32	Rem	0.00096	.	0.00047	.	.	.	0.0067	.	.	0.0048	0.0051	0.00080	0.76	0.0010
IMN WC5	75.03	Rem	0.00084	0.0022	0.0019	.	.	.	0.18	.	.	.	0.0055	0.0011	0.48	0.0044
IMN WC6	75.32	Rem	0.0019	0.00097	0.0012	.	.	.	0.051	.	.	0.0037	0.0036	0.00057	0.58	0.0028
IMN ME2	71.29	Rem	0.87
IMN ME3	70.70	Rem	1.11
IMN ME4	69.40	Rem	1.21
IMN ME5	68.53	Rem	1.42
IMN MB1	60.66	39.39
IMN MB2	67.17	32.80
IMN MB3	73.26	26.67
IMN MB4	78.77	21.20
IMN MB5	84.25	15.63
IMN MB6	90.07	9.95
IMN MB7	95.00	4.99
IMN WR1	55.72	Rem	0.496	0.203	0.00109	0.00045	0.00196	0.00049	0.0577	1.051	3.534	0.00122	0.0496	0.00046	1.097	0.605
IMN WR2	56.99	Rem	1.092	0.0129	0.00642	0.00548	0.00210	0.00705	0.802	1.631	2.683	0.0311	0.291	0.00566	0.817	0.453
IMN WR3	58.95	Rem	1.683	0.0492	0.0118	0.00807	0.0106	0.0149	0.184	1.674	1.799	0.0126	0.514	0.0150	0.566	0.254
IMN WR4	60.07	Rem	2.297	0.00528	0.0211	0.0154	0.0154	0.0190	0.600	2.254	0.989	0.0213	0.683	0.0247	0.279	0.100
IMN WR5	61.20	Rem	3.024	0.00129	0.0278	0.0200	0.0196	0.0253	0.141	3.070	0.251	0.0282	0.885	0.0334	0.0485	0.0116

Number	Cu	Zn	Al	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	P	Pb	Sb	Si	Sn
--------	----	----	----	----	----	----	----	----	----	----	----	---	----	----	----	----

RM TRACE ELEMENTS IN BRASS

cast 50 mm Ø x 10 - 12 mm

Number	Cu	Zn	Al	As	Bi	Fe	Mn	Ni	Pb	Sb	Si	Sn
C30.10	93.8	6.1	<0.002	<0.005	<0.002	<0.005	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01
C30.07	82.0	rem	<0.002	<0.005	<0.002	<0.005	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01
C30.06	74.8	rem	<0.005	<0.005	<0.002	<0.005	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01
CURM 30.05	69.48	30.53	<0.001	<0.001	<0.003	<0.003	<0.0005	<0.0005	<0.002	<0.005	<0.001	<0.001
C38.06	(62)	rem	<0.001	<0.005	<0.001	<0.002	<0.002	<0.005	<0.005	<0.002	<0.002	<0.002
C38.06-1	(62)	rem	<0.001	<0.001	<0.0005	<0.005	<0.001	<0.005	0.002	<0.002	<0.002	<0.002
C30.17	61.6	rem	<0.005	<0.005	<0.005	1.4	<0.005	0.01	0.01	<0.005	<0.005	<0.01
C30.16	61.2	rem	<0.002	<0.005	<0.002	0.90	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01
C38.01	(61)	rem	0.003	0.03	<0.0005	0.01	0.009	0.01	0.20	0.02	<0.0005	0.20
C38.02	(61)	rem	0.004	0.06	0.0005	0.09	0.14	0.03	0.10	0.06	0.01	0.09
C38.03	(61)	rem	0.06	0.08	0.008	0.05	0.07	0.13	0.06	0.08	0.07	0.05
C38.04	(61)	rem	0.02	0.04	0.008	0.04	0.22	0.06	0.03	0.12	0.12	0.02
C38.05	(61)	rem	0.12	0.01	0.01	0.008	0.02	0.19	0.02	0.01	0.14	0.01
C30.12	60.85	rem	<0.005	<0.005	<0.002	<0.005	0.90	0.52	<0.01	<0.005	<0.005	<0.01
C30.03	60.6	39.3	<0.002	<0.005	<0.005	<0.005	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01
C30.13	60.6	rem	<0.002	<0.005	<0.002	<0.005	1.9	<0.01	<0.01	<0.005	<0.005	<0.01
C30.15	60.6	rem	<0.002	<0.005	<0.002	0.55	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01
C30.14	60.5	rem	<0.005	<0.005	<0.005	<0.01	2.4	1.0	<0.01	<0.005	<0.005	<0.005
C30.22	58.28	rem	<0.003	0.011	<0.005	0.006	<0.005	<0.01	1.05	<0.012	<0.005	0.009
C30.02	55.6	rem	<0.002	<0.005	<0.005	<0.005	<0.005	<0.005	<0.01	<0.005	<0.005	<0.01
C30.01	51.48	rem	<0.002	<0.005	0.005	<0.005	<0.005	<0.005	<0.01	<0.005	<0.005	<0.01

last of stock

current batch

RM BRASS MUSHROOMS

chill cast

typical analysis

60 mm Ø x 5 mm

Number	Zn	Cu	Al	As	Be	Fe	Ni	Mg	Mn	P	Pb	Sb	Si	Sn
CTIF L 7	42.45	55.6	0.308	.	.	0.031	0.020	.	0.62	.	0.71	.	0.13	0.038
CTIF L 1-1	39.7	59.60	0.015	.	.	0.017	0.106	.	.	0.080	0.062	.	0.36	0.046
CTIF L 2	35.55	61.55	0.485	.	.	0.216	0.71	.	0.350	.	0.408	.	0.202	0.48
CTIF L 3-1	35.50	(58.60)	1.22	0.073	.	0.357	0.993	.	0.214	0.030	1.32	(0.032)	0.025	1.62
CTIF L 4-1	34.55	61.75	0.100	.	.	0.466	0.227	.	0.109	.	2.017	.	0.12	0.693
CTIF L 6	30.26	66.55	0.139	.	.	0.085	1.21	.	0.055	.	0.205	.	1.25	0.250
CTIF L 23	17.90	81.20	.	0.051	.	0.246	0.033	.	.	0.05	0.058	.	0.280	0.20
CTIF UZ 52	16.90	81.18	.	.	0.014	0.32	0.084	0.04	0.002	0.068	0.11	0.08	0.12	1.06
CTIF UZ 53	16.67	82.60	.	0.01	.	0.255	0.025	.	<0.001	0.055	0.025	.	0.145	0.205
CTIF L 21	15.40	82.50	.	0.103	.	0.086	0.156	.	0.004	0.05	0.209	0.10	0.036	1.5
CTIF L 22	15.0	84.3	<0.02	<0.006	.	0.20	0.10	.	<0.01	.	0.10	.	<0.05	1.0
CTIF L 20	13.10	85.55	0.008	0.122	.	0.115	0.205	.	0.043	.	0.27	.	0.035	0.56

BRASS

= class, where 1 = CRM and 2 = RM

CURM: cast 50 mm Ø x 10-12 mm
SRM: wrought 31 mm Ø x 19 mmPB: 45 mm Ø x 25 mm
others: chill cast ~38-43 mm Ø x ~15-18 mm

#	Number	Zn	Cu	Al	As	Bi	Fe	Mn	Ni	Pb	Sb	Si	Sn
1	31X B25C	42.2	55.6	0.48	0.027	0.061	0.014	0.128	0.255	0.272	0.075	0.235	0.62
1	31X B2N	39.1	60.2	0.161	0.0154	0.0150	0.122	0.0361	0.102	0.053	0.0121	.	0.0129
2	CURM 30.15	38.88	60.66	<0.001	.	.	0.50	<0.001	<0.001	<0.005	.	<0.005	<0.002
2	CURM 30.16	38.33	60.53	<0.001	.	.	1.14	<0.001	<0.001	<0.005	.	<0.005	<0.002
2	CURM 30.11	38.17	59.86	<0.001	.	.	0.002	0.23	1.70	0.005	.	<0.001	<0.002
1	IARM 75C	38.1	60.7	(0.003)	(0.005)	(0.0012)	(0.06)	(0.0024)	(0.013)	0.42	(0.007)	(0.005)	0.69
2	SRM 1107	37.3	61.2	.	.	.	0.037	.	0.098	0.18	.	.	1.04
1	31X TB3L	37.0	62.42	0.044	0.047	0.0085	0.040	0.034	0.031	0.118	0.053	0.020	0.133
1	31X TB1L	36.8	61.5	0.174	0.052	0.049	0.072	0.287	0.199	0.325	0.101	0.097	0.214
1	31X B11H	36.65	60.72	0.0262	0.0061	0.0054	0.802	0.653	1.033	0.0134	0.0057	0.0063	0.0117
1	31X B10N	36.6	60.9	0.149	0.0099	0.021	0.135	0.160	1.56	0.022	0.0207	0.012	0.047
1	31X TB5B	35.6	61.49	0.071	0.396	0.292	0.094	0.283	0.106	0.575	0.229	0.111	0.129
1	31X B3N	35.05	64.56	.	0.0104	0.0152	0.0408	0.0290	0.0171	0.085	0.0148	.	0.0394
1	31X B3M	35.01	64.58	0.074	0.0196	0.0149	0.0264	0.0296	0.0259	0.0299	0.0205	.	0.0202
1	31X TB4G	33.64	66.07	0.0041	0.0106	0.0058	0.0340	0.0013	0.0133	0.0246	0.0095	0.0203	0.0197
1	31X B5L	23.98	75.38	0.0138	0.0357	0.0088	0.038	(0.002)	0.0275	0.084	0.016	(0.005)	0.266
1	31X B22G	17.8	80.5	0.100	0.150	0.148	0.107	0.00076	0.142	0.197	0.147	0.152	0.225
1	31X B7L	15.34	84.22	0.0435	0.0054	0.0607	0.099	0.0088	0.0351	0.0416	0.0196	0.018	0.089
1	SRM 1110	15.2	84.5	.	.	.	0.033	.	0.053	0.033	.	.	0.051
1	SRM 1111	12.8	87.1	.	.	.	0.010	.	0.022	0.013	.	.	0.019
1	31X B9M	4.92	94.81	(0.0006)	0.0103	0.0059	0.0361	0.0006	0.0379	0.090	0.0089	.	0.062
1	31X B24D	1.99	95.65	(0.0024)	0.0116	0.0126	0.0342	0.0030	0.134	0.050	0.118	.	1.93
2	PB MS10	.	84.26	.	0.014	0.37	0.28	0.016	0.025	0.020	(0.009)	0.12	0.052
1	BAM M396	.	65.49	0.223	0.0590	0.00032	0.0235	0.00445	0.0143	.	0.00061	.	.

#	Number	Zn	Cu	Al	As	Bi	Fe	Mn	Ni	Pb	Sb	Si	Sn
	Number	Ag	B	C	Cd	Co	Cr	P	S	Se	Te		
	31X B25C	0.0025	.	.	0.00019	.	(0.0002)	0.116
	31X B2N	0.0118	0.0029	.	0.0032	0.042	.	0.0191	.	.	.	0.0015	.
	CURM 30.15
	CURM 30.16
	CURM 30.11
	IARM 75C	.	<0.1	(0.002)	(0.0015)	(0.0007)	0.0009	(0.004)	(0.0015)	(0.005)	.	.	.
	SRM 1107
	31X TB3L	0.011	0.0014	.	0.0078	0.0043	0.0025	.
	31X TB1L	0.061	0.0005	.	0.0122	0.0017	0.0024	0.0080	(0.002)	(0.0008)	(0.004)	.	.
	31X B11H	last	.	.	.
	31X B10N	0.0030	.	.	0.0005	0.0062	0.0006	0.033	.	(0.0009)	.	.	.
	31X TB5B	0.216	.	.	0.49	0.0202	0.0031	0.0255
	31X B3N	0.0152	0.0008	.	0.0027	0.0066	.	0.0366	.	.	.	0.0056	.
	31X B3M	0.0247	0.0022	.	0.0040	0.0109	.	0.0421	.	.	.	0.0098	.
	31X TB4G	.	(0.0004)	.	0.0032	0.0067	0.0035	.
	31X B5L	.	(0.0009)	.	0.0040	0.0250
	31X B22G	0.0015	0.0029	.	0.0130	0.059	(0.0006)	0.214	.	(0.0007)	.	.	.
	31X B7L	.	0.0013	.	0.0064	0.0044	(0.002)	.
	SRM 1110
	SRM 1111
	31X B9M	0.0065	(0.0005)	0.0047	.	0.0019	0.0181	.	.
	31X B24D	.	.	.	0.0008	.	.	0.0065	0.050
	PB MS10	last	.	.	.
	BAM M396	.	.	.	0.00022	0.00012	0.00079	0.00089	.	<0.001	.	38 mm Ø x 30 mm	.
	Number	Ag	B	C	Cd	Co	Cr	P	S	Se	Te		

ALUMINUM BRASS

= class, where 1 = CRM and 2 = RM

#	Number	Al	Zn	Cu	As	Bi	Fe	Mn	Ni	Pb	Sb	Si	Sn	Other	Units
2	CTIF LH1-1	7.99	16.90	64.90	.	.	4.48	5.18	0.0944	0.022	0.081	0.205	(0.007)	P: 0.079	60 mm Ø x 5 mm
2	CTIF LH 2	6.20	21.95	61.98	.	.	2.98	3.65	3.00	0.080	.	0.086	0.055		60 mm Ø x 5 mm
2	CTIF LH 6-1	6.09	18.98	63.18	.	.	(3.1)	4.54	3.19	0.25	.	0.20	0.257		60 mm Ø x 5 mm
1	BAM 388	4.972	4.81	89.27	.	.	0.0303	0.0512	0.00736	0.000969	.	.	0.857		40 mm Ø x 30 mm
2	C30.19	4.65	rem	69.9	<0.005	<0.002	<0.005	<0.005	<0.01	<0.01	<0.01	<0.005	1.07		50 mm Ø x 10-12 mm
1	31X B14G	4.02	36.52	58.85	0.0091	0.0103	0.0183	0.0117	0.0190	0.0104	0.0139	0.051	0.486	Ag:0.0130 Co:0.0109	~40mmØ x ~15mm
2	CTIF LH 5-1	3.65	25.72	66.0	.	.	1.26	1.37	1.57	0.110	.	0.114	0.141		60 mm Ø x 5 mm
2	CURM 30.18	3.28	32.33	63.66	.	.	0.006	<0.001	<0.001	<0.005	.	0.131	0.58		50 mm Ø x 10-12 mm
2	CTIF LH 7	3.16	(26.85)	63.40	.	.	(2.35)	2.96	0.70	0.327	.	0.055	0.227		60 mm Ø x 5 mm
1	31X B15H	2.98	36.80	59.07	0.0048	0.0074	0.0176	0.0122	0.0102	0.0073	0.0111	0.109	0.944	Ag:0.0071 Co:0.0046	~40mmØ x ~15mm
2	C30.18	2.91	rem	64.36	<0.005	<0.003	<0.005	<0.005	<0.005	<0.01	<0.005	0.10	0.65		50 mm Ø x 10-12 mm
2	CURM 43.01	2.75	22.44	74.36	0.118	<0.002	0.008	0.064	0.121	<0.002	<0.001	0.063	0.116		50 mm Ø x 10-12 mm
2	CTIF LH 10	2.66	28.90	59.05	.	.	(1.0)	3.57	1.49	1.76	.	1.30	0.203		60 mm Ø x 5 mm
2	CURM 43.02	2.40	20.82	76.21	0.083	<0.001	0.128	0.035	0.068	0.064	<0.001	0.038	0.060		50 mm Ø x 10-12 mm
2	CURM 30.20	2.32	35.71	61.46	.	.	<0.005	<0.001	<0.001	<0.002	.	0.17	0.40		50 mm Ø x 10-12 mm
2	CTIF LH 13	2.00	31.8	55.75	.	.	(2.00)	3.14	3.22	0.67	.	0.21	1.19		60 mm Ø x 5 mm
1	31X B16H	1.98	37.18	58.37	0.0056	0.0042	0.0162	0.0029	0.0076	0.0295	0.0126	0.197	2.13	Ag:0.0052 Co:0.0023	~40mmØ x ~15mm
2	C43.03	1.6	rem	79.7	<0.005	<0.005	0.07	<0.002	<0.005	0.10	<0.01	<0.005	<0.005		50 mm Ø x 10-12 mm
1	BAM 368 *	1.972	rem	77.049	0.0246	.	0.0193	0.0203	0.0258	0.01313	(0.002)	.	0.0147	P: 0.00899	40 mm Ø x 30 mm
2	C30.21	1.44	rem	56.0	<0.005	.	<0.005	<0.005	<0.005	<0.005	<0.01	1.96	1.96		50 mm Ø x 10-12 mm
2	CURM 30.21	1.44	40.08	56.23	.	.	0.003	<0.001	<0.001	0.004	.	0.213	2.01		50 mm Ø x 10-12 mm
2	CTIF LH 12	1.13	33.15	62.75	.	.	(1.2)	0.125	0.505	0.21	.	(0.06)	0.83		60 mm Ø x 5 mm
2	CTIF LH 11	0.46	26.20	66.80	.	.	0.36	0.71	2.91	1.26	.	0.88	0.44		60 mm Ø x 5 mm

* BAM 368 also contains 62.1 ppm Mg

CRM ALUMINUM BRASS SET

IMN WO2 available in SET/4 only, others individually

40 mm Ø x 35 mm

Number	Al	As	Bi	Cd	Cr	Cu	Fe	Mg	Mn	Ni	P	Pb	Sb	Si	Sn	Zn
IMN WO1	1.33	0.056	0.0003	0.013	0.013	78.85	0.13	0.00060	0.014	0.0043	0.0023	0.15	0.0083	0.044	0.011	Rem
IMN WO2	1.76	0.041	0.0014	0.032	0.0098	77.80	0.050	0.0066	0.16	0.031	0.0090	0.098	0.00098	0.013	0.056	Rem
IMN WO3	2.15	0.015	0.0047	0.039	0.0027	77.58	0.029	0.0055	0.051	0.11	0.0062	0.054	0.0035	0.007	0.0071	Rem
IMN WO4	2.50	0.030	0.0098	0.0063	0.00034	76.20	0.022	0.013	0.074	0.077	0.015	0.020	0.0058	0.001	0.13	Rem

CRM BISMUTH BRASS

analysis listed in mass % except * which is mg/kg

~38-40 mm Ø x ~15 mm

Number	Bi	Zn	Cu	Ag*	Al	As	B*	Cd*	Co	Cr*	Fe	Mn	Ni	P	Pb	S*	Sb	Se*	Si	Sn
31X BIB3C	4.04	31.83	63.18	.	0.154	0.0476	.	14	0.0032	.	0.0510	.	0.127	0.0626	0.181	18	0.0321	47	0.0516	0.198
31X BIB1E	1.96	34.0	62.7	14	0.213	0.0290	.	91	0.0057	.	0.074	0.0266	0.301	0.062	0.090	(30)	0.012	(10)	0.065	0.376
31X BIB4D	0.80	34.8	62.9	14	0.435	0.0095	19	22	0.0108	6	0.094	0.00082	0.211	0.039	0.096	(50)	0.022	11	0.060	0.58

RM CARTRIDGE BRASS

cast typical analysis listed in mass %

31X: ~40 mm Ø x ~15 mm

others: 50 mm Ø x 10 - 12 mm

Number	Zn	Cu	Al	As	Bi	Cd	Cr	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Si	Sn
CURM 48.01	32.6	66.98	<0.001	0.067	0.038	<0.0003	*	0.049	0.0008	<0.001	0.134	0.016	0.106	<0.001	0.047	0.041	<0.002
CURM 48.02	32.58	67.16	0.013	0.025	0.004	*	0.004	0.053	*	0.067	<0.001	0.012	0.084	0.007	0.037	0.010	0.035
CURM 48.05	31.0	68.69	<0.002	<0.001	*	<0.0003	*	0.066	*	0.016	0.117	0.007	<0.003	0.013	*	0.026	0.083
31X B4N	30.22	69.3	Cr:0.0013	0.059	0.0139	0.032	0.0083	0.043	.	0.032	0.019	0.0083	0.080	(0.002)	0.006	0.030	0.046
C48.03	rem	70.45	0.007	0.079	0.029	0.013	0.0005	<0.001	0.001	0.040	0.030	<0.001	0.054	0.004	0.097	<0.002	0.047
C48.06	rem	71.6	0.002	0.008	0.004	0.008	0.0006	0.02	0.001	0.006	0.11	0.002	0.02	0.006	0.006	0.006	0.03
CURM 48.04	26.99	72.68	<0.001	0.034	0.014	<0.0003	<0.002	0.008	0.0005	0.012	0.096	0.006	0.043	0.011	0.026	0.004	0.018

* For the above chart, * indicates a value of <0.0005

CRM CARTRIDGE BRASS

available in SET/5 or individually remainder is Zinc

wrought 40 mm Ø x 25 mm

Number	Ag	Al	As	Be	Bi	Cd	Cu	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Te
IMN MH1	0.0029	0.0010	0.0670	0.0088	0.0037	0.0260	65.93	0.0170	0.0350	0.2600	0.0160	0.0065	0.0034	0.0004	0.0740	0.1400	0.0004
IMN MH2	0.0110	0.0190	0.0410	0.0015	0.0022	0.0180	68.25	0.0270	0.0110	0.2200	0.0055	0.0210	0.0055	0.0240	0.0540	0.0970	0.0015
IMN MH3	0.0065	0.0081	0.0160	0.0003	0.0011	0.0089	71.28	0.0810	0.0850	0.1000	0.0035	0.0780	0.0090	0.0130	0.0310	0.0240	0.0046
IMN MH4	.	0.0027	0.0011	0.0045	0.0006	0.0029	69.94	0.1300	0.0017	0.0520	0.0022	0.3300	0.0043	0.0170	0.0160	0.0110	0.0035
IMN MH5	0.0250	0.0140	0.0038	0.00004	.	0.0012	72.87	0.1900	0.0720	0.0072	0.0011	0.2000	0.0180	0.0035	0.0039	0.0021	0.0047

CRM CARTRIDGE BRASS SETS

Number	Cd	Cr	Cu	Se	Zn	Zr	Units
IMN MJ1	0.00355	0.0120	67.77	0.00062	Rem	.	available individually 40 mm Ø x ~28 mm
IMN MJ2	0.00377	0.00440	66.40	0.00037	Rem	.	available individually 40 mm Ø x ~28 mm
IMN MJ3	0.00165	0.00158	67.39	0.00035	Rem	.	available individually 40 mm Ø x ~28 mm
IMN MJ4	0.00130	0.00374	68.06	0.0124	Rem	.	available individually 40 mm Ø x ~28 mm
IMN MJ5	0.000360	0.00065	(67.82)	0.00288	Rem	.	available individually 40 mm Ø x ~28 mm
IMN MJJ1	.	.	67.82	.	Rem	0.0454	available individually 40 mm Ø x ~28 mm
IMN MJJ2	.	.	(68.03)	.	Rem	0.00017	available individually 40 mm Ø x ~28 mm
IMN MJJ3	.	.	67.87	.	Rem	0.00070	available individually 40 mm Ø x ~28 mm
IMN MJJ4	.	.	67.75	.	Rem	0.0074	available individually 40 mm Ø x ~28 mm

CRM FREE CUTTING BRASS SET

40 mm Ø x 25 mm

Number	Al	As	Bi	Cu	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn
IMN WN1	0.33	0.035	0.023	58.44	0.23	0.57	0.29	0.031	0.51	0.099	0.16	1.00	Rem available individually
IMN WN2	0.24	0.011	0.035	60.38	0.29	0.73	0.19	0.051	1.58	0.10	0.22	0.68	Rem available in SET/5 only
IMN WN3	0.14	0.032	0.020	62.32	0.062	0.39	0.098	0.034	2.62	0.020	0.12	0.39	Rem available in SET/5 only
IMN WN4	0.047	0.021	0.0094	57.97	0.11	0.13	0.050	0.014	0.86	0.061	0.036	0.13	Rem available individually
IMN WN5	(0.0004)	0.030	0.0028	64.36	0.0085	0.0020	0.0049	0.0051	3.78	0.0035	(0.0013)	0.019	Rem available individually

LEADED BRASS

= class, where 1 = CRM and 2 = RM

* Provisional Analysis

#	Number	Pb	Sn	Zn	Cu	Al	As	Bi	Co	Fe	Mn	Ni	P	Sb	Si
1	IARM Cu844-18	6.7	3.08	9.5	80.5	0.0010	0.0041	0.030	0.0015	0.030	.	0.209	0.0018	0.037	(0.001)
1	IMN BR1	5.03	4.9	5.07	Rem	0.0074	0.0102	.	.	0.085	0.080	0.48	0.009	0.090	(0.0077)
1	IARM Cu836-18	4.9	5.02	5.09	84.5	.	0.0098	0.035	0.0026	0.049	.	0.423	0.028	0.103	(0.003)
1	SRM 1124	3.363	0.3112	35.19	(62.5)	.	.	(0.0202)	(0.0014)	0.2068	(0.0009)	0.0801	(0.0224)	0.02325	.
2	CURM H30.24	3.02	<0.001	37.92	58.87	<0.001	<0.001	<0.001	.	0.005	<0.001	<0.001	.	<0.001	<0.001
1	33X RB2B	2.99	4.65	9.01	82.02	0.0078	0.0395	0.091	0.0326	0.503	0.0076	0.330	0.0435	0.0494	(0.0017)
1	BAM 375	2.90	0.2090	38.02	58.32	0.0270	0.0231	0.00686	0.01964	0.207	0.0222	0.1053	(0.00086)	0.0122	0.0211
1	BS 360C	2.86	0.104	35.3	61.5	(0.026)	(0.016)	.	(0.0003)	0.096	0.0025	0.020	(0.007)	0.0043	0.0026
1	BS 360B	2.77	0.15	35.7	(61.2)	(0.001)	0.002	.	(0.0002)	0.117	0.0094	0.040	(0.0002)	0.017	0.002
1	IARM Cu360-18	2.73	0.29	35.1	61.6	(0.010)	0.026	(0.0023)	0.0010	0.27	0.0131	0.0120	(0.003)	0.012	(0.010)
1	BS 360D	2.68	0.153	35.0	61.8	(0.0003)	(0.040)	.	(0.0004)	0.155	0.0011	0.029	(0.002)	(0.007)	(0.001)
1	31X B19S	2.36	0.0556	37.3	59.7	0.015	0.0214	0.019	0.0007	0.357	0.0194	0.0249	0.016	0.036	0.015
1	31X 7835-7A	2.29	0.137	7.50	88.87	0.0084	.	0.048	0.0120	0.030	.	0.943	0.080	0.0327	0.039
1	31X 7835-2L	2.07	0.206	33.4	63.7	0.136	0.069	0.013	0.0036	0.25	.	0.051	(0.08)	0.073	0.023
1	31X CZ132A	2.05	0.160	39.90	57.63	0.0007	0.0119	.	0.0009	0.165	.	0.0510	.	0.0054	(0.004)
2	HRT CU2015	2.00	0.19	.	57.57	0.14	.	0.04	0.004	.	.
1	31X CZ122A	1.97	0.0866	36.21	61.51	.	0.150	.	.	0.066	0.00097	0.0261	.	0.0088	(0.0001)
1	BAM M394	1.93	0.232	.	57.70	(0.00010)	0.01001	0.00081	.	0.1191	0.00141	0.0399	0.00157	0.00238	(0.00053)
1	BAM M394a	1.92	0.174	.	57.64	(0.00079)	0.00059	0.00083	.	0.1323	0.00125	0.0386	0.00172	0.00241	(0.00058)
1	31X 7835-3K	1.70	0.355	36.64	59.9	0.488	0.059	0.0298	0.0069	0.484	0.048	0.146	0.033	0.060	(0.077)
1	31X 7835-5A	1.64	0.116	6.23	91.25	0.078	0.104	.	.	0.126	.	0.249	0.018	0.114	.
1	31X 7835-6D	1.31	0.70	37.2	59.9	0.527	0.0069	0.0047	0.0059	0.118	.	0.061	0.038	.	0.004
1	31X CZ114A	1.219	0.511	38.25	57.10	0.714	.	0.0107	.	0.740	1.475	0.0183	0.0018	(0.0032)	(0.0064)
2	BS 857B-1	1.22	1.14	34.91	61.3	0.35	(0.001)	.	.	0.30	0.003	0.61	0.004	(0.002)	0.004
2	BS 857B-2	1.21	1.13	34.91	[62.4]	0.364	0.0004	.	.	0.30	0.003	0.61	0.003	.	0.003
2	BS 857B-3	1.21	1.13	34.91	[62.4]	0.351	0.0003	.	.	0.30	0.003	0.61	0.003	.	0.004
2	BS 857B-4	1.20	1.13	34.91	[62.4]	0.339	0.0004	.	.	0.30	0.003	0.61	0.003	.	0.005
1	31X CZ115A	1.169	0.729	39.20	57.19	0.0007	0.0008	.	.	0.601	1.095	0.0143	0.0091	0.0020	(0.0005)
1	31X 7835-4K	0.98	0.200	38.0	59.9	0.153	0.058	0.018	0.0058	0.239	0.0262	0.099	0.156	0.0284	.
1	31X CZ112A	0.458	1.130	37.07	61.24	(0.0006)	0.0052	.	.	0.0488	0.0010	0.0150	0.0136	0.0043	(0.0033)

Number	Ag	B	Be	C	Cd	Cr	Mg	O	S	Se	Te	Units
IARM Cu844-18	0.0133	.	.	.	(0.0008)	.	.	.	0.023	0.0040	.	~38 mm Ø x ~3 or ~19 mm
IMN BR1	0.014	.	.	40 mm Ø x ~25 mm
IARM Cu836-18	0.0292	.	.	.	0.0014	.	.	.	0.041	0.0016	.	~38 mm Ø x ~3 or ~19 mm
SRM 1124	0.0131	.	.	.	0.00651	0.0155	.	.	(0.0031)	.	.	cont. cast 39 mm Ø x 19 mm
CURM H30.24	(0.2)	.	.	.	50 mm Ø x 10 - 12 mm
33X RB2B	0.105	(0.0013)	.	.	0.069	.	0.0078	chill cast ~42 mm Ø x ~17 mm
BAM 375	0.0166	0.00859	0.00538	wrought 40 mm Ø x 30 mm
BS 360C	0.0040	.	(0.0002)	0.0014	.	(0.0008)	.	(0.0007)	(0.0008)	.	N:(0.0002)	38 mm Ø x ~7 or 19+ mm 17025
BS 360B	0.006	.	(0.001)	(0.002)	.	(0.0001)	.	0.0007	(0.0005)	last	(0.002)	38 mm Ø x 19 mm 17025
BS 360D	0.0059	.	(0.0003)	0.0013	.	(0.0005)	.	(0.0009)	(0.0008)	.	.	38 mm Ø x ~7 or 19+ mm 17025
31X B19S	0.0041	.	.	.	0.0110	0.0012	.	.	(0.003)	0.0010	0.0012	~38 mm Ø x ~15 mm
IARM Cu360-18	0.011	.	.	(0.003)	0.0034	(0.003)	31 mm Ø x 2 or 18 mm
31X 7835-7A	0.0047	.	.	.	0.0075	.	.	chill cast 40 mm Ø x ~15 mm
31X 7835-2L	0.015	0.0012	.	.	0.0040	chill cast ~40 mm Ø x ~15 mm
31X CZ132A	0.0050	.	.	.	0.0012	.	.	.	0.0008	.	.	wrought ~40 mm Ø x ~15 mm
HRT CU2015	40 mm Ø x 20 mm
31X CZ122A	0.0030	(0.0004)	.	.	0.0011	.	.	.	0.0009	.	.	wrought ~40 mm Ø x ~15 mm
BAM M394	0.00070	40 mm Ø x 30 mm
BAM M394a	0.00073	0.00013	40 mm Ø x 30 mm
31X 7835-3K	0.0205	.	.	.	0.0060	0.0107	0.0011	chill cast ~40 mm Ø x ~15 mm
31X 7835-5A	chill cast 42 mm Ø x 18 mm
31X 7835-6D	0.0048	0.0032	.	.	0.0017	.	.	.	(0.001)	(0.001)	0.0007	chill cast ~40 mm Ø x ~15 mm
31X CZ114A	wrought ~38 mm Ø x ~15 mm
BS 857B-1	(0.002)	last	cont. cast 38 mm Ø x 10 or 19 mm
BS 857B-2	(0.002)	.	.	(0.003)	(0.001)	.	(0.004)	cont. cast 38 mm Ø x 12 mm
BS 857B-3	(0.002)	.	.	(0.003)	(0.001)	.	(0.004)	cont. cast 38 mm Ø x 12 mm
BS 857B-4	(0.002)	.	.	(0.003)	(0.001)	.	(0.004)	cont. cast 38 mm Ø x 12 mm
31X CZ115A	0.0041	0.0005	wrought ~41 mm Ø x ~15 mm
31X 7835-4K	.	0.0020	.	.	0.0092	0.0051	chill cast ~40 mm Ø x ~15 mm
31X CZ112A	0.0043	wrought ~41 mm Ø x ~15 mm

CRM LEADED BRASS SET

40 mm Ø x 30 mm

Number	Al	Bi	Cu	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn	
IMN WG1	0.096	0.0013	60.99	0.0084	0.16	0.20	0.029	0.71	(0.062)	(0.0046)	0.29	Rem	available individually
IMN WG2	(0.00095)	0.016	56.99	0.42	(0.0024)	0.0051	.	2.66	(0.0024)	(0.021)	(0.0025)	Rem	available individually
IMN WG3	0.041	0.0057	58.20	0.31	0.037	0.029	0.013	2.29	0.018	(0.014)	0.091	Rem	available in set only
IMN WG4	0.073	0.014	60.05	0.10	0.12	0.16	0.020	1.41	(0.042)	(0.016)	0.21	Rem	# 4 sold out
IMN WG5	0.058	0.0094	59.32	0.18	0.074	0.078	0.016	1.66	0.034	(0.022)	0.14	Rem	available in set only
IMN WG6	0.020	0.023	60.67	0.18	0.21	0.29	0.044	3.70	(0.0078)	(0.019)	0.40	Rem	available individually

CRM MANGANESE BRASS

chill cast analysis listed in mass % except * which is mg/kg

31X: ~40 mm Ø x ~15-18 mm

CTIF: 2 Discs 60 mm Ø x 5 mm

Number	Mn	Zn	Cu	Al	Fe	Ni	Pb	Si	Sn	As	Co	P	Sb	Ag*	Bi*	Cd*	Cr*
31X MNB12C *	16.1	21.2	58.3	0.70	0.29	0.696	1.97	0.046	0.171	0.0100	0.012	0.078	0.0101	21	101	22	26
31X B13G	2.84	36.67	60.03	0.0148	0.182	0.212	0.0188	0.032	0.0127	0.0120	.	.	0.0056	.	116	.	.
31X MNB3F	2.11	25.57	66.41	1.41	1.25	0.377	0.509	1.642	0.423	0.044	0.036	0.056	0.044	99	.	97	360
31X B12G	1.720	36.66	60.51	0.081	0.430	0.491	0.0244	0.0207	0.0229	0.0181	.	.	0.0194	.	198	.	.
31X MNB6C	0.871	28.51	70.01	0.0148	0.0697	0.261	0.016	0.0196	0.0308	0.0107	0.0107	0.0226	0.0128	509	.	.	.

* 31X MNB12Ca lso contains C:0.009

CRM MANGANESE BRASS DISC AND ROD SETS

Number	Al	As	Bi	Cu	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn	availability	Units
IMN MA1	1.51	0.085	0.0020	55.50	0.073	3.37	0.39	0.10	0.16	0.0061	0.071	1.04	Rem	set only	10 mm Ø x 100 mm
IMN MA2	3.35	0.0081	0.0029	60.88	1.27	1.30	0.011	0.015	0.020	0.0019	0.042	0.41	Rem	set only	10 mm Ø x 100 mm
IMN MA3	.	0.029	0.028	57.04	0.55	0.78	0.13	0.040	0.049	0.14	0.50	0.74	Rem	set only	10 mm Ø x 100 mm
IMN MA4	0.33	.	.	57.40	0.20	2.75	0.69	0.15	.	0.20	0.27	0.015	Rem	set only	10 mm Ø x 100 mm
IMN MA5	1.04	0.11	0.020	58.51	0.70	1.97	1.01	0.062	1.20	0.072	0.65	0.046	Rem	set only	10 mm Ø x 100 mm
IMN MA6	2.15	0.013	0.0072	60.45	1.72	0.50	0.056	0.019	0.60	0.016	0.013	0.13	Rem	set only	10 mm Ø x 100 mm
IMN WF1	.	.	0.00059	56.47	0.097	2.16	0.010	(0.0012)	0.010	0.00058	.	0.012	Rem	OK individually	44 mm Ø x 30 mm
IMN WF2	.	.	0.00091	57.66	0.21	1.79	0.040	(0.0032)	0.040	0.0018	.	0.045	Rem	OK individually	44 mm Ø x 30 mm
IMN WF3	.	.	0.0015	58.66	0.29	1.36	0.10	0.0075	0.070	0.0036	.	0.072	Rem	OK individually	44 mm Ø x 30 mm
IMN WF4	.	.	0.0021	60.50	0.42	0.57	0.15	0.0095	0.10	0.0045	.	0.11	Rem	OK individually	44 mm Ø x 30 mm
IMN WF5	.	.	0.0030	58.77	0.68	0.52	0.18	0.014	0.14	0.0061	.	0.16	Rem	set only	44 mm Ø x 30 mm
IMN WF6	.	.	0.00095	59.78	0.05	0.98	0.074	0.0020	0.026	.	.	0.028	Rem	OK individually	44 mm Ø x 30 mm

NAVAL BRASS

= class, where 1 = CRM and 2 = RM

31X NB: 42 mm Ø x ~15 mm

BS: 38 mm Ø x see below

CURM: 50 mm Ø x 10-12 mm

IARM: 38 mm Ø x 3 or 19 mm

#	Number	Sn	Pb	Zn	Cu	Al	As	Bi	Fe	Mn	Ni	P	S	Sb	Si	Ag	B	Co
2	CURM 42.25	2.72	0.0023	39.20	57.78	0.021	0.118	<0.001	0.003	0.169	<0.001	0.050	0.005	<0.001	<0.001	.	.	.
2	CURM 42.24	2.25	0.91	33.75	62.45	0.067	0.065	0.054	0.066	0.065	0.025	0.226	0.012	0.060	0.093	.	.	.
2	C42.25	2.2	<0.01	rem	58.5	0.02	0.10	<0.002	<0.005	0.13	<0.005	0.06	0.001	<0.005	<0.002	.	.	.
1	31X NB 4J	2.01	0.067	32.57	63.71	0.178	0.0062	0.104	0.235	0.0053	0.230	0.230	(0.0032)	0.450	0.203	.	0.0009	.
2	CURM 42.23	1.63	0.575	22.13	74.36	0.008	0.168	0.034	0.354	0.019	0.168	0.128	0.045	0.356	0.015	.	.	.
1	31X NB3J	1.38	0.127	24.46	72.86	0.130	0.0559	0.0786	0.071	0.124	0.0599	0.203	(0.004)	0.197	0.127	0.0464	.	.
1	IARM Cu485-18	0.759	1.76	36.5	60.8	(0.002)	(0.055)	.	0.062	0.0013	0.013	.	.	(0.0018)	(0.003)	C:(0.002)	Cd: 0.0005	.
1	IARM Cu464-21	0.751	0.066	38.5	60.7	0.0006	0.0011	0.0010	0.096	0.0115	0.0084	0.0012	.	0.0016	.	0.0040	.	.
1	IARM 76D	0.73	1.69	36.8	60.7	(0.002)	(0.004)	0.0011	0.013	0.0006	(0.003)	0.0018	0.0012	0.0040	0.0037	0.0014	.	0.0010
1	BS 485A	0.725	1.39	36.2	61.5	0.0022	(0.0003)	.	0.010	(0.001)	0.0017	(0.002)	(0.0005)	(0.006)	(0.005)	C:(0.002)	O:(0.0009)	.
1	IARM Cu486-18	0.692	1.31	36.5	61.2	(0.0030)	(0.025)	(0.0004)	0.036	(0.0003)	0.032	(0.004)	(0.0030)	(0.0050)	(0.002)	(0.004)	.	(0.0006)
1	BS 464B	0.69	0.054	38.7	60.5	(0.004)	0.0005	.	0.050	(0.09)	0.0092	(0.002)	0.0005	(0.001)	0.011	O: 0.0013	.	~7 or 19mm
2	BS 482A	0.65	0.50	38.8	60.0	(0.003)	<0.002	0.020	<0.002	(0.007)	<0.003	<0.002	0.0012	(0.002)	.	.	.	~7 or 19mm
2	BS 464A	0.62	0.056	38.73	60.6	(0.001)	<0.002	0.013	0.0002	0.004	0.012	0.001	(0.001)	<0.01	.	.	.	~7 or 19mm
2	CURM 42.21	0.60	0.259	31.61	66.78	0.003	<0.003	0.013	0.119	<0.001	0.120	0.087	0.034	0.25	0.15	.	.	.
1	IARM 75B	0.59	0.63	38.0	60.63	(0.005)	(0.004)	(0.001)	0.06	(0.003)	0.02	0.003	(0.001)	(0.004)	(0.003)	.	.	.
2	C42.21	0.54	0.23	rem	66.1	0.005	<0.005	0.012	0.06	<0.005	0.096	0.081	0.007	0.19	0.081	.	.	.
1	31X NB 1H	0.535	0.504	29.73	68.35	(0.0004)	0.161	0.0065	0.037	0.051	0.520	0.0223	0.0024	0.0057	0.004	.	.	(0.0006)

BS 464B and **BS 485A** are **17025**

CRM NAVAL BRASS SET

40 mm Ø x 25 mm

Number	Al	Bi	Cu	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn	availability
IMN WK1	0.11	0.014	59.97	0.28	0.13	0.28	0.030	0.17	0.024	0.30	0.11	Rem	ok individually
IMN WK2	0.080	0.011	60.54	0.16	0.088	0.21	0.017	0.33	0.018	0.29	1.34	Rem	ok individually
IMN WK3	0.045	0.0088	62.09	0.066	0.046	0.13	0.017	0.11	0.012	0.16	0.49	Rem	set only
IMN WK4	0.013	0.0052	63.28	0.085	0.020	0.070	0.010	0.050	0.0056	0.082	1.04	Rem	set only
IMN WK5	0.0042	0.0011	64.92	0.0092	0.0056	0.0055	0.0056	0.0062	0.0027	0.0064	0.47	Rem	ok individually

CRM NICKEL AND PHOSPHOR BRASS

analysis listed in mass %

Number	Ni	P	Cu	Zn	Al	Cd	Cr	Fe	Mn	Pb	Sn	Units
31X B29A	4.11	3.33	67.08	24.75	0.219	0.0144	0.062	0.144	0.0625	0.146	0.0328	40 mm Ø x ~15 mm
BAM 387	5.020	.	75.18	19.57	.	.	.	0.0617	0.0796	0.00108	0.00301	40 mm Ø x 30 mm

CRM NICKEL BRASS SETS

analysis listed in mass % except * which is mg/kg

IMN WH, WM: 40 mm Ø x 25 mm

IMN WP: 40 mm Ø x 30 mm

Number	Ni	Zn	Cu	Al	As	Bi	C*	Cd	Co	Fe	Mg	Mn	P	Pb	S	Sb	Si	Sn
available individually																		
IMN WP1	5.45	Rem	67.15	0.020	0.0012	0.00080	.	0.0019	.	0.020	.	0.0069	0.020	0.52	.	0.0010	(0.01)	0.0042
IMN WP2	7.79	Rem	65.08	0.0090	0.0049	0.0052	.	0.0052	.	0.12	.	0.040	0.0067	0.82	.	0.0052	(0.009)	0.11
IMN WP3	10.24	Rem	63.05	0.0020	0.011	0.012	.	0.011	.	0.20	.	0.15	0.0079	1.52	.	0.012	(0.03)	0.18
IMN WP4	12.38	Rem	60.91	0.039	0.015	0.016	.	0.016	.	0.31	.	0.35	0.011	(2)	.	0.015	(0.04)	0.26
IMN WP5	15.63	Rem	58.70	0.049	0.021	0.021	.	0.026	.	0.026	.	0.49	0.0027	(1.8)	.	0.028	(0.03)	0.33
IMN WP6	4.27	Rem	69.37	2.41
IMN WM1	5.03	25.35	69.06	0.083	0.00026	0.011	44	0.0046	0.021	0.011	0.0054	0.38	0.0018	0.018	0.017	0.00098	0.0026	0.0036
IMN WM2	6.66	24.18	68.41	0.050	0.0030	0.014	52	0.022	0.017	0.022	0.019	0.53	0.023	0.011	0.0058	0.013	0.0067	0.011
IMN WM3	6.09	23.57	69.85	0.033	0.0053	0.0055	58	0.0024	0.011	0.077	0.0042	0.19	0.0052	0.0073	0.0073	0.0043	0.037	0.098
IMN WM4	5.36	23.19	71.10	0.0080	0.0072	0.0029	72	0.0021	0.0099	0.13	0.0027	0.011	0.0057	0.0044	0.0058	0.0059	0.071	0.075
IMN WM5	4.68	25.90	68.99	0.0012	0.0089	0.0007	90	0.00077	0.0021	0.22	0.00056	0.0024	0.016	0.0020	0.0030	0.0068	0.094	0.035
available in SET ONLY																		
IMN WH1	5.70	Rem	68.16	.	.	.	(46)	.	0.0061	0.0052	.	0.56	0.0029	.	(0.0055)	.	0.010	.
IMN WH2	6.34	Rem	69.14	.	.	.	(58)	.	0.017	0.038	.	0.36	0.0072	.	(0.0071)	.	0.038	.
IMN WH3	3.44	Rem	70.18	.	.	.	(70)	.	0.031	0.11	.	0.25	0.013	.	(0.011)	.	0.072	.
IMN WH4	4.14	Rem	71.15	.	.	.	(75)	.	0.048	0.13	.	0.11	0.015	.	(0.017)	.	0.12	.
IMN WH5	4.89	Rem	72.28	.	.	.	(87)	.	0.028	0.22	.	0.011	0.017	.	(0.021)	.	0.17	.

SILICON BRASS

= class, where 1 = CRM and 2 = RM

Number	Si	Zn	Cu	Al	Fe	Mn	Ni	P	Pb	Sb	Sn
2 CTIF LS2	4.91	11.60	79.60	0.156	1.022	0.220	1.110	0.064	0.886	0.0103	0.338
1 ERM-EB393a	3.35	(20.8)	75.8	0.00021	0.0143	0.00185	0.00297	0.0454	0.0104	(0.000093)	0.00390
2 CTIF LS3	3.3	19	76	0.43	0.10	0.15	0.11	0.011	0.58	0.107	0.15
1 31X WSB6F	3.13	0.0506	95.40	(0.0013)	0.158	0.924	0.0509	0.0179	0.0310	0.0406	0.0142
1 IARM 313A	3.09	21.3	75.4	(0.001)	0.011	(0.001)	(0.002)	0.09	0.042	0.014	0.006
2 HRT CU2021	2.9	10.0	86.6	0.0008	0.019	0.044	0.002	0.081	0.006	0.001	0.006

Number	Ag	As	B	C	Cd	Co	Cr	S	Zr	Units
CTIF LS2	60 mm Ø x 5 mm
ERM-EB393a	.	0.000134	Bi:(0.000019)	.	0.000061	.	0.000156	Se:(0.00047)	.	40 mm Ø x 30 mm
CTIF LS3	60 mm Ø x 5 mm
31X WSB6F	0.0131	0.0110	0.0054	.	0.0039	0.0095	.	.	.	~40 mm Ø x ~15 mm
IARM 313A	0.0017	0.0010	0.0008	(0.002)	(0.0003)	(0.004)	(0.001)	0.0016	(0.0004)	31 mm Ø x 2 mm
HRT CU2021	.	(0.0006)	Bi:0.0006	.	0.0005	.	0.0006	0.001	.	42 mm Ø x 20 mm

CRM HIGH TENSILE BRASS

Number	Cu	Zn	Al	Fe	Mn	Si	As	C	Ni	P	Pb	S	Sb	Sn	Units
31X HT31B	67.00	17.06	6.82	3.01	5.69	0.0443	0.0005	0.0057	0.226	0.0030	0.0139	0.0007	B:0.0014	0.079	~40 mm Ø x ~15 mm
31X HT37A	60.33	34.69	0.0004	0.0344	2.88	1.38	0.0011	0.003	0.0105	0.003	0.623	<0.0005	0.0007	0.0116	40 mm Ø x 18 mm

RM BRONZE MUSHROOMS

chill cast typical analysis 60 mm Ø x 5 mm

Number	Sn	Zn	Cu	Al	As	Fe	Mn	Ni	P	Pb	S	Sb	Si
CTIF B 1	15.15	0.92	82.90	0.072	.	0.088	.	0.063	0.037	0.202	0.030	0.444	0.055
CTIF B 2	13.55	0.11	85.90	(0.002)	.	0.041	.	(0.003)	0.17	0.0206	0.048	(<0.002)	0.17
CTIF B 3	12.8	2.2	80.2	0.1	.	0.2	0.20	1.5	0.45	1.6	0.04	0.2	0.07
CTIF B 4	11.10	1.34	83.75	.	.	0.021	.	0.57	0.52	2.53	0.019	0.10	0.015
CTIF B 14	10.75	0.15	87.00	<0.01	0.04	0.11	0.02	0.30	0.64	0.50	0.02	0.08	0.075
CTIF B 13	10.05	1.09	86.35	0.016	0.065	0.250	0.046	0.50	0.210	0.99	0.070	0.243	0.085
CTIF B 5	9.90	0.42	85.95	0.039	.	0.18	0.082	2.28	0.041	0.48	0.067	0.47	0.049
CTIF B 30	9.80	1.05	77.45	0.063	.	0.115	0.150	0.97	0.063	10.0	0.048	0.22	0.066
CTIF B 12	9.57	0.61	85.65	0.120	0.111	0.162	0.235	2.63	0.525	0.201	0.013	0.117	0.050
CTIF B 11	8.04	2.10	84.75	.	.	0.170	.	2.0	0.057	1.93	0.09	0.70	0.14
CTIF B 31	7.65	0.79	78.65	(0.031)	.	(0.015)	.	0.489	.	11.79	0.028	0.475	(0.047)
CTIF B 23	7.18	1.46	83.45	0.020	.	(0.040)	.	0.086	0.070	7.20	0.019	0.384	0.025
CTIF B 10	6.95	2.75	83.65	0.205	0.0075	0.165	(0.0045)	1.01	0.014	4.07	0.050	1.14	.
CTIF B 20	6.35	3.77	83.35	0.040	.	0.165	.	0.51	0.072	5.10	0.115	0.520	0.055
CTIF B 32	5.92	1.17	74.80	0.075	0.0056	0.11	.	1.49	0.039	16.10	0.027	0.13	0.070
CTIF B 21	5.13	6.17	83.05	0.13	.	0.285	.	1.21	(0.004)	3.79	0.047	0.18	.
CTIF B 22	3.5	4.0	83.0	.	.	<0.10	.	2.5	.	6.0	0.03	0.05	<0.1
CTIF UN 3S	0.215	1.62	92.65	0.11	.	0.30	0.073	3.45	.	0.20	.	.	1.24

Number	Sn	Zn	Cu	Al	As	Fe	Mn	Ni	P	Pb	S	Sb	Si
--------	----	----	----	----	----	----	----	----	---	----	---	----	----

BRONZE

Number	Cu	Fe	Ni	P	Pb	Sn	Zn	method	Units
32X CSN1A	.	0.0020	(0.0001)	0.0007	.	0.306	0.0039	wrought	~20 mm Ø x ~22 mm
SRM 1115	87.9	0.13	0.074	0.005	0.013	0.10	11.7	wrought	31 mm Ø x 19 mm
SRM C1115	87.9	0.13	0.074	0.005	0.013	0.10	11.7	cast	31 mm x 31 mm x 19 mm
SRM 1116	90.3	0.046	0.048	0.008	0.042	0.04	9.4	wrought	31 mm Ø x 19 mm
SRM 1117	93.0	0.014	0.020	0.002	0.069	0.02	6.8	wrought	31 mm Ø x 19 mm
SRM C1117	93.0	0.014	0.020	0.002	0.069	0.02	6.8	cast	31 mm x 31 mm x 19 mm

CRM ALUMINUM BRONZE SETS

analysis listed in mass % except * which is mg/kg

40 mm Ø x ~25-30 mm

Number Singly?	Al	As	Bi	Cd	Co	Cr*	Fe	Mg*	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	
IMN BF1	10.90	0.061	0.00042	.	.	.	(6.2)	.	0.0059	2.49	(0.012)	0.23	.	(0.002)	0.26	0.011	0.57	no
IMN BF2	9.96	0.050	0.0025	.	.	.	(5.4)	.	0.12	3.54	0.053	0.15	.	(0.013)	0.25	0.081	0.40	yes
IMN BF3	9.58	0.038	0.0039	.	.	.	4.50	.	0.28	4.43	0.098	0.111	.	0.028	0.20	0.17	0.27	no
IMN BF4	9.12	0.022	0.0057	.	.	.	3.25	.	0.39	5.24	0.13	0.059	.	0.037	0.097	0.25	0.10	yes
IMN BF5	8.35	0.0039	0.010	.	.	.	2.44	.	0.50	6.03	0.16	0.014	.	0.048	0.028	0.35	0.018	yes
IMN BP1	8.935	0.00094	0.00053	0.00054	.	3.7	0.00305	.	0.00535	0.243	0.00055	0.00055	.	0.00052	(0.00544)	0.00043	0.0100	yes
IMN BP2	6.136	0.00215	0.00222	0.00214	.	26.7	0.0184	.	0.0189	1.032	0.00208	0.00238	.	0.00468	0.0220	0.00199	0.024	no
IMN BP3	7.120	0.00980	0.0102	0.00928	.	104	0.0743	.	0.152	1.850	0.00661	0.0103	.	0.0108	0.0804	0.0106	0.176	no
IMN BP4	4.632	0.0238	0.0207	0.0226	.	217	0.0131	.	0.304	2.522	0.0238	0.0229	.	0.0215	0.183	0.0229	0.343	no
IMN BP5	3.769	0.0361	0.0349	0.0356	.	374	0.200	.	0.411	3.528	0.0189	0.0347	.	0.0356	0.266	0.0336	0.459	yes
IMN B01	3.16	0.00033	0.00030	0.00035	.	32.7	0.0158	.	0.0167	0.00517	(0.0004)	0.00384	.	0.00035	(0.00471)	2.54	7.10	yes
IMN B02	4.03	0.00199	0.00197	0.00182	.	3.7	0.00569	.	0.00102	0.00204	0.00227	(0.00214)	.	0.00226	0.00979	1.83	6.26	yes
IMN B03	4.67	0.00662	0.00660	0.00570	.	54.8	0.0752	.	0.00884	0.0683	0.00550	0.0537	.	0.00568	0.0552	1.17	5.07	yes
IMN B04	6.15	0.0115	0.0107	0.00881	.	91	0.137	.	0.00612	0.111	0.0100	0.102	.	0.0104	0.0951	0.704	4.28	yes
IMN B05	7.02	0.0161	0.0152	0.0134	.	145	0.218	.	0.0772	0.0355	0.0155	0.0299	.	0.0152	0.0135	0.117	3.08	yes
IMN BJ1	2.88	0.011	0.013	0.016	0.027	.	0.011	58	0.60	6.97	0.0022	0.0025	0.021	0.0012	(0.11)	(0.11)	0.020	yes
IMN BJ2	2.46	0.0089	0.0095	0.011	0.020	.	0.038	98	0.42	6.47	0.011	0.0043	0.014	0.0030	(0.091)	(0.080)	0.038	yes
IMN BJ3	1.97	0.0072	0.0071	0.0076	0.014	.	0.12	65	0.21	5.87	0.014	0.0081	0.0082	0.0056	(0.047)	(0.049)	0.22	no
IMN BJ4	1.50	0.0031	0.0042	0.0048	0.0076	.	0.20	35	0.013	5.49	0.013	0.010	0.0049	0.0088	(0.015)	(0.014)	0.36	no
IMN BJ5	1.09	0.0018	0.0013	0.00075	0.0024	.	0.28	17	0.0030	5.00	0.019	0.017	0.0023	0.010	(0.0071)	(0.0034)	0.51	yes

ALUMINUM BRONZE - LOW NICKEL

= class, where 1 = CRM and 2 = RM

#	Number	Al	Cu	As	Cr	Fe	Mg	Mn	Ni	P	Pb	Si	Sn	Zn
1	32X ALB9C	13.52	81.64	0.0163	0.0206	3.12	0.090	0.159	0.628	0.096	0.267	0.235	0.0601	0.142
1	IARM Cu954-20	10.48	84.7	0.0007	0.028	3.84	.	0.54	0.30	0.009	0.018	0.029	0.010	0.068
1	IARM Cu955-18	10.37	80.8	(0.0020)	0.008	3.50	.	0.77	4.5	(0.013)	0.006	(0.022)	0.0056	0.038
1	IARM Cu954-18	10.36	84.7	(0.0030)	(0.003)	4.23	(0.0013)	0.29	0.134	(0.016)	0.016	0.025	0.047	0.141
1	BS 624	10.2	86.5	<0.01	.	3.02	.	0.16	0.052	<0.005	<0.005	0.019	(0.016)	(0.007)
2	BS 954A	10.17	85.64	(0.006)	.	3.50	.	0.10	0.20	0.012	0.016	0.029	0.033	0.30
2	HRT CU2018	10.00	84.06	.	.	3.06	.	2.49	0.04	0.014	(0.021)	0.020	0.014	0.10
1	VS BR1	9.6	.	.	.	3.32	.	1.41	0.015	0.007	0.016	0.041	0.011	0.075
1	VS BR4	9.4	.	.	.	3.38	.	1.51	0.043	.	0.015	0.077	0.008	0.034
1	32X CA 7A	9.37	88.06	.	0.0028	2.09	0.0004	0.151	0.234	.	(0.004)	0.017	0.0172	0.006
2	BS 623	9.24	(88.1)	<0.01	.	2.25	.	0.16	0.10	0.013	<0.01	0.046	0.01	0.05
1	IARM 79C	9.20	87.6	0.003	(0.002)	2.28	.	0.20	0.55	0.006	<0.005	0.033	0.010	0.014
1	IARM 79B	9.19	88.4	.	(0.003)	2.13	.	0.16	0.075	0.005	(0.003)	0.019	0.017	0.013
2	BS 623A	9.12	88.13	(0.006)	.	2.19	.	0.273	0.146	<0.002	0.001	0.014	0.002	0.008
1	VS BR2	8.53	.	.	.	0.101	.	1.77	0.023	0.0083	0.0085	0.038	0.019	0.011
2	CURM 51.14	8.42	88.57	0.44	.	0.72	.	0.55	0.219	0.012	0.003	0.286	0.113	0.656
2	CURM 51.13	7.30	88.79	0.215	.	1.81	.	0.898	0.057	0.022	0.104	0.174	0.270	0.335
1	BS 642B	7.17	89.9	0.0015	0.0014	0.285	0.0032	0.069	0.222	0.004	0.0152	2.15	0.0056	0.128
1	BS 642C	7.13	90.4	0.0008	0.0009	0.11	0.0014	0.0148	0.0363	0.0040	0.0109	2.20	0.0061	0.039
2	C51.13	6.93	Rem	0.21	.	2.05	.	0.77	0.053	0.021	0.12	0.16	0.19	0.30
1	32X 61400A	6.81	89.99	.	.	2.74	0.0050	0.082	0.0242	0.0008	(0.0007)	0.0124	0.301	0.060
1	BS 642D	6.73	91.2	(0.002)	0.0004	0.152	(0.0003)	0.018	0.047	0.0007	0.0038	1.77	0.019	0.093
1	IARMCu642-18	6.5	90.0	.	.	0.039	.	0.0024	(0.014)	(0.009)	0.019	1.96	0.019	1.19
2	CURM 51.12	6.36	88.29	0.111	.	2.87	.	1.33	0.112	<0.001	0.219	0.005	0.196	0.45
1	32X CA12A	6.14	90.48	.	0.0008	0.657	0.0005	0.0290	0.088	.	(0.0017)	2.57	0.0157	0.0405
2	C51.12	6.06	Rem	0.11	.	2.90	.	1.25	0.11	<0.005	0.25	<0.01	0.18	0.42
2	CURM 51.11	5.27	93.95	<0.001	.	0.060	.	<0.001	0.012	0.035	0.33	0.159	0.027	0.111

Number	Ag	Be	C	Co	N	O	S	Sb	Zr	Units
32X ALB9C	0.0417	.	.	0.0027	Te:0.0058	~40 mm Ø x ~15 mm
IARM Cu954-20	0.00015	.	Bi:0.0012	0.0012	.	.	(0.005)	0.0018	.	38 mm Ø x 3 or 19 mm
IARM Cu955-18	0.0019	.	(0.0080)	0.0027	.	.	(0.0012)	(0.0020)	.	31 mm Ø x 2 or 18 mm
IARM Cu954-18	.	Bi:0.0011	(0.007)	0.017	(0.0006)	(0.0010)	(0.0020)	(0.0009)	(0.0004)	31 mm Ø x 2 or 18 mm
BS 624	.	.	0.0041	.	.	(0.0005)	<0.005	<0.01	.	44 mm Ø x ~7 or 19+ mm 17025
BS 954A	.	.	0.004	.	.	.	<0.0001	0.001	.	38 mm Ø x ~7 mm last
HRT CU2018	40 mm Ø x 20 mm
VS BR1	38 mm Ø x 18 mm
VS BR4	38 mm Ø x 18 mm
32X CA 7A	0.0009	.	0.0028	0.0003	42 mm Ø x 18 mm
BS 623	.	.	(0.002)	.	.	.	(0.001)	<0.01	.	37 mm Ø x 12 mm last
IARM 79C	<0.005	.	0.003	<0.005	.	.	<0.001	<0.005	.	31 mm Ø x 2 or 18 mm
IARM 79B	0.002	.	0.002	(0.002)	.	.	(0.001)	.	.	31 mm Ø x 2 or 18 mm
BS 623A	.	.	(0.002)	.	.	.	<0.0005	<0.002	.	38 mm Ø x ~7 or 19+ mm
VS BR2	(0.004)	.	38 mm Ø x 18 mm
CURM 51.14	50 mm Ø x 10 - 12 mm
CURM 51.13	50 mm Ø x 10 - 12 mm
BS 642B	.	<0.005	0.0013	<0.005	<0.0005	<0.0005	<0.0005	0.0004	<0.0005	38 mm Ø x ~7 or 19 mm 17025
BS 642C	.	<0.005	<0.005	<0.005	<0.005	<0.0005	<0.0005	<0.0005	<0.0005	38 mm Ø x ~7 or 19 mm 17025
C51.13	50 mm Ø x 10 - 12 mm
32X 61400A	0.0010	(0.0004)	.	~45 mm Ø x ~15 mm
BS 642D	0.0011	.	0.0011	(0.0007)	(0.0005)	0.0007	(0.0003)	(0.001)	(0.0001)	38 mm Ø x ~7 or 19+ mm 17025
IARMCu642-18	31 mm Ø x 2 or 18 mm
CURM 51.12	50 mm Ø x 10 - 12 mm
32X CA12A	0.0010	.	(0.002)	(0.0003)	42 mm Ø x 18 mm
C51.12	50 mm Ø x 10 - 12 mm
CURM 51.11	50 mm Ø x 10 - 12 mm

Need a larger size?
Most BS items are
available in any height.

ALUMINUM BRONZE - HIGH NICKEL

= class, where 1 = CRM and 2 = RM

#	Number	Al	Cu	As	Cr	Fe	Mg	Mn	Ni	P	Pb	Si	Sn	Zn
1	32X ALB 10B	12.11	73.64	0.0194	0.0152	3.63	0.0122	1.626	7.21	0.069	0.152	0.158	0.201	0.961
1	IARM 94B	10.8	80.6	<0.01	0.017	3.99	.	0.071	4.31	0.011	0.004	0.028	(0.003)	0.14
2	BS 955C	10.68	80.6	<0.002	.	4.04	.	0.06	4.31	0.012	0.003	0.025	0.003	0.15
1	IARM Cu954-21	10.55	85.1	.	0.022	3.66	0.0013	0.393	0.105	0.0031	0.012	0.029	0.0053	0.029
1	IARM 204A	10.55	83.3	<0.01	0.008	3.87	.	0.052	1.95	0.007	0.004	0.034	0.005	0.22
1	32X ALB 3S	10.43	80.01	0.0213	0.0392	3.720	0.0659	0.243	3.51	0.0345	0.117	0.155	0.1209	1.313
2	BS 954C	10.21	83.9	(0.006)	.	3.9	.	0.29	1.38	0.011	0.050	0.07	0.08	0.09
1	BS 954B	10.20	83.9	(0.005)	.	3.90	.	0.27	1.38	0.012	0.047	0.07	0.07	0.10
2	BS 630A	10.05	81.0	(0.002)	.	3.73	.	0.11	4.81	<0.01	0.0069	0.037	0.019	0.17
2	HRT CU2001	10.05	79.09	.	.	4.79	.	0.36	4.94	0.011	0.015	0.08	0.018	0.17
2	C52.51	10.0	Rem	.	<0.01	4.3	<0.01	<0.01	5.1	.	<0.01	<0.01	<0.01	0.02
2	HRT CU2009	9.93	78.88	.	.	3.73	.	0.29	6.22	0.010	0.037	0.19	0.020	0.54
1	IARM 334B	9.91	80.8	(0.003)	(0.004)	3.7	(0.001)	0.60	4.70	0.005	0.006	0.075	0.019	0.122
1	BS 630C	9.90	80.7	0.0007	0.0030	3.82	0.0011	0.325	4.82	0.0043	0.0093	0.064	0.0152	0.234
1	BS 630B	9.78	80.8	0.0007	0.0017	3.90	0.0009	0.281	4.88	0.0028	0.0056	0.0166	0.0289	0.254
1	IARM 334A	9.76	80.7	(0.004)	(0.01)	3.82	(0.001)	0.69	4.77	(0.005)	0.010	0.073	0.025	0.110
1	IARM 80D	9.67	(81.7)	(0.009)	(0.005)	2.99	(0.003)	0.346	5.01	(0.005)	(0.005)	0.025	0.093	(0.007)
1	32X ALB 6K	9.69	80.77	0.0116	(0.1)	2.71	0.0104	0.787	5.42	(0.006)	0.0749	0.073	0.120	0.126
1	VS BR3	9.6	.	.	.	4.00	.	0.227	3.85	(0.003)	0.007	0.071	0.005	0.009
2	BS CC954	9.28	84.0	0.003	.	3.61	.	0.353	1.12	0.013	0.13	0.092	0.061	1.30
2	C52.56	8.9	Rem	.	0.14	4.6	0.09	0.74	5.6	.	0.17	0.15	0.11	0.28
1	32X ALB 12A	8.29	82.90	.	.	1.094	0.0013	0.958	6.33	0.0101	0.0018	0.0202	0.310	0.0625
2	CURM 52.54	7.85	81.59	.	<0.005	3.31	<0.005	1.20	5.40	.	0.086	0.022	0.135	0.39
1	32X ALB 5K	7.21	83.72	.	0.192	2.04	0.179	1.416	3.92	(0.051)	0.0512	0.107	0.0293	0.80
1	32X ALB 13A	7.09	84.96	.	.	1.171	.	5.39	1.381	0.009	(0.0009)	0.086	0.0072	0.0194
1	32X ALB 8E	6.38	77.17	0.145	0.36	5.54	0.015	1.562	6.68	0.171	0.071	0.603	0.312	0.352
1	32X ALB 8F	6.21	77.04	0.189	0.088	5.37	0.194	1.57	6.11	0.261	0.049	0.513	0.435	1.395

#	Number	Al	Cu	As	Cr	Fe	Mg	Mn	Ni	P	Pb	Si	Sn	Zn
---	--------	----	----	----	----	----	----	----	----	---	----	----	----	----

Number	Ag	Be	Bi	C	Co	S	Sb	Se	Units
32X ALB 10B	0.0144	.	.	.	0.0984	.	.	Te:0.0108	~40 mm Ø x ~15 mm
IARM 94B	0.017	.	.	(0.006)	0.011	0.002	(0.011)	.	31 mm Ø x 2 mm
BS 955C	0.014	<0.002	.	38 mm Ø x ~7 or 19+ mm
IARM Cu954-21	0.0012	.	(0.0009)	.	(0.002)	(0.0019)	(0.0019)	.	38 mm Ø x 3 or 19 mm
IARM 204A	0.009	.	.	0.006	0.008	(0.002)	<0.01	.	31 mm Ø x 2 mm
32X ALB 3S	0.0272	.	.	.	0.0760	.	.	Nb:0.018	~40 mm Ø x ~15 mm
BS 954C	.	.	.	(0.004)	.	<0.0005	<0.003	.	38 mm Ø x ~7 or 19+ mm
BS 954B	.	.	.	(0.005)	.	<0.0005	(0.001)	.	38 mm Ø x ~7 or 19+ mm
BS 630A	.	.	.	0.005	.	(0.001)	<0.001	.	38 mm Ø x ~7 mm
HRT CU2001	0.003	.	.	40 mm Ø x 20 mm
C52.51	50 mm Ø x 10 - 12 mm
HRT CU2009	40 mm Ø x 20 mm
IARM 334B	0.0013	(0.001)	(0.001)	0.005	(0.003)	0.0008	(0.004)	(0.004)	31 mm Ø x 2 or 18 mm
BS 630C	.	<0.0005	.	0.0060	0.0019	<0.0005	0.0003	.	38 mm Ø x ~7 or 19 mm+
BS 630B	.	<0.0005	.	0.0067	0.0017	0.0013	<0.0005	.	38 mm Ø x ~7 or 19 mm+
IARM 334A	(0.001)	(0.001)	(0.001)	0.0058	(0.003)	0.0007	0.004	.	31 mm Ø x 2 or 18 mm
IARM 80D	(0.04)	<0.002	(0.004)	(0.004)	0.022	(0.003)	<0.02	<0.03	31 mm Ø x 2 or 18 mm
32X ALB 6K	0.0082	.	.	.	0.139	.	.	.	~40 mm Ø x ~15 mm
VS BR3	38 mm Ø x 18 mm
BS CC954	.	.	.	(0.007)	.	(0.002)	0.004	.	32 mm Ø x 17 mm
C52.56	50 mm Ø x 10 - 12 mm
32X ALB 12A	0.044	.	.	.	0.0056	.	.	(0.0007)	~41 mm Ø x ~15 mm
CURM 52.54	50 mm Ø x 10 - 12 mm
32X ALB 5K	0.0061	.	.	0.0606	.	Nb:0.181	.	Te:0.047	~40 mm Ø x ~15 mm
32X ALB 13A	0.0011	.	.	(0.0007)	~35 mm Ø x ~15 mm
32X ALB 8E	0.0099	.	.	.	0.554	.	0.024	.	~40 mm Ø x ~15 mm
32X ALB 8F	0.0100	.	.	0.0204	0.425	.	0.0250	.	~40 mm Ø x ~15 mm Nb:(0.002) Te:(0.003)

Number	Ag	Be	Bi	C	Co	S	Sb	Se	Units
--------	----	----	----	---	----	---	----	----	-------

Need a larger size?
Most BS items are
available in any height.

RM ALUMINUM BRONZE MUSHROOMS

chill cast	typical analysis													60 mm Ø x 5 mm
Number	Al	Cu	Fe	Mn	Ni	Pb	Si	Sn	Zn	Bi	Cd	Cr	Mg	
CTIF CA 36	12.60	77.25	2.93	0.131	6.33	0.0154	0.113	0.201	0.244	0.058	.	0.041	0.130	
CTIF 2158-W	11.95	85.00	2.53	0.26	0.10	<0.005	0.015	<0.01	<0.01	
CTIF 4065-P	11.85	81.20	3.40	0.075	3.18	0.03	0.034	0.18	0.03	
CTIF CA 35	11.4	75.6	6.1	1.6	3.80	0.10	0.25	0.30	0.55	
CTIF 2154-V	11.25	85.00	3.05	0.12	0.41	<0.005	0.015	<0.01	<0.01	
CTIF CA 13	11.20	82.45	3.82	1.22	0.50	0.0230	0.11	(0.01)	0.65	
CTIF CA 3	10.9	86.5	0.80	0.06	0.80	0.15	0.08	0.20	0.30	
CTIF CA 21	10.82	81.9	3.45	0.30	3.09	0.05	0.07	0.07	0.100	.	0.0095	.	.	
CTIF CA11	10.54	84.45	1.27	0.779	1.95	0.109	0.254	0.258	0.211	.	.	.	0.125	
CTIF CA 22	10.45	80.50	2.51	0.745	4.54	0.0243	0.32	0.30	0.605	
CTIF 3011-G	10.35	84.80	1.98	0.165	2.00	0.10	0.16	0.125	0.25	
CTIF CA 27	10.25	81.1	2.81	1.195	3.88	0.11	0.127	0.054	0.428	.	0.012	.	.	
CTIF CA 10	10.15	80.65	4.55	0.333	3.39	0.16	0.46	0.16	0.067	
CTIF 3299-J	10.10	87.60	0.38	1.12	0.21	0.110	0.136	0.106	0.19	
CTIF 3297-Y	10.00	87.45	1.88	0.03	.	0.11	0.15	0.10	0.27	
CTIF CA37	9.84	76.79	6.85	0.752	4.98	0.0503	0.040	0.147	0.364	0.0118	.	0.085	0.077	
CTIF 4149-G	9.84	84.95	2.00	0.21	1.96	0.15	0.18	0.34	0.37	
CTIF 2152-S	9.78	85.05	3.99	0.42	0.68	<0.005	0.015	.	<0.01	
CTIF 2151-R	9.43	84.75	4.48	0.73	0.56	<0.005	0.015	<0.01	<0.01	
CTIF 3296-L	9.40	88.55	0.07	0.37	0.41	0.30	0.20	0.06	0.62	
CTIF CA 31	9.15	76.5	3.18	3.27	7.51	0.020	0.064	0.063	0.145	.	.	.	0.02	
CTIF CA 26	9.10	81.25	4.36	0.188	4.87	0.058	0.035	0.005	0.038	.	0.034	.	.	
CTIF 3300-M	8.73	89.5	0.45	0.165	0.205	0.205	0.415	0.205	0.085	
CTIF 3301-Z	8.10	87.30	4.00	0.26	0.125	0.032	0.057	0.028	0.06	
CTIF 2794-H	8.0	90.3	0.82	<0.01	0.69	<0.01	0.048	0.105	<0.01	
CTIF CA 20	8.00	87.15	0.79	1.85	1.18	0.18	0.17	0.19	0.41	.	0.05	.	.	
CTIF CA 12	8.0	84.1	2.77	3.09	1.385	0.047	0.058	0.036	0.45	
CTIF CA 25	7.97	79.12	6.10	0.51	5.74	0.03	0.084	0.177	0.252	
CTIF CA 30	7.55	81.6	5.2	2.05	3.10	0.142	0.15	0.099	0.066	
CTIF 3018-F	7.25	81.90	4.45	1.57	4.50	0.02	0.085	0.06	0.06	
CTIF 3610-Q	7.10	82.32	3.98	0.045	5.40	0.23	0.065	0.25	0.51	.	0.090	.	.	
Number	Al	Cu	Fe	Mn	Ni	Pb	Si	Sn	Zn	Bi	Cd	Cr	Mg	

CRM BISMUTH BRONZE

Number	Bi	Cu	Ni	P	Pb	Sn	Zn	Al	Fe	O	S	Sb	Se	Units
IARM CuMB1-18	4.51	88.98	0.58	0.049	0.015	5.58	0.47	(0.0012)	(0.0016)	(0.003)	(0.0020)	(0.003)	(0.0025)	31 mm Ø x 2 mm or 18 mm

MANGANESE BRONZE

#	Number	Mn	Al	Fe	Sn	Zn	Cu	As	C	Co	Cr	Ni	P	Pb	S	Sb	Si
# = class, 1=CRM and 2=RM		BS 675B, 863B, 675A: 38 Ø x ~7 to 19+ mm										BS 675: 38 Ø x 12 mm		IARM: 31 Ø x 2 or 18 mm			
1	BS 863B	2.97	5.25	2.84	0.033	26.1	[62.4]	0.0004	0.0028	0.0009	0.0042	0.081	0.0010	0.0205	0.0007	0.0012	0.0103
1	IARM 88C	2.99	5.79	2.98	0.147	22.86	64.5	(0.007)	0.005	0.0010	0.008	0.276	0.020	0.133	0.0010	(0.003)	0.091
2	BS 675A	0.32	<0.002	1.12	0.8	39.1	58.5	0.003	(0.0007)	.	.	0.019	0.010	0.074	(0.0005)	0.0011	(0.005)
1	BS 675B	0.175	(<0.005)	1.10	0.92	39.3	58.7	0.0009	(<0.001)	(0.0002)	(0.0002)	0.0071	0.0020	0.071	0.0002	0.0011	(<0.005)
1	IARM 83B	0.13	0.002	0.97	0.85	39.3	58.7	.	0.003	.	.	0.010	0.004	0.017	(0.001)	(0.004)	(0.003)
2	BS 675	0.11	<0.01	0.73	0.92	39.7	Rem.	<0.005	(0.0004)	.	last	<0.01	<0.01	<0.01	(0.0013)	<0.01	<0.02

BS 675B and 863B are 17025

CRM NICKEL BRONZE SET

available in SET/5 or individually		analysis listed in mass %												40 mm Ø x ~30 mm
Number	Al	Bi	Cu	Fe	Ni	P	Pb	S	Sb	Se	Si	Sn	Zn	
IMN BN5	0.0245	0.0298	rem	0.00731	2.69	0.0634	0.00612	0.0018	0.0314	0.00636	(0.00211)	11.82	0.0560	
IMN BN1	0.00286	0.118	rem	0.495	0.226	0.123	0.0239	0.113	0.117	0.00335	(0.00839)	6.47	0.135	
IMN BN2	0.00371	0.0707	rem	0.589	1.64	0.0769	0.00514	0.213	0.0656	0.0104	.	6.21	0.369	
IMN BN3	0.00126	0.00098	rem	0.153	1.04	0.00038	0.0054	(0.0017)	0.0088	.	.	9.29	0.0625	
IMN BN4	0.00055	0.00595	rem	0.0216	0.635	0.0066	0.0145	0.112	0.0055	0.0134	(0.00064)	9.81	0.00771	

Need a larger size?
Most BS items are
available in any height.

PHOSPHOR BRONZE

= class, where 1 = CRM and 2 = RM

* Provisional Analysis

#	Number	P	Sn	Zn	Cu	Mn	Ni	Pb	Al	As	Fe	Mg	S	Sb	Si
1	32X PB11H	0.89	3.07	1.53	91.3	0.0404	0.70	1.07	0.070	0.187	0.377	0.015	0.011	0.446	0.084
1	BS 510C	0.335	5.43	0.13	94.1	<0.001	0.015	0.0051	(0.0009)	<0.005	0.0042	.	0.0019	<0.01	0.0028
1	32X 51000A	0.300	4.85	0.0105	94.87	.	0.0084	0.0032	0.0007	.	0.0024	.	0.0021	.	.
1	33X 54400A	0.243	3.97	3.87	86.79	.	0.244	4.69	0.0009	0.0156	0.072	.	0.0251	0.0362	.
1	IARM 78B	0.19	4.73	3.55	87.7	(0.002)	0.077	3.87	(0.002)	<0.003	0.02	.	0.010	0.01	<0.002
1	IARM Cu510-18 (0.16)	4.54	0.0034	95.2	(<0.0010)	(0.017)	(0.0027)	(0.0004)	(0.0007)	(0.0008)	.	.	(0.0020)	(0.0008)	(<0.0050)
1	IARM 77B	0.148	4.66	0.007	95.2	(0.002)	0.002	0.016	(0.001)	(0.001)	0.002	.	0.002	0.005	(0.003)
1	32X 52100A	0.146	7.73	0.0026	92.10	.	0.0111	0.0031	0.0009	0.0009	0.0008	.	0.0008	.	.
1	32X PB14E	0.128	9.65	0.103	89.70	0.0141	0.103	0.0354	0.0201	0.0235	0.0211	.	0.070	0.0433	(0.003)
2	BS 510A	0.11	4.6	0.21	95.10	<0.002	0.020	0.016	<0.002	0.0008	0.005	.	0.008	(0.003)	<0.003
2	CURM 54.02	0.107	5.53	0.410	92.87	0.101	0.109	0.663	0.020	0.023	0.102	0.0020	0.030	0.026	0.012
1	32X PB15B	0.104	2.04	0.75	.	0.0006	0.145	0.046	0.064	0.102	0.044	0.023	0.0016	0.020	.
1	32X PB13E	0.089	6.55	0.301	92.48	0.0440	0.0953	0.109	0.0251	0.0391	0.0549	.	.	0.092	0.053
1	BS 510B	0.074	4.6	0.251	[95.0]	0.0004	0.0211	0.0112	(0.006)	0.0010	0.009	.	0.007	(0.002)	(0.003)
1	IARM Cu544-18	0.069	4.14	3.80	88.0	.	0.019	3.92	.	.	(0.010)
2	CURM 54.01	0.053	3.17	0.346	95.42	0.158	0.348	0.307	0.040	0.044	0.028	0.008	0.023	0.070	0.039
2	HRT CU2016	0.050	7.23	0.006	92.67	.	0.007	0.006	.	.	0.004	.	0.003	0.006	.
2	C54.01	0.05	3.2	0.31	Rem	0.13	0.26	0.29	0.009	0.04	0.01	<0.001	0.03	0.08	0.006
1	BS 544B	0.0258	4.06	3.51	88.2	(0.0009)	0.068	3.9	(0.0009)	0.0043	0.087	.	0.0249	0.0244	0.0042
1	32X PB17A	0.017	21.8	0.0188	77.3	.	0.044	0.213	.	0.175	0.0009	.	0.0220	0.051	.
1	BS 544C	0.0092	4.10	3.78	88.4	<0.005	0.153	3.31	<0.05	(0.008)	0.055	.	0.058	0.0045	0.0029
1	32X PB16A	0.0073	17.60	0.0082	82.02	.	0.127	0.088	(0.0006)	0.0035	(0.001)	.	0.0049	0.013	0.005

Number	Ag	Bi	C	Co	Cr	N	O	Se	Units
32X PB11H	B:0.0021	0.023	.	0.034	~40 mm Ø x ~15 mm
BS 510C	(0.004)	.	(0.0010)	0.0008	<0.005	.	0.0006	.	38 mm Ø x ~7 or 19+ mm 17025
32X 51000A	0.0022	38 mm Ø x ~15 mm
33X 54400A	0.0124	.	.	0.0013	~38 mm Ø x ~15 mm
IARM 78B	31 mm Ø x 2 mm (OK) or 18 mm (LAST)
IARM Cu510-18	0.0019	.	(0.0018)	.	.	.	0.0011	.	31 mm Ø x 2 or 18 mm
IARM 77B	.	.	0.003	31 mm Ø x 2 or 18 mm
32X 52100A	0.0011	0.0019	38 mm Ø x ~15 mm
32X PB14E	0.0152	0.146	.	0.0047	~40 mm Ø x ~15 mm
BS 510A	.	.	(0.0006)	38 mm Ø x ~7 or 12 mm
CURM 54.02	50 mm Ø x 10-12 mm
32X PB15B	.	(0.0002)	.	0.037	0.0004	.	.	(0.0008)	~40 mm Ø x ~15 mm
32X PB13E	0.0205	0.0224	.	0.0088	~40 mm Ø x ~15 mm
BS 510B	Zr: (0.0004)	0.0010	(0.0006)	(0.0008)	(0.0001)	0.0009	.	.	38 mm Ø x ~7 or 19+ mm 17025
IARM Cu544-18	38 mm Ø x ~3 or 19 mm
CURM 54.01	50 mm Ø x 10-12 mm
HRT CU2016	40 mm Ø x 20 mm
C54.01	50 mm Ø x 10-12 mm
BS 544B	0.0173	.	0.0031	(0.0012)	(0.0007)	(0.0007)	0.0005	.	38 mm Ø x ~7 or 19+ mm 17025
32X PB17A	0.017	0.026	.	0.0018	(0.0004)	.	.	0.0022	~40 mm Ø x ~15 mm
BS 544C	<0.005	.	0.0018	(0.0020)	<0.005	.	0.0006	.	38 mm Ø x ~7 or 19+ mm 17025
32X PB16A	0.0166	0.0530	.	(0.0004)	.	.	.	Te: (0.002)	~40 mm Ø x ~15 mm

SILICON BRONZE

= class, where 1 = CRM and 2 = RM

#	Number	Si	Cu	Mn	Al	As	C	Cr	Fe	Ni	P	Pb	Sn	Zn
1	BS 655B	3.25	95.7	0.928	(<0.005)	0.0004	0.0012	0.0006	0.042	0.0043	0.0047	0.0205	0.0053	0.0248
1	BS 655C	3.22	95.6	0.958	(<0.005)	0.0006	(<0.005)	0.0021	0.052	0.0030	0.0035	0.0047	0.0049	0.0152
1	IARM 82B	3.22	95.3	1.04	0.002	<0.002	(0.003)	0.004	0.080	0.011	0.004	0.011	0.017	0.38
1	37X 65500A	3.13	95.75	0.960	0.0028	.	(0.0044)	0.0029	0.035	0.0059	0.0046	0.0034	0.0426	0.0353
1	IARM Cu655-18	3.15	95.5	0.98	(0.0020)	(0.0004)	(0.0100)	.	0.055	0.0034	(0.0020)	(0.018)	0.009	0.149
2	BS 655A	3.14	95.74	0.91	(0.002)	<0.002	(0.0006)	.	0.075	0.008	(0.004)	0.008	0.07	0.02
1	IARM Cu647-18	0.70	(96.5)	(0.099)	0.0027	.	.	.	(0.0056)	2.69	(<0.02)	(<0.007)	(<0.01)	(0.005)

Number	Be	Co	Mg	N	O	S	Sb	Zr	Units
BS 655B	(<0.0005)	(<0.005)	(<0.0005)	(<0.0005)	(<0.0005)	0.0010	0.0002	(<0.0005)	38 mm Ø x ~7 or 19+ mm 17025
BS 655C	(<0.0005)	(<0.005)	(<0.0005)	(<0.0005)	(<0.001)	0.0007	(<0.0005)	.	38 mm Ø x ~7, ~12 or 19+ mm 17025
IARM 82B	.	.	.	<0.0005	(0.001)	0.003	<0.01	.	31 mm Ø x 2 mm last
37X 65500A	0.0014	0.0010	.	.	~38 mm Ø x ~15 mm
IARM Cu655-18	.	Ag: (0.0015)	.	.	.	(0.0010)	(0.0008)	.	31 mm Ø x 2 or 18 mm
BS 655A	(0.0006)	<0.002	.	38 mm Ø x ~7, 12 or 19+ mm
IARM Cu647-18	.	.	(0.0086)	0.044	31 mm Ø x 2 or 18 mm

CRM

SILICON BRONZE SET

BH1 BH3 and BH6 set only, others ok individually

40 mm Ø x 25 mm

Number	Al	As	Bi	Cu	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn
IMN BH1	0.027	0.0047	0.018	Rem	1.67	0.0065	0.25	0.96	0.0047	0.74	0.012	0.066	4.77	0.044	2.03
IMN BH2	0.079	0.015	0.014	Rem	1.28	0.0066	0.54	0.74	0.023	0.57	0.0092	0.042	4.14	0.21	2.99
IMN BH3	0.14	0.022	0.0091	Rem	0.96	0.0075	1.00	0.53	0.039	0.40	0.0062	0.026	3.07	0.37	3.84
IMN BH4	0.22	0.054	0.006	Rem	0.55	0.0057	1.46	0.28	0.059	0.24	0.0064	0.016	2.29	0.55	4.91
IMN BH5	0.29	0.071	0.0019	Rem	0.093	0.0024	1.80	0.047	0.073	0.015	0.0055	0.0054	1.45	0.69	5.58
IMN BH6	0.32	0.078	0.018	Rem	0.35	0.01	0.80	0.39	0.078	0.017	0.016	0.056	1.51	0.32	6.27

LEADED, TIN, AND LEADED TIN BRONZE CHART 1 of 2

= class, where 1 = CRM and 2 = RM

#	Number	Sn	Pb	Zn	Cu	Al	Fe	Mn	Ni	P	S	Sb	Si
2	CTIF B1	15.15	0.202	0.92	82.90	0.072	0.088	.	0.063	0.037	0.030	0.444	0.055
1	32X SN7B	12.4	2.31	1.14	81.21	0.0254	0.036	.	0.276	0.0051	0.027	0.235	.
2	CURM 50.04	11.30	9.94	0.66	76.11	0.014	0.10	0.028	1.10	0.032	0.14	0.50	0.011
2	HRT CU2000	11.03	0.78	0.42	86.4	(0.001)	0.04	(0.01)	1.28	0.009	0.014	.	(0.01)
1	IARM 310A	10.56	0.064	0.10	89.2	0.0009	0.006	(0.001)	0.043	0.094	0.0021	(0.002)	(0.001)
2	CURM 50.02	10.34	10.67	0.006	78.84	0.046	.	.	.
1	32X 52480A	10.33	0.329	0.397	88.54	.	0.020	.	0.369	0.0103	0.0071	0.0182	(0.002)
1	BS 905A-2	10.3	0.032	2.3	[87.3]	(<0.005)	0.014	(<0.005)	0.018	0.056	(0.004)	0.004	(<0.005)
2	BS 905A-3	10.3	0.033	2.3	[87.3]	(<0.005)	0.013	(<0.005)	0.018	0.052	(0.004)	0.004	(<0.005)
2	BS 905A-4	10.3	0.033	2.2	[87.3]	(<0.005)	0.012	(<0.005)	0.018	0.049	(0.004)	0.004	(<0.005)
2	BS 905A-1	10.25	0.030	2.27	87.3	(<0.003)	0.015	(<0.003)	0.018	0.055	.	0.004	(<0.004)
1	BS 937C	9.99	9.15	0.196	80.0	(0.0008)	0.0033	(0.0007)	0.26	0.0009	0.025	0.55	(0.002)
1	32X 93700A	9.95	8.38	0.78	80.43	.	0.0011	.	0.307	(0.0015)	0.0017	0.0051	.
1	NCS HS45742	9.79	1.43	2.88	Rem	0.037	0.191	.	0.153	0.56	.	0.288	0.010
1	IARM 92C	9.65	9.42	0.146	80.35	0.0013	(0.008)	(0.0016)	0.170	0.073	0.026	0.078	(0.0019)
1	32X LB12E	9.63	8.64	0.459	79.76	0.0337	0.029	.	0.354	0.240	0.053	0.484	0.0099
2	HRT CU2017	9.24	8.91	0.37	80.11	.	0.011	.	1.25	0.007	0.026	0.14	.
1	IARM 89C	9.14	0.17	3.0	87.5	(0.002)	0.004	(0.001)	0.008	0.004	0.0011	0.008	(0.003)
1	BS 929	9.07	1.98	0.0055	85.3	(<0.00005)	0.0030	(<0.00005)	3.37	0.119	0.0026	0.0146	(<0.001)
1	NCS HS45743	9.06	4.20	1.39	Rem	0.028	0.100	.	0.056	0.38	.	0.206	0.020
2	CURM 50.01	9.01	11.13	0.91	75.38	<0.0005	0.074	<0.001	1.93	0.069	0.188	0.50	<0.001

Number	Ag	As	Bi	C	Cd	Co	Cr	Mg	Se	Te	Units
CTIF B1	60 mm Ø x 5 mm
32X SN7B	0.328	1.13	0.198	.	0.020	0.339	.	.	0.066	0.0204	~40 mm Ø x ~15 mm
CURM 50.04	.	0.06	0.10	50 mm Ø x 10-12 mm
HRT CU2000	40 mm Ø x 20 mm
IARM 310A	0.0020	(0.002)	(0.001)	(0.005)	(0.001)	0.0011	(0.001)	.	(0.001)	.	31 mm Ø x 2 or 18 mm
CURM 50.02	50 mm Ø x 10-12 mm
32X 52480A	0.0131	.	0.0013	~40 mm Ø x ~15 mm
BS 905A-2	0.002	0.002	.	(0.002)	38 mm Ø x 12 mm
BS 905A-3	(0.002)	0.002	.	(0.001)	38 mm Ø x 12 mm
BS 905A-4	(0.002)	0.002	.	(0.002)	38 mm Ø x 12 mm
BS 905A-1	(0.002)	(0.001)	38 mm Ø x 12 mm
BS 937C	(0.015)	0.0112	(0.018)	(0.0015)	(0.0002)	0.0006	(0.00004)	0:0.0060	(0.0008)	(0.0005)	38 mm Ø x 19+ mm 17025
32X 93700A	0.0004	~42 mm Ø x ~15 mm
NCS HS45742	40 mm Ø x 30 mm
IARM 92C	(0.05)	(0.005)	(0.011)	(0.002)	.	(0.0007)	(0.0007)	.	(0.001)	.	31 mm Ø x 2 or 18 mm
32X LB12E	0.0450	0.112	0.0338	.	.	0.061	.	.	.	0.0215	~40 mm Ø x ~15 mm
HRT CU2017	40 mm Ø x 20 mm
IARM 89C	0.005	0.004	(0.003)	(0.002)	(0.001)	(0.001)	(0.002)	0:0.006	(0.001)	(0.0004)	31 mm Ø x 2 or 18 mm
BS 929	(<0.005)	0.0017	(<0.005)	(<0.005)	.	0.0031	(<0.005)	.	0:0.0031	.	51 mm Ø x ~7 or 19+ mm 17025
NCS HS45743	40 mm Ø x 30 mm
CURM 50.01	0.19	.	0.024	50 mm Ø x 10 - 12 mm

LEADED, TIN, AND LEADED TIN BRONZE CHART 2 of 2

= class, where 1 = CRM and 2 = RM

#	Number	Sn	Pb	Zn	Cu	Al	Fe	Mn	Ni	P	S	Sb	Si
1	BS 929MOD	8.9	2.9	0.25	84.2	(0.13)	0.11	0.007	3.34	(0.011)	(0.014)	(0.026)	0.0057
1	BS 903E	8.63	0.100	4.11	87.0	(0.001)	0.0072	.	0.293	0.056	0.0092	0.010	(0.0018)
2	CURM 50.03	8.41	8.86	1.72	77.42	0.005	0.018	0.037	2.89	0.159	0.064	0.24	0.005
1	IARM Cu903-18	8.3	(0.066)	4.6	86.5	(0.0010)	(0.012)	(0.0004)	0.41	(0.060)	(0.0017)	(0.002)	(0.0040)
1	32X LB10G	8.29	12.60	0.110	77.10	(0.0005)	0.0011	.	0.690	0.0034	0.0100	0.599	.
2	BS 903B	7.9	0.10	4.39	86.7	(0.001)	0.049	0.0004	0.50	0.073	0.006	0.003	0.002
1	NCS HS45741	7.77	2.92	4.04	Rem	0.057	0.27	.	0.204	0.093	.	0.108	0.051
1	BAM 374	7.60	0.00083	0.00404	92.22	.	0.0040	0.00043	0.00327	0.1697	(0.0013)	(0.00063)	(0.0010)
2	BS 938-1	7.16	14.8	0.26	77.1	(<0.002)	(0.015)	(0.001)	0.49	(0.059)	0.009	0.033	(0.004)
1	BS 936	6.99	10.7	0.244	81.5	0.0007	0.0026	(0.0006)	0.36	(0.053)	0.009	0.102	0.0040
1	IARM Cu932-18	6.82	7.95	3.44	81.2	(0.0007)	0.070	.	0.454	0.040	0.031	0.31	.
1	IARM 91E	6.69	7.59	3.68	81.3	0.0015	0.110	0.0007	0.300	0.026	0.028	0.168	0.0021
1	BS 932G	6.35	7.78	2.92	82.0	(0.002)	0.028	(0.0005)	0.39	0.11	0.035	0.173	0.0014
1	BS 932F	6.30	7.32	3.39	[82.1]	(0.0008)	0.057	(0.0002)	0.388	0.0105	0.0368	0.199	0.0011
1	BS 932H	6.28	7.62	2.79	82.4	0.0020	0.019	(0.0005)	0.41	(0.11)	0.038	0.185	(0.002)
1	IARM 184A	6.0	19.0	0.37	(74)	0.0016	(0.003)	(0.002)	0.30	0.008	0.021	0.27	(0.002)
1	32X LB13D	5.98	7.04	0.77	85.1	0.0014	0.0159	.	0.629	0.033	0.074	0.092	0.008
1	BAM 377	5.92	0.00449	0.01006	94.04	0.00451	0.01042	0.000921	0.01074	(<0.0010)	(0.00068)	0.00130	(0.0134)
2	BS 922B-1	5.8	1.33	3.95	88.4	(0.001)	0.010	(0.002)	0.61	0.037	.	0.002	(0.001)
2	BS 922B-2	5.8	1.33	3.91	88.4	(0.001)	0.008	(0.002)	0.61	0.031	.	0.002	(0.001)
2	BS 922B-4	5.8	1.33	3.82	88.4	(0.001)	0.007	(0.002)	0.61	0.021	.	0.002	(0.001)
2	BS 922B-5	5.8	1.33	3.78	88.4	(0.001)	0.006	(0.002)	0.61	0.017	.	0.002	(0.001)
1	BAM 378	5.738	(0.00042)	(0.00073)	94.13	(<0.0001)	0.0182	(0.000074)	0.00183	0.0602	(0.00091)	0.00861	(0.0010)
1	32X LB16A	5.55	18.78	0.450	74.42	(0.0012)	0.0040	.	0.793	(0.0018)	0.0011	(0.0012)	.
1	32X LB14H	5.16	15.04	0.254	78.4	0.0008	0.041	.	0.300	0.039	0.036	0.103	0.0012
1	IARM 267A	4.95	0.026	2.06	87.8	0.003	0.019	(0.002)	5.1	0.037	0.0014	<0.03	0.003
1	BS 836D	4.82	4.9	4.84	84.8	0.0011	0.026	(0.0002)	0.370	0.086	0.039	0.108	0.0027
1	BS 836B	4.71	4.6	4.85	85.2	0.0015	0.022	(0.0007)	0.377	0.096	0.036	0.102	(0.0032)
1	BS 836C	4.7	4.72	4.91	85.0	(0.0015)	0.017	(0.0007)	0.370	0.066	0.038	0.104	0.0032
1	32X LB15F	4.53	20.15	0.147	74.5	0.0009	0.0039	.	0.104	0.063	0.021	0.198	0.0018
1	BAM M397	3.99	0.229	1.96	0.336	.	0.45	0.097	.
1	BAM M397a	3.9	0.227	1.87	0.337	.	0.45	0.097	.
1	IARM 72B	0.029	1.99	7.81	90.08	.	0.007	.	0.004	0.005	0.0015	0.006	(0.002)

#	Number	Sn	Pb	Zn	Cu	Al	Fe	Mn	Ni	P	S	Sb	Si
---	--------	----	----	----	----	----	----	----	----	---	---	----	----

Number	Ag	As	Bi	C	Cd	Co	Cr	Mg	Se	Te	Units	
BS 929MOD	.	0.0020	.	(0.003)	.	(0.0017)	.	O:0.0007	.	.	51 mm Ø x ~7 or 19+ mm	17025
BS 903E	.	(0.002)	.	(0.002)	.	(0.002)	(0.0007)	N:(0.0004)	O:(0.007)	.	38 mm Ø x ~7 or 19+ mm	17025
C50.03	.	0.094	0.027	50 mm Ø x 10-12 mm	
IARM Cu903-18	0.0059	(0.0010)	.	(0.0020)	.	0.0019	.	O:0.0013	.	.	31 mm Ø x 2 or 18 mm	
32X LB10G	0.0686	0.169	0.093	.	.	0.084	~40 mm Ø x ~15 mm	
BS 903B	.	0.003	.	(0.0004)	38 mm Ø x ~7 or 19+ mm	last
NCS HS45741	40 mm Ø x 30 mm	
BAM 374	0.00121	(0.00043)	(0.00022)	(<0.0002)	.	40 mm Ø x 30 mm	
BS 938-1	0.0048	(0.004)	38 mm Ø x 12 mm	
BS 936	O:0.0026	0.0045	N:(0.0001)	(0.0025)	.	(0.003)	(0.00004)	.	.	Ti:(0.00006)	50 mm Ø x 19+ mm	17025
IARM Cu932-18	0.019	0.0073	0.094	(0.0025)	0.0007	(0.0024)	.	.	(0.009)	.	38 mm Ø x ~3 or 19 mm	
IARM 91E	0.015	0.008	0.109	(0.003)	0.0011	0.0024	(0.0008)	.	0.004	.	31 mm Ø x 2 mm	
BS 932G	.	0.0096	.	(0.011)	.	0.0025	(0.001)	.	O:0.0014	.	38 mm Ø x ~7 or 19+ mm	17025
BS 932F	.	0.0091	.	(0.0053)	.	O:0.0025	.	.	.	last	38 mm Ø x ~11 mm	17025
BS 932H	.	0.010	.	(0.007)	.	0.0028	.	O:0.0016	.	.	38 mm Ø x ~7 or 19+ mm	17025
IARM 184A	(0.01)	0.010	(0.03)	(0.004)	.	(0.001)	(0.001)	.	.	.	31 mm Ø x 2 or 18 mm	
32X LB13D	0.0249	0.118	0.058	.	0.0006	0.0044	~40 mm Ø x ~15 mm	
BAM 377	0.00644	(<0.0010)	0.00422	.	.	.	0.00669	.	0.0055	.	40 mm Ø x 30 mm	
BS 922B-1	(0.001)	0.001	41 mm Ø x 12 mm	
BS 922B-2	(0.001)	0.001	41 mm Ø x 12 mm	
BS 922B-4	(0.001)	0.001	41 mm Ø x 12 mm	
BS 922B-5	(0.001)	0.001	41 mm Ø x 12 mm	
BAM 378	0.00266	0.00995	(<0.0001)	.	0.01007	0.0089	0.0311	0.00287	(<0.0002)	0.00850	40 mm Ø x 30 mm	
32X LB16A	0.0016	0.0120	32 mm Ø x 17 mm	
32X LB14H	0.046	0.055	0.496	.	0.0005	0.0018	~40 mm Ø x ~15 mm	
IARM 267A	(0.002)	(0.004)	(0.005)	(0.003)	.	(0.002)	(0.001)	.	(0.002)	.	31 mm Ø x 2 or 18 mm	
BS 836D	0.023	0.0081	0.093	(0.003)	.	0.0027	O:0.0012 (0.0004)	Be:(0.00009)	.	.	44 mm Ø x ~7 or 19+ mm	17025
BS 836B	0.025	0.0081	0.10	(0.0032)	.	0.0027	O:0.0010 (0.0005)	Be:(0.00009)	.	.	44 mm Ø x ~7 or 19+ mm	17025
BS 836C	0.024	0.0082	0.10	(0.003)	.	0.0027	O:0.0014 (0.0007)	Be:(0.000005)	.	.	44 mm Ø x ~7 or 19+ mm	17025
32X LB15F	0.023	0.0163	0.129	.	0.0006	0.0004	~40 mm Ø x ~15 mm	
BAM M397	.	(0.00029)	<0.0001	<0.0001	40 mm Ø x 30 mm	
BAM M397a	.	(0.00029)	<0.0001	<0.0001	40 mm Ø x 30 mm	
IARM 72B	.	(0.003)	.	0.002	31 mm Ø x 2 or 18 mm	

Number	Ag	As	Bi	C	Cd	Co	Cr	Mg	Se	Te	Units
--------	----	----	----	---	----	----	----	----	----	----	-------

CRM LEADED, TIN, AND LEADED TIN BRONZE DISC AND ROD SETS

available individually except IMN WL4 and WL5 are SET ONLY IMN BB: 10 mm Ø x 100 mm IMN BL: 40 mm Ø x 27 mm IMN BI, WL: 40 mm Ø x 25 mm

Number	Al	As	Bi	C	Cd	Co	Cu	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn
IMN BL1	0.11	0.058	0.024	.	0.060	.	Rem	0.38	0.051	0.062	0.25	0.49	0.25	(0.0081)	0.053	0.059	2.58	0.68
IMN BL2	0.15	0.039	0.014	.	0.040	.	Rem	0.21	0.11	0.055	0.37	0.29	0.14	(0.0063)	0.039	0.031	4.04	0.40
IMN BL3	0.019	0.025	0.0099	.	0.022	.	Rem	0.10	.	0.026	0.13	0.084	0.065	.	0.021	0.015	6.12	0.15
IMN BL4	.	0.0089	0.0058	.	0.0092	.	Rem	0.014	.	0.0092	0.015	0.010	0.013	(0.022)	0.0095	0.011	8.38	0.017
IMN BL5	0.00052	0.00057	0.0015	.	0.0015	.	Rem	0.0061	0.0030	0.0011	0.0074	0.0042	0.0069	0.031	0.0039	(0.0038)	11.05	0.0078
IMN BB1	0.019	0.086	0.032	.	.	.	84.82	0.33	.	0.081	0.061	0.055	1.55	.	0.60	0.037	8.10	3.90
IMN BB2	0.032	0.12	0.024	.	.	.	84.09	0.28	.	0.12	0.097	0.085	2.64	.	0.49	0.055	7.11	4.70
IMN BB3	0.0021	0.0079	0.0021	.	.	.	80.88	0.037	.	0.0012	2.42	(0.014)	6.73	.	0.052	0.0044	3.36	6.23
IMN BB4	0.0062	0.029	0.011	.	.	.	81.32	0.086	.	0.020	1.20	0.030	6.14	.	0.21	0.018	2.58	8.11
IMN BB5	0.015	0.051	0.018	.	.	.	82.25	0.14	.	0.054	0.49	0.037	5.18	.	0.31	0.028	4.11	7.21
IMN BB6	0.040	0.16	0.041	.	.	.	83.54	0.31	.	0.15	0.23	0.12	3.52	.	0.62	0.083	5.47	5.40
IMN BI1	0.15	0.14	0.12	.	.	.	Rem	0.42	.	0.26	2.41	0.70	6.97	(0.011)	0.58	0.23	3.19	3.55
IMN BI2	0.077	0.11	0.070	.	.	.	Rem	0.31	.	0.15	1.46	0.59	5.39	(0.0055)	0.43	0.13	4.18	5.73
IMN BI3	0.034	0.052	0.028	.	.	.	Rem	0.17	.	0.082	0.29	0.32	4.52	(0.003)	0.24	0.075	5.01	7.16
IMN BI4	0.0020	0.010	0.0030	.	.	.	Rem	0.083	.	0.025	0.088	0.029	3.82	(0.002)	0.075	0.014	7.69	10.22
IMN WL1	0.082	0.0010	0.0093	0.0050	0.0017	0.0010	95.54	0.072	0.00036	0.0041	0.44	0.012	0.013	0.020	.	0.057	0.22	3.52
IMN WL2	0.057	0.0078	0.0073	0.0082	0.0023	0.0065	97.49	0.13	0.00097	0.0038	0.32	0.016	0.011	0.0070	0.0050	0.046	0.32	1.56
IMN WL3	0.0034	0.020	0.0050	0.010	0.010	0.0096	96.51	0.20	0.0016	0.38	0.22	0.021	0.0083	0.0088	0.0085	0.0037	0.37	2.21
IMN WL4	.	0.0034	0.0026	0.0032	0.0068	0.013	96.41	0.012	.	.	0.019	.	0.0066	0.0050	.	0.0019	0.55	2.97
IMN WL5	0.0014	0.0011	0.0011	.	0.0038	0.019	97.62	0.0025	.	0.00073	0.0014	.	0.0030	0.0019	0.0006	0.0009	0.73	1.61
IMN WL6	0.10	0.024	0.012	0.016	0.025	0.019	95.76	0.31	0.015	0.14	0.091	0.032	0.016	0.017	0.011	0.13	0.80	2.48

COPPER ALLOY XRF SET

Part Number: BS CU-22 AVAILABLE INDIVIDUALLY ~7 mm thick discs (BS 938-1 ~12mm) **17025**

CDA	Number	Cu	Al	Fe	Mn	Ni	Pb	Si	Sn	Zn	As	C	P	S	Sb	Be	Co	Te	Cr
110	BS 110B	99.94	<0.0002	0.0005	<0.0001	<0.0002	0.00052	<0.0004	<0.0002	<0.0003	<0.0001	0.0007	<0.0006	0.00030	<0.0005	<1ppm	<1ppm	0: 0.0363	
145	BS 14500	99.4	(<0.0006)	0.0041	0.00004		0.0008	(<0.002)	0.0002	0.004	(<0.0005)	0.0005	0.0075	0.0033	(<0.001)	(<1ppm)	(<1ppm)	0: 0.0007	Te: 0.53
172	BS 172Be-1	97.68	(0.02)	0.052	0.0010	0.039	(0.002)	0.055	0.033	0.0070	(0.001)	(0.001)	0.003	(<0.0002)		1.89	0.206		Cr: 0.0032
360	BS 360A	61.42	<0.001	0.151	0.0007	0.058	2.51	<0.005	0.13	35.63	0.002	(0.0032)	0.001	(0.0003)	0.008				
464	BS 464A	60.6	(0.001)	0.013	0.0002	0.004	0.056	<0.01	0.62	38.73	<0.002	(0.0006)	0.012	0.001	(0.001)				
482	BS 482A	60.0	(0.003)	0.020	<0.002	(0.007)	0.50	(0.002)	0.65	38.8	<0.002	(0.0015)	<0.003	<0.002	0.0012				
510	BS 510A	96.10	<0.002	0.005	<0.002	0.020	0.016	<0.003	4.6	0.21	0.0008	(0.0006)	0.11	0.008	(0.003)				
544	BS 544A	88.4	(0.0005)	0.092	<0.002	0.16	4.16	<0.002	4.42	3.42	(0.006)	(0.002)	<0.002	0.038	0.040				
623	BS 623A	88.13	9.12	2.19	0.273	0.146	0.001	0.014	0.002	0.008	(0.002)	(0.002)	<0.002	<0.0005	<0.002				
630	BS 630A	81.0	10.05	3.73	0.11	4.81	0.0069	0.037	0.019	0.17	(0.002)	0.001	<0.01	(0.001)	<0.001				
642	BS 642A	91.0	6.70	0.17	0.005	0.025	0.001	1.80	0.018	0.011	<0.002	0.001	0.001	<0.001	<0.002				
655	BS 655A	95.74	(0.002)	0.075	0.91	0.008	0.008	3.14	0.07	0.02	<0.002	(0.0006)	(0.004)	(0.0003)	<0.002				
675	BS 675A	58.5	<0.002	1.12	0.32	0.019	0.074	(0.005)	0.80	39.1	<0.002	(0.0007)	0.010	(0.0005)	0.0011				
706	BS 706A	87.60	(0.002)	1.30	0.66	10.18	0.008	<0.005	0.011	0.13	<0.0005	0.004	0.006	0.012	0.0006				
715	BS 715A	69.0	(0.01)	0.61	0.82	30.22	(0.007)	0.10	0.008	0.10	(0.0014)	0.03	0.006	0.001	(0.003)				
863	BS 863A	64.1	5.21	2.41	3.00	0.29	0.022	0.034	0.013	24.8	0.010	0.003	(0.007)	<0.0005	0.003				
903	BS 903B	86.7	(0.001)	0.049	0.0004	0.50	0.10	0.002	7.9	4.39	0.003	(0.0004)	0.073	0.006	0.003				
922	BS 922B-1	88.4	(0.001)	0.010	(0.002)	0.61	1.33	(0.001)	5.8		0.001		0.037		0.002				Ag: (0.001)
929	BS 929	85.3	(<0.00005)	0.0030		3.37	1.98	(<0.001)	9.07	0.0055	0.0017	(<0.005)	0.119	0.0026	0.0146		0.0031	0: 0.0031	
938	BS 938-1	77.1	(<0.002)	0.015	(0.001)	0.49	14.8	(<0.004)	7.16	0.26	(0.004)		0.059	0.009	0.033				Ag: 0.0048
954	BS 954A	85.64	10.17	3.50	0.10	0.20	0.016	0.029	0.033	0.30	(0.006)	0.004	0.012	<0.0001	0.001				
955	BS 955C	80.6	10.68	4.04	0.06	4.31	0.003	0.025	0.003	0.15	(<0.002)		0.012		(<0.002)				Ag: 0.014

CDA	Number	Cu	Al	Fe	Mn	Ni	Pb	Si	Sn	Zn	As	C	P	S	Sb	Be	Co
-----	--------	----	----	----	----	----	----	----	----	----	----	---	---	---	----	----	----

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
101		IARM Cu101-18	630		BS 630A	922		BS 922B-1
110	17025	BS 110B	630	17025	BS 630B	922		BS 922B-2
110	17025	BS 110C	630	17025	BS 630C	922		BS 922B-4
110		IARM Cu110-18	630		IARM 80D	922		BS 922B-5
110		IARM 70C	642	17025	BS 642B	927.1		32X SN1
122.2		CURM 09.03	642	17025	BS 642C	929	17025	BS 929
125		CURM 09.02	642	17025	BS 642D	929 MOD	17025	BS 929MOD
145	17025	BS 14500	642		IARM 81B	931 MOD		C71.34
145	17025	BS 14500A	642		IARM Cu648-18	932	17025	BS 932F
145		IARM 278A	647		IARM Cu647-18	932	17025	BS 932G
172		BS 172Be-1	655		37X 65500	932	17025	BS 932H
172	17025	BS 172Be-2	655		BS 655A	932		IARM 91E
172		CTIF 4872	655	17025	BS 655B	932		IARM Cu932-18
172		IARM Cu172-18	655	17025	BS 655C	932 MOD		CTIF B23
172		IARM Cu172-19	655		IARM 82B	936	17025	BS 936
173		36X CBC4	655		IARM Cu655-18	936		CTIF B31
175	17025	BS 17500	673		31X HT37	937		32X 93700
175.1		36x CBC5	675		BS 675	937	17025	BS 937C
175.1	17025	BS 17510	675		BS 675A	937		CURM 50.02
180		36X 274	675	17025	BS 675B	937		IARM 92C
181.50	17025	BS 18150	675		IARM 83B	938		BS 938-1
181.50	17025	BS 18150A	687		BAM 368	941		32x LB16
181.55		36X CCR1	693		ERM-EB393A	941		IARM 184A
182		IARM 279A	693		IARM 313A	945 MOD		CTIF B32
182		IARM Cu182-18	702.6		37X 218	947		IARM 267A
240		C30.07	706		36X 70600A	952.2		CTIF 2152-S
260		C48.06	706		BS 706	953		CTIF CA3
260		CURM 48.04	706		BS 706A	954		BS 954A
261.3		C48.03	706		BS 706B	954		BS 954B
274		C38.06	706	17025	BS 706C	954		BS 954C
274		C38.06-1	706		CTIF CuNi 10	954		BS CC954
280		C30.03	706		IARM 84C	954		IARM Cu954-18
280		C30.12	706		HRT CU2014	954		IARM Cu954-19
314		IARM 72B	713		BAM 389	954		IARM Cu954-21
316		31X 7835-7	715		36X 71500	954 MOD		IARM 204A
360	17025	BS 360B	715		BS 715A	955		BS 955C
360	17025	BS 360C	715	17025	BS 715B	955		IARM 94B
360	17025	BS 360D	715	17025	BS 715C	955		IARM Cu955-18
360		IARM Cu360-18	715		IARM 85C	955 MOD		CTIF CA10
360		SRM 1124	715		IARM Cu715-18	955.1		IARM 334A
370		31X B18	715		IARM Cu715-20	955.1		IARM 334B
371		C30.22	715		SRM 1276a	955.1 MOD		CTIF CA22
464		BS 464A	767		C65.28	956		32X CA12
464	17025	BS 464B	798.3		34X 79830	964		IARM 236A
464		IARM Cu464-21	815		IARM 158B	976		IARM 298A
482		BS 482A	815		IARM 158C	Coinage Alloy		36X CN21
482		IARM 75B	836	17025	BS 836B	Coinage Alloy		36X CN23
482		IARM 75C	836	17025	BS 836C	Cu IX		SRM C1252a
485		BS 485a	836	17025	BS 836D	Cu VIII		SRM C1251a
485		IARM 76D	836		IARM Cu836-18	Cu X		SRM C1253a
485		IARM Cu485-18	836 + Al		IMN BR1	Envirobrass 2-1		IARM 226A
486		IARM Cu486-18	838		33X GM8	Envirobrass 2-2		IARM 227A
510		32X 51000	844		IARM Cu844-18	Envirobrass 2-3		IARM 228A
510		BS 510A	855		31X B2N	Federalloy I-836		IARM 265A
510	17025	BS 510B	855		31X TB3	Federalloy I-844		IARM 264A
510	17025	BS 510C	855		C38.01	Federalloy I-848A		IARM 263A
510		IARM 77B	855		C38.02	Federalloy III-932		IARM 266A
510		IARM Cu510-18	855		C38.03	Hiduron 130		IARM CuH130-18
512		32X 92100	855		C38.04	Hiduron 191		IARM CuH191-18
521		32X 52100	855		C38.05	NARloy-A		IARM 159A
521		HRT CU2016	857		BS 857B-1	NARloy-Z		IARM 160A
524		C11.04	857		BS 857B-2	Spinodal Alloy		36X SP1
544		33X 54400	857		BS 857B-3	Spinodal Alloy		36X SP2
544	17025	BS 544B	857		BS 857B-4			
544		BS 544C	862		CTIF LH7			
544		IARM 78B	863	17025	BS 863B			
544		IARM Cu544-18	863		IARM 88C			
544 MOD	17025	BS 544c	873		31X WSB6			
610 MOD		31X B17	893.2, Magnolia B		IARM CuMB1-18			
614		32X 61400	902		BAM 377			
615.5		36X CN22	903		BS 903B			
622		CTIF 2154-V	903	17025	BS 903E			
623		32X CA7	903		IARM 89C			
623		BS 623	905		BS 905A-1			
623		BS 623A	903		IARM Cu903-18			
623		IARM 79B	905		BS 905A-2			
623		IARM 79C	905		BS 905A-3			
624		32X ALB3	905		BS 905A-4			
624	17025	BS 624	907		IARM 310A			
624		C52.51	908		32X PB10			
624		CTIF 3011-G	908		HRT CU2000			
624		CTIF CA21	910 MOD		CTIF B1			

Please use the Adobe Acrobat "search" function to find the complete chemistry of these samples listed within this catalog.

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
101	Impurity Limits	>99.99	<0.0025	.	<0.0010	<0.0005	<0.0010	<0.0003	<0.0005	<0.0018	<0.0004	.	<0.0002	<0.0001	<0.0005	.	<0.0001
102	Cu = Ag+Cu, Cd<0.0010	>99.95
103	Cu = Ag+Cu, Cd<0.0010	>99.95	0.001-0.005
104	Cu = Ag+Cu, Cd<0.0010	>99.95	>0.027
105	Cu = Ag+Cu, Cd<0.0010	>99.95	>0.034
107	Cu = Ag+Cu, Cd<0.0010	>99.95	>0.085	0.005-0.012
108	Cu = Ag+Cu+P	>99.95
109.1	Cu = Ag+Cu, Cd<0.005	>99.95
109.2	Cu = Ag+Cu, Cd<0.02	>99.90
109.3	Cu = Ag+Cu, Cd<0.02	>99.90	>0.044
109.4	Cu = Ag+Cu, Cd<0.02	>99.90	>0.085
110	Cu = Ag+Cu	>99.90
110.1	Cu = Ag+Cu	>99.90
110.2	Cu = Ag+Cu	>99.90
110.3	Cu = Ag+Cu	>99.90
110.4	Impurity Limits, O 0.010-0.065	>99.90	<0.0025	.	<0.0010	<0.0005	<0.0010	.	<0.0005	<0.0015	<0.0004	.	<0.0005	<0.00010	<0.0005	
111	Cu = Ag+Cu	>99.90
113	Cu = Ag+Cu	>99.90	>0.027
114	Cu = Ag+Cu	>99.90	>0.034
115	Cu = Ag+Cu	>99.90	>0.054
116	Cu = Ag+Cu	>99.90	>0.85
117	Cu = Cu+P, B 0.004-0.020	>99.90	<0.04
119.04	Cu = Ag+Cu	>99.90	>0.027
119.05	Cu = Ag+Cu	>99.90	>0.034
119.06	Cu = Ag+Cu	>99.90	>0.054
119.07	Cu = Ag+Cu	>99.90	>0.085	0.004-0.012
120	Cu = Ag+Cu	>99.90	0.005-0.012
121	Cu = Ag+Cu	>99.90	>0.014	0.015-0.040
122	Cu = Ag+Cu	>99.90	0.015-0.025
122.1	Cu = Ag+Cu	>99.90
122.2	Cu = Ag+Cu	>99.90	0.040-0.065
123	Cu = Ag+Cu	>99.90	0.015-0.040
125	Cu=Ag+Cu, Te=Se <0.025	>99.88	.	.	<0.05	.	<0.050	>0.03	<0.004	.	<0.003	.	<0.05	<0.080	<0.012	.	<0.003	
125.1	Cu=Ag+Cu, Te=Se <0.025	>99.90	<0.050	.	<0.004	.	<0.003	.	<0.05	<0.080	<0.012	.	<0.003	
127	Cu=Ag+Cu, Te=Se <0.025	>99.98	>0.027	.	.	.	<0.050	.	<0.004	.	<0.003	.	<0.05	<0.080	<0.012	.	<0.003	
128	Cu=Ag+Cu, Te=Se <0.025	>99.88	>0.034	.	.	.	<0.050	.	<0.004	.	<0.003	.	<0.050	<0.080	<0.012	.	<0.003	
129	Cu=Ag+Cu, Te=Se <0.025	>99.88	>0.054	.	.	.	<0.050	.	<0.004	.	<0.003	.	<0.050	<0.080	<0.012	.	<0.003	
130	Cu=Ag+Cu, Te=Se <0.025	>99.88	>0.085	.	.	.	<0.050	.	<0.004	.	<0.003	.	<0.050	<0.080	<0.012	.	<0.003	
131	Cu = Ag+Cu	>99.80	0.15-0.50
141	Cu = Ag+Cu	>99.40
141.8	Cu = Ag+Cu	>99.90	.	<0.01	.	.	.	<0.075	<0.02
141.81	Cu=Ag+Cu, C<0.005, Cd<0.002	>99.90	.	.	<0.03	.	.	<0.002	<0.002	.	.	.	<0.002	<0.05	
142	Cu = Ag+Cu	>99.40	.	.	<0.05	.	.	0.015-0.040	0.15-0.50	
142.1	Cu = Ag+Cu	>99.20	.	.	<0.05	.	.	0.013-0.050	0.30-0.50	
143	Cu = Ag+Cu+Cd, Cd 0.05-0.15	>99.90	
143.1	Cu = Ag+Cu+Cd, Cd 0.10-0.30	>99.90	.	.	<0.03	.	<0.05	0.013-0.025	0.10-0.20	<0.05	
144	Cu=Ag+Cu+Sn+P, Te=Se <0.02	>99.90	.	.	<0.05	.	.	0.005-0.020	<0.05	.	.	.	0.003-0.22	<0.05	
144.1	Cu = Ag+Cu+Sn	>99.90	.	.	<0.05	.	.	0.010-0.030	0.10-0.20	<0.05	
144.15	Cu = Ag+Cu+Sn	>99.96	.	.	<0.05	.	.	0.10-0.030	0.10-0.15	<0.05	
144.2	Cu=Ag+Cu+Sn+Te, Te=Se 0.02-0.05	>99.90	.	.	<0.05	.	.	0.004-0.020	0.05-0.15	<0.05	
144.3	Cu = Ag+Cu	>99.90	.	.	<0.05	0.25-0.35	<0.05	
144.4	Cu = Ag+Cu+Sn	>99.96	.	.	<0.05	0.005-0.010	<0.05	
145	Cu = Ag+Cu+Te, Te 0.40-0.70	>99.90	.	.	<0.05	.	.	0.004-0.012	0.003-0.22	<0.05	
145.1	Cu = Ag+Cu+Te, Te 0.30-0.70	>99.85	.	.	<0.05	.	.	0.010-0.030	<0.05	.	.	.	0.003-0.22	<0.05	
145.2	Cu = Ag+Cu+Te, Te 0.40-0.70	>99.40	.	.	<0.05	.	.	0.004-0.020	0.003-0.22	<0.05	
145.3	Cu = Ag+Cu, Te 0.003-0.022	>99.95	.	.	<0.05	.	.	0.001-0.005	0.003-0.22	<0.05	
147	Cu = Ag+Cu+P+S	>99.90	.	.	<0.05	.	.	0.002-0.005	.	0.20-0.50	.	.	0.003-0.22	<0.05	
147.1	Cu = Ag+Cu+P+S	>99.90	.	.	<0.05	.	.	0.010-0.030	<0.05	0.05-0.15	.	.	0.003-0.22	<0.05	
147.2	Cu = Ag+Cu+P+S	>99.50	.	.	<0.05	.	.	0.10-0.030	<0.10	0.20-0.50	.	.	0.003-0.22	<0.05	
147.3	Cu = Ag+Cu+P+S	>99.80	.	.	<0.05	.	.	0.10-0.030	<0.10	0.20-0.50	.	.	0.003-0.22	<0.05	
150	Cu = Ag+Cu	>99.80	.	.	<0.05
151.5	Cu = Ag+Cu+Zn	>99.80	.	.	<0.05
155	Cu = Ag+Cu	>99.96	.	.	<0.05	.	.	0.040-0.080
156	Cu = Ag+Cu	>99.75	0.027-0.10	.	<0.05	.	.	0.06-0.09
157.1	Cu = Ag+Cu, O 0.07-0.15	>99.71	.	0.08-0.12	<0.01	.	.	.	<0.01
157.15	Cu = Ag+Cu, O 0.12-0.19	>99.62	.	0.13-0.17	<0.01	.	.	.	<0.01
157.2	Cu=Ag+Cu, B 1.2-1.8, O <0.19	>97.82	.	0.13-0.17	<0.01	.	.	.	<0.01
157.2	Cu = Ag+Cu, O 0.16-0.24	>99.52	.	0.18-0.22	<0.01	.	.	.	<0.01
157.25	Cu = Ag+Cu, O 0.20-0.28	>99.43	.	0.23-0.27	<0.01	.	.	.	<0.01
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
157.35	Cu = Ag+Cu, O 0.28-0.37	>99.24		0.33-0.37	<0.01				<0.01													
157.6	Cu = Ag+Cu, O 0.52-0.59	>98.77		0.58-0.62	<0.01				<0.01													
162	Cu = Ag+Cu, CH 0.70-1.20	rem			<0.02																	
162.1	Cu = Ag+Cu, CH 0.50-1.20	rem																				
164	Cu = Fe-Cu, ALL, CH 0.60-0.90	>99.80			<0.02								0.20-0.40									
165	Cu = Ag+Cu, CH 0.60-1.00	rem		<0.20	<0.02							<0.20	0.50-0.70			1.60-1.78						
170	Cu = Ag+Cu, Ni+CO >0.20	rem		<0.20								<0.20				1.80-2.00						
172	Cu = Ag+Cu, Ni+CO >0.20	rem		<0.20					0.20-0.60			<0.20				1.90-2.00						
173	Cu = Ag+Cu, Ni+CO >0.20	rem		<0.20								<0.20				0.15-0.50		0.15-0.50				
174	Cu = Ag+Cu	rem		<0.20	<0.20							<0.20				0.05-0.50		0.35-0.60				
174.1	Cu = Ag+Cu	rem		<0.20	<0.20							<0.20				0.05-0.50		0.05-0.60				<0.50
174.2	Cu = Ag+Cu	rem		<0.20	<0.20							<0.20				0.15-0.50		0.05-0.60				<0.50
174.5	Cu = Ag+Cu	rem		<0.20	<0.20				0.20-0.60			<0.20				0.15-0.50						
174.55	Cu = Ag+Cu	rem		<0.20	<0.20							<0.20				0.15-0.50						
174.6	Cu = Ag+Cu	rem		<0.20	<0.20							<0.20				0.15-0.50		0.15-0.50				
174.65	Cu = Ag+Cu	rem		<0.20	<0.20							<0.20				0.15-0.50						<0.50
175	Cu = Ag+Cu	rem		<0.20	<0.10							<0.20				0.40-0.70						
175.1	Cu = Ag+Cu	rem		<0.20	<0.10							<0.20				0.20-0.60		2.4-2.7				0.10-0.30
175.2	Cu = Ag+Cu	rem		<0.20	<0.10							<0.20				0.10-0.30						0.10-0.30
175.3	Cu = Ag+Cu, Ni = Ni+CO	rem		<0.6	<0.20							<0.20				0.20-0.40						0.10-0.30
176	Cu = Ag+Cu	rem	0.90-1.10	<0.20	<0.20							<0.20				0.25-0.50		1.4-1.7				
177	Cu = Ag+Cu, Te 0.40-0.60	rem		<0.20	<0.10							<0.20				0.40-0.70		2.4-2.7				
180	Cu = Ag+Cu, Ni = Ni+CO	rem			<0.15							0.40-0.80						0.10-0.60				
180.3	Cu = Ag+Cu	>99.90					2.0-3.0					0.08-0.12						0.10-0.20				
180.4	Cu = Ag+Cu	>99.90						0.005-0.150				0.20-0.30		0.05-0.15				0.25-0.35				
180.45	Cu = Ag+Cu	>99.10										<0.05	0.20-0.30	0.15-0.30				0.20-0.35				
180.5	Cu = Ag+Cu, Te 0.005-0.015	>99.80										0.02-0.07						0.05-0.15				0.01-0.40
180.7	Cu = Ag+Cu	>99.00										0.01-0.10						0.15-0.40				0.01-0.15
180.8	Cu = Ag+Cu	rem										0.01-0.10						0.20-0.70				0.15-0.80
180.9	Cu = Ag+Cu	>96.00					0.30-1.20						0.50-1.20					0.30-1.00				
181	Cu = Ag+Cu	>98.70																0.4-1.0	0.03-0.06			0.08-0.20
181.35	Cu = Ag+Cu, CH 0.20-0.60	rem																0.20-0.60				
181.4	Cu = Ag+Cu	rem										0.005-0.05						0.15-0.45				0.05-0.25
181.45	Cu = Ag+Cu	rem																0.10-0.30				0.05-0.15
181.5	Cu = Ag+Cu	rem																0.10-0.30				0.02-0.20
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																0.50-1.50				
181.5	Cu = Ag+Cu	rem																				

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
197.1	Ni<0.10	rem			0.30-1.20	<0.05	<0.05	0.10-0.40	<0.05				<0.02	<0.20				<0.05		0.01-0.20		
197.2	Ni<0.10	rem			0.05-0.40	<0.05	<0.10	0.07-0.15	<0.05				<0.20	<0.20						0.02-0.06		
197.5		rem			0.05-0.50	<0.05	<0.10	0.05-0.15	<0.05				0.05-0.40	<0.20						0.05-0.20		
198		rem			0.35-1.20	<0.05	<0.05	0.10-0.40	<0.05				0.10-1.00	0.30-1.50						0.01-0.20		
198.1		rem			0.02-0.50			0.01-0.10	<0.05				0.10-1.00	0.30-1.50						0.10-1.00		
199	>99.50				1.5-3.0			<0.10						1.0-5.0					<0.10	<0.10	<0.10	<0.10
205		97.0-98.0			<0.05				<0.02					rem							2.9-3.4	
210		94.0-96.0			<0.05				<0.03					rem								
220		89.0-91.0			<0.05				<0.05					rem								
226		86.0-89.0			<0.05				<0.05					rem								
230		84.0-86.0			<0.05				<0.05					rem								
230.3		81.5-85.5			<0.05				<0.05			0.20-0.40		rem								
234		81.0-84.0			<0.05				<0.05					rem								
240		78.5-81.5			<0.05				<0.05					rem								
240.8		78.0-82.0		<0.10	<0.05				<0.20					rem								
250		74.0-76.0			<0.05				<0.05					rem								
256		71.0-73.0			<0.05				<0.05					rem								
260		68.5-71.5			<0.05				<0.07					rem								
261		68.5-71.5			<0.05			0.02-0.05	<0.05					rem								
261.3		68.5-71.5			<0.05				<0.05					rem	0.02-0.08							
262		67.0-70.0			<0.05				<0.07					rem								
263.8		68.0-72.0		<0.10	<0.05				<0.30					rem								
268		64.0-68.5			<0.05				<0.15					rem								
270		63.0-68.5			<0.07				<0.10					rem								
272		62.0-65.0			<0.07				<0.10					rem								
274		61.0-64.0			<0.05				<0.10					rem								
280		59.0-63.0			<0.07				<0.30					rem								
282		58.0-61.0		<0.005	<0.05			0.12-0.22	<0.03				<0.05	rem								
285.8		49.0-52.0		<0.10	<0.10				<0.50					rem								
298		49.0-52.0		<0.10	<0.10				<0.50					rem								
310		89.0-91.0			<0.10				0.30-0.70					rem								
312		87.5-90.5			<0.10		<0.25		0.7-1.2					rem								
314		87.5-90.5			<0.10		<0.7		1.3-2.5					rem								
316		87.5-90.5			<0.10		0.7-1.2	0.04-0.10	1.3-2.5					rem								
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
320		83.5-86.5			<0.10		<0.25		1.5-2.2					rem								
325		72.0-74.5			<0.10				2.5-3.0					rem								
325.1		69.0-72.0			<0.07				0.30-0.70					rem	0.02-0.06							
330		65.0-68.0			<0.06				0.25-0.70					rem								
331		65.0-68.0			<0.06				0.8-1.5					rem								
332		65.0-68.0			<0.07				1.5-2.5					rem								
335		62.0-65.0			<0.15				0.25-0.70					rem								
335.3		62.5-66.5			<0.10				0.30-0.80					rem	0.02-0.06							
340		62.0-65.0			<0.15				0.8-1.5					rem								
342		62.0-65.0			<0.15				1.5-2.5					rem								
344		62.0-66.0			<0.10				0.50-1.00					rem								
345		62.0-65.0			<0.15				1.5-2.5					rem								
347		62.5-64.5			<0.10				1.0-1.8					rem								
348		61.5-63.5			<0.10				0.40-0.80					rem								
349		61.0-64.0			<0.10				0.10-0.50					rem								
350		60.0-63.0			<0.15				0.8-2.0					rem								
353		60.0-63.0			<0.15				1.5-2.5					rem								
353.3		60.5-64.0			<0.10				1.5-3.5					rem	0.02-0.25							
353.4		60.0-63.0			0.10-0.30				1.5-2.5					rem								
356		60.0-63.0			<0.15				2.0-3.0					rem								
360		60.0-63.0			<0.35				2.5-3.7					rem								
362		60.0-63.0			<0.15				3.5-4.5					rem								
365		58.0-61.0			<0.15				0.25-0.70					rem								
366		58.0-61.0			<0.15				0.25-0.70					rem	0.02-0.06							
367		58.0-61.0			<0.15				0.24-0.70					rem								
368		58.0-61.0			<0.15			0.02-0.10	0.25-0.70					rem								
370		59.0-62.0			<0.15				0.8-1.5					rem								
371		58.0-62.0			<0.15				0.6-1.2					rem								
377		58.0-61.0			<0.30				1.5-2.5					rem								
377.1		56.5-60.0			<0.30				1.0-2.5					rem								
378		56.0-59.0			<0.30				1.5-2.5					rem								
380		55.0-60.0		<0.50	<0.35				1.5-2.5					rem								
380.1		0.10-0.60			<0.30				1.5-3.0				<0.30	rem								
385		55.0-59.0			<0.35				2.5-3.5					rem								
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr	
385.1		56.0-60.0							2.5-4.5					rem									
385.9		56.5-60.0			<0.35				2.0-3.5					rem									
386		56.0-59.0			<0.35				2.5-3.5					rem									
404		94.0-96.0			<0.05				<0.05					0.35-0.70									
405		94.0-96.0			<0.05				<0.05					0.7-1.3									
408.1		94.0-96.0			<0.05				<0.05					1.8-2.2									
408.2		94.5-96.5			0.08-0.12				<0.05					1.8-2.2									
408.5		>94.00			0.05-0.20				0.02-0.04					1.0-2.5									
408.6		94.5-96.5			0.05-0.20				0.02-0.04					0.20-2.50									
408.8		94.0-96.0			0.01-0.05				<0.05					rem									
409		92.0-94.0			<0.05				<0.05					0.50-0.80									
410		91.0-93.0			<0.05				<0.05					2.0-2.8									
411		89.0-92.0			<0.05				<0.10					0.30-0.70									
411.2		89.0-92.0			0.05-0.20				<0.05					0.30-0.70									
413		89.0-93.0			<0.05				<0.10					rem									
415		89.0-93.0			<0.05				<0.10					1.5-2.2									
419		89.0-92.0			<0.05				<0.10					4.8-5.5									
420		88.0-91.0			<0.05				<0.10					1.5-2.0									
421		87.5-89.0			<0.05	0.15-0.35			<0.25					2.2-3.0									
422		86.0-89.0			<0.05				<0.35					0.8-1.4									
422.2		88.0-91.0			0.05-0.20				<0.05					0.7-1.4									
425		87.0-90.0			<0.05				<0.35					1.5-3.0									
425.2		88.0-91.0			0.05-0.20				<0.05					1.5-3.0									
426		87.0-90.0			0.05-0.20				<0.05					2.5-4.0									
430	Ni = Ni+Co	84.0-87.0			<0.05				<0.10					1.7-2.7									
432		85.0-88.0			<0.05				<0.05					0.40-0.60									
434		84.0-87.0			<0.05				<0.05					0.40-1.00									
435		78.0-83.0			<0.05				<0.10					0.6-1.2									
436		80.0-83.0			<0.05				<0.05					0.20-0.50									
438		79.0-82.0			<0.05				<0.05					1.0-1.5									
442.5		73.0-76.0			<0.20		<0.20		<0.07					0.50-1.50									
443		70.0-73.0			<0.06				<0.07					0.8-1.2									
444		70.0-73.0			<0.06				<0.07					0.8-1.2									
445		70.0-73.0			<0.06				<0.07					0.8-1.2									
454.5		65.0-66.0		0.20-0.40					<0.10-0.30					0.10-0.30									
462		62.0-65.0		<0.03	<0.10				<0.20					0.50-1.00									
462.1		61.0-64.0			<0.10				<0.05					<1.00									
464		59.0-62.0			<0.10				<0.20					0.50-1.00									
464.2		61.0-63.5			<0.20				<0.20					1.0-1.4									
465		59.0-62.0			<0.10				<0.20					0.50-1.00									
466		59.0-62.0			<0.10				<0.20					0.50-1.00									
467		59.0-62.0			<0.10				<0.20					0.50-1.00									
470		57.0-61.0		<0.01	<0.10				<0.05					0.25-1.00									
472		49.0-52.0			<0.10				<0.50					3.0-4.0									
476		86.0-88.0			<0.05	0.05-0.15			1.8-2.2					1.8-2.2									
479.4	Ni = Ni+Co	63.0-66.0			0.10-1.00		0.10-0.50		1.0-2.0					1.2-2.0									
482		59.0-62.0			<0.10				0.40-1.00					0.50-1.00									
485		59.0-62.0			<0.10				1.3-2.2					0.50-1.00									
485.1		59.0-62.0			<0.10				1.0-2.5					0.7-1.5									
486		59.0-62.0			<0.10				1.0-2.5					0.8-1.5									
490.8		49.0-52.0		<0.10	<0.05				<0.50					3.0-4.0									
501		rem			<0.05				<0.05					0.50-0.80									
502		rem			<0.10				<0.05					1.0-1.5									
505		rem			<0.10				<0.05					1.0-1.7									
505.1		rem			<0.10		0.15-0.40		<0.05					0.10-0.25									
505.8		rem			0.05-0.20		0.05-0.20		<0.05					1.0-1.7									
505.9		>97.00			0.05-0.40				<0.02					0.5-1.5									
507		rem			<0.10				<0.30					<0.50									
507.05		>96.50			0.10-0.40				<0.02					<0.50									
507.1		rem			<0.10		0.10-0.40		<0.15					1.7-2.3									
507.15		rem			0.05-0.15				<0.02					1.7-2.3									
507.25		>94.00			0.05-0.20				<0.02					1.5-2.5									
507.8		rem			0.05-0.20		0.05-0.20		<0.05					1.7-2.3									
508		rem			<0.10				<0.05					2.6-3.4									
509		rem			<0.10				<0.05					2.5-3.8									
510		rem			<0.10				<0.05					4.2-5.8									
510.8		rem			0.05-0.20		0.05-0.20		<0.05					4.8-5.8									
511		rem			<0.10				<0.05					3.5-4.9									
511.8		rem			0.05-0.20		0.11-0.20		<0.05					<0.30									
511.9		rem			0.05-0.15				<0.02					3.0-6.5									
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr	

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr	
655	Cu = Ag+Cu	rem		<0.01	<0.80	0.50-1.30	<0.6		<0.05			2.8-3.8		<1.50									
656	Cu = Ag+Cu	rem			<0.50	<1.50			<0.02			<1.50		<1.50									
656.2	Cu = Ag+Cu	>90.00			1.0-2.0	<1.00		<0.10	<0.05			2.4-4.0		1.5-4.0									
658	Cu = Ag+Cu	rem			<0.25	0.50-1.30	<0.6		<0.02			2.8-3.8		1.5-4.0									
661	Cu = Ag+Cu	rem			<0.25	<1.50			0.20-0.80			2.8-3.5		<1.50									
662	Cu = Ag+Cu	86.6-91.0			<0.05		0.30-1.00	0.05-0.20	<0.05				0.20-0.70	rem									
663	Cu = Ag+Cu	84.5-87.5			1.3-1.7		<0.05	<0.02	<0.015			<0.05	1.5-3.0	rem				<0.20					
664	Cu = Ag+Cu	rem		<0.05	1.8-2.3		<0.05	<0.02	<0.015			<0.05	<0.05	11.0-12.0	<0.05			0.30-0.70					
664.1	Cu = Ag+Cu	rem			0.50-1.50									12.7-17.0									
664.2	Cu = Ag+Cu	rem																					
667	Cu = Ag+Cu	68.5-71.5			<0.10	0.8-1.5			<0.07					rem									
668	Cu = Ag+Cu	60.0-63.0		<0.25	<0.35	2.0-3.15	<0.25		<0.05			0.50-1.50		rem									
669	Cu = Ag+Cu	62.5-64.5			<0.25	11.5-12.5			<0.01					rem									
669.5	Cu = Ag+Cu	rem		1.0-1.5	<0.50	14.0-15.0			<0.01					14.0-15.0									
670	Cu = Ag+Cu	63.0-68.0		3.0-6.0	2.0-4.0	2.5-5.0			<0.20				<0.50	rem									
671.3	Cu = Ag+Cu	56.0-59.0		0.10-1.00	<0.50	0.50-1.50	0.50-1.50		0.50-1.50				0.50-1.50	rem									
671	Cu = Ag+Cu	58.0-63.0		<0.25	<0.50	2.0-3.15	<0.25		0.40-3.00				0.50-1.50	rem									
674	Cu = Ag+Cu	57.0-60.0		0.50-2.00	<0.35	2.0-3.15	<0.25		<0.8				0.50-1.50	rem									
674.1	Cu = Ag+Cu	55.5-59.0		1.3-2.3	<1.00	1.0-2.4	<2.0		<0.8			0.7-1.3	<0.50	rem									
674.2	Cu = Ag+Cu	57.0-58.5		1.0-2.0	0.15-0.55	1.5-2.5	<0.25		0.25-0.80			0.25-0.70	<0.35	rem									
675	Cu = Ag+Cu	57.0-60.0		<0.25	0.8-2.0	0.05-0.50			<0.20				0.50-1.50	rem									
676	Cu = Ag+Cu	57.0-60.0			0.40-1.30	0.05-0.50			0.50-1.50				0.05-1.50	rem									
676.2	Cu = Ag+Cu	55.0-57.0			0.50-1.30	1.0-2.0			0.50-1.50				0.50-1.50	rem									
677	Cu = Ag+Cu	55.5-58.0			0.7-1.5	0.05-0.30	1.5-2.3		0.50-1.00					rem									
678	Cu = Ag+Cu	56.0-59.0		0.50-1.50	0.7-1.5	0.20-0.60			<0.30				<0.20	rem									
678.1	Cu = Ag+Cu	56.5-59.5		0.40-1.60	<1.00	0.40-1.80	<1.5		<1.0			<0.60	<0.50	rem									
678.2	Cu = Ag+Cu	56.5-59.5		0.30-1.30	0.50-1.20	0.30-2.00	<1.5		<0.10			0.30-1.00	<0.30	rem									
681	Cu = Ag+Cu	56.0-60.0		<0.01	0.25-1.25	0.01-0.50	0.20-0.80		<0.05			0.04-0.15	0.75-1.10	rem									
681	Cu = Ag+Cu	56.0-60.0		<0.01	0.25-1.25	0.01-0.50	0.20-0.80		<0.05			0.04-0.15	0.75-1.10	rem									
682	Cu = Ag+Cu	58.0-60.0			0.6-1.0	0.6-1.0			<0.05			0.07-0.15		rem									
686	Cu = Ag+Cu	56.0-60.0		0.30-1.50	0.50-1.20	0.30-2.00			0.50-1.50				0.20-1.00	rem									
687	Cu = Ag+Cu	76.0-79.0		1.8-2.5	<0.06				<0.07					rem									
688	Cu = Ag+Cu	3.0-3.8			<0.20				<0.05					21.3-24.1				0.25-0.55					
690	Cu = Ag+Cu	72.0-74.6		3.0-3.8	<0.05		0.50-0.80		<0.025					rem									
690.5	Cu = Ag+Cu	70.0-75.0		3.0-4.0			0.50-1.50					0.10-0.60		rem								0.01-0.20	
691	Cu = Ag+Cu	81.0-84.0		0.7-1.2	<0.25	<0.10	0.8-1.4		<0.05			0.8-1.3	<0.10	rem									
694	Cu = Ag+Cu	80.0-83.0			<0.20				<0.30			3.5-4.5		rem									
694.3	Cu = Ag+Cu	80.0-83.0			<0.20				<0.30			3.5-4.5		rem									
694.4	Cu = Ag+Cu	80.0-83.0			<0.20				<0.30		0.03-0.06	3.5-4.5		rem									
694.5	Cu = Ag+Cu	80.0-83.0			<0.20	<0.40		0.03-0.06	<0.30			3.5-4.5		rem									
697	Cu = Ag+Cu	75.0-80.0			<0.20	<0.40	<0.50		0.50-1.50			2.5-3.5		rem									
697.1	Cu = Ag+Cu	75.0-80.0			<0.20	<0.40			0.50-1.50			2.5-3.5		rem									
697.2	Cu = Ag+Cu	75.0-80.0			<0.20	<0.40			0.50-1.50			2.5-3.5		rem									
697.3	Cu = Ag+Cu	75.0-80.0			<0.20	<0.40		0.03-0.06	0.50-1.50			2.5-3.5		rem									
698	Cu = Ag+Cu	66.0-70.0			<0.4		<0.50		<0.8			0.7-1.3		rem									
699	Cu=Ag+Cu; C, Cd	<0.05		1.4-2.3	<0.10	40.0-48.0	<0.10		<0.02					<0.14	<0.01			<0.20					
699.1	Cu = Ag+Cu	rem		0.25-0.80	1.0-1.4	28.0-32.0	<0.10		<0.01					3.0-5.0									
699.5	Cu = Ag+Cu	51.0-54.0			<0.05	36.0-40.0	8.5-10.5		<0.05					rem									
701	Cu = Ag+Cu	rem			<0.05	<0.50	3.0-4.0		<0.05					<0.25									
702	Cu = Ag+Cu	rem			<0.10	<0.40	2.0-3.0		<0.05					rem									
702.3	Cu = Ag+Cu	rem			<0.015				<0.02					rem									
702.5	Cu = Ag+Cu	rem			<0.20	<0.10	2.2-3.2		<0.05			0.40-0.80	0.10-0.50	0.50-2.00					0.05-0.30				
702.6	Cu = Ag+Cu	rem			<0.20	<0.10	2.2-4.2		<0.05			0.20-0.70		<1.00									
702.7	Cu = Ag+Cu	rem			0.28-1.00	<0.15	1.0-3.0	<0.01	<0.05			0.20-1.00	0.10-1.00	<1.00									
702.8	Cu = Ag+Cu	rem			<0.015		1.3-1.7	0.020-0.040	<0.02			0.22-0.30	1.0-1.5	<0.30									
702.9	Cu = Ag+Cu	rem			<0.015		1.3-1.7	0.020-0.040	<0.02			0.22-0.30	2.1-2.7	<0.30									
703	Cu = Ag+Cu	>99.50			<0.05	<0.50	4.7-5.7							rem									
703.2	Cu = Ag+Cu	rem		0.20-1.20	1.3-1.7	0.30-0.80	2.5-5.0		<0.05			0.20-1.20		rem				0.18-0.50					
704	Cu = Ag+Cu	rem			1.0-1.8	0.50-1.50	4.5-6.0		<0.05			0.35-0.45		rem									
704.4	Cu = Ag+Cu	rem			1.0-1.8	0.50-1.50	4.5-6.0		<0.05			0.35-0.45		rem									
705	Cu = Ag+Cu	rem			<0.10	<0.15	5.8-7.8		<0.05					rem									
706	Cu = Ag+Cu	rem			1.0-1.8	0.50-1.00	9.0-11.0		<0.05					rem									
706.1	Cu = Ag+Cu	rem			1.0-2.0	1.0-1.00	10.0-11.0		<0.01					rem									
706.2	Cu = Ag+Cu	>86.50			1.0-1.8	<0.01	9.0-11.0	<0.02	<0.02					rem									
706.9	Cu=Ag+Cu, C<0.03, H<0.0005	rem		<0.002	<0.005	<0.001	9.0-11.0	&															

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
711.1	Cu = Ag+Cu	rem			<0.20	<0.35	21.5-23.5					<1.00							<0.05	
713	Cu = Ag+Cu	rem			0.40-1.00	<1.00	23.5-26.5					<1.00								
715	Cu = Ag+Cu	rem			0.40-1.00	<1.00	29.0-33.0	<0.02				<1.50								
715.2	Cu = Ag+Cu	>65.00			0.40-1.00	<1.00	29.0-33.0	<0.02				<1.50								
715.8	Cu = Ag+Cu, C <0.70	rem			<0.50	<0.30	29.0-33.0	<0.03		<0.15		<0.05								
715.81	Cu = Ag+Cu	rem			0.40-0.70	<1.00	29.0-32.0	<0.02		<0.25		<0.001							0.20-0.50	
715.9	Cu = Ag+Cu, C<0.02, Hg<0.0005	rem			0.40-1.00	<1.00	29.0-31.0	<0.001		<0.015	<0.001	<0.001			<0.001	<0.05		<0.10	<0.001	
716.2	Cu = Ag+Cu, C<0.06	rem			0.40-1.00	0.50-1.50	30.0-32.0	<0.01												
716.3	Cu = Ag+Cu, C<0.06	rem			1.7-2.3	1.5-2.5	29.0-32.0	<0.08												
716.4	Cu = Ag+Cu, C<0.06	rem			0.40-1.00		29.0-33.0	<0.03												
717	Cu = Ag+Cu	rem			0.40-1.00		29.0-33.0	<0.03						0.30-0.70						
719	Cu = Ag+Cu, C<0.04	rem			<0.50	0.20-1.00	28.0-33.0	<0.02				<0.05				2.2-3.0			0.01-0.20	0.02-0.35
721.5	Cu = Ag+Cu, C<0.10	rem			<0.10	<0.05	43.0-46.0			<0.25		<0.20								
723	Cu = Ag+Cu, C<0.03	rem			0.5-1.0	<1.00	15.0-18.0			<0.03		<1.00				0.30-0.70			<0.03	
724	Cu = Ag+Cu	rem			1.5-2.5	<1.00	11.0-15.0					<0.50								
724.2	Cu = Ag+Cu, C<0.05	rem			1.0-2.0	3.5-5.5	13.5-16.5	<0.01		<0.15		<0.20				<0.50		0.05-0.40		
725	Cu = Ag+Cu	rem			<0.60	<0.20	8.5-10.5					<0.50								
726	Cu = Ag+Cu	rem			<0.60	<0.20	3.5-4.5	<0.05				<0.50								
726.5	Cu = Ag+Cu	91.0-93.0			<0.10	<0.10	7.0-8.0					<0.50								
727	Cu = Ag+Cu	rem			<0.50	0.05-0.30	8.5-9.50					<0.50								
728	Cu=Ag+Cu, Nb 0.1-0.3, B <0.001	rem			<0.50	0.05-0.30	9.5-10.5	<0.005	<0.02	<0.05		<0.50			<0.001			0.005-0.15	<0.01	
729	Cu = Ag+Cu	rem			<0.50	<0.30	14.5-15.5					<0.50								
729.5	Cu = Ag+Cu	rem			<0.60	<0.60	20.0-22.0					<0.50								
731.5	Cu = Ag+Cu	rem			<0.25	<0.50	4.0-7.0					<0.50								
732	Cu = Ag+Cu	rem			<0.06	<1.00	19.0-23.0					<0.50								
735	Cu = Ag+Cu	70.5-73.5			<0.25	<0.50	16.5-19.5					rem								
738	Cu = Ag+Cu	rem			<0.25	<0.50	11.0-13.0					<0.50								
740	Cu = Ag+Cu	68.5-71.5			<0.25	<0.50	16.5-19.5					rem								
743	Cu = Ag+Cu	69.0-73.5			<0.25	<0.50	14.0-16.0					rem								
744	Cu = Ag+Cu	62.0-66.0			<0.25	<0.50	11.0-13.0					rem								
744	Cu = Ag+Cu	62.0-66.0			<0.25	<0.50	11.0-13.0					rem								
745	Cu = Ag+Cu	63.5-66.5			<0.25	<0.50	17.0-19.0					rem								
752	Cu = Ag+Cu	63.5-66.5			<0.25	<0.50	16.5-19.5					rem								
754	Cu = Ag+Cu	63.5-66.5			<0.25	<0.50	14.0-16.0					rem								
757	Cu = Ag+Cu	63.5-66.5			<0.25	<0.50	11.0-13.0					rem								
757.2	Cu = Ag+Cu	60.0-65.0			<0.25	0.05-0.30	11.0-13.0					rem								
759	Cu = Ag+Cu, Ni = Ni+Co	60.0-65.0			<0.25	<0.50	17.0-19.0					rem								
760	Cu = Ag+Cu, Ni = Ni+Co	60.0-63.0			<0.25	<0.50	7.0-9.0					rem								
761	Cu = Ag+Cu, Ni = Ni+Co	59.0-63.0			<0.25	<0.50	7.0-9.0					rem								
762	Cu = Ag+Cu, Ni = Ni+Co	57.0-61.0			<0.25	<0.50	11.0-13.5					rem								
763	Cu = Ag+Cu, Ni = Ni+Co	60.0-64.0			<0.50	<0.50	17.0-19.0	0.50-2.00				rem								
763.9	Cu = Ag+Cu, Ni = Ni+Co	59.0-63.0			<0.50	<0.50	23.0-26.0				0.40-0.60	rem								
764	Cu = Ag+Cu, Ni = Ni+Co	58.5-61.5			<0.25	<0.50	16.5-19.5					rem								
766	Cu = Ag+Cu, Ni = Ni+Co	55.0-58.0			<0.25	<0.50	11.0-13.5					rem								
767	Cu = Ag+Cu, Ni = Ni+Co	55.0-58.0			<0.25	<0.50	14.0-16.0					rem								
770	Cu = Ag+Cu, Ni = Ni+Co	53.5-56.5			<0.25	<0.50	16.5-19.5					rem								
770.1	Cu = Ag+Cu, Ni = Ni+Co	54.0-56.0			<0.30	0.05-0.35	17.0-19.0					rem								
773	Cu = Ag+Cu, Ni = Ni+Co	46.0-50.0		<0.01	<0.30		9.0-11.0	<0.25		0.04-0.25		rem								
773.1	Cu = Ag+Cu, Ni = Ni+Co	46.0-56.0		<0.01		<0.50	9.0-11.0	<0.25		0.04-0.25		rem								
774	Cu = Ag+Cu, Ni = Ni+Co	43.0-47.0			<0.20	<0.25	12.0-14.0					rem								
776	Cu = Ag+Cu, Ni = Ni+Co	42.0-45.0			<0.20	<0.25	9.0-11.0				<0.15	rem								
782	Cu = Ag+Cu, Ni = Ni+Co	63.0-67.0			<0.35	<0.50	7.0-9.0					rem								
788	Cu = Ag+Cu, Ni = Ni+Co	63.0-67.0			<0.25	<0.50	9.0-11.0					rem								
790	Cu = Ag+Cu, Ni = Ni+Co	63.0-67.0			<0.35	<0.50	11.0-13.0					rem								
792	Cu = Ag+Cu, Ni = Ni+Co	59.5-66.5			<0.25	<0.50	11.0-13.0					rem								
793	Cu = Ag+Cu, Ni = Ni+Co	55.0-59.00			<0.50	<0.50	11.0-13.0					rem								
796	Cu = Ag+Cu, Ni = Ni+Co	43.5-46.5				1.5-2.5	9.0-11.0					rem								
796.2	Cu = Ag+Cu, Ni = Ni+Co	46.0-48.0			<0.25	<0.50	8.0-11.0					rem								
798	Cu = Ag+Cu, Ni = Ni+Co	45.5-48.5			<0.25	<0.50	9.0-11.0					rem								
798.1	Cu = Ag+Cu, Ni = Ni+Co	46.0-48.0			<0.25	<0.50	8.0-11.0					rem								
798.2	Ni = Ni+Co	46.0-48.0			<0.50	<0.50	8.0-11.0					rem								
798.3	Cu = Ag+Cu, Ni = Ni+Co	45.5-47.0			<0.45	0.15-0.55	9.0-10.5					rem								
799	Cu = Ag+Cu, Ni = Ni+Co	47.5-50.5			<0.25	<0.50	6.5-8.5					rem								
801	Cu = Ag+Cu, Ni = Ni+Co	>99.95										rem								
803	Cu = Ag+Cu, Ni = Ni+Co	>99.95										rem								
804.1	Cu = Ag+Cu, Ni = Ni+Co	>99.90	>0.034									rem								
805	Cu=Ag+Cu, Ni=Ni+Co, B <0.02	>99.75	>0.034									rem								
807	B <0.02	>99.75										rem								
809		>99.70	>0.034									rem								
812		>99.70					0.040-0.065					rem								
813		>98.50										rem								
814		>98.50										rem								
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
815		>98.00		<0.10	<0.10				<0.02			<0.15	<0.10	<0.10					0.40-1.50			
815.4		>95.10		<0.10	<0.15		2.0-3.0		<0.02			0.40-0.80	<0.10	<0.10					0.25-1.50			
817		>94.20	0.80-1.20				0.25-1.50		<0.02										1.4-1.7			
818		>95.60	0.80-1.20				<0.20												2.4-2.7			
820		>95.00		<0.10	<0.10		<0.20		<0.02			<0.15	<0.10	<0.10					<0.10			
821		>95.50					0.25-1.50												0.25-1.50			
822		>95.50					1.0-2.0												0.25-1.50			
824		>96.40		<0.15	<0.20		<0.10		<0.02				<0.10	<0.10					0.20-0.40			
825		>95.50		<0.15	<0.25		<0.20		<0.02			0.20-0.35	<0.10	<0.10					0.35-0.70			
825.1		>95.50		<0.15	<0.25		<0.20		<0.02			0.20-0.35	<0.10	<0.10					1.0-2.0			
826		>95.20		<0.15	<0.25		<0.20		<0.02			0.20-0.35	<0.10	<0.10					0.35-0.70			
827		>94.60		<0.15	<0.25		1.0-1.5		<0.02			0.20-0.35	<0.10	<0.10					0.35-0.70			
828		>94.80		<0.15	<0.25		<0.20		1.0-2.0			0.20-0.35	<0.10	<0.10					0.35-0.70			
833		92.0-94.0							1.0-2.0					2.0-6.0					0.35-0.70			
834		86.0-92.0							<0.50				<0.20	8.0-12.0					0.35-0.70			
834.1		88.0-91.0		<0.05	<0.05		<0.05		<0.10			<0.005	0.25-0.70	rem					0.35-0.80			
834.2		88.0-92.0		<0.10	<0.10		<0.10		<0.50			<0.005	0.25-0.70	rem					0.35-0.80			
834.5		87.0-89.0		<0.005	<0.30		0.8-2.0	<0.03	1.5-3.0	<0.08	<0.25	<0.005	2.0-3.5	5.5-7.5					1.65-1.75			
835.2		86.0-88.0		<0.008	<0.35		0.50-1.00	<0.03	3.5-4.5	<0.08	<0.25	<0.005	5.5-6.5	1.0-2.5					1.90-2.15			
835.2		rem		<0.30	<0.30		<1.0		3.5-4.5	<0.08	<0.25	<0.005	3.5-4.5	1.5-4.0					1.90-2.15			
836		84.0-86.0		<0.005	<0.30		<1.0	<0.05	4.0-6.0	<0.08	<0.25	<0.005	4.0-6.0	4.0-6.0	0.05-0.20				2.25-2.45			
837		83.0-88.0		<0.005	<0.30		<0.30	<0.05	4.0-6.0	<0.08	<0.25	<0.005	4.0-6.0	4.0-6.0	0.05-0.20				2.25-2.45			
838		82.0-83.8		<0.005	<0.30		<1.0	<0.03	5.0-7.0	<0.08	<0.25	<0.005	3.0-4.2	5.0-8.0					2.25-2.45			
838.1		83.8		<0.01	<0.50		<2.0	<0.03	4.0-6.0	<0.08	<0.25	<0.005	2.0-3.5	7.5-9.5	<0.10				2.25-2.45			
842		78.0-82.0		<0.005	<0.40		<0.8	<0.05	2.0-3.0	<0.08	<0.25	<0.005	4.0-6.0	10.0-16.0					2.25-2.45			
844		78.0-82.0		<0.005	<0.40		<1.0	<0.20	6.0-8.0	<0.08	<0.25	<0.005	2.0-3.5	7.0-10.0					2.25-2.45			
844.1		77.0-79.0		<0.01	<0.40		<1.0	<0.02	7.0-9.0	<0.08	<0.25	<0.005	3.0-4.5	7.0-11.0					2.25-2.45			
845		75.0-77.0		<0.005	<0.40		<1.0	<0.02	6.0-7.5	<0.08	<0.25	<0.005	2.0-4.0	10.0-14.0					2.25-2.45			
848		75.0-77.0		<0.005	<0.40		<1.0	<0.02	5.5-7.0	<0.08	<0.25	<0.005	2.0-3.0	13.0-17.0					2.25-2.45			
852		70.0-74.0		<0.005	<0.60		<1.0	<0.02	1.5-3.8	<0.05	<0.20	<0.005	0.7-2.0	20.0-27.0					2.25-2.45			
852.1		70.0-75.0		<0.005	<0.80		<1.0		2.0-5.0			<0.005	1.0-3.0	rem	0.02-0.06				2.25-2.45			
853		68.0-72.0		<0.01	<0.80		<1.0		<0.50			<0.005	<0.50	rem	0.02-0.06				2.25-2.45			
853.1		68.0-73.0		<0.35	<0.70		<1.0		1.5-3.8			<0.005	0.50-1.50	24.0-32.0					2.25-2.45			
854		65.0-70.0		<0.35	<0.70		<1.0		1.5-3.8			<0.005	<0.20	rem					2.25-2.45			
855		59.0-63.0		<0.20	<0.20		<0.20		<0.20				<0.20	rem					2.25-2.45			
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
856		59.0-63.0		<0.20	<0.20		<0.20		<0.20				<0.20	rem								
857		58.0-64.0		<0.8	<0.80		<1.0		<0.20			<0.05	0.50-1.50	32.0-40.0								
857.1		58.0-63.0		0.20-0.80	<0.80		<1.0		1.0-2.5			<0.05	<1.00	rem								
858		>57.00		<4.5-5.5	<0.50		<0.50	<0.01	<1.5	<0.05	<0.05	<1.50	<0.20	31.0-41.0	<0.05							
861		66.0-68.0		4.5-5.5	2.0-4.0		2.5-5.0		<0.20				<0.20	rem								
862		60.0-66.0		3.0-4.9	2.0-4.0		2.5-5.0		<0.20				<0.20	22.0-28.0								
863		60.0-66.0		2.0-4.0	2.0-4.0		2.5-5.0		<0.20				<0.20	22.0-28.0								
864		56.0-62.0		0.50-1.50	0.40-2.00		0.10-1.00		0.50-1.50				0.50-1.50	34.0-42.0								
865		55.0-60.0		0.50-2.50	0.40-2.00		1.0-1.5		<0.40				<1.00	36.0-42.0								
865.5		>57.00		0.50-2.50	0.7-2.0		0.10-3.00		<0.50				<1.00	rem								
867		53.0-60.0		1.0-3.0	1.0-3.0		1.0-3.5		0.5-1.5				<1.50	30.0-38.0								
868		53.5-57.0		<2.0	1.0-2.5		2.5-4.0		<0.20				<1.00	rem								
872		>89.00		<1.5	<2.50		<1.50		<0.50			1.0-5.0	<1.00	<5.00								
873		>94.00		<0.8	<0.20		0.8-1.5		<0.20			3.5-4.5	<1.00	<0.25								
874		>79.00		<0.8	<0.20				<1.0			2.5-4.0	<1.00	12.0-16.0								
874.1		>79.00		<0.8	<0.20				<1.0			2.5-4.0	<1.00	12.0-16.0	0.03-0.06							
874.2		>79.00		<0.8	<0.20				<1.0		0.03-0.06	2.5-4.0	<1.00	12.0-16.0								
874.3		>79.00		<0.8	<0.20			0.03-0.06	<1.0			2.5-4.0	<1.00	12.0-16.0								
875		>79.00		<0.5	<0.20				<0.50			3.0-5.0	<1.00	12.0-16.0								
875.1		>79.00		<0.50	<0.20				<0.50			3.0-5.0	<1.00	12.0-16.0								
875.2		>79.00		<0.50	<0.20				<0.50			3.0-5.0	<1.00	12.0-16.0								
875.3		>79.00		<0.50	<0.20				<0.50			3.0-5.0	<1.00	12.0-16.0								
876		>88.00		<0.20	<0.20		<0.25		<0.50			3.5-4.5	<1.00	4.0-7.0								
876.1		>90.00		<0.20	<0.20		<0.25		<0.20			3.5-4.5	<1.00	3.0-5.0								
878		>80.00		<0.15	<0.15		<0.15	<0.01	<0.15	<0.05	<0.05	3.8-4.2	<0.25	12.0-16.0	<0.05							<0.01
879		>63.00		<0.15	<0.40		<0.15	<0.01	<0.25	<0.05	<0.05	0.8-1.2	<0.25	30.0-36.0	<0.05							
893.2		87.0-91.0		<0.005	<0.20		<1.0															

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
898.44		83.0-86.0		<0.005	<0.30	<0.20	<1.0	<0.05	<0.20	<0.08	<0.25	<0.005	3.0-5.0	7.0-10.0			2.0-4.0					
899.4		64.0-68.0		<0.005	0.7-2.0	<0.20	20.0-23.0	0.10-0.15	<0.01	<0.05	<0.10	<0.15	3.0-5.0	3.0-5.0			4.0-5.5					
902		91.0-94.0		<0.005	<0.25	<0.10	<0.50	<0.05	<0.30	<0.05	<0.20	<0.005	6.0-8.0	6.0-8.0								
902.5		82.0-91.0		<0.005	<0.25	<0.10	<1.0	<0.05	<0.30	<0.05	<0.20	<0.005	7.5-9.0	3.0-5.0								
903		86.0-89.0		<0.005	<0.20		<1.0	<0.05	<0.30	<0.05	<0.20	<0.005	9.0-11.0	1.0-3.0								
905		86.0-89.0		<0.005	<0.20		<1.0	<0.05	<0.30	<0.05	<0.20	<0.005	10.0-12.0	<0.50								
907		88.0-90.0		<0.005	<0.15		<0.10	0.50-1.20	<0.50	<0.05	<0.20	<0.005	11.0-13.0	<0.25								
907.1		85.0-89.0		<0.005	<0.15		<0.50	0.15-0.80	<0.25	<0.05	<0.20	<0.005	12.0-14.0	<0.25								
908.1		rem		<0.005	<0.15		<0.50	<0.05	<0.25	<0.05	<0.20	<0.005	14.0-16.0	<1.50								
909		86.0-89.0		<0.005	<0.15		<0.8	<0.05	<0.20	<0.05	<0.20	<0.005	15.0-17.0	<0.25								
910		84.0-86.0		<0.005	<0.10		<0.50	<1.00	<0.25	<0.05	<0.20	<0.005	18.0-20.0	<0.25								
911		99.70		<0.005	<0.25		<0.50	<1.00	<0.25	<0.05	<0.20	<0.005	10.0-12.0	<0.25								
911		82.0-85.0		<0.005	<0.25		<0.50	<1.00	<0.25	<0.05	<0.20	<0.005	9.7-10.8	<0.25								
913		79.0-82.0		<0.005	<0.25		<0.50	<1.00	<0.25	<0.05	<0.20	<0.005	11.3-12.5	<0.25								
916		86.0-89.0		<0.005	<0.20		1.2-2.0	<0.30	<0.25	<0.05	<0.20	<0.005	5.5-6.5	3.0-4.5								
917		84.0-87.0		<0.005	<0.20		1.2-2.0	<0.30	<0.25	<0.05	<0.20	<0.005	5.0-6.0	3.0-5.5								
922		86.0-90.0		<0.005	<0.25		<1.0	<0.05	1.0-2.0	<0.05	<0.25	<0.005	9.5-10.5	1.7-2.8								
922.1		86.0-89.0		<0.005	<0.25		0.7-1.0	<0.03	1.7-2.5	<0.05	<0.20	<0.005	10.0-12.0	<0.80								
922.2		86.0-88.0		<0.005	<0.25		0.5-1.0	<0.05	1.5-2.5	<0.05	<0.20	<0.005	15.0-17.0	<0.80								
923		85.0-89.0		<0.005	<0.25		<1.0	<0.05	0.30-1.00	<0.05	<0.25	<0.005	7.5-9.0	2.5-4.5								
923.1		rem		<0.005	<0.25		<1.0	<0.05	0.30-1.50	<0.05	<0.25	<0.005	9.5-10.5	1.7-2.8								
924		86.0-89.0		<0.005	<0.25		<1.0	<0.05	1.0-2.5	<0.05	<0.25	<0.005	10.0-11.0	1.0-3.0								
924.1		85.0-88.0		<0.005	<0.20		<0.20	<0.05	1.5-3.5	<0.05	<0.25	<0.005	6.0-8.0	1.5-3.0								
925		85.0-88.0		<0.005	<0.30		0.8-1.5	<0.30	1.0-1.5	<0.05	<0.25	<0.005	10.0-12.0	<0.50								
926		86.0-88.5		<0.005	<0.20		<0.7	<0.03	0.8-1.5	<0.05	<0.25	<0.005	9.3-10.5	1.3-2.5								
926.1		rem		<0.005	<0.15		<1.0	<0.05	0.30-1.50	<0.05	<0.25	<0.005	9.5-10.5	1.7-2.8								
927		87.0-90.0		<0.005	<0.20		<1.0	<0.05	1.0-2.5	<0.05	<0.25	<0.005	9.0-11.0	<0.70								
927.1		rem		<0.005	<0.20		<2.0	<0.10	4.0-6.0	<0.05	<0.25	<0.005	9.0-11.0	<1.00								
928		78.0-82.0		<0.005	<0.20		<0.8	<0.05	4.0-6.0	<0.05	<0.25	<0.005	15.0-17.0	<0.80								
928.1		78.0-82.0		<0.005	<0.50		0.8-1.2	<0.05	4.0-6.0	<0.05	<0.25	<0.005	12.0-14.0	<0.50								
929		82.0-86.0		<0.005	<0.20		2.8-4.0	<0.50	2.0-3.2	<0.05	<0.25	<0.005	9.0-11.0	<0.25								
931		81.0-85.0		<0.005	<0.25		<1.0	<0.30	2.0-5.0	<0.05	<0.25	<0.005	6.5-8.5	<2.00								
932		81.0-85.0		<0.005	<0.20		<1.0	<0.15	6.0-8.0	<0.05	<0.35	<0.005	6.3-7.5	1.0-4.0								
934		82.0-85.0		<0.005	<0.20		<1.0	<0.50	7.0-9.0	<0.05	<0.50	<0.005	7.0-9.0	<0.80								
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
935		83.0-86.0		<0.005	<0.20		<1.0	<0.05	8.0-10.0	<0.08	<0.30	<0.005	4.3-6.0	<2.00								
936		79.0-83.0		<0.005	<0.20		<1.0	<0.15	11.0-13.0	<0.08	<0.55	<0.005	6.0-8.0	<1.00								
937		80.0-82.0		<0.005	<0.70		<0.50	<0.10	8.0-11.0	<0.08	<0.50	<0.005	9.0-11.0	<0.80								
937.2		>83.00		<0.005	<0.15		<0.50	<0.10	7.0-9.0	<0.08	<0.80	<0.005	3.5-4.5	<4.00								
938		75.0-79.0		<0.005	<0.70		<1.0	<0.05	13.0-16.0	<0.08	<0.80	<0.005	6.3-7.5	<0.80								
939		76.5-79.5		<0.005	<0.40		<0.8	<1.50	14.0-18.0	<0.08	<0.50	<0.005	5.0-7.0	<1.50								
940		69.0-72.0		<0.005	<0.25		0.50-1.00	<0.05	14.0-16.0	<0.08	<0.50	<0.005	12.0-14.0	<0.50								
941		72.0-79.0		<0.005	<0.25		<1.0	<0.05	18.0-22.0	<0.08	<0.80	<0.005	4.5-6.5	<1.00								
942		68.5-75.5		<0.005	<0.35		<0.50	<0.30	3.0-4.0	<0.08	<0.80	<0.005	3.0-4.0	<3.00								
943		67.0-72.0		<0.005	<0.15		<1.0	<0.08	22.0-25.0	<0.08	<0.80	<0.005	4.5-6.0	<0.80								
943.1		rem		<0.005	<0.50		0.25-1.00	<0.05	27.0-34.0	<0.08	<0.50	<0.005	1.5-3.0	<0.50								
943.2		rem		<0.005	<0.35		<0.50	<0.10	24.0-32.0	<0.08	<0.50	<0.005	4.0-7.0	<0.50								
943.3		68.5-75.5		<0.005	<0.70		<0.50	<0.10	21.0-25.0	<0.08	<0.50	<0.005	3.0-4.0	<3.00								
944		rem		<0.005	<0.15		<1.0	<0.05	9.0-12.0	<0.08	<0.80	<0.005	7.0-9.0	<0.80								
945		rem		<0.005	<0.15		<1.0	<0.05	16.0-22.0	<0.08	<0.80	<0.005	6.0-8.0	<1.20								
947		85.0-89.0		<0.005	<0.25	<0.20	4.5-6.0	<0.05	<0.10	<0.05	<0.15	<0.005	4.5-6.0	1.0-2.5								
948		84.0-89.0		<0.005	<0.25	<0.10	4.5-6.0	<0.05	0.30-1.00	<0.05	<0.15	<0.005	4.5-6.0	1.0-2.5								
949		79.0-81.0		<0.005	<0.30	<0.10	4.0-6.0	<0.05	4.0-6.0	<0.08	<0.25	<0.005	4.0-6.0	4.0-6.0								
952		>86.00		8.5-9.5	2.5-4.0		<1.00	<0.05	<0.05	<0.08	<0.25	<0.005	4.0-6.0	<0.80								
952.1		>86.00		8.5-9.5	2.5-4.0		<1.00	<0.05	<0.05	<0.08	<0.25	<0.005	4.0-6.0	<0.80								
952.2		rem		9.5-10.5	2.5-4.0		<0.50	<0.05	<0.05	<0.08	<0.25	<0.005	4.0-6.0	<0.80								
953		>86.00		9.0-11.0	0.8-1.5		<0.50	<0.05	<0.05	<0.08	<0.25	<0.005	4.0-6.0	<0.80								
954		>83.00		10.0-11.5	3.0-5.0																	

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr	
958.2		>77.50		9.0-10.0 12.0-13.5	4.0-5.0 3.0-5.0	<1.50 <1.50	4.5-5.8 <0.50		<0.02			<0.10	<0.20	<0.20									
959	C <0.10, No <1.00	rem		1.0-1.8	1.0-1.8	0.25-1.50	9.0-11.0	<0.02	<0.01	<0.02		<0.50											
963	C <0.15, No 0.50-1.50	rem		0.50-1.50	0.25-1.50	18.0-22.0	18.0-22.0	<0.02	<0.01	<0.02		<0.50											
964	C <0.15, No 0.50-1.50	rem		0.25-1.50	<1.50	28.0-32.0	28.0-32.0	<0.02	<0.03	<0.02		<0.50											
966		rem			0.8-1.1	<1.00	29.0-33.0		<0.01			<0.15				0.40-0.70							
967	No 0.10-0.30, B <0.01	rem		0.7-1.0	<0.70	29.0-33.0	29.0-33.0	<0.0025	<0.01	<0.0025	<0.02	<0.15				1.10-1.20					0.01-0.20	0.1-0.2	
969	No <0.10	rem		<0.10	<0.50	0.05-0.30	9.5-10.5		<0.005			<0.05					<0.001			0.005-0.15	<0.01		
969.5	No <0.10	rem			<0.50	0.50-0.30	14.5-15.5		<0.02			<0.30								<0.15			
		rem			<0.50	0.05-0.40	11.0-15.5		<0.02			<0.30								<0.15			
973		53.0-58.0		<0.005	<1.50	<0.50	11.0-14.0	<0.05	8.0-11.0	<0.08	<0.35	<0.15	1.5-3.0	17.0-25.0									
974		58.0-61.0		<0.005	<1.50	<0.50	15.5-17.0		4.5-5.5	<0.08	<0.25	<0.15	2.5-3.5	rem									
976		63.0-67.0		<0.005	<1.50	<1.00	19.0-21.5	<0.05	3.0-5.0	<0.08	<0.20	<0.15	3.5-4.5	3.0-9.0									
978		64.0-67.0		<0.005	<1.50	<1.00	24.0-27.0	<0.10	1.0-2.5	<0.08	<0.50	<0.15	4.0-5.5	1.0-4.0									
982		73.0-79.0			<0.70		<0.50	<0.10	21.0-27.0		<0.50		0.6-2.0	<0.50									
984		rem	<1.50		<0.70		<0.50	<0.10	26.0-33.0		<0.50		<0.50	<0.50									
986		60.0-70.0	<1.50		<0.35			<0.02	30.0-40.0				<0.25	<0.10									
988		56.5-62.5	<5.50		<0.35				37.5-42.5				<0.25										
988.2		rem			<0.35				40.0-44.0				1.0-5.0										
988.4		rem			<0.35				44.0-58.0				1.0-5.0										
993	Incramet 800	rem		10.7-11.5	0.40-1.00		13.5-16.5		<0.02			<0.02	<0.05					1.0-2.0					
993.5		rem		9.5-10.5	<1.00	<0.25	14.5-16.0		<0.15					7.5-9.5									
994		rem		0.50-2.00	1.0-3.0	<0.50	1.0-3.5		<0.25			0.50-2.00		0.50-5.00									
995		rem		0.50-2.00	3.0-5.0	<0.50	3.5-5.5		<0.25			0.50-2.00		0.50-2.00									
996	C <0.05	rem		1.0-2.8	<0.20	39.0-45.0	<0.20		<0.02			<0.10	<0.10	<0.20				<0.20					
997	No 4.0-6.0	>54.00		0.50-3.00	<1.00	11.0-15.0	4.0-6.0		<2.0				<1.00	19.0-25.0									
997.5		55.0-61.0		0.25-3.00	<1.00	17.0-23.0	<5.0		0.50-2.50				0.50-2.50	17.0-23.0									

These are specifications for reference purposes only, not samples for sale.

